CONTACT INFORMATION
Mining Records Curator
Arizona Geological Survey
1520 West Adams St.
Phoenix, AZ 85007
602-771-1601
http://www.azgs.az.gov
inquiries@azgs.az.gov

The following file is part of the

Arizona Department of Mines and Mineral Resources Mining Collection

ACCESS STATEMENT

These digitized collections are accessible for purposes of education and research. We have indicated what we know about copyright and rights of privacy, publicity, or trademark. Due to the nature of archival collections, we are not always able to identify this information. We are eager to hear from any rights owners, so that we may obtain accurate information. Upon request, we will remove material from public view while we address a rights issue.

CONSTRAINTS STATEMENT

The Arizona Geological Survey does not claim to control all rights for all materials in its collection. These rights include, but are not limited to: copyright, privacy rights, and cultural protection rights. The User hereby assumes all responsibility for obtaining any rights to use the material in excess of "fair use."

The Survey makes no intellectual property claims to the products created by individual authors in the manuscript collections, except when the author deeded those rights to the Survey or when those authors were employed by the State of Arizona and created intellectual products as a function of their official duties. The Survey does maintain property rights to the physical and digital representations of the works.

QUALITY STATEMENT

The Arizona Geological Survey is not responsible for the accuracy of the records, information, or opinions that may be contained in the files. The Survey collects, catalogs, and archives data on mineral properties regardless of its views of the veracity or accuracy of those data.

Dec. 5, 2002: B R X (file # 3) This file contains unbound and folder reports:

1.) International Platinum Annual Reports, 1993.
2.) International Platinum Annual Reports, 1994
3.) International Platinum Form 20-F, 1994.
4.) Printed Material From IPM'S, World Wide Website. (1997)
5.) International Precious Metals Annual Report 1995.
6.) International Precious Metals Annual Report 1996.

mils #838, BRX, < LA PAZ COUNTY FILE 3 OF 11. tmm.

Information printed from

International Precious Metals' world wide web site

on March 18, 1997

a gold & platinum exploration company



President's message

message archive

3rd Party Reports

USA
traded: NASDAQ
symbol: IPMCF
CANADA
traded: CDN
symbol: IPMC
MANUALS:
Standard & Poor's & CA

shares issued: 16,759,407
shares in float: 8,000,000

chart
IPM trading history

quote
Security APL Server

links

email
or go to form on contact page

EXECUTIVE SUMMARY

OVERVIEW International Precious Metals (IPM) is an Ontario, Canada registered international Exploration Company with operational headquarters in Phoenix, Arizona.

The company currently has five properties in various stages of mining progress. Four of the properties are in Canada and one in the U.S. Although each property is appealing on its own economic merits, the company has deferred any decisions regarding advancement of its Canadian holdings. This is due to the commitment IPM has made to its U.S. project known as BRX.

Over the last three years IPM has focused its resources on its prospect located ninety miles west of Phoenix. Based on the convincing technical evidence amassed during two years of exploration, and results indicating a large precious metals geochemical anomaly, the company was convinced of the potential value of the BRX asset. It has assigned the highest priority to moving the project forward to production.

CURRENT developments Consistent with mining parameters IPM set out six grids in the basin area of BRX, each grid one square kilometer. The company completed a resource-drilling program on the first grid in December 1995. The program was targeted to test the heart of the anomaly and covered the square kilometer to a depth of 30 meters or about 100 feet. The objective of the drill program was to measure the BRX mineralization and to define a precious metals resource. By April of 1996 IPM had announced the results from over 6,000 gold and platinum assays. Moreover, early in February 1996 the company discovered the primary source rocks for the precious metals on

BRX. Subsequent structural geology investigations identified and confirmed primary gold and platinum in a host-rock environment. IPM plans to expand its drill program over the total six square kilometer area of the original grids and perform deeper exploration on them and the source rock.

Metallurgical evaluation to identify methods of improving and ultimately optimizing metal recovery has received the highest technical priority. In December of 1996 IPM announced that a private research facility, that had been commissioned by the company, had made a breakthrough in recovery technology. Tests from bench up to bulk scale began on December 16, 1996 to confirm the recovery results.

Last Updated: Wed Mar 12 12:46:00 1997

This world wide web publication is for informational purposes only. This is an original unpublished work protected under copyright laws of the United States and other countries. All Rights Reserved. Should publication occur, then the following notice shall apply: © Copyright 1996 International Precious Metals. The information contained herein is not a solicitation to purchase or sell securities of International Precious Metals and may not be construed as investment advice.

design+media
site design

March 12, 1997

INTERNATIONAL PRECIOUS METALS CORPORATION

LATEST PRESS RELEASE

NASDAQ: IPMCF
CDN: IPMC

Statement To Shareholders

Toronto, Ontario March 12, 1997 -- On March 11th an article concerning International Precious Metals (IPM) was disseminated by the Bloomberg Business Wire. The article, written by Loren Steffy, featured interviews with IPM's Corporate Secretary, David Kornhauser, and Nyal Niemuth of the Arizona Department of Mines and Mineral Resources. IPM takes the strongest exception to the statements attributed to Mr. Niemuth, as well as Mr. Steffy's completely inaccurate portrayal of the Company and its BRX (Black Rock Extended) property. IPM has consulted with its legal counsel in Toronto, New York and Phoenix regarding the actions the company may be able to take.

In response to the misinformation contained in the article, and to provide absolute clarity to its shareholders regarding the BRX project, the Board of Directors of IPM has issued the following Statement to Shareholders:

> As most of you know, for over three years, IPM has been engaged in an effort to prove that the precious metals contained on BRX can be economically recovered. The company has employed the most advanced scientific instruments and methods to substantiate the presence of the precious metals, and to aid in their recovery from BRX material. Thousands of scientific tests have proven to us conclusively that economically significant amounts of precious metals are deposited on the property. Furthermore, after many months of intense applied science, IPM believes that it has the processing methods in hand to recover economically attractive amounts of the metals.
>
> The achievements we have made did not come easily. While we hit a roadblock or two along the way — they did not lessen our commitment. In addition to the three years work devoted to BRX, the company has invested over $12 million in its development. Our understanding of the geology, mineralization and complexities inherent to BRX has increased daily. This has served to further strengthen our conviction as to the importance of the project to IPM shareholders.
>
> IPM has been extremely careful and conservative in releasing information to the market in order not to be promotional. Additionally, we have always recognized the importance of third party verification of the mineralization and have consistently worked towards that goal. To assure shareholders that the company is pursuing a project of significant merit — IPM has utilized, and will continue to do so, the services of many of the premier geological, geophysical, mining and engineering consultants from around the world. Their independent confirmations of the economic potential of BRX are reinforcing, particularly due to the high standards they implement. Likewise, IPM believes that it has

adhered to the highest standards of the mining industry and the market.

In the aforementioned article, incorrect information and misleading conclusions on the company and the property were made by Mr. Niemuth and Mr. Steffy. Although IPM is nearing completion of its precious metals recovery program, the data is incomplete. IPM intends to provide the data necessary for a full and fair analysis of the BRX project when that information is conclusive — a time fast approaching. Certainly, full and fair discussions of the project's merits and IPM's corporate record are a legitimate part of a public discourse, but these should be based upon facts and scientific findings rather than on supposition or speculation. We believe that statements having impact on a public company and its shareholders should not be based on misinformation, or the lack of accurate information.

The Board believes that within a short period of time IPM will reach an important milestone in the development of BRX, and that the achievements the Company has struggled to realize will finally gain recognition. It is our hope that the purveyors of misinformation and misrepresentations will then cease and scientific fact will prevail. The Board would like to express its gratitude to IPM's loyal and patient shareholders. Moreover, the Board reconfirms its total commitment to bringing the BRX property to production.

The Board of Directors
International Precious Metals Corporation

ISSUED AND OUTSTANDING CAPITAL 16, 759,407

Internet Message From: Ron Starr

Feb. 18, 1997 - 9:21 p.m. est.

High Noon at Black Rock:

A Trip Report to Assess IPM on Feb 15, 1997

There were about 20 people in attendance and I didn't get to meet but half of them we were so busy. I won't mention any names since I think everyone will speak for themselves if they want to make a public statement. I believe there will be a story related to IPMCF in the media in the not too distant future since a large shareholder runs a media-marketing firm that specializes in matching journalists with stories. He was accompanied by one of his staff and they were in my pickup truck. In addition there were 2 newsletter writers, several stockbrokers, large individual shareholders, a mining analyst for a major international bank that finances early mining development projects, a "dealmaker" that brought along his own consultant who is a chemical engineering professor at the University of New Mexico, and a mining analyst who said his style was unique in that he does no due diligence prior to meeting top management in person as he does not want to bias his first impressions. Unfortunately he didn't bias my first impression by telling me his first impressions. I also enjoyed meeting a couple of fellow IPMCF posters as well as a couple of lurkers, it was a pleasure gentlemen, I hope your impressions were as favorable as mine were and perhaps you'll post them as well.

They now have 23 sq miles (59.6 sq km) of BLM (Bureau of Land Management land, i.e. federally owned land. BRX is next to the Interstate 10 freeway 92 miles west of Phoenix and 53 miles east of the California border and the Colorado River. The Central Aqueduct Project runs next to the property and IPM has already secured a water permit for 5 acre feet annually. High power transmission lines (330,000 volt) run across BRX as well as 12,000 volt secondary power lines and telephone lines. A natural gas pipeline with an available off-take valve is on BRX and also a petroleum line. Since a telecommunications repeater station is on a hill next to BRX La Paz County maintains a very nice graded dirt road from I-10 across BRX up to the repeater station. There are numerous other bumpy dirt roads crossing BRX which provide access to the entire property. They also have a 3,300-foot dirt airstrip. Mining BRX should have low cost reclamation since the desert is a very common cresote bush field with minimal wildlife and no known rare or endangered species are present. The leaching residue will have a neutral pH and be environmentally friendly. They are debt-free and will have $10 million in working capital available this year.

Alan Doyle (Chairman) made two statements that I found extremely encouraging. First, they have no intention of implementing any kind of poison-pills. He said they believe that if management is doing their job right then the shareholders will have enough confidence in them that they will not sell out in a hostile takeover bid for less than the company is worth. Second, he said that although insiders control 10-15% of the fully diluted shares they have so many shares in the strong hands of long term shareholders that they don't think someone could takeover IPMCF today.

I was able to talk personally with Lee Furlong (CEO), Paul Mentzer (VP Operations), Tom Dodge (Senior Geologist), Bill Allred (CFO), and Jake Henneman (BRX Site Supervisor). Somehow I overlooked talking to Alan Doyle who was with us the whole day.

Concentrates from the recent bulk samples from the first sq km grid will be sent to the refiners this month.

It was stated IPM is negotiating with Phoenix International Mining Corporation to acquire 100% of the property. Although they've yet to sign on the dotted line they see no impediments to ultimately concluding a successful agreement.

Behre Dolbear's order of magnitude mine engineering report is in hand and they expect to make a press release regarding it this month. BD has started on the pre-feasibility study for a 10 million metric tonne/yr mine on the first sq km grid. Tenders are out for quotes to do infill and deep drilling to move the first sq km grid into the Measured Resource category. The mine will operate about 350 days/yr for 28,571 t/day.

I don't believe the capital outlay or the mine capacity will be any issue at all. For relative comparisons see http://www.bema.com/ news/dec2 96.html to compare Bema's new Refugio mine operating in a high altitude desert: "In November (96), approximately 20,000 ounces of gold were produced at the Refugio Mine. Mine throughput for this month averaged 37,136 tonnes per day of ore through the primary crusher and 28,824 tonnes per day through the secondary and tertiary crushers." See http://www.barrick.com/min021.htm to compare Barrick's Carlin Trend Mine: "The processing facility consists of a mill and six autoclaves for the treatment of sulphide ores. As the Betze-Post sulphide ore is refractory, autoclaves are key to the Mine's high performance. Autoclaving oxidizes the sulphide minerals and triples gold recovery from 30% without oxidation to 90% after autoclaving. Mill and autoclave throughput for 1995 exceeded design capacity, averaging 16,245 tons per day with mill and autoclave availability of over 93%. By the end of 1995, total processing capacity for sulphide ore at Goldstrike was raised from 16,000 to 17,500 tons per day, through the addition of a new boiler and water treatment plant, a thickener and two carbon-in-leach tanks, at a cost of $20 million." See http://web20.mindlink.net/info-data/profiles/ilp.html for International Panorama's project feasibility projections prepared by Bateman Minerals & Industrial Ltd of South Africa for a Cu-Co tailings mine in Zaire: "Capital costs for a processing facility capable of 5 million tonnes annual throughput, are estimated at less than US$190 million. The plant will consist of agitated vat-leaching, solvent extraction and electrowinning treatment, and a sulphuric acid production facility."

I'm assuming 0.25 opt with a 90% yield for 6,429 oz/day. I believe the production cost will be very low and will assume $150/oz. For example, the cost to move the Desert Dirt from its ancient resting place into the recovery plant has been estimated to be less than $1/t. With spot gold at $350 IPMCF will net $200/oz for $1,285,714/day or $450 million/year.

So what does that yield for the share price target of a debt-free company based on 25 million shares outstanding to allow for 25% growth in the number of shares outstanding?

On John Doody's Gold Stock Analyst web page http://www.goldstockanalyst.com/page15_full.html he tabulates statistics for 60 producers and gives two stats I'll use here: the average market cap per ounce of gold production is $2,128 and the average market cap per Proven & Probable ounces of gold is $141.

1. $180/share if Mr. Market assigns a PE ratio of 10

2. $191/share target price on an average market cap per ounce of gold production basis

3. $80/share on an average market cap per P&P ounces of gold basis assuming the first sq km to 30 m deep plus the 45-degree sidewalls for the open pit yielding 63 million tonnes

4. $570/share on a gold valued at $50/oz in the ground basis assuming the first 6 sq kms are homogeneous at 0.25 opt with specific gravity of 1.67, yield 90%, average depth of 120 m, and including the 45 degree sidewall cuts. Ignoring the additional 45-degree sidewall contribution of the open pit mine drops it to $540/share.

Models 1 and 2 are essentially the same and represent a good target after production begins. Model 3 is my target for the next year or so since the main objective is to move the first grid into the Measured Resource category. Model 4 is the price a buyer should offer me to induce me to tender my shares in a takeover bid. These speculative projections ignore the value of the palladium, platinum, and rhodium. I saw data from many samples indicating these metals are present. If so, the speculative targets rise. Right now IPMCF needs to get the first sq km grid into the Measured Resource category and complete the bankable feasibility plan to obtain financing for the mine construction. I see no rush to prove the PGM's and Mr. Furlong assured us they know the PGM's are there. I believe they'll just let the output of the refiners where they send the concentrate prove the PGM's are there to everybody's satisfaction. This mine appears it can be very profitable even without the PGM's and I view them as icing on the cake.

Bill Allred told me that once they complete a bankable feasibility plan they'll decide how to finance the mine but it's likely to be mostly a bank loan. The revenues will be large enough they can pay off the loan rapidly. I told him that the latest PR from ILP.v says they estimate their 5 million t/yr Cu-Co tailings mine in Zaire will cost them $190 million to build. He said that IPMCF has yet to get into any detailed cost estimates but that sounded like it was in the ballpark. He pointed out Alan Doyle was planning a mine in Namibia and I should compare notes with him. If you consider the financing and one made the crude estimate that if ILP.v will pay $190 million for a 5 million t/yr tailings mine in Zaire then IPMCF will have to pay twice that for a 10 million t/yr mine. If they then go to the bank and borrow the whole $400 million at once at prime plus 3% which today would be 11.25% and amortize it over 4 years they'd have to pay $123,380,040 a year in principal and interest payments. The mine would take 16 months to put into production and then be producing about $450 million in annual sales. After P&I payments IPM will still have plenty to pay salaries, conduct exploration, expand the BRX mine, and pay shareholders a dividend. I think this is a high estimate for several reasons:

1. I don't think it'll cost twice because it's being build in Arizona with a lot of industrial and mining infrastructure, a skilled labor pool, and not in Zaire

2. You'd get a line of credit facility, which you'd draw on, as you needed to pay bills

3. Could probably negotiate better than prime plus 3%

4. They could increase the principal repayment after sales begin and pay the loan off early. There's no need to alienate IPMCF shareholders by issuing enough stock to pay for the mine, however, a few shares or warrants may be used to reduce the interest rate. Shear speculation on my part and I'm sure these gentlemen are far more business savvy than I

A 50-foot deep dry hole showing no gold was found about due east of the east-west leg of the airstrip and due north of the western boundary of the drilled-out first sq km grid. That makes it just shy of 2 km north of the northern edge of the first sq km grid. Mr. Furlong was glad they found this dry hole because it may indicate a fault line that will help them develop the geological model of the BRX deposit.

From the gold concentration gradient map I have the N-S direction of the BRX deposit is about 3 km wide and the E-W direction is about 5.7 km long. It appears like it'll run beyond the eastern property boundary and well beyond the southern boundary. It's a horizontal slice at 50-foot depth through the 3-dimensional assay data model they're building. It shows 7 different concentrations superimposed on the surface map. It's beautiful and a picture's worth a thousand words, but suffice it to say for now, that the first sq km grid is not centered in the sweet spot of highest gold concentration but its SW corner intersects it. Eli Constantine (IR) at IPM tells me they plan to post this map at http://www.ipmcf.com on their Web site. The sweet spot is oblong and runs in a NW-SW'erly direction off the southern BRX boundary and is roughly 0.8 km x 2.7 km. I don't know the grade in that zone since the map does not have a key on it. Besides, this kind of representation is relative and I suspect that it'll be input into the total resource calculation. There is a lot more data in the first sq km grid than the rest of BRX and some of this gradient map may have been extrapolated through just one drill hole. It's preliminary and far from being bankable across the entire property. I expect this 3-D map to change with every new drill core assay they obtain.

According to Tom Dodge the stockworks hill is presently believed to be only a partial contributor of gold in the BRX deposit and not the source. There has only been a limited amount of ground magnetometer work done and he plans at some point to conduct an aeromagnetic survey to study subsurface conductors. The deep drilling that will begin soon may be just as revealing in terms of his ability to locate dikes (dams sitting or protruding through the bedrock) which may have enriched zones associated with them. The Harquahala Plain is a restrictive basin that has been an Inland Sea about 15 times over the eons. At one point many millions of years ago the area was about 5,000 feet higher and the mountains have eroded away and the alluvial detritus has filled the Harquahala Plain with up to 590 feet of desert dirt, some of which has been enriched in gold, palladium, platinum, and rhodium in classic hydrothermal processes. Whatever the geological model ends up being, although it's fascinating to me, it's irrelevant in deciding I'm going to invest in IPMCF.

Note: Ron Starr is a physicist with a major electronic component manufacturer. In his spare time he studies the stock market so that one day soon he can found a closed-end mutual fund.

BRX PROJECT
First Grid Resource Drilling Program
Raw Data

The following data is provided on the actual samples taken at the indicated depth of the numbered holes. All holes were drilled to 100 feet or auger refusal.

121 HOLES REPORTED

All values in ounces per ton.

Hl-Dpth	Au	Pt
101-005	0.114	0.063
101-010	0.055	0.170
101-015	0.033	0.065
101-020	0.022	0.212
101-025	0.055	0.321
101-030	0.073	0.071
101-035	0.077	0.096
101-040	0.026	0.206
101-045	0.034	0.009
101-050	0.018	0.055
101-055	0.070	0.001
101-060	0.073	0.057
101-065	0.027	0.066
101-070	0.051	0.005
101-075	0.041	0.201
101-080	0.000	0.000
101-085	0.087	0.112
101-090	0.072	0.100
101-095	0.062	0.072
101-100	0.016	0.021

HOLE #1
Au AVE .05
Pt AVE .095

Hl-Dpth	Au	Pt
102-005	0.053	0.001
102-010	0.074	0.124
102-015	0.016	0.011
102-020	0.093	0.099
102-025	0.070	0.105
102-030	0.011	0.008
102-035	0.061	0.216
102-040	0.105	0.000
102-045	0.020	0.101
102-050	0.086	0.195
102-055	0.041	0.066
102-060	0.022	0.067
102-065	0.052	0.001
102-070	0.000	0.038
102-075	0.066	0.061
102-080	0.051	0.093
102-085	0.070	0.001
102-090	0.050	0.001
102-095	0.066	0.174
102-100	0.083	0.001

Hl-Dpth	Au	Pt
103-005	0.026	0.057
103-010	0.058	0.008
103-015	0.048	0.106
103-020	0.067	0.106
103-025	0.025	0.073
103-030	0.096	0.171
103-035	0.054	0.016
103-040	0.001	0.058
103-045	0.027	0.000
103-050	0.074	0.079
103-055	0.000	0.019
103-060	0.046	0.094
103-065	0.140	0.177
103-070	0.072	0.158
103-075	0.001	0.089
103-080	0.102	0.096
103-085	0.151	0.000
103-090	0.073	0.000
103-095	0.000	0.028
103-100	0.086	0.219

Hl-Dpth	Au	Pt
104-005	0.071	0.006
104-010	0.074	0.094
104-015	0.039	0.113
104-020	0.062	0.058
104-025	0.045	0.088
104-030	0.090	0.071
104-035	0.018	0.141
104-040	0.101	0.044
104-045	0.066	0.029
104-050	0.001	0.088
104-055	0.074	0.079
104-060	0.061	0.028
104-065	0.072	0.013
104-070	0.074	0.079
104-075	0.106	0.068
104-080	0.017	0.051
104-085	0.055	0.046
104-090	0.030	0.173
104-095	0.084	0.006
104-100	0.081	0.203

Hl-Dpth	Au	Pt
105-005	0.033	0.119
105-010	0.035	0.165
105-015	0.003	0.253
105-020	0.039	0.113
105-025	0.038	0.059
105-030	0.038	0.000
105-035	0.030	0.361
105-040	0.056	0.043
105-045	0.068	0.016
105-050	0.051	0.071
105-055	0.105	0.178
105-060	0.007	0.217
105-065	0.024	0.092
105-070	0.067	0.111
105-075	0.102	0.136
105-080	0.019	0.061
105-085	0.029	0.100
105-090	0.040	0.055
105-095	0.021	0.057

105-100	0.023	0.017

Hl-Dpth	Au	Pt
106-005	0.041	0.094
106-010	0.106	0.016
106-015	0.090	0.060
106-020	0.031	0.225
106-025	0.045	0.070
106-030	0.040	0.000
106-035	0.038	0.000
106-040	0.080	0.006
106-045	0.061	0.077
106-050	0.037	0.068
106-055	0.112	0.057
106-060	0.078	0.052
106-065	0.063	0.055
106-070	0.059	0.055
106-075	0.020	0.077
106-080	0.052	0.063
106-085	0.025	0.273
106-090	0.077	0.144
106-095	0.069	0.068
106-100	0.017	0.075

Hl-Dpth	Au	Pt
107-005	0.085	0.000
107-010	0.047	0.056
107-015	0.049	0.099
107-020	0.056	0.102
107-025	0.052	0.099
107-030	0.041	0.103
107-035	0.044	0.001
107-040	0.087	0.169
107-045	0.045	0.001
107-050	0.030	0.177
107-055	0.060	0.159
107-060	0.044	0.020
107-065	0.054	0.000
107-070	0.073	0.051
107-075	0.038	0.064
107-080	0.042	0.001
107-085	0.049	0.069
107-090	0.051	0.074
107-095	0.092	0.057
107-100	0.048	0.064

Hl-Dpth	Au	Pt
108-005	0.112	0.162
108-010	0.088	0.002
108-015	0.058	0.194
108-020	0.060	0.060
108-025	0.059	0.078
108-030	0.085	0.070
108-035	0.055	0.086
108-040	0.071	0.053
108-045	0.086	0.096
108-050	0.051	0.015
108-055	0.042	0.022
108-060	0.091	0.000
108-065	0.038	0.088
108-070	0.069	0.173
108-075	0.072	0.062
108-080	0.031	0.007
108-085	0.087	0.064

108-090	0.082	0.282
108-095	0.068	0.219
108-100	0.025	0.093

Hl-Dpth	Au	Pt
109-005	0.064	0.001
109-010	0.122	0.012
109-015	0.053	0.070
109-020	0.066	0.042
109-025	0.049	0.000
109-030	0.076	0.001
109-035	0.075	0.097
109-040	0.088	0.000
109-045	0.139	0.027
109-050	0.051	0.000
109-055	0.134	0.091
109-060	0.035	0.020
109-065	0.039	0.058
109-070	0.031	0.111
109-075	0.218	0.144
109-080	0.041	0.000
109-085	0.130	0.000
109-090	0.051	0.047
109-095	0.000	0.088
109-100	0.095	0.049

Hl-Dpth	Au	Pt
110-005	0.051	0.053
110-010	0.041	0.042
110-015	0.010	0.001
110-020	0.067	0.075
110-025	0.037	0.001
110-030	0.055	0.012
110-035	0.069	0.204
110-040	0.040	0.005
110-045	0.042	0.000
110-050	0.059	0.006
110-055	0.026	0.014
110-060	0.046	0.051
110-065	0.066	0.067
110-070	0.039	0.059
110-075	0.051	0.032
110-080	0.015	0.007
110-085	0.105	0.208
110-090	0.054	0.000
110-095	0.039	0.022
110-100	0.043	0.001

Hl-Dpth	Au	Pt
111-005	0.118	0.374
111-010	0.115	0.306
111-015	0.036	0.021
111-020	0.079	0.264
111-025	0.038	0.127
111-030	0.066	0.135
111-035	0.091	0.259
111-040	0.079	0.264
111-045	0.064	0.127
111-050	0.080	0.069
111-055	0.069	0.226
111-060	0.069	0.226
111-065	0.023	0.157
111-070	0.033	0.065
111-075	0.085	0.130

111-080	0.085	0.130
111-085	0.029	0.253
111-090	0.028	0.100
111-095	0.088	0.217
111-100	0.077	0.210

Hl-Dpth	Au	Pt
112-005	0.000	0.001
112-010	0.034	0.059
112-015	0.017	0.061
112-020	0.089	0.059
112-025	0.038	0.060
112-030	0.028	0.059
112-035	0.035	0.022
112-040	0.023	0.119
112-045	0.061	0.088
112-050	0.037	0.001
112-055	0.000	0.000
112-060	0.042	0.001
112-065	0.006	0.084

Hl-Dpth	Au	Pt
113-005	0.038	0.027
113-010	0.053	0.043
113-015	0.050	0.107
113-020	0.075	0.101
113-025	0.093	0.071
113-030	0.038	0.017
113-035	0.091	0.085
113-040	0.021	0.114
113-045	0.044	0.026
113-050	0.051	0.102
113-055	0.029	0.026
113-060	0.047	0.043
113-065	0.053	0.033
113-070	0.029	0.095
113-075	0.052	0.030
113-080	0.019	0.124
113-085	0.017	0.048
113-090	0.105	0.042
113-095	0.049	0.038
113-100	0.041	0.040

Hl-Dpth	Au	Pt
114-005	0.041	0.135
114-010	0.055	0.166
114-015	0.086	0.023
114-020	0.086	0.023
114-025	0.064	0.180
114-030	0.031	0.074
114-035	0.034	0.069
114-040	0.003	0.011
114-045	0.012	0.027
114-050	0.042	0.007
114-055	0.039	0.006
114-060	0.030	0.071
114-065	0.049	0.014
114-070	0.040	0.007
114-075	0.012	0.051
114-080	0.050	0.053
114-085	0.088	0.057
114-090	0.022	0.056
114-095	0.039	0.070
114-100	0.035	0.065

Hl-Dpth	Au	Pt
115-005	0.036	0.120
115-010	0.010	0.174
115-015	0.029	0.119
115-020	0.031	0.100
115-025	0.000	0.001
115-030	0.006	0.113
115-035	0.020	0.090
115-040	0.001	0.034
115-045	0.050	0.101
115-050	0.018	0.012
115-055	0.003	0.044
115-060	0.024	0.090
115-065	0.039	0.067
115-070	0.046	0.021
115-075	0.041	0.012
115-080	0.052	0.097
115-085	0.002	0.004
115-090	0.018	0.085
115-095	0.015	0.205
115-100	0.027	0.081

Hl-Dpth	Au	Pt
116-005	0.091	0.167
116-010	0.048	0.100
116-015	0.026	0.152
116-020	0.023	0.024
116-025	0.029	0.133
116-030	0.040	0.032
116-035	0.018	0.245
116-040	0.029	0.025
116-045	0.042	0.109
116-050	0.030	0.152
116-055	0.015	0.066
116-060	0.028	0.014
116-065	0.036	0.021
116-070	0.104	0.067
116-075	0.020	0.072
116-080	0.023	0.103
116-085	0.009	0.066
116-090	0.073	0.046
116-095	0.047	0.068
116-100	0.023	0.026

Hl-Dpth	Au	Pt
117-005	0.068	0.143
117-010	0.036	0.058
117-015	0.025	0.080
117-020	0.025	0.111
117-025	0.038	0.264
117-030	0.016	0.000
117-035	0.024	0.000
117-040	0.050	0.260
117-045	0.031	0.217
117-050	0.025	0.120
117-055	0.055	0.065
117-060	0.071	0.233
117-065	0.044	0.024
117-070	0.042	0.076
117-075	0.110	0.211
117-080	0.029	0.110
117-085	0.068	0.190
117-090	0.086	0.160
117-095	0.026	0.051

117-100	0.061	0.305

Hl-Dpth	Au	Pt
118-005	0.038	0.000
118-010	0.025	0.000
118-015	0.084	0.000
118-020	0.037	0.049
118-025	0.042	0.030
118-030	0.046	0.054
118-035	0.063	0.061
118-040	0.027	0.030
118-045	0.083	0.164
118-050	0.039	0.054
118-055	0.057	0.062
118-060	0.045	0.132
118-065	0.117	0.079
118-070	0.048	0.236
118-075	0.124	0.213
118-080	0.081	0.131
118-085	0.052	0.091
118-090	0.028	0.090
118-095	0.039	0.232
118-100	0.065	0.113

Hl-Dpth	Au	Pt
119-005	0.032	0.086
119-010	0.046	0.057
119-015	0.080	0.044
119-020	0.031	0.018
119-025	0.065	0.090
119-030	0.080	0.117
119-035	0.065	0.237
119-040	0.002	0.001
119-045	0.085	0.214
119-050	0.055	0.246
119-055	0.038	0.311
119-060	0.153	0.189
119-065	0.076	0.111
119-070	0.106	0.121
119-075	0.009	0.113
119-080	0.025	0.031
119-085	0.073	0.277
119-090	0.002	0.001
119-095	0.042	0.044
119-100	0.025	0.067

Hl-Dpth	Au	Pt
120-005	0.040	0.013
120-010	0.028	0.006
120-015	0.016	0.022
120-020	0.036	0.001
120-025	0.113	0.063
120-030	0.028	0.098
120-035	0.024	0.120
120-040	0.086	0.060
120-045	0.050	0.029
120-050	0.040	0.000
120-055	0.001	0.202
120-060	0.048	0.068
120-065	0.023	0.000
120-070	0.031	0.000
120-075	0.059	0.200
120-080	0.031	0.044
120-085	0.031	0.109

120-090	0.067	0.000
120-095	0.040	0.113
120-100	0.025	0.059

Hl-Dpth	Au	Pt
121-005	0.018	0.202
121-010	0.019	0.156
121-015	0.048	0.114
121-020	0.042	0.301
121-025	0.050	0.105
121-030	0.016	0.089
121-035	0.042	0.163
121-040	0.041	0.152
121-045	0.028	0.092
121-050	0.048	0.026
121-055	0.051	0.027
121-060	0.048	0.019
121-065	0.000	0.024
121-070	0.035	0.232
121-075	0.034	0.037
121-080	0.044	0.069
121-085	0.039	0.103
121-090	0.033	0.033
121-095	0.106	0.099
121-100	0.006	0.177

Hl-Dpth	Au	Pt
122-005	0.009	0.005
122-010	0.012	0.093
122-015	0.001	0.067
122-020	0.047	0.081
122-025	0.124	0.079
122-030	0.031	0.046
122-035	0.029	0.062
122-040	0.017	0.055
122-045	0.036	0.083
122-050	0.075	0.029
122-055	0.023	0.088
122-060	0.103	0.108
122-065	0.032	0.110
122-070	0.148	0.112
122-075	0.000	0.096
122-080	0.015	0.026
122-085	0.005	0.013
122-090	0.034	0.187
122-095	0.000	0.020
122-100	0.068	0.088

Hl-Dpth	Au	Pt
123-005	0.088	0.131
123-010	0.055	0.117
123-015	0.072	0.013
123-020	0.085	0.048
123-025	0.058	0.189
123-030	0.008	0.007
123-035	0.101	0.044
123-040	0.060	0.078
123-045	0.002	0.010
123-050	0.056	0.109

Hl-Dpth	Au	Pt
124-005	0.042	0.417
124-010	0.028	0.186
124-015	0.018	0.009

124-020	0.041	0.011
124-025	0.025	0.001
124-030	0.047	0.482
124-035	0.017	0.088

Hl-Dpth	Au	Pt
125-005	0.035	0.000
125-010	0.067	0.111
125-015	0.032	0.290
125-020	0.039	0.074
125-025	0.004	0.022
125-030	0.026	0.099
125-035	0.039	0.025
125-040	0.023	0.091
125-045	0.025	0.088
125-050	0.037	0.089
125-055	0.031	0.150
125-060	0.028	0.077
125-065	0.045	0.081
125-070	0.031	0.154
125-075	0.054	0.056
125-080	0.051	0.091
125-085	0.026	0.096
125-090	0.002	0.002
125-095	0.037	0.023
125-100	0.040	0.073

Hl-Dpth	Au	Pt
126-005	0.036	0.044
126-010	0.029	0.088
126-015	0.026	0.108
126-020	0.021	0.151
126-025	0.049	0.172
126-030	0.069	0.100
126-035	0.043	0.024
126-040	0.048	0.001
126-045	0.047	0.001
126-050	0.016	0.069
126-055	0.041	0.316
126-060	0.051	0.051
126-065	0.047	0.034
126-070	0.043	0.052
126-075	0.026	0.061
126-080	0.044	0.099
126-085	0.000	0.190
126-090	0.045	0.260
126-095	0.029	0.111
126-100	0.039	0.106

Hl-Dpth	Au	Pt
127-005	0.062	0.046
127-010	0.056	0.044
127-015	0.050	0.071
127-020	0.033	0.013
127-025	0.034	0.099
127-030	0.019	0.059
127-035	0.059	0.062
127-040	0.041	0.074
127-045	0.044	0.000
127-050	0.073	0.084
127-055	0.035	0.070
127-060	0.029	0.040
127-065	0.020	0.406
127-070	0.048	0.090

127-075	0.050	0.068
127-080	0.039	0.078
127-085	0.056	0.117
127-090	0.065	0.029
127-095	0.041	0.118
127-100	0.054	0.006

Hl-Dpth	Au	Pt
128-005	0.025	0.066
128-010	0.037	0.046
128-015	0.025	0.019
128-020	0.039	0.070
128-025	0.042	0.007
128-030	0.076	0.097
128-035	0.025	0.012
128-040	0.031	0.029
128-045	0.063	0.023
128-050	0.039	0.024
128-055	0.026	0.009
128-060	0.053	0.017
128-065	0.051	0.123
128-070	0.048	0.031
128-075	0.062	0.073
128-080	0.052	0.035
128-085	0.060	0.033
128-090	0.048	0.112
128-095	0.000	0.000
128-100	0.015	0.078

Hl-Dpth	Au	Pt
129-005	0.066	0.094
129-010	0.038	0.079
129-015	0.032	0.107
129-020	0.048	0.070
129-025	0.030	0.305
129-030	0.072	0.059
129-035	0.041	0.283
129-040	0.034	0.140
129-045	0.045	0.217
129-050	0.033	0.114
129-055	0.063	0.061
129-060	0.043	0.070
129-065	0.072	0.177
129-070	0.087	0.112
129-075	0.051	0.069
129-080	0.030	0.116
129-085	0.019	0.063
129-090	0.031	0.088
129-095	0.116	0.162
129-100	0.044	0.109

Hl-Dpth	Au	Pt
130-005	0.089	0.026
130-010	0.043	0.000
130-015	0.021	0.090
130-020	0.042	0.145
130-025	0.037	0.071
130-030	0.026	0.208
130-035	0.007	0.093
130-040	0.011	0.000
130-045	0.051	0.069
130-050	0.052	0.074
130-055	0.019	0.044
130-060	0.026	0.000

130-065	0.035	0.001
130-070	0.036	0.057
130-075	0.018	0.070
130-080	0.038	0.182
130-085	0.041	0.105
130-090	0.053	0.080
130-095	0.015	0.035
130-100	0.027	0.001

Hl-Dpth	Au	Pt
131-005	0.017	0.123
131-010	0.033	0.077
131-015	0.033	0.060
131-020	0.031	0.006
131-025	0.051	0.095
131-030	0.015	0.000
131-035	0.034	0.099
131-040	0.007	0.139
131-045	0.028	0.147
131-050	0.014	0.040
131-055	0.068	0.000
131-060	0.070	0.001
131-065	0.046	0.000
131-070	0.036	0.089
131-075	0.031	0.069
131-080	0.025	0.001
131-085	0.040	0.072
131-090	0.019	0.000
131-095	0.017	0.188
131-100	0.009	0.000

Hl-Dpth	Au	Pt
132-005	0.078	0.060
132-010	0.014	0.046
132-015	0.072	0.000
132-020	0.073	0.014
132-025	0.039	0.000
132-030	0.036	0.000
132-035	0.037	0.204
132-040	0.130	0.271
132-045	0.052	0.177
132-050	0.010	0.081
132-055	0.064	0.139
132-060	0.037	0.225
132-065	0.090	0.070
132-070	0.035	0.062
132-075	0.007	0.072
132-080	0.036	0.000
132-085	0.064	0.000
132-090	0.085	0.000

Hl-Dpth	Au	Pt
133-005	0.059	0.066
133-010	0.027	0.067
133-015	0.065	0.124
133-020	0.029	0.104
133-025	0.048	0.201
133-030	0.030	0.292
133-035	0.027	0.000
133-040	0.067	0.112
133-045	0.001	0.000
133-050	0.039	0.028
133-055	0.036	0.100
133-060	0.018	0.176

133-065	0.028	0.056
133-070	0.022	0.000
133-075	0.014	0.050
133-080	0.042	0.193
133-085	0.066	0.188
133-090	0.018	0.000
133-095	0.010	0.193
133-100	0.032	0.036

Hl-Dpth	Au	Pt
134-005	0.049	0.058
134-010	0.004	0.064
134-015	0.100	0.217
134-020	0.004	0.006
134-025	0.040	0.037
134-030	0.033	0.032
134-035	0.002	0.058
134-040	0.017	0.081
134-045	0.027	0.055
134-050	0.031	0.014
134-055	0.035	0.080
134-060	0.022	0.201
134-065	0.043	0.046
134-070	0.080	0.063
134-075	0.038	0.076
134-080	0.010	0.058
134-085	0.048	0.080
134-090	0.000	0.003
134-095	0.039	0.081
134-100	0.037	0.070

Hl-Dpth	Au	Pt
135-005	0.029	0.401
135-010	0.044	0.123
135-015	0.066	0.059
135-020	0.036	0.177
135-025	0.034	0.010
135-030	0.038	0.000
135-035	0.041	0.195
135-040	0.024	0.177
135-045	0.067	0.206
135-050	0.044	0.061
135-055	0.062	0.180
135-060	0.063	0.422
135-065	0.048	0.056
135-070	0.018	0.000
135-075	0.032	0.073
135-080	0.038	0.355
135-085	0.031	0.050
135-090	0.057	0.037
135-095	0.134	0.218
135-100	0.025	0.055

Hl-Dpth	Au	Pt
136-005	0.005	0.114
136-010	0.025	0.077
136-015	0.024	0.239
136-020	0.004	0.164
136-025	0.035	0.120
136-030	0.028	0.090
136-035	0.006	0.181
136-040	0.017	0.009
136-045	0.001	0.070
136-050	0.014	0.107

136-055	0.033	0.061
136-060	0.015	0.066
136-065	0.110	0.148
136-070	0.000	0.063
136-075	0.012	0.097
136-080	0.035	0.072
136-085	0.033	0.080
136-090	0.038	0.114
136-095	0.022	0.085
136-100	0.032	0.099

Hl-Dpth	Au	Pt
137-005	0.066	0.217
137-010	0.033	0.178
137-015	0.040	0.117
137-020	0.048	0.075
137-025	0.045	0.134
137-030	0.084	0.091
137-035	0.027	0.170
137-040	0.052	0.059
137-045	0.044	0.116
137-050	0.033	0.091
137-055	0.031	0.121
137-060	0.025	0.069
137-065	0.041	0.060

Hl-Dpth	Au	Pt
138-005	0.036	0.232
138-010	0.067	0.128
138-015	0.043	0.000
138-020	0.045	0.142
138-025	0.022	0.000
138-030	0.064	0.028
138-035	0.061	0.052
138-040	0.069	0.017
138-045	0.063	0.265
138-050	0.046	0.077
138-055	0.038	0.121
138-060	0.058	0.068

Hl-Dpth	Au	Pt
139-005	0.032	0.022
139-010	0.025	0.134
139-015	0.043	0.078
139-020	0.039	0.080
139-025	0.028	0.058
139-030	0.035	0.081
139-035	0.026	0.056
139-040	0.079	0.077
139-045	0.024	0.027
139-050	0.047	0.031
139-055	0.026	0.059
139-060	0.034	0.112
139-065	0.031	0.108
139-070	0.023	0.225
139-075	0.052	0.234
139-080	0.038	0.103
139-085	0.014	0.107
139-090	0.028	0.043
139-095	0.036	0.099

Hl-Dpth	Au	Pt
140-005	0.012	0.046
140-010	0.052	0.046

140-015	0.054	0.059
140-020	0.012	0.081
140-025	0.054	0.001
140-030	0.030	0.074
140-035	0.060	0.055
140-040	0.024	0.096
140-045	0.055	0.126
140-050	0.041	0.118
140-055	0.027	0.057
140-060	0.031	0.087
140-065	0.029	0.117
140-070	0.007	0.000
140-075	0.083	0.134
140-080	0.025	0.061
140-085	0.052	0.079
140-090	0.065	0.111
140-095	0.050	0.108

Hl-Dpth	Au	Pt
141-005	0.069	0.055
141-010	0.034	0.068
141-015	0.041	0.066
141-020	0.064	0.122
141-025	0.033	0.062
141-030	0.076	0.044
141-035	0.107	0.228
141-040	0.030	0.164
141-045	0.038	0.000
141-050	0.044	0.029
141-055	0.027	0.135
141-060	0.047	0.001
141-065	0.070	0.000
141-070	0.052	0.073
141-075	0.048	0.050
141-080	0.042	0.121
141-085	0.062	0.113
141-090	0.028	0.158

Hl-Dpth	Au	Pt
142-005	0.041	0.095
142-010	0.044	0.048
142-015	0.040	0.044
142-020	0.064	0.171
142-025	0.038	0.008
142-030	0.070	0.017
142-035	0.064	0.189
142-040	0.026	0.210
142-045	0.101	0.116
142-050	0.052	0.088
142-055	0.061	0.119
142-060	0.051	0.139
142-065	0.030	0.135
142-070	0.024	0.110
142-075	0.066	0.261
142-080	0.068	0.358
142-085	0.053	0.060
142-090	0.068	0.053
142-095	0.048	0.072
142-100	0.069	0.069

Hl-Dpth	Au	Pt
143-005	0.047	0.203
143-010	0.064	0.133
143-015	0.092	0.110

143-020	0.045	0.031
143-025	0.028	0.059
143-030	0.056	0.068
143-035	0.036	0.060
143-040	0.049	0.030
143-045	0.029	0.099
143-050	0.040	0.094
143-055	0.094	0.000
143-060	0.039	0.001
143-065	0.033	0.000
143-070	0.022	0.028
143-075	0.035	0.107
143-080	0.065	0.085
143-085	0.037	0.100
143-090	0.009	0.005
143-095	0.013	0.156
143-100	0.029	0.176

Hl-Dpth	Au	Pt
144-005	0.003	0.000
144-010	0.011	0.022
144-015	0.015	0.000
144-020	0.005	0.009
144-025	0.006	0.000
144-030	0.008	0.028
144-035	0.002	0.018
144-040	0.005	0.003
144-045	0.001	0.009
144-050	0.016	0.094
144-055	0.009	0.009
144-060	0.013	0.000
144-065	0.031	0.062
144-070	0.003	0.018
144-075	0.007	0.000
144-080	0.019	0.147
144-085	0.004	0.010
144-090	0.032	0.058
144-095	0.024	0.067
144-100	0.002	0.020

Hl-Dpth	Au	Pt
145-005	0.046	0.044
145-010	0.033	0.076
145-015	0.096	0.095
145-020	0.030	0.112
145-025	0.026	0.155
145-030	0.045	0.113
145-035	0.033	0.094
145-040	0.035	0.062
145-045	0.039	0.153
145-050	0.062	0.203
145-055	0.030	0.180
145-060	0.050	0.166

Hl-Dpth	Au	Pt
146-005	0.105	0.167
146-010	0.059	0.217
146-015	0.019	0.094
146-020	0.064	0.239
146-025	0.059	0.100
146-030	0.026	0.013
146-035	0.057	0.066
146-040	0.068	0.068
146-045	0.087	0.077

146-050	0.063	0.439
146-055	0.049	0.031

Hl-Dpth	Au	Pt
147-005	0.103	0.027
147-010	0.101	0.000
147-015	0.039	0.056
147-020	0.088	0.158
147-025	0.049	0.195
147-030	0.033	0.059
147-035	0.095	0.182
147-040	0.069	0.173
147-045	0.092	0.020
147-050	0.034	0.119
147-055	0.040	0.106
147-060	0.028	0.000
147-065	0.085	0.060
147-070	0.056	0.088
147-075	0.090	0.121
147-080	0.082	0.000

Hl-Dpth	Au	Pt
148-005	0.013	0.112
148-010	0.020	0.077
148-015	0.027	0.000
148-020	0.055	0.000
148-025	0.016	0.000
148-030	0.020	0.000
148-035	0.005	0.000
148-040	0.002	0.106
148-045	0.014	0.093
148-050	0.004	0.148
148-055	0.013	0.195

Hl-Dpth	Au	Pt
149-005	0.048	0.069
149-010	0.039	0.009
149-015	0.046	0.394
149-020	0.059	0.204
149-025	0.034	0.052
149-030	0.001	0.001
149-035	0.033	0.047
149-040	0.038	0.000
149-045	0.076	0.016
149-050	0.022	0.108
149-055	0.039	0.045

Hl-Dpth	Au	Pt
150-005	0.048	0.070
150-010	0.021	0.022
150-015	0.006	0.076
150-020	0.098	0.031
150-025	0.026	0.023
150-030	0.017	0.053
150-035	0.028	0.050
150-040	0.015	0.122
150-045	0.028	0.063
150-050	0.038	0.078
150-055	0.000	0.289

Hl-Dpth	Au	Pt
151-005	0.137	0.144
151-010	0.109	0.074
151-015	0.044	0.075

151-020	0.084	0.036
151-025	0.112	0.055
151-030	0.038	0.123
151-035	0.085	0.053
151-040	0.069	0.151
151-045	0.096	0.013
151-050	0.000	0.000
151-055	0.046	0.109
151-060	0.096	0.041
151-065	0.024	0.097
151-070	0.080	0.064
151-075	0.056	0.019
151-080	0.040	0.027
151-085	0.019	0.111
151-090	0.064	0.098
151-095	0.061	0.000
151-100	0.040	0.057

Hl-Dpth	Au	Pt
152-005	0.081	0.203
152-010	0.055	0.177
152-015	0.043	0.234
152-020	0.066	0.162
152-025	0.071	0.006
152-030	0.076	0.307
152-035	0.063	0.087
152-040	0.062	0.058
152-045	0.045	0.139
152-050	0.066	0.029
152-055	0.061	0.057
152-060	0.084	0.006
152-065	0.090	0.071
152-070	0.059	0.164
152-075	0.078	0.305
152-080	0.055	0.046
152-085	0.106	0.068
152-090	0.017	0.051
152-095	0.056	0.058
152-100	0.048	0.070

Hl-Dpth	Au	Pt
153-005	0.024	0.108
153-010	0.036	0.001
153-015	0.031	0.044
153-020	0.046	0.046
153-025	0.021	0.078
153-030	0.039	0.200
153-035	0.017	0.111
153-040	0.030	0.059
153-045	0.068	0.202
153-050	0.009	0.011
153-055	0.037	0.228
153-060	0.029	0.040
153-065	0.008	0.022
153-070	0.035	0.013
153-075	0.009	0.040
153-080	0.038	0.026
153-085	0.040	0.048
153-090	0.038	0.039
153-095	0.000	0.000
153-100	0.027	0.039

Hl-Dpth	Au	Pt
154-005	0.006	0.002

154-010	0.000	0.064
154-015	0.024	0.022
154-020	0.093	0.018
154-025	0.033	0.126
154-030	0.072	0.171
154-035	0.091	0.104
154-040	0.038	0.035
154-045	0.063	0.004
154-050	0.091	0.000
154-055	0.052	0.138
154-060	0.096	0.002
154-065	0.092	0.113
154-070	0.119	0.324
154-075	0.035	0.214
154-080	0.091	0.000
154-085	0.171	0.182
154-090	0.027	0.053
154-095	0.059	0.054
154-100	0.021	0.071

Hl-Dpth	Au	Pt
155-005	0.030	0.090
155-010	0.059	0.026
155-015	0.022	0.066
155-020	0.029	0.067
155-025	0.030	0.015
155-030	0.010	0.194
155-035	0.028	0.013
155-040	0.056	0.155
155-045	0.039	0.135
155-050	0.023	0.128
155-055	0.004	0.273
155-060	0.037	0.001
155-065	0.036	0.088
155-070	0.035	0.080
155-075	0.027	0.247
155-080	0.034	0.140
155-085	0.030	0.001
155-090	0.021	0.046
155-095	0.001	0.046
155-100	0.027	0.079

Hl-Dpth	Au	Pt
156-005	0.019	0.000
156-010	0.016	0.162
156-015	0.015	0.038
156-020	0.027	0.140
156-025	0.057	0.051
156-030	0.047	0.036
156-035	0.060	0.032
156-040	0.045	0.097
156-045	0.032	0.195
156-050	0.028	0.099
156-055	0.106	0.052
156-060	0.055	0.283
156-065	0.036	0.040
156-070	0.041	0.000
156-075	0.049	0.085
156-080	0.043	0.002
156-085	0.052	0.138
156-090	0.065	0.027
156-095	0.054	0.263

Hl-Dpth	Au	Pt

157-005	0.032	0.085
157-010	0.034	0.138
157-015	0.033	0.069
157-020	0.051	0.094
157-025	0.024	0.099
157-030	0.035	0.082
157-035	0.051	0.078
157-040	0.034	0.088
157-045	0.039	0.170
157-050	0.045	0.118
157-055	0.039	0.097
157-060	0.026	0.133

Hl-Dpth	Au	Pt
158-005	0.060	0.202
158-010	0.019	0.233
158-015	0.088	0.131
158-020	0.032	0.161
158-025	0.030	0.065
158-030	0.081	0.088
158-035	0.034	0.017
158-040	0.073	0.105
158-045	0.033	0.156
158-050	0.054	0.029
158-055	0.000	0.167
158-060	0.100	0.088
158-065	0.024	0.104
158-070	0.007	0.059
158-075	0.009	0.506
158-080	0.017	0.099
158-085	0.061	0.034
158-090	0.041	0.121
158-095	0.047	0.294
158-100	0.039	0.102

Hl-Dpth	Au	Pt
159-005	0.108	0.066
159-010	0.042	0.024
159-015	0.022	0.139
159-020	0.049	0.017
159-025	0.028	0.054
159-030	0.087	0.078
159-035	0.007	0.296
159-040	0.037	0.032
159-045	0.052	0.027
159-050	0.043	0.019
159-055	0.034	0.026
159-060	0.038	0.026
159-065	0.031	0.078
159-070	0.033	0.030
159-075	0.042	0.071
159-080	0.041	0.008
159-085	0.037	0.055
159-090	0.033	0.000
159-095	0.033	0.001
159-100	0.101	0.020

Hl-Dpth	Au	Pt
160-005	0.047	0.238
160-010	0.055	0.116
160-015	0.043	0.103
160-020	0.040	0.114
160-025	0.048	0.001
160-030	0.059	0.251

160-035	0.039	0.304
160-040	0.061	0.030
160-045	0.035	0.004
160-050	0.045	0.052
160-055	0.050	0.488
160-060	0.086	0.123
160-065	0.009	0.004
160-070	0.051	0.097
160-075	0.039	0.169
160-080	0.051	0.129
160-085	0.049	0.059
160-090	0.038	0.379

Hl-Dpth	Au	Pt
161-005	0.014	0.000
161-010	0.036	0.000
161-015	0.047	0.025
161-020	0.063	0.339
161-025	0.092	0.334
161-030	0.000	0.253
161-035	0.106	0.097
161-040	0.042	0.122
161-045	0.031	0.001
161-050	0.058	0.177
161-055	0.039	0.066
161-060	0.044	0.193

Hl-Dpth	Au	Pt
162-005	0.074	0.094
162-010	0.062	0.050
162-015	0.044	0.325
162-020	0.051	0.479
162-025	0.054	0.072
162-030	0.076	0.207
162-035	0.055	0.117
162-040	0.018	0.071
162-045	0.032	0.099
162-050	0.042	0.108
162-055	0.102	0.078
162-060	0.028	0.065
162-065	0.068	0.117
162-070	0.045	0.204
162-075	0.048	0.096
162-080	0.032	0.061
162-085	0.056	0.244
162-090	0.033	0.056
162-095	0.043	0.044
162-100	0.073	0.066

Hl-Dpth	Au	Pt
163-005	0.006	0.181
163-010	0.026	0.033
163-015	0.046	0.072
163-020	0.047	0.088
163-025	0.040	0.000
163-030	0.045	0.009
163-035	0.034	0.179
163-040	0.043	0.099
163-045	0.045	0.138
163-050	0.038	0.149
163-055	0.047	0.087
163-060	0.042	0.098
163-065	0.088	0.138
163-070	0.050	0.013

163-075	0.041	0.123
163-080	0.087	0.096
163-085	0.000	0.000
163-090	0.049	0.076
163-095	0.061	0.132
163-100	0.042	0.041

Hl-Dpth	Au	Pt
164-005	0.046	0.064
164-010	0.038	0.026
164-015	0.051	0.068
164-020	0.034	0.116
164-025	0.057	0.099
164-030	0.036	0.094
164-035	0.061	0.066
164-040	0.056	0.117
164-045	0.100	0.108
164-050	0.044	0.053
164-055	0.037	0.071
164-060	0.050	0.042
164-065	0.039	0.072
164-070	0.044	0.070
164-075	0.052	0.096
164-080	0.037	0.182
164-085	0.092	0.100
164-090	0.013	0.120
164-095	0.034	0.128
164-100	0.034	0.086

Hl-Dpth	Au	Pt
165-005	0.009	0.122
165-010	0.026	0.030
165-015	0.027	0.137
165-020	0.078	0.059
165-025	0.066	0.098
165-030	0.041	0.045
165-035	0.035	0.039
165-040	0.045	0.223
165-045	0.026	0.033
165-050	0.043	0.101
165-055	0.050	0.070
165-060	0.041	0.037
165-065	0.039	0.090
165-070	0.067	0.079
165-075	0.029	0.112
165-080	0.041	0.086
165-085	0.061	0.057
165-090	0.049	0.062
165-095	0.054	0.037
165-100	0.021	0.034

Hl-Dpth	Au	Pt
166-005	0.044	0.012
166-010	0.016	0.006
166-015	0.046	0.116
166-020	0.029	0.006
166-025	0.039	0.151
166-030	0.055	0.103
166-035	0.080	0.013
166-040	0.096	0.035
166-045	0.043	0.043
166-050	0.056	0.000
166-055	0.079	0.001
166-060	0.071	0.033

166-065	0.064	0.042
166-070	0.055	0.008
166-075	0.061	0.035
166-080	0.053	0.164
166-085	0.068	0.008
166-090	0.060	0.024
166-095	0.051	0.000
166-100	0.073	0.001

Hl-Dpth	Au	Pt
167-005	0.103	0.121
167-010	0.065	0.090
167-015	0.028	0.021
167-020	0.095	0.049
167-025	0.000	0.072
167-030	0.062	0.109
167-035	0.130	0.018
167-040	0.040	0.082
167-045	0.045	0.000
167-050	0.021	0.008
167-055	0.034	0.071
167-060	0.062	0.060
167-065	0.041	0.064
167-070	0.025	0.033
167-075	0.134	0.097
167-080	0.033	0.083
167-085	0.035	0.071
167-090	0.058	0.028
167-095	0.020	0.052
167-100	0.054	0.056

Hl-Dpth	Au	Pt
168-005	0.013	0.006
168-010	0.044	0.037
168-015	0.076	0.007
168-020	0.045	0.046
168-025	0.042	0.004
168-030	0.017	0.022
168-035	0.035	0.002
168-040	0.067	0.034
168-045	0.032	0.026
168-050	0.051	0.001
168-055	0.044	0.059
168-060	0.027	0.009
168-065	0.083	0.060
168-070	0.039	0.017
168-075	0.034	0.064
168-080	0.042	0.030
168-085	0.021	0.090
168-090	0.036	0.019

Hl-Dpth	Au	Pt
169-005	0.073	0.039
169-010	0.070	0.111
169-015	0.039	0.065
169-020	0.060	0.096
169-025	0.056	0.092
169-030	0.028	0.041
169-035	0.030	0.001
169-040	0.072	0.208
169-045	0.092	0.045
169-050	0.071	0.036
169-055	0.044	0.016
169-060	0.033	0.047

169-065	0.026	0.041
169-070	0.063	0.101
169-075	0.044	0.167
169-080	0.061	0.019
169-085	0.146	0.123
169-090	0.022	0.108
169-095	0.053	0.020
169-100	0.015	0.072

Hl-Dpth	Au	Pt
170-005	0.032	0.161
170-010	0.027	0.093
170-015	0.069	0.092
170-020	0.028	0.041
170-025	0.014	0.185
170-030	0.101	0.112
170-035	0.032	0.113
170-040	0.029	0.114
170-045	0.026	0.087
170-050	0.001	0.193
170-055	0.046	0.097
170-060	0.046	0.170
170-065	0.070	0.205
170-070	0.076	0.160
170-075	0.030	0.201
170-080	0.034	0.130

Hl-Dpth	Au	Pt
171-005	0.057	0.102
171-010	0.020	0.085
171-015	0.028	0.096
171-020	0.014	0.095
171-025	0.023	0.069
171-030	0.000	0.159
171-035	0.001	0.110
171-040	0.085	0.384
171-045	0.024	0.072
171-050	0.023	0.060
171-055	0.035	0.065
171-060	0.027	0.072
171-065	0.091	0.009
171-070	0.050	0.000
171-075	0.013	0.120
171-080	0.053	0.013
171-085	0.121	0.069
171-090	0.023	0.060
171-095	0.046	0.078
171-100	0.045	0.018

Hl-Dpth	Au	Pt
172-005	0.041	0.051
172-010	0.028	0.058
172-015	0.038	0.054
172-020	0.031	0.044
172-025	0.052	0.030
172-030	0.048	0.041
172-035	0.052	0.051
172-040	0.029	0.043
172-045	0.050	0.107
172-050	0.070	0.002
172-055	0.076	0.054
172-060	0.057	0.010
172-065	0.031	0.026
172-070	0.047	0.044

172-075	0.034	0.032
172-080	0.045	0.029
172-085	0.064	0.052
172-090	0.048	0.047
172-095	0.031	0.050
172-100	0.027	0.052

Hl-Dpth	Au	Pt
173-005	0.070	0.245
173-010	0.036	0.169
173-015	0.030	0.144
173-020	0.101	0.093
173-025	0.035	0.076
173-030	0.031	0.036
173-035	0.063	0.094
173-040	0.037	0.162
173-045	0.026	0.108
173-050	0.022	0.090
173-055	0.050	0.111
173-060	0.025	0.087
173-065	0.025	0.125
173-070	0.034	0.081
173-075	0.042	0.156
173-080	0.033	0.100
173-085	0.019	0.069
173-090	0.036	0.093
173-095	0.051	0.051
173-100	0.025	0.042

Hl-Dpth	Au	Pt
174-005	0.039	0.058
174-010	0.035	0.073
174-015	0.071	0.067
174-020	0.026	0.078
174-025	0.043	0.044
174-030	0.045	0.051
174-035	0.051	0.121
174-040	0.035	0.046
174-045	0.028	0.018
174-050	0.042	0.029
174-055	0.007	0.118
174-060	0.028	0.029
174-065	0.043	0.033
174-070	0.055	0.064
174-075	0.042	0.024
174-080	0.051	0.044
174-085	0.080	0.030
174-090	0.054	0.153
174-095	0.039	0.061

Hl-Dpth	Au	Pt
175-005	0.019	0.080
175-010	0.019	0.023
175-015	0.033	0.030
175-020	0.031	0.065
175-025	0.055	0.012
175-030	0.028	0.033
175-035	0.071	0.006
175-040	0.046	0.046
175-045	0.059	0.038
175-050	0.038	0.090
175-055	0.015	0.069
175-060	0.061	0.028
175-065	0.061	0.079

175-070	0.041	0.024
175-075	0.072	0.157
175-080	0.046	0.001
175-085	0.035	0.000
175-090	0.023	0.118

Hl-Dpth	Au	Pt
176-005	0.027	0.098
176-010	0.009	0.088
176-015	0.020	0.058
176-020	0.036	0.276
176-025	0.038	0.086
176-030	0.035	0.040
176-035	0.080	0.096
176-040	0.035	0.171
176-045	0.012	0.168
176-050	0.026	0.065
176-055	0.032	0.138
176-060	0.051	0.217
176-065	0.054	0.144
176-070	0.054	0.107
176-075	0.050	0.090
176-080	0.023	0.105
176-085	0.042	0.017
176-090	0.037	0.093
176-095	0.100	0.132
176-100	0.105	0.295

Hl-Dpth	Au	Pt
177-005	0.023	0.199
177-010	0.091	0.164
177-015	0.035	0.111
177-020	0.028	0.155
177-025	0.053	0.090
177-030	0.066	0.089
177-035	0.058	0.373
177-040	0.012	0.158
177-045	0.060	0.203
177-050	0.007	0.009
177-055	0.031	0.118
177-060	0.050	0.121
177-065	0.027	0.108
177-070	0.044	0.096
177-075	0.049	0.146
177-080	0.029	0.101
177-085	0.079	0.178
177-090	0.033	0.112
177-095	0.044	0.101
177-100	0.036	0.210

Hl-Dpth	Au	Pt
178-005	0.028	0.038
178-010	0.047	0.093
178-015	0.045	0.090
178-020	0.047	0.111
178-025	0.048	0.067
178-030	0.033	0.056
178-035	0.079	0.010
178-040	0.030	0.099
178-045	0.112	0.075
178-050	0.043	0.091
178-055	0.041	0.115
178-060	0.050	0.090
178-065	0.028	0.046

178-070	0.042	0.091
178-075	0.049	0.101
178-080	0.047	0.088
178-085	0.034	0.064
178-090	0.026	0.041
178-095	0.032	0.143
178-100	0.040	0.086

Hl-Dpth	Au	Pt
179-005	0.049	0.000
179-010	0.064	0.001
179-015	0.035	0.100
179-020	0.068	0.181
179-025	0.042	0.071
179-030	0.041	0.087
179-035	0.068	0.045
179-040	0.068	0.096
179-045	0.052	0.151
179-050	0.053	0.123
179-055	0.063	0.003
179-060	0.055	0.078
179-065	0.029	0.120
179-070	0.041	0.056
179-075	0.054	0.099
179-080	0.055	0.023
179-085	0.051	0.094
179-090	0.071	0.186
179-095	0.051	0.133
179-100	0.03	0.180

Hl-Dpth	Au	Pt
180-005	0.066	0.123
180-010	0.081	0.058
180-015	0.009	0.107
180-020	0.024	0.047
180-025	0.026	0.033
180-030	0.059	0.019
180-035	0.028	0.083
180-040	0.017	0.166
180-045	0.043	0.193
180-050	0.076	0.158
180-055	0.054	0.151
180-060	0.070	0.066
180-065	0.044	0.082
180-070	0.052	0.029
180-075	0.069	0.199
180-080	0.023	0.180
180-085	0.018	0.222
180-090	0.020	0.200
180-095	0.115	0.197
180-100	0.047	0.079

Hl-Dpth	Au	Pt
181-005	0.053	0.153
181-010	0.051	0.577
181-015	0.039	0.038
181-020	0.043	0.090
181-025	0.048	0.088
181-030	0.013	0.109
181-035	0.052	0.109
181-040	0.047	0.122
181-045	0.062	0.154
181-050	0.049	0.140
181-055	0.065	0.237

181-060	0.083	0.451
181-065	0.048	0.136
181-070	0.062	0.294
181-075	0.054	0.202
181-080	0.043	0.087
181-085	0.044	0.111
181-090	0.046	0.193
181-095	0.041	0.217
181-100	0.060	0.569

Hl-Dpth	Au	Pt
182-005	0.065	0.047
182-010	0.055	0.060
182-015	0.049	0.069
182-020	0.052	0.082
182-025	0.054	0.068
182-030	0.045	0.077
182-035	0.055	0.189
182-040	0.054	0.042
182-045	0.051	0.001
182-050	0.049	0.094
182-055	0.034	0.079
182-060	0.053	0.130
182-065	0.054	0.245
182-070	0.100	0.001
182-075	0.051	0.017
182-080	0.047	0.175
182-085	0.060	0.010
182-090	0.051	0.117
182-095	0.036	0.366
182-100	0.072	0.003

Hl-Dpth	Au	Pt
183-005	0.066	0.029
183-010	0.034	0.056
183-015	0.046	0.004
183-020	0.020	0.045
183-025	0.043	0.031
183-030	0.072	0.027
183-035	0.024	0.013
183-040	0.025	0.024
183-045	0.052	0.016
183-050	0.024	0.012
183-055	0.079	0.115
183-060	0.038	0.030
183-065	0.015	0.023
183-070	0.039	0.000
183-075	0.062	0.045
183-080	0.026	0.000
183-085	0.014	0.024
183-090	0.015	0.000
183-095	0.048	0.020
183-100	0.047	0.019

Hl-Dpth	Au	Pt
184-005	0.030	0.016
184-010	0.023	0.038
184-015	0.019	0.059
184-020	0.032	0.040
184-025	0.045	0.038
184-030	0.016	0.047
184-035	0.041	0.062
184-040	0.015	0.069
184-045	0.028	0.039

184-050	0.057	0.068
184-055	0.059	0.127
184-060	0.041	0.036
184-065	0.050	0.104
184-070	0.001	0.143
184-075	0.011	0.145
184-080	0.028	0.060
184-085	0.093	0.085
184-090	0.043	0.093
184-095	0.010	0.042
184-100	0.028	0.063

Hl-Dpth	Au	Pt
185-005	0.050	0.066
185-010	0.046	0.123
185-015	0.034	0.101
185-020	0.053	0.099
185-025	0.006	0.081
185-030	0.019	0.055
185-035	0.036	0.085
185-040	0.012	0.031
185-045	0.087	0.078
185-050	0.014	0.022
185-055	0.032	0.074
185-060	0.021	0.079
185-065	0.036	0.072
185-070	0.001	0.006
185-075	0.017	0.055
185-080	0.022	0.030
185-085	0.063	0.048
185-090	0.018	0.090
185-095	0.066	0.076
185-100	0.028	0.069

Hl-Dpth	Au	Pt
186-005	0.027	0.062
186-010	0.046	0.100
186-015	0.034	0.172
186-020	0.052	0.027
186-025	0.038	0.135
186-030	0.037	0.040
186-035	0.022	0.038
186-040	0.066	0.041
186-045	0.032	0.080
186-050	0.020	0.099
186-055	0.035	0.080
186-060	0.034	0.112
186-065	0.057	0.094
186-070	0.048	0.099
186-075	0.052	0.067
186-080	0.036	0.034
186-085	0.026	0.050
186-090	0.042	0.066
186-095	0.030	0.116
186-100	0.018	0.113

Hl-Dpth	Au	Pt
187-005	0.020	0.060
187-010	0.065	0.088
187-015	0.018	0.054
187-020	0.019	0.071
187-025	0.013	0.078
187-030	0.047	0.088
187-035	0.016	0.102

187-040	0.015	0.202
187-045	0.031	0.043
187-050	0.025	0.136
187-055	0.035	0.042
187-060	0.010	0.036
187-065	0.040	0.063
187-070	0.023	0.024
187-075	0.037	0.021
187-080	0.022	0.045
187-085	0.016	0.009
187-090	0.033	0.110
187-095	0.029	0.008
187-100	0.027	0.023

Hl-Dpth	Au	Pt
188-005	0.030	0.100
188-010	0.038	0.082
188-015	0.033	0.067
188-020	0.002	0.026
188-025	0.034	0.031
188-030	0.010	0.036
188-035	0.021	0.027
188-040	0.033	0.020
188-045	0.007	0.030
188-050	0.021	0.033
188-055	0.020	0.046
188-060	0.029	0.111
188-065	0.016	0.040
188-070	0.034	0.129
188-075	0.071	0.105
188-080	0.013	0.100
188-085	0.045	0.113
188-090	0.019	0.047
188-095	0.029	0.109
188-100	0.035	0.062

Hl-Dpth	Au	Pt
189-005	0.056	0.096
189-010	0.070	0.070
189-015	0.030	0.086
189-020	0.026	0.028
189-025	0.034	0.071
189-030	0.039	0.040
189-035	0.000	0.046
189-040	0.019	0.049
189-045	0.029	0.026
189-050	0.064	0.034
189-055	0.065	0.022
189-060	0.103	0.023
189-065	0.050	0.027
189-070	0.028	0.011
189-075	0.038	0.095
189-080	0.036	0.034
189-085	0.053	0.053
189-090	0.075	0.037
189-095	0.072	0.060
189-100	0.068	0.014

Hl-Dpth	Au	Pt
190-005	0.105	0.180
190-010	0.061	0.068
190-015	0.037	0.012
190-020	0.029	0.147
190-025	0.019	0.113

190-030	0.001	0.104
190-035	0.04	0.204
190-040	0.069	0.158
190-045	0.056	0.102
190-050	0.106	0.089
190-055	0.045	0.074
190-060	0.053	0.014
190-065	0.041	0.173
190-070	0.001	0.195
190-075	0.025	0.074
190-080	0.05	0.129
190-085	0.038	0.102
190-090	0.041	0.120
190-095	0.038	0.102
190-100	0.009	0.011

Hl-Dpth	Au	Pt
191-005	0.017	0.052
191-010	0.055	0.090
191-015	0.038	0.108
191-020	0.031	0.156
191-025	0.086	0.065
191-030	0.022	0.069
191-035	0.045	0.100
191-040	0.083	0.110
191-045	0.031	0.041
191-050	0.039	0.012
191-055	0.096	0.150

Hl-Dpth	Au	Pt
192-005	0.080	0.121
192-010	0.025	0.154
192-015	0.029	0.050
192-020	0.001	0.078
192-025	0.027	0.020
192-030	0.013	0.014
192-035	0.107	0.110
192-040	0.005	0.022
192-045	0.056	0.016
192-050	0.030	0.019
192-055	0.024	0.062
192-060	0.111	0.002
192-065	0.056	0.115
192-070	0.063	0.099
192-075	0.000	0.176
192-080	0.028	0.016
192-085	0.066	0.095
192-090	0.003	0.030
192-095	0.008	0.010
192-100	0.061	0.094

Hl-Dpth	Au	Pt
193-005	0.032	0.123
193-010	0.040	0.068
193-015	0.026	0.121
193-020	0.028	0.038
193-025	0.040	0.102
193-030	0.087	0.116
193-035	0.034	0.116
193-040	0.027	0.126
193-045	0.049	0.066
193-050	0.059	0.066
193-055	0.021	0.049
193-060	0.016	0.130

193-065	0.015	0.140
193-070	0.039	0.077
193-075	0.026	0.062
193-080	0.019	0.063
193-085	0.036	0.055
193-090	0.026	0.077
193-095	0.047	0.075
193-100	0.030	0.094

Hl-Dpth	Au	Pt
194-005	0.038	0.194
194-010	0.022	0.090
194-015	0.036	0.055
194-020	0.026	0.066
194-025	0.030	0.068
194-030	0.019	0.034
194-035	0.027	0.102
194-040	0.004	0.076
194-045	0.033	0.074
194-050	0.029	0.120
194-055	0.046	0.013
194-060	0.056	0.197
194-065	0.011	0.104
194-070	0.040	0.077
194-075	0.029	0.083
194-080	0.040	0.036
194-085	0.042	0.019
194-090	0.000	0.063
194-095	0.105	0.129
194-100	0.034	0.073

Hl-Dpth	Au	Pt
195-005	0.044	0.074
195-010	0.024	0.158
195-015	0.024	0.163
195-020	0.025	0.083
195-025	0.009	0.114
195-030	0.026	0.122
195-035	0.067	0.060
195-040	0.038	0.065
195-045	0.025	0.308
195-050	0.032	0.205
195-055	0.035	0.097
195-060	0.032	0.098
195-065	0.030	0.080
195-070	0.030	0.180
195-075	0.027	0.041
195-080	0.051	0.071
195-085	0.042	0.046
195-090	0.050	0.091
195-095	0.016	0.083
195-100	0.043	0.063

Hl-Dpth	Au	Pt
196-005	0.095	0.110
196-010	0.070	0.040
196-015	0.026	0.055
196-020	0.043	0.011
196-025	0.016	0.060
196-030	0.034	0.038
196-035	0.047	0.072
196-040	0.074	0.031
196-045	0.058	0.052
196-050	0.030	0.099

196-055	0.038	0.111
196-060	0.048	0.102
196-065	0.045	0.044
196-070	0.110	0.023
196-075	0.039	0.029
196-080	0.045	0.076
196-085	0.051	0.021
196-090	0.049	0.066
196-095	0.009	0.060
196-100	0.045	0.062

Hl-Dpth	Au	Pt
197-005	0.015	0.047
197-010	0.034	0.052
197-015	0.037	0.066
197-020	0.029	0.097
197-025	0.043	0.020
197-030	0.104	0.018
197-035	0.025	0.071
197-040	0.040	0.042
197-045	0.059	0.019
197-050	0.043	0.009
197-055	0.060	0.101
197-060	0.050	0.080
197-065	0.048	0.055
197-070	0.048	0.052
197-075	0.031	0.069
197-080	0.033	0.043
197-085	0.051	0.028
197-090	0.017	0.011
197-095	0.019	0.015
197-100	0.050	0.038

Hl-Dpth	Au	Pt
198-005	0.004	0.002
198-010	0.040	0.001
198-015	0.063	0.001
198-020	0.037	0.001
198-025	0.034	0.028
198-030	0.042	0.001
198-035	0.038	0.029
198-040	0.035	0.240
198-045	0.034	0.194
198-050	0.037	0.173
198-055	0.042	0.131
198-060	0.045	0.096
198-065	0.047	0.066
198-070	0.080	0.072
198-075	0.045	0.054
198-080	0.046	0.050
198-085	0.054	0.051
198-090	0.026	0.089
198-095	0.068	0.090
198-100	0.066	0.105

Hl-Dpth	Au	Pt
199-005	0.068	0.092
199-010	0.018	0.076
199-015	0.031	0.043
199-020	0.049	0.078
199-025	0.034	0.100
199-030	0.054	0.146
199-035	0.026	0.039
199-040	0.032	0.056

199-045	0.048	0.068
199-050	0.052	0.073
199-055	0.097	0.090
199-060	0.057	0.083
199-065	0.031	0.096
199-070	0.035	0.058
199-075	0.059	0.009
199-080	0.038	0.066
199-085	0.041	0.004
199-090	0.075	0.029
199-095	0.046	0.052
199-100	0.038	0.044

Hl-Dpth	Au	Pt
200-005	0.001	0.001
200-010	0.065	0.143
200-015	0.028	0.030
200-020	0.064	0.153
200-025	0.037	0.019
200-030	0.085	0.092
200-035	0.000	0.044
200-040	0.025	0.026
200-045	0.069	0.111
200-050	0.021	0.040
200-055	0.078	0.096
200-060	0.034	0.015
200-065	0.001	0.023
200-070	0.017	0.021
200-075	0.031	0.097
200-080	0.060	0.128
200-085	0.011	0.083
200-090	0.057	0.000
200-095	0.028	0.077
200-100	0.001	0.004

Hl-Dpth	Au	Pt
201-005	0.061	0.066
201-010	0.004	0.186
201-015	0.003	0.174
201-020	0.049	0.304
201-025	0.003	0.329
201-030	0.015	0.083
201-035	0.029	0.087
201-040	0.083	0.211
201-045	0.049	0.079
201-050	0.028	0.135
201-055	0.12	0.090
201-060	0.041	0.112
201-065	0.123	0.169
201-070	0.02	0.183
201-075	0.006	0.180
201-080	0.016	0.069
201-085	0.001	0.093
201-090	0.004	0.177
201-095	0.019	0.137
201-100	0.059	0.284

Hl-Dpth	Au	Pt
202-005	0.003	0.001
202-010	0.061	0.090
202-015	0.018	0.066
202-020	0.057	0.383
202-025	0.060	0.068
202-030	0.071	0.046

202-035	0.070	0.170
202-040	0.095	0.183
202-045	0.083	0.071
202-050	0.030	0.222
202-055	0.067	0.119
202-060	0.148	0.190
202-065	0.031	0.100
202-070	0.067	0.373
202-075	0.063	0.330
202-080	0.063	0.487
202-085	0.044	0.000
202-090	0.071	0.071
202-095	0.024	0.074
202-100	0.063	0.119

Hl-Dpth	Au	Pt
203-005	0.035	0.006
203-010	0.014	0.008
203-015	0.031	0.027
203-020	0.028	0.028
203-025	0.037	0.016
203-030	0.047	0.025
203-035	0.016	0.058
203-040	0.042	0.066
203-045	0.007	0.078
203-050	0.030	0.090
203-055	0.037	0.039
203-060	0.013	0.023
203-065	0.044	0.040
203-070	0.020	0.024
203-075	0.025	0.018
203-080	0.055	0.010
203-085	0.034	0.033
203-090	0.022	0.027
203-095	0.019	0.021
203-100	0.015	0.040

Hl-Dpth	Au	Pt
204-005	0.080	0.308
204-010	0.008	0.020
204-015	0.019	0.171
204-020	0.023	0.158
204-025	0.009	0.055
204-030	0.070	0.094
204-035	0.007	0.106
204-040	0.064	0.134
204-045	0.080	0.156
204-050	0.050	0.069
204-055	0.042	0.076
204-060	0.090	0.038
204-065	0.064	0.013
204-070	0.060	0.120
204-075	0.044	0.162
204-080	0.049	0.076
204-085	0.000	0.126
204-090	0.051	0.209
204-095	0.007	0.065

Hl-Dpth	Au	Pt
205-005	0.033	0.062
205-010	0.024	0.071
205-015	0.032	0.115
205-020	0.040	0.138
205-025	0.040	0.196

205-030	0.035	0.180
205-035	0.026	0.173
205-040	0.028	0.093
205-045	0.026	0.103
205-050	0.008	0.051
205-055	0.031	0.060
205-060	0.011	0.046
205-065	0.017	0.075
205-070	0.010	0.095
205-075	0.006	0.107

Hl-Dpth	Au	Pt
206-005	0.056	0.008
206-010	0.028	0.012
206-015	0.039	0.036
206-020	0.035	0.009
206-025	0.035	0.038
206-030	0.023	0.085
206-035	0.038	0.094
206-040	0.065	0.108
206-045	0.051	0.040
206-050	0.006	0.046
206-055	0.025	0.084
206-060	0.024	0.107
206-065	0.034	0.027
206-070	0.009	0.071
206-075	0.047	0.131
206-080	0.048	0.093
206-085	0.087	0.048
206-090	0.050	0.111
206-095	0.016	0.133
206-100	0.041	0.055

Hl-Dpth	Au	Pt
207-005	0.027	0.102
207-010	0.036	0.088
207-015	0.052	0.073
207-020	0.061	0.082
207-025	0.041	0.074
207-030	0.038	0.197
207-035	0.026	0.090
207-040	0.039	0.117
207-045	0.058	0.171
207-050	0.086	0.201
207-055	0.037	0.100
207-060	0.037	0.096
207-065	0.045	0.144
207-070	0.037	0.213
207-075	0.100	0.152
207-080	0.036	0.071
207-085	0.038	0.111
207-090	0.053	0.143
207-095	0.033	0.054
207-100	0.046	0.105

Hl-Dpth	Au	Pt
208-005	0.031	0.041
208-010	0.055	0.026
208-015	0.045	0.037
208-020	0.036	0.000
208-025	0.071	0.030
208-030	0.028	0.053
208-035	0.091	0.056
208-040	0.064	0.038

208-045	0.038	0.001
208-050	0.016	0.100
208-055	0.017	0.017
208-060	0.026	0.081
208-065	0.032	0.077
208-070	0.033	0.040
208-075	0.031	0.032
208-080	0.039	0.053
208-085	0.046	0.013
208-090	0.042	0.023
208-095	0.036	0.064
208-100	0.020	0.092

Hl-Dpth	Au	Pt
209-005	0.026	0.247
209-010	0.042	0.246
209-015	0.057	0.149
209-020	0.049	0.100
209-025	0.031	0.029
209-030	0.064	0.001
209-035	0.068	0.066
209-040	0.051	0.069
209-045	0.039	0.282
209-050	0.034	0.094
209-055	0.052	0.075
209-060	0.037	0.052
209-065	0.023	0.001
209-070	0.024	0.008
209-075	0.017	0.012
209-080	0.032	0.071
209-085	0.054	0.125
209-090	0.025	0.058
209-095	0.013	0.117
209-100	0.030	0.096

Hl-Dpth	Au	Pt
210-005	0.022	0.044
210-010	0.023	0.049
210-015	0.022	0.087
210-020	0.017	0.008
210-025	0.010	0.068
210-030	0.038	0.091
210-035	0.068	0.153
210-040	0.031	0.085
210-045	0.015	0.064
210-050	0.004	0.031
210-055	0.001	0.041
210-060	0.026	0.138
210-065	0.032	0.142
210-070	0.052	0.155
210-075	0.026	0.067
210-080	0.034	0.096
210-085	0.035	0.184
210-090	0.028	0.122
210-095	0.015	0.026
210-100	0.001	0.008

Hl-Dpth	Au	Pt
211-005	0.041	0.005
211-010	0.015	0.217
211-015	0.030	0.053
211-020	0.040	0.052
211-025	0.066	0.186
211-030	0.037	0.034

211-035	0.005	0.193
211-040	0.062	0.200
211-045	0.026	0.083
211-050	0.060	0.162
211-055	0.023	0.114
211-060	0.068	0.097
211-065	0.028	0.040
211-070	0.019	0.031
211-075	0.038	0.073
211-080	0.072	0.089
211-085	0.045	0.007
211-090	0.050	0.077
211-095	0.065	0.026
211-100	0.051	0.002

Hl-Dpth	Au	Pt
212-005	0.043	0.055
212-010	0.026	0.080
212-015	0.007	0.072
212-020	0.044	0.066
212-025	0.017	0.091
212-030	0.061	0.101
212-035	0.047	0.074
212-040	0.055	0.071
212-045	0.012	0.056
212-050	0.072	0.069
212-055	0.012	0.060
212-060	0.011	0.065
212-065	0.023	0.112
212-070	0.009	0.104
212-075	0.024	0.220

Hl-Dpth	Au	Pt
213-005	0.076	0.000
213-010	0.097	0.016
213-015	0.059	0.098
213-020	0.052	0.052
213-025	0.048	0.324
213-030	0.049	0.136
213-035	0.070	0.162
213-040	0.048	0.083
213-045	0.045	0.143
213-050	0.063	0.307
213-055	0.054	0.042
213-060	0.070	0.144
213-065	0.048	0.098
213-070	0.046	0.039
213-075	0.052	0.033
213-080	0.059	0.070
213-085	0.043	0.026
213-090	0.046	0.125
213-095	0.054	0.063
213-100	0.052	0.001

Hl-Dpth	Au	Pt
214-005	0.033	0.020
214-010	0.030	0.059
214-015	0.018	0.016
214-020	0.058	0.007
214-025	0.039	0.008
214-030	0.068	0.028
214-035	0.029	0.008
214-040	0.043	0.001
214-045	0.035	0.043

214-050	0.079	0.002
214-055	0.015	0.041
214-060	0.057	0.014
214-065	0.045	0.000
214-070	0.057	0.046
214-075	0.075	0.009
214-080	0.032	0.062
214-085	0.060	0.025
214-090	0.045	0.014
214-095	0.033	0.069
214-100	0.021	0.011

Hl-Dpth	Au	Pt
215-005	0.032	0.156
215-010	0.023	0.014
215-015	0.000	0.102
215-020	0.024	0.004
215-025	0.029	0.163
215-030	0.049	0.083
215-035	0.046	0.171
215-040	0.033	0.095
215-045	0.071	0.098
215-050	0.060	0.000
215-055	0.052	0.139
215-060	0.044	0.207
215-065	0.006	0.061
215-070	0.012	0.046
215-075	0.068	0.099
215-080	0.037	0.070

Hl-Dpth	Au	Pt
216-005	0.045	0.027
216-010	0.026	0.010
216-015	0.009	0.016
216-020	0.034	0.103
216-025	0.069	0.278
216-030	0.049	0.324
216-035	0.058	0.162
216-040	0.045	0.027
216-045	0.081	0.000
216-050	0.035	0.053

Hl-Dpth	Au	Pt
217-005	0.002	0.007
217-010	0.010	0.005
217-015	0.003	0.001
217-020	0.024	0.069
217-025	0.023	0.050
217-030	0.048	0.002
217-035	0.032	0.077
217-040	0.043	0.085
217-045	0.072	0.064
217-050	0.045	0.099
217-055	0.030	0.124
217-060	0.020	0.075
217-065	0.038	0.073
217-070	0.056	0.054
217-075	0.002	0.060
217-080	0.032	0.099
217-085	0.013	0.039
217-090	0.041	0.078

Hl-Dpth	Au	Pt
218-005	0.020	0.053

218-010	0.056	0.074
218-015	0.038	0.093
218-020	0.058	0.062
218-025	0.100	0.106
218-030	0.041	0.218
218-035	0.085	0.124
218-040	0.039	0.062
218-045	0.093	0.086
218-050	0.031	0.090
218-055	0.056	0.111
218-060	0.061	0.048
218-065	0.020	0.157
218-070	0.029	0.000
218-075	0.028	0.020
218-080	0.045	0.177
218-085	0.037	0.345
218-090	0.024	0.023
218-095	0.037	0.194
218-100	0.035	0.169

Hl-Dpth	Au	Pt
219-005	0.047	0.330
219-010	0.041	0.022
219-015	0.049	0.203
219-020	0.030	0.075
219-025	0.032	0.001
219-030	0.045	0.060
219-035	0.055	0.002
219-040	0.050	0.005
219-045	0.027	0.010
219-050	0.012	0.001
219-055	0.044	0.024
219-060	0.020	0.038
219-065	0.011	0.047
219-070	0.023	0.103
219-075	0.022	0.043
219-080	0.032	0.058
219-085	0.015	0.066
219-090	0.027	0.014
219-095	0.049	0.000
219-100	0.052	0.158

Hl-Dpth	Au	Pt
220-005	0.034	0.056
220-010	0.018	0.153
220-015	0.033	0.069
220-020	0.017	0.200
220-025	0.051	0.039
220-030	0.020	0.068
220-035	0.039	0.070
220-040	0.062	0.047
220-045	0.035	0.065
220-050	0.030	0.083
220-055	0.038	0.026
220-060	0.019	0.069
220-065	0.018	0.053
220-070	0.034	0.030
220-075	0.045	0.083
220-080	0.052	0.071
220-085	0.046	0.049
220-090	0.029	0.017
220-095	0.065	0.068
220-100	0.051	0.028

Hl-Dpth	Au	Pt
221-005	0.065	0.065
221-010	0.045	0.021
221-015	0.044	0.068
221-020	0.016	0.070
221-025	0.038	0.092
221-030	0.037	0.173
221-035	0.042	0.202
221-040	0.054	0.099
221-045	0.100	0.138
221-050	0.049	0.072
221-055	0.047	0.112
221-060	0.035	0.015
221-065	0.054	0.019
221-070	0.043	0.088