

4469
4470

West End Mine

Sample No	width	% CaF ₂	% SiO ₂
4469	2.6	54.95	22.30
4470	1.5	92.26	2.56
4471	2.0	66.92	15.66
4472	2.7	77.63	3.20

6	5	4	3	2	1	6	5	4	3	2	1
7	8	9	10	11	12	7	8				13



Fig. 3

Map of West End and Good Luck Mine
Wickburg Mining District
Maricopa County, Ariz.

Good Luck

Sample No	width	% CaF ₂	% SiO ₂
4466	2.9	65.87	13.32
4467	2.8	86.31	4.77
4468	2.5	59.92	6.60

Scale 1" = 100'
10 ft Contours
Stadia Survey

contact
use rock