



Samples by F.R. Wicks; E.M.

No.	Width	% CaF ₂	% SiO ₂
1	21"	92.00	4.03
2	21"	93.80	2.68
3	13"	90.00	3.24
4	13"	83.33	8.23
5	13"	93.00	3.43
6	30"	84.40	10.60

DMEA		Samples	
No.	Width	% CaF ₂	% SiO ₂
14658	18"	99.00	0.6
14659	20"	96.2	2.7
14660	20"	88.7	9.2

Figure 3 — Longitudinal Projection, Polly Anne Fluorspar Mine
Greenlee County, Arizona

Mop Furnished by Applicant.