

# Assay Sheet

Marconi

Mine

	Width of Vein	Date 1929	Gold OZ	Silver OZ	Copper %	Lead %	Zinc %	Total Value
From Cross Cut 28 feet		July 29	.02	1.6	.1	2.5		\$ 5.45
" " " face 46 "		Aug 3	.02	5.5	.2	2.14		7.40
" " " " 49 "		" 5	.01	3.2	.5	1.6		5.55
" " " " 90 "	2 feet	" 13	.03	1.3	.1	.5	13.2	20.01
Car Sample 90-94		" 29	.02	2.8	.07	4.2	6.1	18.07
Face 96-98		" 23	.06	7.2	.45	12.8	14.7	43.74
Car Sample 98-103		" 29	.04	3.0	.05	3.5	11.5	22.45
" " 103-107		" "	.04	3.6	.05	3.5	11.1	22.65
" " 113-116	5 "	" 31	.02	4.4	.05	4.5	14.5	28.96
" " 116-120	6 "	" "	.02	4.2	.05	4.1	10.5	22.50
Drill Hole Hang Wall 127	2 1/2 "	Sept 4	.04	6.2	.07	6.1	3.8	20.38
Car Sample 110-112	5 "	" "	.02	5.7	.05	8.0	12.2	30.87
" " 120-124	5 "	" "	.01	5.8	1.05	12.2	14.1	42.55
" " 128-132	5 "	" 6	.02	2.7	.1	4.1	3.9	13.05
" " 132-135	6 "	" 9	.01	2.6	.12	5.1	4.1	14.21
" " 135-138	8 "	" 9	.02	2.8	.15	5.5	3.6	14.70
" " 138-145	3 "	" 10	.02	2.5	.5	4.1	3.6	14.25
" " 145-149	3 "	" 10	.02	2.4	.25	3.5	2.7	11.70
" " 149-154	3 "	" 19	.02	2.6	1.5	6.1	1.6	17.76
" " 154-180	3 "	" "	.01	2.1	.9	5.0	1.2	13.06
Car 133	3 "	" 23	.03	3.9	1.35	6.6	2.1	19.00
" " 144	4 "	" "	.02	2.2	.3	6.9	1.5	14.16
" " 154	4 1/2 "	" "	.03	1.8	.2	4.1	1.2	9.52
" " 163-170	4 "	" "	Tr	.3	Tr	1.6	Tr	2.35
" " 170-175	2 "	" "	.02	1.2	.5	2.1	1.1	7.17
Face 176	2 "	" "	.01	2.1	.1	10.2	1.5	15.15
" " 172-176		" 26	.01	3.2	.15	11.5	1.1	19.73
" " 176-182		" "	.02	2.8	.02	6.1	.8	11.49
Car 182	2 "	" "	.01	2.9	.05	5.0	.6	9.56
" " 185	3 "	" "	Tr	2.1	.05	3.6	.9	7.42
Drill Hole at 181	6 "	" "	.02	13.1	Tr	1.5	.6	9.96
Grab Sample 185-190	3 "	" 25	.01	3.1	.07	3.7	1.6	9.29
Car " 185-190		" "	.01	4.3	.15	4.6	2.5	12.54
" " 190-195		" Oct 2	.02	4.2	.3	5.9	3.6	16.62
" " 195-198		" "	.01	2.9	.05	2.3	1.5	7.04
Cross Cut 195-198	3 1/2 "	" "	.01	2.1	.05	2.4	2.0	7.56
4 feet at 200		" "	Tr	1.5	.05	1.6	2.2	6.26
1st Right Face "		" 3	.01	2.5	.25	2.9	4.0	11.87
Car Sample 200-204		" "	.12	2.3	.25	3.5	2.5	10.28
" " 204	4 "	" "	.01	2.00	.05	4.6	2.2	10.74
" " 204-210	4 "	" 7	.01	2.5	.1	3.9	4.1	12.84
" " 210-215	1 1/2 "	" "	.01	2.1	.1	3.1	2.0	8.58
Face 225		" "	.01	2.0	.25	3.3	1.9	9.22
Car Sample 222-226		" 9	.02	3.1	.3	3.5	1.6	10.02
Car 180		" "	.01	1.8	.35	3.5	1.7	12.24
Face 234	2 "	" "	.01	2.0	1.15	9.5	1.9	21.42
" " 242		" 11	.01	.6	.05	1.4	1.0	3.96
" " 250		" 14	.01	.9		4.6	.9	8.20
" " 256		" "	.16	.7	.05	.5	1.1	5.90
" " 250		" "	.17	1.6	.1	.2	4.9	7.39
" " 26 "		" "	.03	.6	.05	.3	.5	3.26
North Side Bottom 262		" 18	.02	.6	.1	2.6	1.7	6.93
Drill Sample 155		" 28	.04	10.1	.15	3.6	1.3	13.10
Black strip 6" wide 15 from X cut	4 feet	July 26	.02	72.0	6.55	12.0		99.50
Quartz 1543 from Cross Cut	3 feet	" 27	.02	21.0	3.15	10.5		36.70
Face Right 6" wide 20 from X cut	2 "	" 29		.8	.05	.7		1.55
" Left " " "	2 "	" "	.03	6.2	1.45	6.1		17.35
" " 35 " " "	2 1/2 "	Aug 1	.05	7.8	2.6	10.2		25.75
Drift 39 " " "	3 "	" 3	.03	4.1	2.25	5.1		17.75
Face " " "	2 1/2 "	" "	.04	8.1	1.6	5.1		17.75
Face of Mine 25	2 "	" "	.05	36.5	3.65	13.2	18.6	70.42
Car Sample from 50-55	3 1/2 "	Sept 19	.01	.9	.5	1.3	.9	5.57

	Width of Vein	Date 1929	Gold OZ	Silver OZ	Copper %	Lead %	Zinc %	Total Value
Car Sample from 85-90	5 "	Sept 19	.02	1.4	.8	1.2	2.1	\$ 8.15
" " 90-94	" "	" "	Tr	.7	.3	1.1	1.6	4.81
" " 94-100	5 "	" "	Tr	.2	Tr	.2	.3	1.71
" " 100-104	" "	" "	.01	.4	.1	.1	.5	1.71
" " 104-106	" "	" "	.01	1.0	.05	1.8	1.4	3.92
" " 106-111	" "	" "	Tr	.2	Tr	.1	1.1	1.73
" " 111-116	" "	" "	Tr	.2	Tr	.05	.3	1.57
" " 116-122	" "	" "	Tr	.3	Tr	.1	1.0	4.2
" " 122-126	" "	" "	.01	.5	.05	1.1	1.4	2.69
" " 126-131	" "	" "	Tr	.1	Tr	.05	.6	1.93
" " 131-134	" "	" "	.02	1.5	.05	1.3	1.1	6.64
" " 140-145	" "	" 23	.01	2.4	.2	.3	1.0	3.92
" " 145-150	" "	" "	Tr	.3	Tr	1.5	.5	2.84
" " 160-167	" "	Oct 7	.06	.1	.05	.2	1.1	3.18
" " 167-170	" "	" "	.01	.1	.2	2.7	2.2	4.53
" " 170-175	" "	" "	.12	2.1	.05	.3	1.0	3.26
From Cross Cut 12 feet	10 feet	Jan 16	.01	1.2	.5	1.2	1.5	5.60
" " 27 "	15 "	" 20	.05	.7	1.35	6.3	2.1	15.75
" " 31 "	4 1/2 feet	" 22	.06	1.0	.15	3.2	4.6	10.84
" " 31-37	" "	" 27	.1	1.6	.8	2.5	1.6	10.70
" " 37-41	" "	" "	.06	2.1	.6	.5	1.2	6.10
" " 47	2 1/2 "	" "	.02	2.6	.4	.6	.4	4.15
" " 51	4 "	" "	.12	3.7	.5	6.1	1.8	15.15
" " 51-54	2 "	" 29	.11	5.5	1.75	4.2	5.4	21.75
" " 54-58	3 1/2 "	" 31	.03	3.3	.2	1.8	2.9	7.95
" " 58-61	3 "	" "	.11	4.8	.1	2.6	4.5	16.05
" " 61-65	4 "	" "	.01	1.4	.2	1.1	1.4	4.50
" " 65-69	4 "	Feb 3	.02	2.2	.8	3.7	1.8	9.45
" " 69-73	4 1/2 "	" "	.04	6.1	2.1	2.4	2.1	16.20
" " 73-77	5 1/2 "	" "	.05	12.1	4.25	7.1	4.1	37.75
" " 77-80	5 "	" 8	.02	3.9	.12	3.5	2.6	9.56
" " 80-83	" "	" "	.02	2.8	.1	5.8	3.9	12.25
" " 83-86	5 "	" "	.01	2.9	.15	2.1	2.1	6.73
" " 86-93	5 1/2 "	" "	.02	3.1	.1	2.1	2.1	6.50
Face 93	" "	" "	.02	4.6	.1	2.6	1.6	7.66
" " 93-97	5 "	" 10	.04	2.3	.05	1.6	2.0	6.18
" " 97-101	4 "	" "	.02	1.4	.05	.8	1.8	3.98
" " 101-115	5 "	" 12	.04	2.9	.1	5.0	2.6	14.10
" " 105-112	5 "	" "	.05	2.5	.1	1.8	2.6	12.23
" " 119-124	5 "	" 15	.01	2.1	.3	.8	2.1	5.30
From Cross Cut 10 feet	5 "	Jan 14	.01	.2	.1	.1	1.1	4.54
" " 15 "	3 1/2 "	" 16	.05	1.3	.85	.8	1.1	6.70
" " 15-22	3 1/2 "	" 20	.02	1.1	.85	2.2	1.2	5.23
" " 26-30	4 "	" "	.02	1.2	1.1	4.2	2.1	14.30
" " 30-35	5 "	" "	.04	1.2	.25	1.5	2.6	8.15
" " 35-39	" "	" "	.03	1.0	.25	1.1	1.4	1.75
" " 42	5 1/2 "	" "	.05	2.1	.1	.5	1.5	4.06
" " 42-48	5 "	" 27	.02	.2	.4	.1	.2	2.25
" " 48-52	5 "	" "	.04	.3	.3	.2	2.1	4.35

West Drift 300 Ft Level

West Drift 400 Ft Level