

WEST

EAST

C.O.D. SHAFT

OLD C.O.D. SHAFT
CAVED & INACCESSIBLE

C.O.D. MINE UNDERGROUND WEST ZONES

Section of Underground	Avg. Width (ft.)	Avg. Au (oz.)	Avg. Ag (oz.)	# of Samp.	Cum. Width (ft.)	Cum. Au (oz.)	Cum. Ag (oz.)	Cum. Ft. Assay Au	Cum. Ft. Assay Ag
Area A	4.182	0.295	28.576	11	4.182	1.217	313.33	1312.18	942.86
Area B	6.239	0.295	8.396	8	10.421	112.33	13.03	942.86	942.86
Area C	6.239	0.295	8.396	8	16.660	112.33	13.03	942.86	942.86
Area D	5.372	0.476	8.340	10	22.032	54.8	96.7	26.11	806.45
Area E	5.372	0.476	8.340	10	27.404	54.8	96.7	26.11	806.45
Area F	5.108	0.291	10.710	21	32.512	91.8	199.2	26.65	2133.42
Area G	4.900	0.108	13.147	15	37.412	46.5	117.6	4.82	1845.11
Area H	4.820	0.291	11.621	21	42.232	91.5	168.7	26.65	1960.51
Area I	4.278	0.108	16.913	12	46.510	44.5	77	4.82	1302.32
Area JA	4.444	0.291	2.527	9	50.954	40	40	101.08	101.08
Area CA	4.363	0.189	3.348	23	55.317	86.7	104.7	14.63	350.53
Area DA	4.363	0.189	3.348	23	59.680	86.7	104.7	14.63	350.53
Area EA	4.414	0.291	6.897	7	64.094	30.9	30.9	215.12	215.12
Area FA	4.414	0.291	6.897	7	68.508	30.9	30.9	215.12	215.12
Area GA	3.881	0.184	4.005	21	72.389	81.5	81.5	14.99	326.37
Area HA	4.845	0.025	5.774	2	77.234	9.8	53.3	0.25	301.782
Area IA	3.881	0.184	4.005	21	81.270	81.5	81.5	14.99	326.37
Area JA	4.845	0.025	5.774	2	86.115	9.8	53.3	0.25	307.76

C.O.D. MINE UNDERGROUND EAST ZONES

Section of Underground	Avg. Width (ft.)	Avg. Au (oz.)	Avg. Ag (oz.)	# of Samp.	Cum. Width (ft.)	Cum. Au (oz.)	Cum. Ag (oz.)	Cum. Ft. Assay Au	Cum. Ft. Assay Ag	
Area K	4.931	0.163	18.505	2	4.931	0.809	1.47	1460.06	1460.06	
Area L	5.102	0.257	20.369	15	10.033	78.9	20.01	5534.49	5534.49	
Area M	4.931	0.163	18.505	2	14.964	1.672	3.94	1460.06	1460.06	
Area N	4.947	0.197	22.588	8	19.911	35.5	178.1	6.99	4022.95	
Area O	5.525	0.182	13.330	8	25.436	16	22	38.4	4.22	1222.56
Area P	4.963	0.194	20.290	10	30.399	44.4	94.3	8.61	1914.06	
Area Q	5.139	0.190	17.689	15	35.538	67.4	143.9	12.83	2545.46	
Area RA	3.147	0.291	3.910	17	52.685	53.5	53.5	209.17	209.17	
Area SA	4.500	0.291	4.500	1	57.185	4.5	4.5	209.17	209.17	
Area TA	6.367	0.235	2.335	3	63.552	19.1	19.1	40.79	40.79	
Area UA	6.075	0.382	3.842	4	69.627	24.3	24.3	93.36	93.36	
Area VA	6.075	0.382	3.842	4	75.702	24.3	24.3	93.36	93.36	
Area WA	5.667	0.192	12.003	2	81.369	18.5	17	2021	204.06	

SAMPLE # & ASSAYS

ASSAY #	Au (oz.)	Ag (oz.)	WIDTH (feet)	ASSAY #	Au (oz.)	Ag (oz.)	WIDTH (feet)		
1	4.5	4	97	0.01	0.25	3.5	192		
2	2.35	5	98	0.24	18.04	3.5	193		
3	0.98	4.5	99	0.45	7	1.27	6.9	194	
4	4.48	4.5	100	0.07	7.46	1.01	6.9	195	
5	0.49	5	101	0.08	22.46	4	196		
6	1.18	4	102	0.07	7.46	1.01	6.9	197	
7	2.29	4.5	103	1.16	4.3	198	16.37	1.9	
8	8.36	4	104	0.14	42.07	4.7	200	17.43	1
9	1.18	4	105	0.26	54.48	2.5	201	0.98	9
10	21.6	5	106	0.26	54.48	2.5	202	14.24	2.4
11	0.07	0.84	107	0.07	0.84	1.01	6.9	199	0.7
12	0.8	4	108	0.21	52.97	4	203	0.17	5.7
13	43.57	4.5	109	24.25	5	204	5.32	7.8	205
14	1.18	4	110	0.16	15.88	4	206	9.85	4.9
15	35.92	4	111	0.08	8.12	6	206	19.1	2.4
16	16.68	3.5	112	0.07	7.46	1.01	6.9	3.78	5
17	10	4	113	0.07	7.46	1.01	6.9	77.69	6.1
18	20.34	4	114	0.07	7.46	1.01	6.9	17.96	6
19	30.98	4	115	0.07	7.46	1.01	6.9	16.35	5.4
20	5.12	5	116	0.07	7.46	1.01	6.9	19.96	5.5
21	26.61	4	117	0.07	7.46	1.01	6.9	19.08	6.5
22	2.08	3.5	118	0.7	8.6	5	212	3.59	5.4
23	8.27	4.3	119	0.14	9.14	6	214	38.97	4.8
24	7.36	3	120	0.26	2.56	6.5	215	1.69	5.9
25	1.19	5.1	121	0.04	10.1	5	216	32.72	6.1
26	1.79	5	122	0.78	13.08	5	217	5.44	6.2
27	1.19	4	123	0.07	7.46	1.01	6.9	12.3	5
28	7	5	124	0.26	14.68	4	219	20.62	5.3
29	0.9	5.1	125	0.26	5.02	5	220	8.99	6.9
30	0.9	6	126	0.26	5.02	5	221	8.99	6.9
31	0.9	7	127	0.3	4.62	4	222	18.93	6.5
32	0.2	5	128	0.46	2.24	5.6	223	22.46	7.1
33	0.9	6	129	0.46	24.08	6	224	28.16	5
34	6.3	4.5	130	0.69	40.69	6.3	225	19.97	6.2
35	0.4	4.04	131	0.26	4.98	5	226	28.16	5
36	3.4	2	132	0.19	17.85	5	227	10.1	5.2
37	3.4	2	133	0.12	4.24	5	228	30.94	4.7
38	0.45	6.7	134	0.26	4.98	5	229	1.88	5.9
39	1.29	6	135	0.32	9.68	4	230	16.4	4.6
40	5.565	5.5	136	0.4	6.04	5	231	12.16	3
41	0.4	5.5	137	0.4	6.04	5	232	79.45	3
42	0.4	5.5	138	0.76	34.46	6	233	3.69	4.5
43	0.4	5.5	139	0.4	6.04	5	234	5.84	6
44	0.45	6.05	140	0.26	19.06	6	235	6.99	6
45	0.45	6.05	141	0.26	19.06	6	236	0.32	9.3
46	0.42	6.4	142	0.12	4.46	3	237	1.2	5.4
47	1.1	4.44	143	0.04	4.48	3	238	78.42	2.2
48	13.48	6.3	144	0.12	5.46	3	239	4.19	6.8
49	0.2	6.92	145	0.12	5.46	3	240	12.78	6.3
50	0.45	13.16	146	0.12	1.98	4	241	29.11	6
51	3.14	7.3	147	0.44	22.44	2.5	242	1.38	6
52	0.95	7.4	148	0.12	4.46	3	243	21.26	1.6
53	18.26	7.2	149	0.08	2.26	3	244	0.84	6.3
54	3.34	7.1	150	0.07	7.72	5	245	0.86	2.2
55	1.5	2.56	151	0.16	5.2	3	246	5.49	5.6
56	7.94	7	152	0.04	8.04	4.8	247	2.76	5.4
57	1.98	6.3	153	0.33	5.1	3.3	248	7.7	8
58	0.25	4.44	154	0.29	8.2	4	249	2.28	4.7
59	0.2	4.6	155	0.2	4	8	250	0.89	6.2
60	14.36	5.3	156	0.4	6.4	4	251	0.48	5.9
61	14.62	7.3	157	0.2	5	3.3	252	8.02	7.5
62	5.14	6	158	0.21	6.3	3.3	253	5.2	5.2
63	5.14	6	159	0.12	3.75	4	254	0.6	4.6
64	1.88	4.8	160	0.07	1.85	4.5	255	0.36	21.5
65	0.14	1.4	161	0.14	1.4	4	256	3.38	21.5
66	3.1	7.1	162	0.2	2.2	3.8	257	22.08	5.3
67	0.24	7.08	163	0.16	2.6	3	258	0.16	28.4
68	0.2	4.6	164	0.28	4.72	4.3	259	18.96	6.4
69	0.2	4.3	165	0.24	2.64	4.1	260	0.06	15.4
70	0.16	2.2	166	0.2	3.06	4.5	261	16.49	6.5
71	0.11	5.95	167	0.3	0.67	5	262	0.12	23.08
72	0.26	4.3	168	0.08	0.08	5	263	15.14	6
73	0.14	4.22	169	0.08	0.07	6	264	15.9	6
74	0.2	0.96	170	0.02	0.38	6.5	265	15.26	5
75	0.85	2.96	171	0.04	0.3	6.5	266	10.22	5
76	0.06	0.6	172	0.12	0.1	1.5	267	0.6	3.3
77	0.03	1.11	173	0.1	0.740	2	268	27.14	6.4
78	0.04	2.16	174	0.11	2.99	2	269	0.6	3.3
79	0.1	0.65	175	0.08	4.23	6	270	15.6	6.9
80	0.03	4.35	176	0.12	4.81	6	271	0.32	7.44
81	0.28	3.78	177	0.09	8.4	8	272	0.08	4.7
82	0.08	2.1	178	0.08	3	3	273	0.04	9.92
83	1.51	2.8	179	0.1	4.1	4.1	274	42.82	6.5
84	1.7	4.3	180	0.1	4.1	4.1	275	0.21	45.65
85	3.9	5.8	181	0.08	3	2.96	276	11.78	6.5
86	1.28	4.9	182	0.08	4.8	4.8	277	0.06	12.02
87	2.46	4.3	183	0.19	4.1	2.78	278	0.22	3.14
88	1.04	7	184	0.19	4.3	2.79	279	0.01	0.72
89	6.14	1.8	185	0.36	5.7	2.09	280	49.68	2
90	0.03	8.25	186	0.51	4.5	2.81	281	0.18	28.6
91	0.02	9.54	187	0.16	3.4	0.82	282	1.89	5.5
92	2.46	4.3	188	0.26	6.5	2.82	283	0.06	93.44
93	6.94	4.2	189	0.08	5.9	2.84	284	0.49	5.9
94	0.1	5.9	190	0.34	0.7	2.85	285	0.38	35.06
95	0.04	0.6	191	0.08	4.6	2.86	286	0.02	1.42
96	0.4	7.3	192	0.08	4.6	2.86	287	0.02	1.42

SAMPLE # & ASSAYS

ASSAY #	Au (oz.)	Ag (oz.)	WIDTH (feet)	ASSAY #	Au (oz.)	Ag (oz.)	WIDTH (feet)
1001	0.208	22.35	6.5	1017	0.132	23.09	6.5
1002	0.626	17.26	7.2	1018	0.84	3.57	6.5
1003	0.702	18.04	2	1019	0.148	99.81	6.5
1004	0.114						