

SAMPLE	WIDTH	AU	AG	CU	PB	ZN
CA-1	2.25	.002	0.46		0.39	0.76
CA-2	2.70	.006	0.29		0.16	0.19
CA-3	1.70	.006	0.26		0.30	0.26
CA-4	2.90	.016	0.56		0.09	0.42
CA-5	2.00	.009	1.21		1.67	3.18
CA-6	2.50	.011	0.61		0.68	2.36
CA-7	5.10	.026	5.76		1.14	2.85
CA-8	5.50	.008	1.31		0.25	0.66
CA-9	3.70	.016	0.81		1.85	0.78
CA-10	3.30	.021	0.39		2.27	8.38
CA-11	1.90	.009	0.40		6.20	9.90
CA-12	3.80	.034	1.64		1.63	1.83
CA-13	1.80	.031	2.02		3.70	3.16
CA-14	3.50	.026	1.02		0.55	0.38
CA-15	2.80	.016	0.20		1.03	1.85
CA-16	2.10	.016	2.39		0.89	0.97
CA-17	2.80	.023	1.47		2.14	4.55
CA-18	0.75	.167	2.05		3.08	3.25
CA-19	2.00	.032	0.66		1.53	1.97
CA-20	1.50	.038	1.92		0.06	0.17
CA-21	1.90	.065	2.83		1.32	2.19
CA-22	2.70	.009	0.50		0.89	2.47
CA-23	1.40	.001	0.08		3.09	4.80
CA-24	3.30	.011	1.94		1.05	3.95
CA-25	2.30	.026	5.08		1.26	5.20
CA-26	2.10	.004	1.15		2.31	8.45
CA-27	1.60	.002	1.64		1.62	2.11
CA-30	1.80	.187	2.23		1.86	6.60
CA-31	2.20	.006	2.00		0.67	3.35
CA-32	1.40	.004	0.38		0.82	2.04
CA-33	1.40	.167	1.91		1.50	2.67

HAULAGE LEVEL

SAMPLE	WIDTH	AU	AG	CU	PB	ZN
CM-1	2.10	.029	1.94		0.06	0.07
CM-2	1.80	.031	4.52		0.02	0.04
CM-3	1.70	.034	2.58		3.18	0.18
CM-4	2.00	.008	1.94		0.22	0.80
CM-5	2.70	.008	1.96		0.17	0.10
CM-6	3.60	.010	1.78		5.05	7.00
CM-7	3.30	.006	0.27		0.86	1.42
CM-8	2.35	.019	1.96		0.24	2.80
CM-9	4.20	.060	0.39		0.55	3.04
CM-10	3.80	.192	3.18		0.98	2.44
CM-13	3.80	.002	0.89		0.51	1.04
CM-14	2.10	.006	0.31		2.35	2.89
CM-16	2.50	.004	1.73		0.49	1.12
CM-18	1.20	.005	1.30		0.02	0.28
CM-17	0.80	.004	0.55		0.03	0.23
CM-20	3.20	.031	3.91		2.25	5.00
CM-21	3.90	.005	1.61		3.40	4.40
CM-22	2.40	.049	3.60		3.00	4.85

2nd LEVEL

SAMPLE	WIDTH	AU	AG	CU	PB	ZN
CT-1	1.70	.016	2.03		0.42	1.28
CT-2	1.80	.028	8.92		2.12	4.80
CT-3	2.30	.016	3.37		4.10	9.00
CT-4	2.00	.008	0.59		0.18	0.40
CT-6	1.50	.002	0.56		0.03	0.03
CT-6	1.60	.023	0.84		0.05	0.04
CT-7	1.20	.001	0.65		0.05	0.02
CT-8	1.80	.031	2.05		0.19	1.30
CT-9	2.90	.047	3.15		2.35	4.95
CT-10	2.10	.016	2.98		0.32	6.00
CT-11	2.00	.026	2.84		0.34	3.75
CT-12	3.00	.050	3.83		0.53	4.85
CT-13	2.00	.059	4.11		0.26	1.57
CT-14	2.80	.010	2.45		0.17	0.67
CT-15	3.20	.005	1.34		0.06	0.70
CT-16	2.80	.281	1.94		1.28	4.10
CT-17	4.40	.009	5.83		9.90	4.48
CT-18	2.40	.011	7.02		0.12	2.00
CT-19	2.70	.027	1.11		0.05	1.10
CT-20	3.10	.002	0.16		1.07	1.88
CT-21	1.70	.004	0.56		0.30	2.46
CT-22	1.60	.005	0.61		2.40	7.10
CT-23	4.00	.011	1.32		2.40	7.10


1st LEVEL

TOTAL WEIGHTED AVERAGE ASSAY					
SAMPLE	AU	AG	CU	PB	ZN
.034	3.48		.98		1.76

TOTAL TONS

Legend	
CA - MAIN ADIT	HAULAGE LEVEL
CM - SUB LEVEL	2nd LEVEL
CT - TOP ADIT	1st LEVEL

COPPER AGE MINE
 WALLAPAI MING. DIST.
 SEC. II - T23N-R18W
 MOHAVE COUNTY MINE STUDY
 OCT. 1976
 Scale 1" = 100'



ADPWR 08119-003