


IRON CAP MINE
ASSAYS IN LOWER TUNNEL & RAISES

Sample No.	Per Cent Zn	Per Cent Pb	Per Cent Cu	Sample No.	Per Cent Zn	Per Cent Pb	Per Cent Cu
1	15.7	3.45	.32	24	21.2	9.48	.23
2F	14.9	3.71	.38	25	17.6	8.54	.08
2H	14.1	4.64	.13	26	14.2	5.70	.45
3	18.2	10.22	.09	27	15.2	2.08	.19
4	7.6	1.96	.06	28	13.2	4.68	.07
5	5.7	4.94	.06	29	15.1	8.58	.27
6	12.5	8.72	.10	30	14.2	3.00	.04
7	12.8	4.40	.05	31	13.2	5.66	.07
8F	25.9	7.56	.07	32	14.4	2.26	.05
8H	31.8	6.90	.05	33	19.1	2.30	.08
9	28.8	9.86	.05	34	19.2	9.48	.31
10	24.1	10.36	.04	35	3.2	.90	.22
11	22.3	11.97	.28	36	22.3	8.04	.08
12	19.2	3.30	.19	37	7.1	4.94	.10
13	10.5	4.86	.40	38	6.2	6.03	.08
14	10.7	5.60	.05	39	19.8	4.60	.06
15	7.2	3.10	.05	40	16.1	10.20	.56
16	7.7	15.26	.05	41	12.2	4.24	.06
17	19.4	3.52	.60	42	13.6	4.64	.56
18	14.0	7.10	.23	43	12.1	3.00	.25
19	14.7	0.68	.40	44	8.7	1.04	.13
20	19.9	11.18	.40	45	3.9	1.90	.09
21	17.2	7.03	.13	46	7.4	1.82	.29
22	19.4	10.48	.33	47	14.6	1.02	.30
23	23.6	7.74	.23				

ASSAYS IN UPPER TUNNEL

48	6.2	2.14	.07	16"	56	12.6	5.94	.13	5'
49	11.4	3.60	.08	2'6"	57	10.1	6.98	1.68	4'6"
50	16.6	6.10	.12	4'6"	57-A	5.8	7.87	.15	5'6"
51	7.0	3.70	.17	4'	58	8.4	11.96	.46	5'6"
52	7.6	8.30	.27	4'	59	5.8	2.46	1.80	4'6"
53	6.6	2.50	.24	4'	59-A	3.2	15.34	.25	5'6"
54	4.8	2.88	.07	8'	60	6.6	4.54	.71	5'6"
54-A	8.8	4.22	.20	4'	61	5.6	8.50	.31	10'
55	9.8	6.02	.75	5'6"	62	5.0	1.10	.25	5'
					63	3.8	0.44	.75	5'

ARVIAPA
IRON CAP MINE
SCALE 1" = 20'
Sampling in plane of vein
Vein width = 8 ft plus
Hanging Wall Clean and Firm
Footwall not defined Contains Ore
January, 1942
Survey & Sampling by A.L.K.
Drawing by A.L.K.
Tracing by J.F.D.



See 270 letter Nov 10, 1941