

FIG. 1 PLAN




FIG. 3 SECTION CD




FIG. 2 SECTION AB

SAMPLES			
NO.	WIDTH	CU %	ZN %
156R	0.8'	2.80	15.81
40T	1.3'	—	35.90
41T	1.0'	—	33.70
157R	3.0'	4.33	20.22
158R	3.0'	5.24	28.80
159R	1.7'	5.84	30.00
42T	1.6'	—	30.80
160R	4.0'	7.90	37.78
43T	3.6'	5.84	29.40
161R	5.5'	5.01	25.11
162R	3.0'	6.93	24.09
44T	1.4'	5.02	40.70
163R	1.5'	3.95	34.63
164R	4.0'	4.11	36.20
165R	5.6'	7.15	28.15
166R	5.0'	5.66	16.92
45T	5.0'	4.31	40.20
167R	4.2'	3.97	11.01
168R	5.0'	5.90	16.84
173R	8.5'	2.33	20.97
174R	6.0'	7.91	18.88
175R	5.0'	6.60	26.83
48T	5.4'	11.30	32.40
B-4	4.0'	5.20	31.30
47T	1.3'	10.14	—
B 3	1.0'	16.01	1.10
46T	1.2'	2.65	5.40
D 11	3.0'	7.60	3.00
D 12	8.0'	3.30	1.20
D —	0.9'	4.20	27.60
49T	0.3'	4.40	38.20
169R	4.3'	3.62	2.25
DB-3	4.5'	8.28	2.40
DB-4	4.5'	4.24	3.50
170R	5.0'	4.91	13.66
171R	3.5'	9.88	16.24
172R	5.7'	8.20	4.95
DB-5	2.5'	9.68	31.30
DB-6	5.5'	9.30	20.50
DB-7	5.0'	9.42	22.70
DB-8	5.5'	12.94	17.80
DB-1	3.5'	5.50	14.10
176R	5.5'	6.85	35.67
177R	4.0'	6.75	40.20

SAMPLES						
NO	WIDTH	AU OZS	AG OZS	CU %	ZN %	
4283	3.0'	0.030	0.55	1.78	4.0	
4284	3.0'	0.005	0.20	0.25	0.1	
4285	3.75'	0.005	1.05	7.63	32.4	
4286	1.6'	TR	0.75	4.44	36.4	
4287	6.0'	TR	0.50	3.10	26.0	
4288	5.5'	TR	1.05	8.13	28.4	
4289	5.5'	0.010	1.70	7.30	15.0	
4290	5.0'	TR	0.95	4.54	10.6	
4291	3.0'	TR	0.00	0.36	0.4	
4292	2.0'	TR	0.85	9.76	24.6	
4293	2.3'	TR	0.80	8.34	18.2	
4294	2.5'	TR	0.30	2.86	0.2	
4295	2.0'	0.005	0.80	4.25	0.2	
4296	3.9'	TR	0.55	5.62	0.2	
4297	3.8'	TR	1.05	6.15	1.0	
4298	2.5'	TR	0.40	3.97	0.5	
4390	4.0'	TR	1.40	8.72	0.1	
4391	4.0'	0.005	0.65	4.02	0.6	
4392	10.0'	TR	1.40	1.59	12.8	
4393	10.0'	TR	0.90	4.52	1.8	
4394	10.0'	TR	0.25	3.00	4.1	
4395	7.0'	TR	0.20	3.38	0.1	
4396	10.0'	TR	1.05	5.83	11.9	
4397	6.0'	TR	0.40	2.28	0.1	

--- UPPER WORKINGS

— LOWER WORKINGS


156R SAMPLES BY RASOR

40T SAMPLES BY TAVOTE

DB-3 SAMPLES BY DYE & BATHRICK

4283 SAMPLES BY U.S.B.M.

BRUNTON-PACE SURVEY



COPPER WORLD MINE, MOHAVE COUNTY, ARIZONA.