


SAMPLE DATA - 100-FT. LEVEL

SAMP No.	WIDTH FT.	OZ./TON		Pb-%
		Au	Ag	
1	3.5	0.09	4.31	12.52
2	4.0	.07	4.99	1.50
3	6.0	.03	4.97	4.41
4	5.0	Tr	3.80	1.00
5	5.0	.04	10.96	5.11
6	4.0	.02	4.68	0.30
7	5.0	.03	7.17	1.20
8	5.0	.05	6.25	1.30
9	7.0	.09	10.31	0.10
10	6.0	.01	5.19	.10
11	3.5	.01	5.19	3.01
12	3.0	.03	2.17	0.10
13	1.1	.01	9.79	12.23
Weighted Av. 1-13		0.03	6.25	2.51
Composite 1-12		0.04	5.56	2.81
		Cu	1.53	
		Zn	9.64	

Weighted Av. 1-13 0.03 6.25 2.51
 Composite 1-12 0.04 5.56 2.81

Cu 1.53
 Zn 9.64

100 FT. LEVEL - SHELDON VEIN



Sketch by Lawrence B. Wright
 Sampling by same
 Assays by Abbot A. Hanks, Inc.
 Dec. 1940

**PACE-COMPASS SURVEY
 160-FT. LEVEL - SHELDON VEIN**




Assays by A.C. Nedeker-1929
 Location of samples only
 approximate - taken from
 longitudinal section

SAMPLE DATA - 160-FT. LEVEL

SAMP No.	WIDTH FT.	OZ./TON		PERCENT		
		Au	Ag	Pb	Cu	Zn
1	3.5	Tr	1.5	0.12	0.20	0.50
2	2.0	"	1.2	Tr	0.75	-
3	2.0	"	1.5	"	.75	-
4	2.0	"	1.0	-	.75	-
5	1.5	"	1.2	-	.75	-
6	1.5	"	1.0	1.5	1.5	-
7	1.5	"	0.5	1.0	1.2	-
8	3.0	"	1.1	0.75	1.2	-
9	1.2	0.01	3.1	2.5	4.0	1.2
10	1.5	.02	3.0	2.2	1.8	0.4
11	1.7	.01	2.5	2.5	1.9	.95
12	1.5	.02	13.8	12.1	4.1	.50
13	3.0	.01	2.0	1.1	1.5	-

Raise
 Slope



463.2/15/133 Rocky Mtn Mines

1-B-5

1-B-5

Fig. 4- Plan and section of mine workings on Sheldon Vein, Rocky Mountain Mines, Ariz.

SEAWER 18