


SAMPLES BY HARRISON SCHMITT

SAMPLE NO.	WIDTH FT.	% Zn	% Pb	OZ. Au	OZ. Ag	Zn OXIDE
①	3.0	26.5	TR.	TR.	.64	4.05
②	4.0	5.0	TR.	TR.	.48	1.68
③	7.0	14.5	TR.	TR.	1.36	1.88
④	7.0	4.5	TR.	TR.	1.24	.75



DMEA 2711 IDME 478

PROGRESS MAP SEPT. 1953

IRENE MINE
800 FT. LEVEL

GLOBE - MIAMI COPPER ZINC CORPORATION
GLOBE, ARIZONA