


Examined Sept., 1943 — Workings accessible



BUREAU OF MINES SAMPLES						
NO.	WID.	% PB	% ZN	% CU	OZ. AU	OZ. AG
2851	2.5'	5.2	11.0	.44	.005	11.05
2852	2.0'	5.3	25.1	.02	.005	9.25
2853	2.5'	0.1	2.8	.02	TR	1.20
2854	1.5'	2.1	7.1	.03	TR	2.30
2855	1.3'	0.1	7.4	.08	TR	1.20
2856	1.0'	11.0	10.0	.30	.005	12.45
2857	1.5'	2.1	0.5	.02	TR	1.65
2858	1.2'	0.1	15.7	.05	TR	1.50
2859	4.0'	2.4	6.5	.04	TR	2.25
2860	2.5'	0.1	3.5	.02	TR	0.40
2861	1.6'	0.1	6.5	.05	TR	0.50
2862	1.8'	0.5	5.4	.02	TR	0.70
2863	2.2'	0.1	3.2	.05	TR	0.25
2864	1.1'	0.2	1.6	.03	TR	0.10
2865	1.8'	0.1	2.5	.03	TR	0.20
2866	1.7'	0.2	2.2	.09	TR	0.25
2867	1.9'	1.1	2.6	.08	TR	0.30
2868	2.3'	0.2	0.1	.09	TR	0.20
2869	3.3'	5.8	8.4	.71	TR	7.80
2870	2.3'	8.6	5.4	.47	TR	13.30

BUREAU OF MINES SAMPLES						
NO.	WID.	% PB	% ZN	% CU	OZ. AU	OZ. AG
2871	1.8'	0.1	15.6	.21	TR	1.40
2872	2.5'	1.5	10.8	.61	TR	3.75
2873	2.0'	0.3	13.6	.14	TR	0.40
2874	0.3'	1.3	19.0	.11	TR	4.25
2884	2.4'	5.2	7.8	.55	.020	4.95
2885	2.0'	1.5	14.4	.04	TR	1.85
2886	1.8'	0.1	8.3	.02	TR	1.00
2887	1.0'	6.3	8.6	.16	TR	3.30
2888	0.8'	6.9	6.8	.28	.005	7.40
2889	4.0'	5.9	8.9	1.10	.005	11.35
2890	2.0'	0.2	3.7	.02	TR	0.60
2891	2.3'	0.1	5.6	.02	TR	0.20
2892	2.0'	0.1	4.3	.03	TR	0.20
2893	1.1'	0.1	0.6	.02	TR	0.10
2894	3.0'	0.1	5.6	.06	TR	0.25
2895	2.0'	0.1	12.0	.02	TR	0.95
2896	3.0'	0.1	0.6	.04	TR	2.00
2896	from upper tunnel (NO. 1)					

FIG. 19-SAMPLE PLAT SHOWING ORE RESERVES, EUREKA MINE
After map by F. D. Shuck

Concord Sect