


- Sample by U.S. Bureau of Mines
- / Sample by Producers Mine

No.	Ft. Wid.	% Pb	% Zn	oz. Au	oz. Ag
2806	3.0	1.56	1.20	.02	2.70
2807	4.0	Tr	0.60	.005	Tr
2808	4.0	0.25	1.15	.01	.90
2809	5.0	3.54	0.80	.01	.90
2810	5.0	2.25	1.30	.01	3.90
2811	8.0	6.00	1.40	.03	1.30
2812	5.0	3.65	1.30	.04	29.40
2813	6.0	2.10	0.80	.01	.70
2815	4.5	1.30	1.00	.005	.50
2816	3.0	10.30	1.80	.01	2.40
2817	4.0	3.55	2.60	.02	1.00
2818	4.5	8.10	3.10	.01	1.50
2819	5.5	7.65	0.70	.01	1.30
2820		0.55	0.50	.005	.40
2821	4.5	Tr	1.00	.02	.30
2822	4.0	5.50	4.25	.08	6.10
2823	3.5	11.35	2.90	.02	2.30
2824	5.5	7.80	1.90	.03	3.80



No.	Ft. Wid.	% Pb	% Zn	% Cu	oz. Au	oz. Ag
2844	4.0	1.4	0.2	.02	Tr	0.70
2845	5.0	0.2	0.2	.02	Tr	0.20
2846	5.3	2.4	0.2	.03	Tr	0.60
2847	5.1	2.8	0.1	.05	.005	1.40
2848	5.2	6.3	0.3	.05	Tr	1.35
2849	6.5	7.3	1.8	.04	.005	1.30
2850	6.5	0.1	0.4	.02	Tr	0.15

Stope accessible in September, 1943

**FIG 2 - STOPE ASSAY PLAN, JIM KANE, MINE, MOHAVE CO., ARIZ.**