


NORTHWEST

SOUTHEAST



EXAMINED SEPT., 1943 - WORKINGS SHOWN ACCESSIBLE

200 FOOT LEVEL

JUNE 7, 1943
SAMPLES BY J. B. TENNEY
AU 1.20 OZ., AG 8.87 OZ., PB 3.7%, ZN 3.6%
AU 0.38 OZ., AG 8.40 OZ., PB 12.5%, ZN 7.5%
AU 0.46 OZ., AG 7.50 OZ., PB 12.3%, ZN 5.1%


STOPE

SHAFT

300 FOOT LEVEL

VALUES			VALUES			VALUES		
NO.	WID.	AU & AG	NO.	WID.	AU & AG	NO.	WID.	AU & AG
413	12"	20.43	409	14"	45.31	405	18"	44.04
412	10"	17.35	408	12"	38.90	404	4"	19.13
411	11"	18.45	407	4"	14.72	403	8"	16.25
410	8"	17.58	406	16"	24.12	402	8"	10.85
								PB 1.9%, ZN 6.4%

FAULT



CAR - MAY 31, 1943
54.68 TONS - 400' LEVEL
AU 0.37 OZ., AG 6.05 OZ.
PB 7.7%, ZN 3.7%

400 FOOT LEVEL

99	6"	5.24	94	18"	81.61	88	24"	16.21
98	8"	14.34	93	8"	9.49	87	24"	7.98
97	18"	43.70	92	13"	29.87	86	12"	24.95
		PB 9.2%, ZN 11.7%	91	14"	31.04	85	14"	11.95
96	30"	34.96	90	12"	40.28	84	14"	16.81
95	24"	60.42	89	30"	20.09			
					PB 7.2%, ZN 9.1%			

CAR - APRIL 20, 1943
30 TONS - 400' LEVEL; 17.8 TONS - RAISE
AU 0.64 OZ., AG 7.30 OZ.
PB 5.35%, ZN 6.2%

500 FOOT LEVEL

79	12"	47.83	70	24"	19.41	63	5"	13.11
76	12"	20.49	69	16"	26.02	62	11"	9.90
75	22"	30.43	68	24"	15.27	61	7"	9.47
74	12"	13.16	67	12"	28.09	60	7"	4.55
73	12"	12.29	66	12"	12.59	59	6"	7.95
72	8"	18.75	65	8"	10.09	58	5"	7.12
71	17"	20.06	64	5"	9.69			
		PB 4.6%						

CAR - OCT. 31, 1942
15 TONS - 500' LEVEL; 20.25 TONS - RAISE
AU 0.505 OZ., AG 6.4 OZ.
PB 5.45%, ZN 4.2%

600 FOOT LEVEL

40	7"	9.27	33	6"	21.04	25	7"	11.52
39	6"	8.83	32	7"	20.11	23	3"	9.41
38	5"	10.39	31	14"	12.05	22	8"	16.77
37	1"	3.66	30	7"	34.00	21	4"	29.08
36	5"	4.49	29	8"	7.10	20	14"	3.37
35	4"	14.73	28	5"	12.55			
34	13"	8.21	26	7"	33.22			

BUREAU OF MINES SAMPLES						
NO.	WID.	% PB	% ZN	% CU	OZ. AU	OZ. AG
3279	0.7'	14.5	15.1	.22	.190	12.30
3280	1.3'	4.6	3.8	.39	.055	8.80
3281	0.7'	10.1	6.0	.29	.500	8.35
3282	1.0'	21.2	8.2	.24	.500	11.20
3283	0.25'	3.3	3.5	.09	.125	3.05
3284	0.3'	4.1	7.2	.28	.390	5.65
3285	0.3'	4.9	7.3	.12	.200	4.50
3286	0.8'	13.1	5.8	.31	.995	10.65
3287	2.1'	9.4	5.4	.45	.435	8.40
3288	1.3'	15.2	4.9	.38	.530	19.70
3289	1.0'	11.0	8.8	.28	1.230	16.55
3290	0.7'	6.1	5.0	.32	1.160	7.34

12" AU 0.34 OZ., AG 3.50 OZ.
(AU & AG - \$14.39)

700 FOOT LEVEL

MAIN CROSSCUT ENTRY

FIG. 2 - ASSAY PLAT, BRIGHTER DAYS MINE, MOHAVE COUNTY, ARIZONA

After map by Lewis A. Dunham, dated June, 1943