



ASSAYS - 160 FOOT LEVEL

NO.		WID.	OZ. AU	OZ. AG	% CU	% PB	% ZN
1	a	1.83'	TR	0.4	0.15	0.0	0.0
	b	2.0'	0.34	4.9	0.52	5.8	2.8
	c	3.75'	0.01	0.4	0.05	0.0	0.7
2	b	2.58'	0.96	2.0	0.20	1.6	2.8
	a	2.33'	0.04	2.4	0.31	1.9	3.7
	b	2.50'	0.58	7.0	0.77	7.6	14.7
4	a	2.92'	0.02	1.6	0.21	0.5	1.8
	b	1.92'	NO RETURNS				
	a	3.00'	0.02	6.6	1.91	0.0	1.0
	b	1.75'	0.05	0.7	0.21	0.0	1.5
	c	2.58'	0.65	2.3	0.31	2.0	6.67
6	a	1.33'	0.02	6.6	2.84	0.0	0.5
	b	1.08'	0.03	1.4	0.36	1.2	1.6
	c	2.67'	0.72	3.3	0.36	4.0	7.6
7	a	2.50'	0.02	4.9	0.93	0.0	0.0
	b	1.83'	0.12	2.3	0.36	0.0	2.6
	a	1.92'	0.01	5.4	0.80	0.0	0.2
	b	2.50'	0.197	5.5	1.44	0.0	4.0
9	a	2.00'	0.12	2.1	0.46	0.0	0.2
	b	2.75'	0.14	1.9	0.31	0.6	4.4
10	a	2.58'	0.12	1.3	0.21	0.4	1.5
	b	2.25'	0.08	5.9	0.69	7.2	5.1
	a	1.25'	0.23	6.1	0.87	8.2	7.3
	b	2.25'	0.24	4.5	0.67	5.5	8.7
13		1.08'	0.07	6.0	0.62	3.5	7.5
14		2.33'	0.20	4.2	0.51	4.3	6.3
15	a	2.83'	0.005	0.4	0.10	0.0	0.2
	b	1.17'	0.15	13.4	3.45	0.0	2.4
	c	1.08'	0.04	2.4	0.31	0.8	2.7
	d	1.08'	0.115	2.2	0.31	0.6	5.3
18	a-b	4.50'	0.21	5.2	0.51	5.2	5.7
	c	4.75'	0.02	1.3	0.31	0.0	0.2
	d	2.42'	0.15	3.5	0.46	3.9	6.0
19		2.08'	0.005	0.4	0.20	0.0	0.0
20		2.67'	0.02	0.6	0.10	0.0	1.0

ASSAYS - 160 FOOT LEVEL

NO.		WID.	OZ. AU	OZ. AG	% CU	% PB	% ZN
21	a	1.92'	0.10	6.5	0.87	0.5	2.7
	b	2.67'	0.02	2.7	0.56	1.0	1.5
	c	1.42'	0.44	4.1	0.41	3.3	4.2
	d	4.25'	0.03	1.5	0.36	0.0	1.3
	e	2.50'	0.07	2.1	0.36	1.4	10.3
22	a	1.50'	0.18	2.8	0.46	0.4	4.7
	b	2.00'	0.01	0.3	0.15	0.0	1.0
	c	1.67'	0.13	10.5	0.97	13.4	4.7
	d	2.50'	0.06	5.2	0.67	7.0	5.3
	e	3.00'	0.105	2.5	0.46	3.2	6.5
23	a	2.58'	0.45	3.1	0.46	1.8	4.6
	b	1.75'	0.16	4.7	0.46	5.6	9.0
	c	0.92'	0.08	4.5	0.67	4.6	9.5
24	a	2.08'	0.01	1.0	0.15	0.0	0.4
	b	2.58'	0.07	4.8	0.72	7.2	3.2
	c	1.50'	0.01	0.2	0.10	0.4	0.4
25	a	2.00'	0.05	1.7	0.26	2.3	2.0
	b	2.08'	0.35	4.4	0.56	6.8	3.9
	c	2.33'	0.47	11.5	0.72	22.1	4.0
26	a	2.92'	0.245	4.8	0.62	4.4	5.75
27	a	2.00'	0.03	2.4	0.31	2.8	4.2
	b	3.00'	TR	0.2	0.10	0.0	0.0
28	a	1.92'	0.03	1.2	0.21	0.0	1.2
	b	3.08'	TR	0.4	0.05	0.0	0.7
29	a	2.00'	0.08	1.8	0.25	2.1	3.7
	b	3.58'	TR	0.6	0.10	0.0	0.0
30	a	2.00'	0.20	3.6	0.36	2.0	4.4
	b	2.75'	0.02	3.4	0.77	0.8	1.5
31	a	0.75'	0.10	5.0	0.41	0.5	3.0
32	a	1.25'	0.03	3.3	0.46	2.3	2.2
	b	2.00'	0.02	0.5	0.05	0.0	1.0
	c	1.00'	0.03	2.1	0.31	1.6	7.3
	d	1.58'	TR	0.3	0.10	0.0	0.0
	e	1.17'	0.02	9.5	3.35	0.4	0.0
33	a	1.50'	0.15	2.7	0.36	1.4	9.0
	b	1.75'	0.02	1.4	0.15	0.5	1.9
	c	1.25'	0.02	44.8	7.94	0.0	0.0
34	a	1.67'	0.03	6.4	0.72	6.3	3.2
	b	2.33'	TR	0.2	0.10	0.0	0.0
	c	0.92'	0.09	3.6	0.41	3.1	7.8
	d	2.25'	0.01	0.8	0.10	0.0	1.5
	e	1.08'	0.06	17.3	3.04	1.1	0.3
35		1.17'	0.06	1.9	0.25	1.9	2.8
36		1.08'	0.07	1.9	0.31	2.6	2.3
37	a	2.50'	0.01	2.7	0.21	1.2	1.2
	b	1.83'	0.06	4.6	0.36	7.5	5.5
	c	2.50'	0.005	0.7	0.10	0.5	0.2
	d	1.92'	0.09	5.7	0.77	9.2	6.1
	e	1.58'	0.10	5.4	0.72	1.4	2.2

ASSAYS - 160 FOOT LEVEL

NO.		WID.	OZ. AU	OZ. AG	% CU	% PB	% ZN
38	a	3.08'	0.03	5.7	0.57	9.8	3.5
	b	2.92'	0.16	4.0	0.41	3.1	4.3
	c	1.58'	0.02	1.1	0.15	0.4	0.2
39	a	1.25'	0.05	6.0	0.72	9.1	6.7
	b	2.58'	0.03	1.0	0.15	1.3	0.8
	c	2.17'	0.02	1.8	0.21	3.8	2.0
40		2.42'	0.005	0.3	0.10	0.0	0.5
41		2.58'	0.6	3.0	0.36	3.8	3.0
42		2.08'	0.8	3.3	0.31	3.4	4.8
43	a	3.33'	0.005	0.6	0.15	0.0	0.3
	b	3.00'	0.07	0.9	0.15	1.0	2.7
44	a	2.33'	0.005	1.0	0.36	0.0	0.6
	b	2.50'	0.03	1.5	0.25	1.4	3.2
45		2.92'	0.11	4.0	3.7	0.31	2.7
46		2.67'	0.17	7.1	0.41	3.8	5.3
47		3.33'	0.005	0.9	0.46	0.0	0.5
48		4.00'	TR	0.3	0.7	0.0	0.3
49		3.00'	0.05	3.1	0.31	0.0	3.4
50		2.17'	0.02	1.9	0.15	0.0	1.4
51		2.08'	0.02	3.5	0.56	0.5	1.0
52		2.75'	0.01	2.4	0.20	3.7	3.0
53		2.67'	0.01	2.0	0.20	2.9	1.9
54	a	1.67'	0.11	9.0	0.52	17.7	3.8
	b	2.67'	0.03	0.7	0.10	0.0	0.7
	c	3.17'	0.07	6.3	0.82	6.6	7.5
55	a	1.42'	0.02	5.9	0.46	19.0	7.4
	b	1.50'	0.20	1.5	0.10	0.4	1.0
56	a	1.50'	0.04	3.6	0.31	3.5	1.9
	b	2.50'	0.02	1.8	0.15	1.6	3.0
	c	2.75'	0.025	5.1	0.41	3.9	8.9
	d	1.42'	0.07	4.0	0.33	7.8	11.4
	e	1.83'	0.245	1.5	0.10	0.0	0.0
57	a	5.25'	0.04	4.2	0.46	4.0	5.2
	b	2.33'	0.01	1.6	0.21	1.8	4.3
	c	2.67'	0.03	1.0	0.10	0.0	0.0
58		4.17'	0.02	3.5	0.46	3.2	5.0
59		2.58'	0.15	1.8	0.20	1.1	3.3
60	a	4.42'	0.04	5.2	0.62	6.6	9.4
	b	1.42'	0.01	1.0	0.15	1.2	2.9
	c	2.42'	0.04	2.1	0.46	0.6	1.2
	d	1.17'	0.01	1.0	0.26	0.9	0.8
61	a	5.08'	0.04	11.0	1.75	6.5	15.3
	b	2.17'	0.03	1.4	0.15	1.8	1.4
	c	3.58'	0.04	3.4	0.41	3.9	8.8
62	a	1.75'	0.01	1.0	0.15	1.2	1.5
	b	2.75'	0.01	2.5	0.31	1.0	5.0
63	a	3.67'	0.05	8.4	0.72	16.6	6.2
	b	2.08'	0.07	0.9	0.10	0.6	0.4
	c	1.67'	0.06	5.8	0.67	20.8	5.0
64	a	3.58'	0.07	6.7	0.67	12.2	6.2
	b	3.67'	0.05	5.0	0.62	5.3	13.5
65		5.42'	0.03	6.0	0.67	8.3	7.0
66		4.33'	0.03	8.7	1.44	3.8	11.3
67		1.83'	0.185	1.0	0.15	0.0	1.0
68	a	2.08'	TR	0.5	0.10	0.5	0.3
	b	2.92'	0.05	5.1	0.67	6.5	12.0
69		2.17'	0.01	3.9	0.72	4.4	4.5
70	a	1.92'	0.01	1.8	0.36	0.0	0.8
	b	1.08'	0.03	2.2	0.33	3.2	6.6
	c	1.75'	0.02	2.7	0.36	3.6	7.8

CHECK SAMPLES BY U.S. BUREAU OF MINES

2274	28 a	0.020	1.36	0.18	0.7	1.0
2275	28 b	0.10	0.30	0.03	0.3	0.8
2276	30 a	0.11	2.90	0.21	1.1	3.5
2277	30 b	0.025	1.25	0.07	0.3	0.7

FIG. 9-ELEVATION OF SUMMIT MINE & SAMPLE PLAT OF 160 FT. LEVEL