



No. WIDTH GOLD SILVER COPPER LEAD ZINC IRON

5/13/43	5.0'	0.02	2.16	0.30	0.25	1.50	4.50
241	5.0'	0.01	2.4	0.45	0.4	0.50	
239	1.5	0.005	0.25	0	0	0	
213	4.0	0.02	2.65	0.4	1.3	0.8	
212	4.0	0.04	3.10	0.77	0.7	0.8	
211	3.0	0.04	4.60	1.10	2.60	1.30	
210	3.0	0.04	7.20	1.00	4.40	1.50	
234	4.5	0.04	3.90	1.00	2.00	1.00	
209	3.0	0.04	10.85	2.77	9.40	1.40	

242	4.0	0.02	2.0	0.3	0	0.8	
240	5.0	0.09	4.35	0.5	0	1.0	
238	4.0	0.02	1.85	0.4	0.9	0.7	
237	4.0	0.04	5.00	0.45	1.50	0.4	
236	3.5	0.02	3.30	0.55	0.80	0.7	
235	3.0	0.04	4.60	1.40	1.20	0.6	

No. WIDTH GOLD SILVER COPPER LEAD ZINC IRON

207	5.0'	0.02	5.38	1.20	4.63	11.77	
206	5.0	0.02	6.23	0.80	2.20	9.76	
Av. 20'	4.25	0.028	5.44	1.51	2.61	7.17	AVERAGE
205	5.0	0.015	3.98	1.25	3.69	10.73	
204	5.0	0.03	4.17	1.30	3.15	10.24	
203	4.5	0.02	5.38	1.60	5.40	12.20	
202	3.5	0.02	5.98	1.40	7.20	9.27	
201	5.0	0.015	4.60	1.30	2.34	4.39	
200	4.5	0.02	8.00	1.00	5.44	9.27	
Av. 38'	4.5	0.021	5.54	1.31	5.08	11.80	AVERAGE
199	3.5	0.04	8.66	0.40	6.30	12.20	
198	5.0	0.03	8.17	0.75	3.38	7.90	
197	5.0	0.03	3.67	0.90	7.15	9.27	
196	5.0	0.02	4.48	0.75	1.62	4.88	
195	6.0	0.04	4.00	0.35	3.92	5.85	
Av. 75'	4.34	0.036	5.48	0.70	4.32	7.40	AVERAGE

No. WIDTH GOLD SILVER COPPER LEAD ZINC IRON

DH	3.5	0.03	4.10	1.10	1.10	3.10	7.60
217	1.5	0.07	4.40	1.79	3.50	5.70	

Av. 36'

6-7	4.75	0.03	4.4	1.42	2.46	4.32	Av.
No.	WIDTH	GOLD	SILVER	COPPER	LEAD	ZINC	IRON
192	5.0'	0.02	6.35	1.49	3.70	4.50	
193	6.75	0.01	4.00	0.88	2.20	4.00	
194	6.0	0.04	4.85	1.40	2.20	2.40	
216	6.5	0.01	1.15	0.32	0.10	0.50	
215	6.3	0.01	3.60	1.05	0.20	0.80	
191	6.0	0.06	2.00	0.47	6.70	13.70	
173	5.5	0.02	2.78	1.30	4.14	6.72	
No.	WIDTH	GOLD	SILVER	COPPER	LEAD	ZINC	IRON
179	6.5	0.04	4.80	1.50	2.50	8.30	
179	6.5	0.06	5.60	1.40	2.40	9.80	
189		0.02	2.78	1.00	2.47	5.86	
172	6.5	0.06	4.94	1.75	5.40	6.38	
188	9.0	0.03	6.75	1.60	3.65	5.29	
104	8.5	0.045	7.88	0.68	1.15	2.8	
103	5.5	0.04	6.6	1.5	1.8	2.0	

Av. 182

182	5.0'	0.03	4.77	1.15	3.60	7.32	
183	1.5	0.09	5.50	0.63	1.30	11.40	
184	4.5'	0.03	1.30	0.75	0.90	1.10	
107	6.5	0.04	5.0	1.20	0.90	0.50	8.0
108	2'	0.06	5.8	1.10	6.70	18.40	2.7
No.	WIDTH	GOLD	SILVER	COPPER	LEAD	ZINC	IRON
109	4.25	0.02	3.72	0.98	0.30	0.85	9.0
110	4.25	0.02	2.98	0.87	0.20	2.50	8.6
111	2'	0.16	7.52	0.29	5.50	17.2	5.0
190	6.0	0.04	2.55	0.51	1.40	2.00	
180	6.5	0.05	4.05	1.20		0.80	
Av. 56'	6.6	0.045	3.87	1.25	2.50	4.83	AVERAGE
177	7.0	0.04	4.00	1.40	1.10	4.50	
214	3.0	TR	0.75	0.35	0	0	

No. WIDTH GOLD SILVER COPPER LEAD ZINC IRON

5/13/43	1.5	0.06	4.84	1.20	1.30	25.20	2.55
6/29	2'		0.40	3.20	4.30	4.00	
7/29/42	HW.	0.02	10.08	0.24	8.50	10.00	3.50
7/29/42	FACE	0.09	8.50	3.10	5.00	6.40	5.20
102	5.5	0.10	6.6	1.5	2.1	2.2	6.3
Av. 40'	6.5	0.05	6.53	1.06	1.26	2.05	9.8
Sc. Dr.	6.5						

101

101	6.5'	0.02	4.62	0.82	0.3	1.0	11.3
FW		0.01	6.1	2.05	TR	0.2	2.24

4/12/43

4/12/43	6'	0.01	3.59	1.30	0.85	0.88	11.10
---------	----	------	------	------	------	------	-------

4/25/43

4/25/43	2'	0.08	2.28	0.40	1.30	1.20	5.80
---------	----	------	------	------	------	------	------

SOUTH PORTION TIGER MINE  
GOLDEN CROWN MINING COMPANY  
CROWN KING, ARIZONA. D.C. CORNER

**TIGER ASSAY MAP**  
SCALE 1" = 20'  
DATE - JUNE 15, 1943  
Copied from tracing by D.C. Corner