


ASSAYS

Location Number	Sample Number	Length Feet	% Copper	% Lead	% Zinc	Oz. Gold	Oz. Silver	Ass. % Zinc
1	5925	3.5	0.13	3.4	0.8	Tr.	0.70	0.8
2	5911	2.4	0.39	0.1	0.4	Tr.	0.60	0.4
3	5909	1.1	0.41	0.1	22.8	Tr.	1.15	18.7
	5997	1.2	0.13	0.1	15.0	Tr.	1.20	0.4
	5910	1.5	0.05	0.1	0.4	Tr.	0.20	0.4
4	5908	3.5	0.04	0.1	0.2	Tr.	—	0.2
5	5907-23	3.0	0.09	0.2	13.0	Tr.	0.35	13.0
	3900	4.0	0.08	0.2	0.8	0.005	—	0.8
6	5902	4.0	0.05	0.1	10.0	Tr.	0.35	—
	5905	3.7	0.08	0.1	14.8	Tr.	—	12.3
7	5906	4.5	0.21	0.1	20.4	Tr.	0.45	20.4
8	5901-24	7.6	0.04	0.2	5.1	Tr.	0.15	5.1
9	5903	1.2	0.07	0.1	0.2	Tr.	0.15	0.2
10	5912	4.0	0.11	0.2	0.2	Tr.	0.20	0.2
11	5913	3.2	0.11	0.1	0.4	Tr.	0.20	0.4
12	5914	0.5	2.49	5.8	8.0	0.005	5.75	8.0
13	3899	1.9	0.53	0.1	0.6	Tr.	0.35	0.6
14	5915	2.7	0.20	0.1	0.4	Tr.	0.20	0.4
15	5916	0.7	4.88	8.4	6.6	0.005	5.10	6.6
16	5917	1.1	0.08	0.1	0.2	Tr.	0.20	0.2
17	5918	grab	0.27	8.0	10.8	0.005	2.75	10.8
18	3898	1.2	1.10	10.0	13.2	Tr.	1.30	13.2
19	5919	1.3	2.28	0.5	26.4	Tr.	0.80	26.4
20	5904	1.4	3.37	1.0	20.0	0.010	1.80	10.4
	5920	4.0	1.24	0.6	7.0	Tr.	0.65	—
21	5921	4.2	0.48	1.0	5.8	0.010	0.90	5.8
22	5922	3.2	1.08	7.0	0.4	0.005	3.95	0.4



SAMPLE MAP OF MOHAWK-SILVER ZINC DEPOSIT, PIMA COUNTY
SCALE 1"=100'