

COPPER, GOLD, SILVER AND MOLYBDENUM RECOVERED
FROM MINES IN ARIZONA IN 1957 AND 1958

Source: U.S.B.M. Area Reports

	<u>1957</u>	<u>1958</u>
Tons copper concentrating and leaching ore mined . .	58,948,055	55,805,752
% Copper in ore (Estimated Assay) . .	0.910	0.933
Tons direct smelting copper ore	623,779	450,057
% Copper in ore (Estimated Assay) . .	5.380	5.932
TOTAL TONS COPPER ORE MINED	<u>59,571,834</u>	<u>56,255,809</u>
Pounds copper recovered from all copper ores mined .	<u>947,840,100</u>	<u>913,973,800</u>
Ounces gold recovered from all copper ores mined . .	123,375	114,262
Ounces silver recovered from all copper ores mined .	4,088,618	3,543,044
Pounds molybdenum recovered from all copper ores mined	2,385,000	2,320,000
Pounds copper recovered from mine waters	75,180,700	53,129,500
TOTAL POUNDS COPPER RECOVERED FROM ALL COPPER MINES .	<u>1,023,020,800</u>	<u>967,103,300</u>
TOTAL POUNDS COPPER RECOVERED FROM MINES OTHER THAN COPPER	8,687,200	4,574,700
GRAND TOTAL POUNDS COPPER RECOVERED FROM <u>ALL</u> ARIZONA MINES	<u>1,031,708,000</u>	<u>971,678,000</u>