



CONTACT INFORMATION  
Mining Records Curator  
Arizona Geological Survey  
416 W. Congress St., Suite 100  
Tucson, Arizona 85701  
602-771-1601  
<http://www.azgs.az.gov>  
[inquiries@azgs.az.gov](mailto:inquiries@azgs.az.gov)

The following file is part of the JABA, Inc. Tombstone Mining Records

### **ACCESS STATEMENT**

These digitized collections are accessible for purposes of education and research. We have indicated what we know about copyright and rights of privacy, publicity, or trademark. Due to the nature of archival collections, we are not always able to identify this information. We are eager to hear from any rights owners, so that we may obtain accurate information. Upon request, we will remove material from public view while we address a rights issue.

### **CONSTRAINTS STATEMENT**

The Arizona Geological Survey does not claim to control all rights for all materials in its collection. These rights include, but are not limited to: copyright, privacy rights, and cultural protection rights. The User hereby assumes all responsibility for obtaining any rights to use the material in excess of "fair use."

The Survey makes no intellectual property claims to the products created by individual authors in the manuscript collections, except when the author deeded those rights to the Survey or when those authors were employed by the State of Arizona and created intellectual products as a function of their official duties. The Survey does maintain property rights to the physical and digital representations of the works.

### **QUALITY STATEMENT**

The Arizona Geological Survey is not responsible for the accuracy of the records, information, or opinions that may be contained in the files. The Survey collects, catalogs, and archives data on mineral properties regardless of its views of the veracity or accuracy of those data.

Volume 5 ; Book 6

0072

# TOMBSTONE

Mining District

Cochise County

ARIZONA

Charleston Drilling - #3

Hewitt Report 8/18/75



THE CHARLESTON MINE  
Cochise County, Arizona

JAMES STEWART COMPANY  
3033 North Central Avenue  
Phoenix, Arizona 85012  
(602) 264-2181

8/18/75

V5 B6  
V5 B10  
Box 12

242

CHARLESTON MINE  
Charleston, Arizona

INDEX

1. Report by Loyd A. Hewitt, Geophysist
2. Area Map
- 3-A Property Map of Charleston Mining District
- 3-B Property Map With Drill Sites Overlay
4. Fig. #1 - Electrode Configuration
5. Airborne Magnetic Contour Map
6. Surface Geology
7. Ground Magnetic Contour Map
8. Induced Polarization Contour Map - 1000 foot electrode separation, plus depth profile positions
9. Induced Polarization Contour Map - 2000 foot electrode separation
10. Induced Polarization Contour Map - 3200 foot electrode separation
11. Sample 2 Array Depth Profiles
12. Geologic Cross Section
13. Drill Hole Log - Stewart #1
14. Drill Hole Log - Stewart #2
15. Drill Hole Log - Stewart #4
16. Drill Hole Log - Stewart #5
17. Assays - Stewart Drill Hole #1
18. Assays - Stewart Drill Hole #2
19. Assays - Stewart Drill Hole #4
20. Assays - Stewart Drill Hole #5
21. Drill Hole Log - Chs. #1
22. Drill Hole Log - Chs. #2
23. Drill Hole Log - Chs. #3
24. Assays - Chs. #1 Drill Hole
25. Assays - Chs. #2 Drill Hole
26. Assays - Chs. #3 Drill Hole
27. Geochemical Sites and Geochemical Values (by ASARCO)
28. Thin Section Reports
29. Polished Section Reports

EXCELLENCE

EXCELLENCE

EXCELLENCE

THE CHARLESTON MINE PROJECT  
DATA COMPELATION  
REPORT

August 10, 1970

The Charleston Mine area lies approximately six miles south west of Tombstone, Arizona. The property is reached by the Charleston highway.

In the Charleston Mine area a large zone of mineralization has been discovered. The zone appears to be at least two miles long and 3/4 mile wide. The estimated size of this zone of mineralization is based primarily on deep induced polarization prospecting. Three preliminary drill holes have tested this zone in the immediate vicinity of the old Charleston Lead Mine. All three holes have encountered ore grade mineralization of copper, lead, zinc and silver. These three holes have, in part, covered only a small area within the mineralized zone. A fourth hole, drilled off the mineralized zone, encountered very little mineralization.

The exploration done, to this date on the mineralized zone, suggests an economic mineral deposit to be present. The nature of the ore indicates the operation would be underground, generally along bedding planes. This, ofcourse, is only conjecture needing much better information for a basis of evaluation.

Since a large zone of mineralization appears to exist, it is a good possibility that the Charleston deposits are related to a mineralized intrusive monzonite porphyry similar to those of Bisbee, Mission, San Manuel, and others near by.



In conjunction with the deep mineralization found, the old Charleston Lead Mine itself should not be overlooked. The mineralization in the old Charleston Lead Mine appears to be unrelated to the deeper material. However, this may be due to a time factor and a long series of mineralization periods. The old Charleston Lead Mine may, at depths, contain sufficient reserves of Pb, Zn, Ag, and sericite to be of economic importance.

Further drilling of the mineralized zone is suggested, both to test the ore in the wide spaced holes 1, 2, and 4, and the general area. The drilling is by far the most important next step in exploration.

#### CLAIMS AREA

For the most part, the zone of mineralization is covered by mineral mining claims and state mineral leases. These properties are controlled by Horne Enterprises, 3033 North Central Avenue, Phoenix, Arizona.

#### GEOPHYSICS

Three phases of geophysical exploration were conducted in the Charleston area. Preliminary airborne magnetics covered the general area of interest. This was followed by very broad selected geochemical sampling and then induced polarization plus a small amount of ground magnetics.

#### AIRBORNE MAGNETICS

The general area covered by the magnetic survey is underlain by outcrops of different rock groups, which have a significant susceptibility difference. At the Schieffelin monument and

in the area surrounding, the Schieffelin granodiorite is exposed. Rock samples of this material are fairly magnetic. At the lower end of the Boquillas Land grant, on both sides of the San Pedro River, granodiorite similar to that at the Schieffelin monument is observed. Although in the Boquillas area the rock may be closer to monzonite and is more magnetic. North of the Charleston Mine many outcrops of the Uncle Sam porphyry are observed. This porphyry seems to be andesitic and is surprisingly non-magnetic. Southeast of the Charleston Mine and vicinity, rock outcrops are principally undifferentiated gray and white tuffs with sills and dikes of magnetic andesites and other basic flows. The tuffs are non-magnetic.

From the airborne magnetics the entire Tombstone district appears to be underlain by Schieffelin granodiorite. In most cases this intrusive lies at depths less than 1,000 feet. The intrusive lies as far westward as Section 39, Twp 20 S, R 22 E. A similar intrusive underlies the San Pedro River valley west of the surveyed area. Regional magnetics suggest the San Pedro River intrusive to be far larger in size than the Schieffelin granodiorite.

Between these intrusives lies the Charleston basin. Magnetically the rocks in this basin all appear to be similar. However, the surface geology suggests otherwise. With the abundance of magnetic andesite dikes and sills in the tuffaceous flows it would seem, if the vertical extent of this section were great, there would be some aggregate magnetic effect. Since this is not the case, two choices are possible: the tuffs are underlain at reasonably shallow depths by non-magnetic Uncle Sam porphyry or sediments. Our original interpretation was that sedimentary rocks

underlie the tuffs. This is borne out in drill holes 1, 2 & 4.

The Uncle Sam porphyry is found to be surprisingly uniform magnetically, almost as if it were a sediment rather than an intrusive sill or extrusive flow. This porphyry seems to have very little relationship to other igneous rocks in the area.

#### SURFACE MAGNETICS

Some of the igneous dikes, especially the andesite porphyries in drill holes 2 and 4, are altered and mineralized. Also they are fairly magnetic. Some surface profiles in the vicinity of the Charleston Mine indicate the possibility of an intrusive dike striking northeastward and paralleling the interpreted major mineralization zone along its north side. The significance of a porphyry mass in this area is not yet known. Additional information from further drilling will undoubtedly shed some light here.

#### SURFACE GEOLOGY

In the Charleston basin six geologic units may be observed.

1. Schieffelin granodiorite
2. Uncle Sam porphyry
3. Purple volcanics
4. White volcanic tuffs
5. Green to gray volcanics
6. Recent gravels and soils

1. The Schieffelin granodiorite mass underlying the Tombstone district and the San Pedro River valley is thought by this writer to be older than any of the other units observed, except for the cretaceous Bisbee formation. In the San Pedro River valley

the contacts with the volcanic series show the granodiorite to be much weathered before the deposition of the volcanics. It is believed this unit to be older than the volcanics or the Uncle Sam porphyry.

2. The Uncle Sam porphyry is reported to be of Miocene age and, as stated before; the true nature and age of this unit is not known. It is reported that this unit intrudes the white tuffaceous volcanics but this age relationship is doubted. The porphyry covers a large area to the north of Charleston.

3. The purple volcanics vary from purple tuffs to brown argillites and includes agglomerates with some porphyry fragments. In places these rocks appear to have intruded the white tuffs.

4. White volcanic tuffs cover a large portion of the mine area and southwestward. The rock appears to be bleached and altered along shear zones which strike N 45° E. The rock is very hard and a great amount of silica has been introduced.

5. The green to gray volcanics appear much the same as the purple volcanics and are very similar in mineral composition. They are probably the same unit with insufficient iron for a reddish or purple appearance.

#### SURFACE MINERALOGY

Numerous shears are noted in a zone one and a half miles wide and striking N 45° E, through the Charleston basin. These shears vary from bleached zones with kaolin and sericite to quartz manganese veins. Parallel to the Charleston highway is a shear zone nearly five miles long and 300 feet wide. This zone has much bleaching by hydrothermal solutions and numerous veinlets of



limonite after pyrite. In most places this zone carries very minor traces of copper, with the exception of the southwest end. On the southwest end of this zone quartz veins with minor copper silicates are present.

Near the central part of the suggested Charleston mineralized area, numerous quartz manganese veins are observed. These veins contain larger amounts of copper than the shear zones.

, On the north edge of the outlined mineralized zone the Charleston Mine occupies a shear zone in the volcanics. The shear is noted by considerable sericite alteration containing galena, sphalerite and pyrite. This zone appears to be the only one in any way related to the deep mineralization, and that is questionable.

The only relationship of the surface mineralization to the deeper sulphides is that secondary hydrothermal solution from recent or post mineral faulting may have carried minor amounts of mineral through the overlying volcanics. This in part is the reason for giving emphasis to the deeper sulphide zone.

#### SURFACE GEOCHEMISTRY

In the Charleston basin numerous veins, shears, and altered zones are noted. The great majority of these zones strike N 45° E. As mentioned earlier, three types of mineralized shears are noted. It was felt that these zones, even though they appear to be post mineral, may contain secondary deposition of minerals, especially the quartz manganese veins. Rock sample tests of the three groups indicate anomalous amounts of copper, zinc, and silver in the quartz manganese veins. The mineralized shears with kaolin, limonite, and

bleaching contained the smallest amounts of these elements, only slightly above the fresher volcanic tuffs. These samples though inconclusive do aid in encouraging the possibility of ore mineralization in the underlying subsurface, outlined by the induced polarization.

#### INDUCED POLARIZATION

. Initial tests made on the Charleston basin, using a Wenner configuration with a 1,000 foot electrode spread, indicated nothing of a polarizing nature at depths less than 1,000 feet. Later tests, using this same configuration, suggest that a shallow zone of mineralization exists in the eastern part of the area, Section 30, Twp 20 S, R 22 E. The depth to this zone is estimated to be approximately 185 feet.

With a modified 2 array (note fig. 1) electrode configuration, depth spacings of 3200 feet were attainable. This consisted of placing one current electrode at electrical infinity and the other at the depth station. A reference potential electrode was placed in the direction of the moving potential electrode at 6400 feet from the current energizing electrode. Resistivity and IP readings were made, out from the current electrode, between the reference pot and the moving potential electrode.

Expanders were made in four quadrants, in most cases, depending on accessibility. By doing a sufficient number of these expanders, data was deemed dense enough to contour. Data values were plotted half way between the current electrode and the moving potential electrode for any given depth separation. For example, the IP value would be 10 milliseconds at 1600 feet from the

8-10

TOM:  
Here's who  
did the IP  
survey. Bob

current center. This value was thus plotted at 800 feet in the direction of the reference pot. The data points were then contoured. Note that contours for 2000 and 3000 foot separations are enclosed. The 2000 and 3000 foot contour maps are from data using the modified 2 array configuration. The 1000 foot electrode separation contour map is based on data from Wenner array traverses as mentioned before. Several typical depth curves are enclosed.

Measurements were made using D.C. power-pulses of 4 seconds at 5 to 6 kw. A .35 second delay was used before an IP integration of 0.8 seconds took place. The D.C. pulse system is repetitious for several cycles to give a good repeatable impressed EMF and IP value. The Hewitt Enterprises system is comparable with the Newmont or Huntex methods.

The induced polarization results indicate that a buried polarizer lies beneath the volcanic cover in the Charleston area. The zone appears to be elongated in a northeast southwest direction, striking approximately N 45° E. It appears that this polarization represents sulphide mineralization, having a width of 3000 feet minimum and at least 2 miles in strike length. An average depth to sulphides is estimated at 1000 feet below the surface. From the results of DD#4 it appears that an average total sulphide percentage for the whole mineralized zone may be approximately 3%.

#### GEOLOGIC SECTION

The enclosed geologic section is based on drill holes 1, 2, 3, and 4. The principle rocks of the section are post mineral Bronco volcanics, the Bisbee formation sediments and the Uncle Sam porphyry. The contact between the post mineral volcanics and the

underlying sediments is noticeably a basal conglomerate. The Bisbee formation in this area consists of bands of quartzites, arkose, redbeds, argillites and silicified limestones. It is most difficult, if not impossible, to find a marker bed which is identifiable across any two drill holes. The section interpretation is based primarily on the predominance of redbeds or quartzite.

#### MINERALIZATION

Ore mineralization encountered in the drilling consists of, in order of importance, sphalerite, chalcopyrite, galena, and silver. The mineralization is generally associated with the more arkosic sections of the Bisbee formation. However, in many places mineralization occurs in an andesitic porphyry which seems to be abundant as narrow dikes and sills within the Bisbee formation. The stronger ore sections show considerable sericite and quartz alteration.

Mineralization appears to be disseminated along bedding in most cases, although sections of massive sulphide may form veins.

From the polished sections data enclosed in this report, it appears that several phases of mineralization occurred in this deposit. Pyrite and quartz seem to be the predominant minerals in several of these stages. The polished sample studies suggest the galena and sphalerite are closely associated. The chalcopyrite and silver also appear to be closely related. Since several stages of mineralization seem to be present in the deposit, economic importance may be considerably enhanced.




CONCLUSIONS

Several sections of mineable ore have been encountered in the drilling to date. The reader is referred to the enclosed assay summaries and drill hole logs for an evaluation of the drilling results. Even though many sections of ore grade material were encountered, it is difficult to relate ore in one hole to the next, because of the wide spaced drilling. However, sufficient mineralization has been found to warrant both the use of definitive drilling on shorter hole spacings and general exploration drilling.


It is important that a very minimum number of holes, within the suggested large mineralized area, have found economic mineralization. It is quite possible that this mineralization lies within the vicinity of a significant porphyry copper deposit.

The geologic environment appears to be favorable to economic mineralization. This, in conjunction with the wide zone of interpreted sulphide mineralization, encourages continued exploration and development. Those familiar with recent mineral discoveries in the southwest will realize that each of them were the result of exploration in situations such as this. We appraise this property to be worthy of a vigorous exploration program.

HEWITT ENTERPRISES

  
Lloyd A. Hewitt





(TOMBSTONE)  
3947 II NE

306

304

302

TOMBSTONE 48 MI.

302


T. 20

T. 21










NORTH

EXPLANATION

- Tombstone Mineral Reserve ( lode and patent )
- Sierra Mineral Management ( lode and patent )
- Horne - Stewart Company ( lode and patent )
- Gallager Vanadium & Rare Minerals Corp. ( lode and patent )
- Tenneco Land Grant
- State Mineral
- Withdrawal - Charleston dam & Military purposes

PROPERTY MAP  
OF THE  
CHARLESTON MINING DISTRICT  
T. 20-21 S., R. 21-22 E.  
COCHISE CO., ARIZONA  
SCALE 1:48,000





# DEPTH OF DIAMOND DRILL HOLES


• 1	2107'	• CHS-1	4002'
• 2	3212'	• CHS-2	5020'
• 3	2617'	• CHS-3	3005'
• 4	3310'		
• 5	2528'		
• 6	237'		
• 7	3595'		
• 8	872'		
• 9	940'		

DRILL SITE OVER-LAY

18 AUG 75

R21E

R22E

T20S  
4 T21S







Fig. 1

Modified 2 array electrode configuration





ARCHEOMAGNETIC SURVEY  
HOMESTONE-CHARLESTON AREA  
COCHISE COUNTY, ARIZ.

**ALPHELI: VACC**

Flight elevation: 1000'      date 1-19-99  
concur      Interval 75 seconds













14

13

18


17

23


24

19


2









TOMBSTONE - CHARLESTON PROJECT  
INDUCED POLARIZATION CONTOURS  
1" = 1000'  
SCALE 1" = 1000'



TRUE NORTH









TOMBSTONE - CHARLESTON PROJECT  
INDUCED POLARIZATION CONTOURS  
SCALE 1" = 1000'























IP DEPTH PROFILE NO. 12  
 TONKSTONE OVERLAP  
 PROJECT  
 TWA AREA  
 HELLITT ENTERPRISES  
 MAY 1957









IP DEPTH PROFILE NO. 8  
TOMBSTONE CHARACTER  
PROJECT  
TWO AREA  
HEWITT ENTERPRISES  
MAY 1964












not in section plane



# CHARLESTON MINE AREA

very generalized  
Proposed section looking NE.  
scale 1"=500'

pebble conglomerate  
in porphyry  
note - sedimentary section is based  
on the majority of that rock  
type found.





[illegible]









Drill Hole 1  
Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Charleston  
Cochise County Arizona

Project  
Page 3  
By

Scale  
Started  
Completed

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type		Alteration								
								550	<table><tr><td>% Sericite</td><td>% Garnet</td></tr><tr><td>% Kaolin</td><td>% Serpentine</td></tr><tr><td>% Biotite</td><td>% Biotite</td></tr><tr><td>% Chlorite</td><td>% Feldspar</td></tr></table>	% Sericite	% Garnet	% Kaolin	% Serpentine	% Biotite	% Biotite	% Chlorite	% Feldspar
% Sericite	% Garnet																
% Kaolin	% Serpentine																
% Biotite	% Biotite																
% Chlorite	% Feldspar																
								600	<p>sulfides &lt;0.1% in interval.</p> <p>525-573 Conglomerate, 531-1/2-536, py - 2-6%, then fine light gray siltstone, 2-6% py calcite streaks 570-1/2-573. Sericitized.</p> <p>573-574 Fault, Gouge</p> <p>574-582 Fine gray siltstone, 2-6% pyrite. Sericitized.</p> <p>582-584 Fault, gouge</p> <p>584-586 Greenish gray fine siltstone, 1-2% py, becomes fine quartzite at 586.</p> <p>586-649 Fine quartzite, grades to lmm qtz locally, vuggy after 630, some py in vugs and on seams, (&lt;2% py)</p>								
								650	<p>649-665 Quartzite, lmm, vuggy in part.</p> <p>665-671 Fine grained impure qtz, locally with a streak or two of sphalerite, 1-2% py, &lt;0.1% sph.</p>								
									<p>671-676.4 No core</p> <p>676.4-705 Fine grained impure qtz grades to lmm at 679.5, vuggy, continues to 705</p>								
								700	<p>705-724 Qtz, lmm, but with pyrite on seams, bulk 5-8% py, to 724 Bedding at 724, 75° to axis. Fine grained siltstone, light grey, 1-2% py. Becomes gray banded after 750, some what softer.</p>								
								750									

Drill Hole I.S. 1  
Collar Elevation  
Coordinates  
earing  
epth  
Inclination 90°

Charleston  
Cochise County Arizona  
Scale  
Started  
Completed

Page 4  
By

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	As	Pyrite	Rock Type	Altitude	Alteration	Description
								800		769-818 Fragmental (conglomerate) for about 2 feet, then splochy, local development lime silicates. Gray siltstone with local fragmental horizon, emphasized by epidote sploches, locally fine quartzite for 5-6' intervals to 818.
								850		800 818-824 At 818, bedding at 50° to axis. Fine banded greenish- grey siltstone (epidote and calcite) 824-824.5 Several 1/8" vltz sphalerite and galena 824.5-860 Fine green-grey siltstone, splochy with epidote, be- coming drably uniform after 842-855, then aplotchy.
								900		860-886.4 Porphyry, first 18" qtz free. Altered, probably qtz monz.? Pyritized, argillic - sericite to fault at 886.4. 886.4-934 Brecciated (healed) siltstone to 892, then fine gray siltstone, becoming darker grey with depth. Some dark epidote?
								950		934-971.5 Dark grey siltstone, mottled (fine mottling) to 955.5, then fine dark gray siltstone to 971.5
								1000		971.5-974 24" carbonate vein (not calcite), ankerite or siderite 974-1004.3 Dark grey massive siltstone grades into fine-grained arkose.



Scale \_\_\_\_\_  
 Started \_\_\_\_\_  
 Completed \_\_\_\_\_

Hill Hole N. 1  
 Hillar Elevation \_\_\_\_\_  
 Ordinate \_\_\_\_\_  
 aring \_\_\_\_\_  
 pth \_\_\_\_\_  
 cination 90°

Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration
<div> <div> Sericitic Kaolin Silica Chlorite </div> <div> Garnet Serpentine Biotite K Feldspar </div> </div>						1004.3-1106 At 1056, bedding 55° to axis. Becomes somewhat darker after 1080.	
						1050	
						1100 1106-1162.3	Fine grained, nearly quartzite, grey, gradually becomes coarser (about 1mm) at 1117. Stays coarse to 1141, then grades into finer at 1153. Fine arkosic qtz. - medium gray.
						1150	1162.3-1178 Arkose, fine grained. Sericitized. Becomes fine grained at 1178.
						1200	1178-1248 Grades back into fine grained arkose after 1186. Two or three calcite bands 1207-1208. Mottled locally. 6" healed breccia at 1247.5, then porphyry.
						1250	1248-1261 Meta-andesite porphyry



Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	As	Pyrite	Rock Type		Alteration
									<div style="display: flex; justify-content: space-between;"> <div> <p>Garnet Serpentine Biotite K Feldspar</p> </div> <div> <p>Bericite Kaolin Bilica Chlorite</p> </div> </div>
									<p>1261-1262 8" fault gouge</p> <p>1262-1320.5 Fine massive grey granular siltstone, mottled with epidote; locally impure quartzite (hard). Becomes darker grey after 1286 to purple, 1290-1291, then 16" lime silicate to 1289.5, then purplish siltstone to 1299, then light grey grading back to purple at 1316, then grey, quartzite.</p> <p>1300 1320.5-1350.5 Fine grained light grey siltstone, 1% py, some mottling, becoming medium grey with considerable mottling 1330-1336, then lighter grey with epidote patches and blobs, becoming less splotchy after 1337. Splotches end at 1350.5</p> <p>1350 1350.5-1367 Fine granular impure quartzite. Grades from medium light to medium grey at 1367</p> <p>1367-1482.5 Banded siltstone, some epidote banding, purplish at 1367, becomes gray and mottled, then finely mottled 1378 to 1385. Fine grained grey quartzite (impure).</p> <p>1400 1482.5-1585 Fine grained light gray qtz/ (impure). Some epidote veinlets, sphalerite (<math>\frac{1}{4}</math>" vein) at 1490. Grey to 1496, then mottled, fragmental looking to 1503. Fine grained grainy-looking to 1511. Fragmental to 1514, then fine grained, meta-arkose, fragmental 1524-1525. Fine grained light colored quartzite 1525-1566. 12" breccia 1566-1567 (healed). Fragmental light colored impure fine grained qtz to 1574.5</p> <p>1500</p>

Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Scale  
Started  
Completed

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Altitude	Alteration
								1550	
								1600	
								1650	
								1700	
								1750	

Alteration

±	Sericite	±	Garnet
±	Kaolin	±	Serpentine
±	Silica	±	Biotite
±	Chlorite	±	K Feldspar

1585-1606 Meta-andesite-silicified.

1606-1616 Mixed-meta-andesite.

1616-1630 Mixed-meta-andesite, quartzite (impure)

1630-1650 Mottled meta-arkose-fine

1650 1650-1678 Siltstone, splotchy, grey, grades to light grey at 1657. Fragmental 1662-1664. Purplish 1666-1676.5, bedding 60° to axis, contact 1678

1678-1698 Meta-andesite porphyry, several mixed zones.

1698-1746 Siltstone, purplish, to 1722, 18" fine qtz., then purplish siltstone, gradually grading to more qtz. material.

1746-1757 Siltstone, fragmental (conglomerate)

Drill Hole 1  
Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Charleston  
Cochise  
County Arizona  
Scale  
Started  
Completed

Page  
By

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration								
								<table><tr><td>Sericite</td><td>Garnet</td></tr><tr><td>Kaolin</td><td>% Serpentine</td></tr><tr><td>Silica</td><td>Biotite</td></tr><tr><td>Chlorite</td><td>K K Feldspar</td></tr></table>	Sericite	Garnet	Kaolin	% Serpentine	Silica	Biotite	Chlorite	K K Feldspar
Sericite	Garnet															
Kaolin	% Serpentine															
Silica	Biotite															
Chlorite	K K Feldspar															
	1757-1810 Siltstone, becomes quartzitic at 1763. Fine grained impure light grey qtz.															
1800	1810-1818 Fragmental siltstone (conglomerate)															
1850	1818-1951 Light gray impure siltstone (fine qtz.), fragmental intervals, grades to 1mm qtz. at 1905, 2' basal arkose 1949-51.															
1900																
1950	1951-1954 Light colored grey siltstone 1954-1981 Quartz latite? 1981-1998 Meta-arkose-conglomerate															
2000																

Started

Completed

Alteration

Chalcopyrite

Sphalerite

Galena

3v

Pyrite

Rock Type

10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	-----

ci in ca ri

te

io	oo	kk
----	----	----

\_\_\_\_\_ne \_\_\_\_\_pe \_\_\_\_\_ti \_\_\_\_\_el \_\_\_\_\_

ner  
par

100





Collar Elevation \_\_\_\_\_  
 Coordinates \_\_\_\_\_  
 Bearing \_\_\_\_\_  
 Depth \_\_\_\_\_  
 Inclination 90°

Charleston \_\_\_\_\_ Project \_\_\_\_\_  
 Cochise \_\_\_\_\_ County \_\_\_\_\_ Arizona \_\_\_\_\_  
 Scale \_\_\_\_\_  
 Started \_\_\_\_\_  
 Completed \_\_\_\_\_

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration								
								<table><tr><td>sericite</td><td>Garnet</td></tr><tr><td>kaolin</td><td>Serpentine</td></tr><tr><td>silica</td><td>Biotite</td></tr><tr><td>chlorite</td><td>K Feldspar</td></tr></table>	sericite	Garnet	kaolin	Serpentine	silica	Biotite	chlorite	K Feldspar
sericite	Garnet															
kaolin	Serpentine															
silica	Biotite															
chlorite	K Feldspar															
							✓	0-10 No Core								
							✓	10-248 Weathered meta-andesite tuff. Fragmental to 123, then fine. At 151, 4" breccia. Fragmental interval 165-168.								
							✓	At 181 - bedding 30° to axis. To 189.5, fragmental to 197.								
							✓	Bedding at 199-65°. Fine to 209, fragmental to 248.								
							✓	50								
							✓	100								
							✓	150								
							✓	200								
							✓	248-394 Fine to 262, fragmental to 270, fine and fragmental mixed to 278. Tuff to 323. Fragmental 323-327, fine to 329, fragmental to 394.								
							✓	250								

Charleston \_\_\_\_\_ Project  
Cochise \_\_\_\_\_ County \_\_\_\_\_ Arizona \_\_\_\_\_  
Scale \_\_\_\_\_  
Started \_\_\_\_\_  
Completed \_\_\_\_\_

Charleston \_\_\_\_\_ Project  
Cochise \_\_\_\_\_ County \_\_\_\_\_ Arizona \_\_\_\_\_  
Scale \_\_\_\_\_  
Started \_\_\_\_\_  
Completed \_\_\_\_\_

Alteration	
72	Garnet
73	Serpentine
74	Biotite
75	K Feldspar

394-506. Meta-andesite tuff-coarsely fragmental, bedding at 442 50° to asix to 437.5, bedded tuff to 453, then fragmental to 506.

Drill Hole No. 2  
Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Charleston  
Cochise County Arizona  
Scale  
Started  
Completed

Page 3  
By

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration								
								<table><tr><td>Sericite</td><td>Garnet</td></tr><tr><td>Kaolin</td><td>Serpentine</td></tr><tr><td>Silica</td><td>Biotite</td></tr><tr><td>Chlorite</td><td>K Feldspar</td></tr></table>	Sericite	Garnet	Kaolin	Serpentine	Silica	Biotite	Chlorite	K Feldspar
Sericite	Garnet															
Kaolin	Serpentine															
Silica	Biotite															
Chlorite	K Feldspar															
								506-534 Meta-andesite tuff - fragmental in part to 527, strongly fragmental to 534.								
								534-537 Meta-andesite, bleached, some sericite, fault zone at 536.								
								537-566 Meta-andesite tuff to 566.								
								566-567.5 Gouge and breccia - fault zone.								
								567.5-577.5 Fine grained meta-andesite tuff.								
								577.5-578.5 Gouge and breccia - fault zone.								
								578.5-582 Fine grained meta-andesite tuff.								
								582-591 Fragmental meta-andesite tuff.								
								591-598 Bleached meta-andesite sericite, specks of galena, some silicification, argillic alt. FeOx stain.								
								598-603 Crushed zone, clay, sericite.								
								603-604 Bleached meta-andesite.								
								604-605 Fault Zone.								
								605-623 Crushed and broken zone, bleached meta-andesite tuff 40° dip to axis (fault).								
								623-628 Bleached meta-andesite.								
								628-675.5 Sericitized meta-andesite tuff, grading downward to chloritic meta-andesite tuff.								
								675.5-699.5 Andesite tuff (?)								
								699.5-737.5 Meta-andesite tuff (see specimen at 706.5) dark gray, fine grained, feldspars altered, ferromags altered to chlorite, could also be a meta-volcanic tuff. Splotches of epidote. Epidote bands may reflect bedding? (40° to core)								
								On the whole, prefer to consider this a tuff. Some fine pyrite with epidote. Small fault, 4" gouge and breccia at 724.								
								737.5-761, 12" gouged fault at 30° to axis of core, Meta-andesite tuff, intercalated bands of fine grained medium gray siltstone								



Completed

Inclination  $90^{\circ}$

[illegible]

1250

1249-1280 Fine grained light gray arkose-has stony look, not much quartz. Beddings locally present, one at 1262.5 40° to axis. Rock becomes mottled 1270.5-1275, then gray granular (about 1mm), grading into quartzite at 1280.

1280-1330 Quartzite to 1281, then back to granular gray arkose, as above, rock gradually becoming more quartzitic, fair qtz. after 1301.

1330-1363 Arkose, dense granular to 1332, then fine grained siltstone with minor sulfide on bedding (less than 1% sulfide), to 1334. Quartzitic arkose to 1347.5, then gray granular arkose to 1349.5, then quartz-ark. to 1363.

1363-1368.6 Fine grained gray siltstone.

1368.6-1395 Quartzite with sericite, occasional grain of galena or pyrite. At 1397, 10" altered (bleached) shale and qtz. bedding 45° to axis.

1395-1410 Disseminated sulfides in qtz. after 1397. ½" py vein at 1401, 25° to axis, 1% total sulfides to 1405, then 5% to 1406.5 then 1% again. Sulfides are galena, sphalerite, minor cpy and pyrite. Sulfide content drops to much less than 1% with rock change (1410)

1410-1416 Dense greenish massive, lime silicate rock (diopside?) specimen at 1409-Possible fault at 1416-no gouge but badly broken core.

1450 1416-1457.5 Dense light gray fine grained quartzite. Minor py on seams 1% sulfide. Quartzite gradually becomes coarser, about 1mm at 1454, sulfide content picks up to 2-3%, mostly galena and sphalerite for interval 1454-1457.5

1457.5-1477 Dense light gray fine grained quartzite (sericitized At 1477, bedding plane 50° to core. Sulfide < 1%

500



Collar Elevation

Coordinates

Bearing

Depth

Inclination 90°

Scale

Started

Completed

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Altitude	Alteration
								1477-1512	Quartzite-medium grained (less than 1mm but granular)
									Sulfide < 1%.
								1512-1518.5	Fault zone, minor gouge, poor core
								1518.5-1532	Quartzite, somewhat silicified.
								1532-1533.6	12" heavy pyrite
								1533.6-1543	Quartzite, about 1mm, broken
								1543-1546	Gouge and breccia - barren
								1546-1594	Purplish siltstone to 1549, then bleaching to gray with lime silicate spots, grading to quartzite at 1552.
									(Fine grained-gray)
								1594-1625	Gray siltstone, scattered blebs of py, changing color to lt gy and from siltstone to fine qtz with lime silicate streaks at 1601
								1600	
								1625-1727	Dense gy silicified siltstone, blobs of lime silicate minerals, some scattered py, still much less than 1% sulfide
									This silicified siltstone has a porphyritic look with the quartz grains separate in a dense stony groundmass. Siltstone persists to 1725, then changes to medium grained quartzite, to
								1650	
								1700	
								1727-1733.5	1-2mm quartzite-sericite, from 1-5% total sulfides, sphalerite, cpy, py, minor galena.
								1733.5	6" fault gouge
								1733.5-1920	Quartzite, dense, fine grained, py cubes, less than 1% sulfide. Changes from gray to reddish, becoming purplish
								1750	

## Alteration

++ Sericite	Garnet
+ Kaolin	% Serpentine
+ Silica	Biotite
+ Chlorite	K Feldspar

% Garnet	Garnet
% Serpentine	% Serpentine
Biotite	Biotite
K Feldspar	K Feldspar



Collar Elevation

Coordinates

Bearing

Depth

Inclination 90°

Scale

Started

Completed

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type		Alteration																
									<table><tr><td>2%</td><td>Sericite</td></tr><tr><td>2%</td><td>Kaolin</td></tr><tr><td>4%</td><td>Biotite</td></tr><tr><td>5%</td><td>Chlorite</td></tr></table> <table><tr><td>0%</td><td>Garnet</td></tr><tr><td>0%</td><td>Serpentine</td></tr><tr><td>0%</td><td>Biotite</td></tr><tr><td>0%</td><td>K Feldspar</td></tr></table>	2%	Sericite	2%	Kaolin	4%	Biotite	5%	Chlorite	0%	Garnet	0%	Serpentine	0%	Biotite	0%	K Feldspar
2%	Sericite																								
2%	Kaolin																								
4%	Biotite																								
5%	Chlorite																								
0%	Garnet																								
0%	Serpentine																								
0%	Biotite																								
0%	K Feldspar																								
								1800	siltstone at 1748. Purplish siltstone to 1759, then back to dense, fine to coarse cubic pyrite. Minor lime silicate veining. Gray to 1803 then purplish to 1811, then gray as above. Somewhat coarser 1813-1818; denser 1818-1820																
								1850	1820-1852 Siltstone, dark gray 1820-1831, then light gray 1831-1837, 1mm quartzite 1837-1839, then purple siltstone followed by dull stony quartzite(?) at 1843 - granular. (probably lime silicates) to 1850, then fine grained siltstone to 1852																
								1900	1852-1853 Arkose? with sphalerite and cpy < 15% sulfides 1853-1923 Quartzite, 1-2mm, becoming finer grained, more stony looking. Minor sphalerite-galena, up to 5% for 4" interval, otherwise negligible (less than 1%). Fine grained gray qtz to 1865, then purplish siltstone to 1875. Lighter colored to 1878.5, then purplish again to 1892. Dense light gray 1892-1897.5, purplish to 1901. Lime silicates vlt at 1901 (1/2", 5% sulfide, mostly sphalerite). Fine grained light gray to 1905.5, becomes granular (fine) more quartzitic to 1923. 1923-1924 Arkose, heavy sphalerite, galena. About 10% Z, 3% lead 15-20% total sulfide.																
								1950	1924-1935 Quartzite with less than 1% sulfide to 1925, then purplish siltstone, becoming dark gray at 1927, then light greenish gray lime silicates with minor py (2% sulfides) to 1928.5. Dark gray siltstone grading to purple siltstone, then to greenish dense lime silicates to 1935.																
								2000	1935-2002.3 Dense, fine gray siltstone to 1939, greenish gray lime silicates to 1939.5, purplish dense siltstone to 1943.5,																



Collar Elevation \_\_\_\_\_  
 Coordinates \_\_\_\_\_  
 Bearing \_\_\_\_\_  
 Depth \_\_\_\_\_  
 Inclination 90°

Cochise County Arizona

By \_\_\_\_\_

Scale

Started

Completed

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration																
								<table><tr><td>++</td><td>Sericite</td><td></td><td>Garnet</td></tr><tr><td>++</td><td>Kaolin</td><td></td><td>Serpentine</td></tr><tr><td>++</td><td>Billica</td><td></td><td>Biotite</td></tr><tr><td>++</td><td>Chlorite</td><td></td><td>K Feldspar</td></tr></table>	++	Sericite		Garnet	++	Kaolin		Serpentine	++	Billica		Biotite	++	Chlorite		K Feldspar
++	Sericite		Garnet																					
++	Kaolin		Serpentine																					
++	Billica		Biotite																					
++	Chlorite		K Feldspar																					
2271	Porphyry latite andesitic (Uncle Sam latite por) feldspar qtz fprph dk greenish buff to purple contacts bxt'd and altd composite zone qtz latite porph about 6' at 2222	++	++	++	++	++	++																	
2290	Qtzite-and tuff? siltstone dk gy qtzite-bxt'd zone w/local- ly heavy sphal as cs diss clots and high < 1/16" stringers	++	++	++	++	++	++																	
2300		++	++	++	++	++	++																	
2323	Qtzite-grades from fg silty to med g sandy 2/calcite cement	++	++	++	++	++	++																	
2350		++	++	++	++	++	++																	
2400		++	++	++	++	++	++																	
2407	Siltstone-variable gy, purple buff, local sandy zones numerous fn calcite stringers last 10' strongly alt'd, bxt'd kaolinized 1/2" wide replacement stringers of cpy at 2399 cuts core at 15' to axis.	++	++	++	++	++	++																	
2435	Qtzite siltstone interbedded bxt'd diss sphal 2423 over 8" in a dk gy bxt'd qtzite? some cpy diss	++	++	++	++	++	++																	
2450		++	++	++	++	++	++																	
2452	Tuff? dk gy to buff-incels n fg silty mud at bot of entry	++	++	++	++	++	++																	
2458	Qtzite - pinkish	++	++	++	++	++	++																	
2490	Siltstone-variegated pk and green bleached borders along epidote zones also runs of dk purple mudstone v fg-hemotitic packing (bedding) 45° to core	++	++	++	++	++	++																	
2500		++	++	++	++	++	++																	

Drill Hole No. 2  
Collar Elevation \_\_\_\_\_  
Coordinates \_\_\_\_\_  
Bearing \_\_\_\_\_  
Depth \_\_\_\_\_  
Inclination 90°

Charleston Cochise County Arizona Project \_\_\_\_\_ Page \_\_\_\_\_ By \_\_\_\_\_  
Scale \_\_\_\_\_  
Started \_\_\_\_\_  
Completed \_\_\_\_\_

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration																
								<table><tr><td>qtz</td><td>Sericite</td></tr><tr><td>ep</td><td>Kaolin</td></tr><tr><td>fs</td><td>Silica</td></tr><tr><td>ch</td><td>Chlorite</td></tr></table> <table><tr><td>%</td><td>Garnet</td></tr><tr><td>X</td><td>Serpentine</td></tr><tr><td>X</td><td>Biotite</td></tr><tr><td>X</td><td>K Feldspar</td></tr></table>	qtz	Sericite	ep	Kaolin	fs	Silica	ch	Chlorite	%	Garnet	X	Serpentine	X	Biotite	X	K Feldspar
qtz	Sericite																							
ep	Kaolin																							
fs	Silica																							
ch	Chlorite																							
%	Garnet																							
X	Serpentine																							
X	Biotite																							
X	K Feldspar																							
								2553-2572 Siltstone, purplish red, grades into tactite at 2555, f grained, gy, epidote splotches. This in turn grades into qtz at 2560, med gy qtz to 2572																
								2572-2574.5 Qtz, med gy, grades into banded f gy tactite at 2573. Tactite to 2574.5																
								2574.5-2626.5 Tactite, metamorphosed calcareous arkose, qtz lenses, mudstones, siltstones, strong epidotized. Diss py at intervals in certain intervals, minor sphal and cpy loc in small veins.																
								2626.5-2657 Qtz, with chlorite and iron rich cement, epidote & calcite blebs at intervals, minor sphal and cpy 2247-2248.6-																
								2657-2669 Meta-arkose, qtz, epidote and calcite blebs, to 2669																
								2669-2672 Mudstone, reddish, with epidote spots to 2672																
								2672-2694 Shale, siltstone to 3688, then qtz to 2694																
								2694-2704 Shale, dk purplish shale, grading downward to siltstone epidotized in part																
								2704-2727 Qtz, R gy in color, f grained grades to med grained																
								2727-2754 Shale & qtz. F gy shale, loc purple in color to 2731, then f qtz to 2739, then R gy med f to med grained. Arkosic locally. 2752-2754																
								2750																



Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type													
								<table><tr><td>22</td><td>Bericite</td><td>Garnet</td></tr><tr><td>23</td><td>Anolin</td><td>% Serpentine</td></tr><tr><td>24</td><td>Silica</td><td>Biotite</td></tr><tr><td>25</td><td>Chlorite</td><td>% K Feldspar</td></tr></table> <p>2754-2791 Tactite, Qtzt. Lime-silicate (tactite), locally ser-pentinized, followed by Qtzt to 2759. Two feet of shale, the gy mottled Qtzt to 2770, thereafter increasing lime silicate (epidote), f grained, dense, hard to 2791</p> <p>2791-2839 Qtzt, tactite. Fine to med grained Qtzt to 2808, lime silicate to 2818, f grained Qtzt to 2839</p> <p>2839-2845 Shale and lime-silicate.</p> <p>2845-2882 Qtzt, f, gy, dk shale to 2850 grading through siltstone to f Qtzt to 2868. Med Qtzt for 2', then purple shale, locally epidotized, to 2882.</p> <p>2800</p> <p>2850 2882-2902 Qtzt, f gy, grading into med grained epidotized Qtzt, to 2890. At 2890, 6" interval with cpy. (10% cpy) Below cpy zone, mottled f grained siltstone to 2893, then dk gy f siltstone, becomes lighter with depth and grades into epidotized lime-silicate at 2902</p> <p>2900 2902-2915 Dark purplish shale, lime-silicate 2905-2908, then shale and Qtzt</p> <p>2915-2973.5 Qtzt, lt gy, f grained, banded with epidote, bedding 60° to axis of core, becoming med grained at 2926. 6" med grained Qtzt with cpy at 2929; estimate 5% cpy. Barren shale and lime-silicate below to 2953, then 6" med Qtzt w/cpy, 7% cpy estimated. Underlain by barren shale and Qtzt, 30° angle to axis of core. Estimate 25% cpy in this interval, then 6" barren Qtzt, then 1" solid cpy vein at 30° to axis of core, then barren med grained Qtzt to 2973.5</p> <p>2950</p> <p>2973.5-2997 Qtzt, med to coarse, arkosic, 1/8" cpy vein at 2989, otherwise barren.</p> <p>3000</p>	22	Bericite	Garnet	23	Anolin	% Serpentine	24	Silica	Biotite	25	Chlorite	% K Feldspar
22	Bericite	Garnet																		
23	Anolin	% Serpentine																		
24	Silica	Biotite																		
25	Chlorite	% K Feldspar																		

Drill Hole No. 2  
Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Project \_\_\_\_\_  
County Arizona \_\_\_\_\_

Completed

Chalcopyrite	Sphalerite	Galena	As	Pyrite
--------------	------------	--------	----	--------

Pyrite

---

Ag

Rock Type

Zr	bericite		Garnet
Zr	kaolin	%	Serpentine
Al	illica		Biotite
Al	chlorite	X <sub>2</sub>	K Feldspar

2997-3045 Shale, ls-silicate, minor serpentine, epidote bunches, 2' of dk shale 3043-3045  
3045-3062 Lime-silicate, shale, (some serpentine), to 3049. 2' dense siltstone, 3049-3051, then lime-silicate. 1" cpy 3051.4. Chert 3054-3054.5, qtz 3057-3061. Fault zone 3061-3062  
3062-3072.5 Sericite, argillite, some gouge at 3062, spotted at 3065, py clots and dk angular patches, probably originally a calc-arenaceous rock, sp. 3065.5% py+. Grades downward into quartzitic-looking rock with dark patches, then to 24" dk gy-gr dense hornstone with reddish and greenish patches plus py, to contact with epidotized and pyritized andesite(?) porphyry. Spec. 3074  
3072.5-3128.5 Andesite(?) porphyry. Feldspars are epidotized, rock is pyritized. upper contact not cored. Lower contact at 25' to axis of core. Probably a dike.  
3128.5-3154 Qtz, very f grained, or tactite, grades into granula ls-sil w/splotches, very f grained, it to med ty to 3139.5 (at 3141, bedding at 80° to axis) then darker gy to 3142.5, epidotized zone to 3146, then massive very dk gy siltstone w/qtz. frags (less than 0.5 mm) to 3148. Py & epidote on seams at 3148. Med gy siltstone, minor py on seams. Grades to lt gy tactite with splotches at 3150, then to f lt gy qtz at 3154.  
3154-3177 Qtz, massive to 3163, then banded, alternate f to med. Bands (bedding) at 75° to axis. Banded to 3167, then massive med grained, to 3175.5, then coarse grained, arkosic, w/py (2%) to 3177. Gradational contact with tactite.  
3177-3181.5 Tactite, med gy, v f grained, w/epidote splotches

Scale

Started,

Completed.

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	As	Pyrite	Rock Type									
	<table><tr><td>1/2 Bericite</td><td>Garnet</td></tr><tr><td>2/3 Kaolin</td><td>Serpentine</td></tr><tr><td>1/4 Biotite</td><td>Biotite</td></tr><tr><td>1/2 Chlorite</td><td>K Feldspar</td></tr></table>	1/2 Bericite	Garnet	2/3 Kaolin	Serpentine	1/4 Biotite	Biotite	1/2 Chlorite	K Feldspar							
1/2 Bericite	Garnet															
2/3 Kaolin	Serpentine															
1/4 Biotite	Biotite															
1/2 Chlorite	K Feldspar															
	3181.5-3187 Arkosic Qtz. Epidotized. Spots of cpy at 3185, 8" fairly good cpy 3186.5-3187+. Interval not yet split, will run about 10% cpy - 4%+ copper.															
3300	3187-3193 Tactite, epidote splotches, variable in color, dk gy to lt gy. Spot of cpy 3192.5 in bleached & epidotized spot, grades to very f gy Qtz at 3193.															
	3193-3207 Qtz, f grained, lt gr, impure, locally splotchy w/dk gy spots grades downward into siltstone. Impure siltstone w/epidote clots after 3201, grading back into more quartzitic material after 3207															
3350	3207-3212 Quartzite, light gray, impure, medium grained. Bottom - Complete															
3400																
3450																
3500																





Drill Hole No. 4  
Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Page 1  
By

[illegible]

22	bericite		
23	kaolin		
24	illica		
25	hlorite		

0-852 Meta andesite

Drill Hole No. 4

Collar Elevation

Coordinates

Bearing

Depth

Inclination 90°

Charleston

Cochise

County Arizona

Project

Page 2

By

Scale

Started

Completed

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration
								Garnet
								Serpentine
								Biotite
								K K Feldspar

300 350 400 450 500

Drill Hole No. 4  
 Collar Elevation  
 Coordinates  
 Bearing  
 Depth  
 Inclination 90°

Charleston  
 Cochise  
 Scale  
 Started  
 Completed

Project  
 County Arizona

Page 3  
 By

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	
							✓	550
							✓	
							✓	
							✓	
							✓	600
							✓	
							✓	
							✓	650
							✓	
							✓	
							✓	700
							✓	
							✓	
							✓	750

Alteration	
± Sericite	Garnet
± Kaolin	° Serpentine
+ Biotite	Biotite
± Chlorite	K K Feldspar

Charleston  
Cochise  
Scale  
Started  
Completed

[illegible]



Drill No. 4  
Collar Elevation \_\_\_\_\_  
Coordinates \_\_\_\_\_  
Bearing \_\_\_\_\_  
Depth \_\_\_\_\_  
inclination 90°

Charleston  
Cochise  
Scale  
Started  
Completed

Project  
County Arizona

Page 5  
By

[illegible]



Drill Hole No. 4  
 Collar Elevation  
 Coordinates  
 Bearing  
 Depth  
 Inclination 90°

Charleston  
 Cochise  
 County Arizona  
 Project  
 Scale  
 Started  
 Completed

Page  
 By

Core Recovery	Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alteration								
								<table><tr><td>sericite</td><td>Garnet</td></tr><tr><td>kaolin</td><td>Serpentine</td></tr><tr><td>silica</td><td>Biotite</td></tr><tr><td>chlorite</td><td>K Feldspar</td></tr></table>	sericite	Garnet	kaolin	Serpentine	silica	Biotite	chlorite	K Feldspar
sericite	Garnet															
kaolin	Serpentine															
silica	Biotite															
chlorite	K Feldspar															
	1498.5-1501	++					++	Qtz andesite - porphyry highly altered some sericite w/chlorite and sulphides 5% py 3% gal, 5% sphal								
	1501-1590	++					++	Porphyry broken and altered but less sericite, more chlorite, sulphide, mostly py-1% mineralized plus 3% sulphides some sphal and gal 190-191, several 1/2" stringers, minerals 10" to core axis								
1550	1590-1688	++					++	Greenish grey tuffaceous Qtzt, 3% sulphide 1590-1591; badly broken and gougy 1594-1598; fractures 10" to core axis calcite filling on fractures. Some epidote and chlorite?								
1600		++					++	Mottled, 1611-1612 no core, 1612-1616 60% core, 1612-1616 chlorite with 2% py 1% galena 2% sphal .5% cpy; 1626-1631 grades to siltstone, 1631-1636 highly silicified, quartz and epidote stringers 10" to core axis. 1636-1643 badly broken with some sericite. 1626-1688 silicified pink colored tuff. 1663-1665 gouge and broken, badly broken and gouge 1672-1713								
	1650	++					++									
	1688-1726	++					++	Coarse grey Qtzt, some chlorite, py 2%, sericite and clay in gouge zone. 1727-1730 minor diss sphal, galena								
1700	1726-1745	++					++	Grades back into silicified pink arkose								
	1746-1747	++					++	White quartzite								
1750	1747-1762	++					++	White q to ground to powder								

Drill Hole No. 4  
Collar Elevation  
Coordinates  
Bearing  
Depth  
Inclination 90°

Charleston  
Cochise

County Arizona Project

Page \_\_\_\_\_  
By \_\_\_\_\_

Scale

Started

Completed

Алладонь оло

Chalcopyrite

epitheliale

Galena

35

Pyrite

Rock Type

## Alteration

22	Sericite		Garnet
23	Kaolin	20	Serpentine
24	Billica		Biotite
25	Chlorite	15	K Feldspar

1762-1773 Grades from quartzite to andesite porphyry, very soft and highly altered, some chlorite, 5% py, .5% cpy.  
1773-1791.5 Andesite porphyry, green altered feldspars, some introduced pink K feldspar?

1791.5-1802 Mineralized zone, originally arkosic quartzite or greywacke primarily cpy 10-15% average. Minor galena and sphalerite

1802-1812 Arkosic quartzite, 1802-1803 20% core recovery, gouge  
1806-1810 60% core recovery, 3% sulphides mostly py, 3% diss  
cpy 1810-1812

1812-1822 Quartzite with diss 5% cpy, minor galena and sphal  
1822-1824 Arkose, with numerous calcite stringers 2% sulphides  
mostly py

1824-1831 Quartzite, 2% sulphides, mostly py  
1831-1833 Quartzite, light grey, 1-2% py, silicified vein 6" wide  
sphalerite and lead, 5% sulphides

1833-1854 Silicified arkose, purple and coarse grained with  
diss galena and sphal, 1852.5-1853.5, 6% sulphides  
1854-1871 Arkosic quartzite, light gray to light purple, py .5%

1871-1874. Broken fine grained gray qtz, with 1% py, minor sphal  
specks, some chlorite blebs  
1874-1882. Light gray qtz, py filled fracture 45° to core at 18

sulphides --.5%  
1882--1895.5 Gray quartzite, diss py and sphal 1% sulphides,  
chlorite in last one foot.

1895.5-1903 Mineralized arkosic qtz which appears to be almost porphyritic with introduce chlorite (cpy, sphal, py) 5-6% sulphides

1903-1906 Dark gray very fine grained tuffaceous sandstone with blebs of olivine, diss sulphides, mostly py 3-5%



Well No. 4  
Collar Elevation  
Coordinates  
Easting  
Depth  
Inclination 90°

Charleston  
 Cochise County Arizona  
 Scale  
 Started  
 Completed

Page.  
By

Pyrite	
Ag	
Galena	
Sphalerite	
Chalcopyrite	
Alteration	
Rock Type	

Alteration	
$\frac{2}{2}$ Bericite	Garnet
$\frac{2}{2}$ Kaolin	Serpentine
$\frac{1}{4}$ Silica	Biotite
$\frac{1}{2}$ Chlorite	K Feldspar

## Alteration

1906-1939 Brecciated & cemented arkosic Qtz very much mottled w/chlorite, olivine. Rock appears pink, py --.5%. 1920-1925 very dark gray siltstone silicified with 2% py. Very highly altered and bleached.

1929-1957 Light gray Qtz, 1938-1940 similar to pre section, sulphides .5%, blebs of olivine surrounded by chlorite  
1957-1969 Highly altered arkose? with much sericite and minor chlorite highly bleached, banding 50° to core axis, diss. sphal at 1963, 6" minor py in section -.5%

1969-2001 Very similar to section from 1906-1929, broken with sericite 1978-1979, 1" sphal vein 15° to core axis at 1998, py approx 1%

2001-2003 Very dark gy-wacke, 3% py, minor specks of cpy  
2003-2072 Lt gy arkosic qtzst, py --.5%, 10% py 2023-2026, 2034--  
2041 finer grained with more py and more highly altered,  
1% py, fault zone with sericite, 2044-2046. Fault gouge  
2053-2054. Strong alteration 50° to core axis at 2071.

2072-2196 Siltstone, strong silicification w/olivine blebs and minor chlorite patches, some sericite; Arkose 2090.5-2094; 2097.5-2104 healed breccia, mineralized zone, with intro-duce quartz phenocrysts, 1.5' core lost, 10% sphal, 2% cpy 5% py; 2101-2104 30% core recovery; 2123-2124 core is deep purple colored with white splotches; 2161-2181 core badly broken with much sericite; mineralized arkose, sphal 6%, cpy 2%, py 8%, 2183-2190, one foot core missing; 2190-2196 broken with sericite.

2196-2225 Purple siltstone, bleached and broken with sericite  
2198-2206, very dark purple 2214-2223  
2225-2242 Arkosic quartz lt. gy becomes porphyritic 2241 some  
sericite development near porphyry contact. Mineralized  
zone 2230.5-2236, sphalerite  $\frac{4}{3}$ , cpy 1%

Well Hole No. 4  
Holler Elevation  
Coordinates  
Leaving  
Depth  
inclination 90°

Charleston  
Cochise

County Arizona

Project

Page  
By

Scale  
Started  
Completed

Started

Completed

[illegible]

Drill Hole No. 4  
 Elevation  
 Coordinates  
 Bearing  
 Depth  
 Inclination 90°

Charleston  
 Cochise  
 County Arizona  
 Project  
 Scale  
 Started  
 Completed

Page 1  
 By

Alteration	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Altitude	Alteration	Description
							2497-2510	Gray arkosic qtz	2497-2510 Gray arkosic qtz mixed. 6" sphal at 2500 3% sphal.
							2510-2559	White arkosic quartzite with sericite fairly well broken 2% py.	2510-2559 White arkosic quartzite with sericite fairly well broken 2% py.
							2559-2575	Light gray lime silicates and qtz, grades to gray arkosic qtz	2559-2575 Light gray lime silicates and qtz, grades to gray arkosic qtz
							2575-2613	Light gray arkosic qtz & tuff, with purple bands 30° to core axis, 4% py, gouge zone 2578-2579, mineralized 2597	2575-2613 Light gray arkosic qtz & tuff, with purple bands 30° to core axis, 4% py, gouge zone 2578-2579, mineralized 2597
							2613-2643	Light gray qtz, 5% py, white splashes	2613-2643 Light gray qtz, 5% py, white splashes
							2643-2680	Tuff, gray to 2653 then changes to white arkosic qtz to 2669 then gray qtz to 2673 then grades to highly bleached tuff 2680, 8% py.	2643-2680 Tuff, gray to 2653 then changes to white arkosic qtz to 2669 then gray qtz to 2673 then grades to highly bleached tuff 2680, 8% py.
							2680-2693	Fine grained bleached arkosic qtz, mineralized zone mostly py 5-8% 2691-2693 brecciated with sericite some cpy - .2 average 2% py.	2680-2693 Fine grained bleached arkosic qtz, mineralized zone mostly py 5-8% 2691-2693 brecciated with sericite some cpy - .2 average 2% py.
							2693-2699	Andesite porphyry py - 1%	2693-2699 Andesite porphyry py - 1%
							2699.5-2705.5	Mineralized zone brecciated with much sericite, 50% core recovery split, py 5%, minor diss cpy and sphal.	2699.5-2705.5 Mineralized zone brecciated with much sericite, 50% core recovery split, py 5%, minor diss cpy and sphal.
							2705.5-2712	Gray fine grained silicified qtz, by 3%, very minor specs cpy.	2705.5-2712 Gray fine grained silicified qtz, by 3%, very minor specs cpy.
							2712-2743	Very fine grained silicified qtz/grades from white to gray containing py 1% with minor sphal argillaceous in spots. Brecciated and healed pink quartzite healed fractures 20° to core axis, py not present 2717-2722 white argillaceous qtz	2712-2743 Very fine grained silicified qtz/grades from white to gray containing py 1% with minor sphal argillaceous in spots. Brecciated and healed pink quartzite healed fractures 20° to core axis, py not present 2717-2722 white argillaceous qtz
							2729-2740		2729-2740

Will Hol Co. 4  
 Collar Elevation  
 Coordinates  
 Bearing  
 Depth  
 Inclination 90°

Charleston  
 Cochise  
 County  
 Arizona

Page  
 By

Project

Scale  
 Started  
 Completed

Core recovery	Alt	Chalcopyrite	Sphalerite	Galena	Ag	Pyrite	Rock Type	Alt	Alteration								
									<table><tr><td>1/2 Bericite</td><td>Garnet</td></tr><tr><td>1/2 Kaolin</td><td>Serpentine</td></tr><tr><td>1/2 Biotite</td><td>Biotite</td></tr><tr><td>1/2 Chlorite</td><td>K Feldspar</td></tr></table>	1/2 Bericite	Garnet	1/2 Kaolin	Serpentine	1/2 Biotite	Biotite	1/2 Chlorite	K Feldspar
1/2 Bericite	Garnet																
1/2 Kaolin	Serpentine																
1/2 Biotite	Biotite																
1/2 Chlorite	K Feldspar																
	2800								2743-2755 Light purple arkosic qtz. Sulphides oxidized limonite on fractures 1' cpy and sphal 2754' Cu -.5 Zn 2.0 2755-2781 Light pink to purple siltstone purple 2758-2767. All oxidized. 6" mineralization 2768 (split) bleached hornfels 2769-2781. Splices of epidote and chlorite 2781-2802 Argillaceous quartzite grades to purple siltstone at 2788-2791, mineralized 1' 2784 (split) Bleached with splashes of epidote. Bleached siltstone 2791-2797. Purple siltstone 2797-2802								
	2850								2802-2824 Bleached fine grained arkosic qtz 2824-2840 White coarse grained silicified arkosic qtz. Very minor specks black mineral possibly bornite 2840-2852 Fine grained siltstone bleached 2852-2889 Coarse grained white qtz and tuff, soricite present, minor black specks present. 2882-2885 siltstone dark gray in color 2881-2884 contains 2% py. 2889-2929 Light gray arkosic qtz banding 40-50° to core axis grades to silicified lime 2895-2929								
	2900								2929-2958 Bleached siltstone with sections of lime silicates, purple siltstone, large patches of epidote 2958-2973.5 Light gray, fine grained tuff 2973.5-2981 Very coarse grained greenish gray tuff and qtz. Mineralized slickenside at 2973.5								
	2950								2981-3001 Bleached siltstone, white to purple same as 2929-2958 3001-3018 Wind grained gray arkosic qtz. Coarse grained 3011-3018								
	3000																





Drill Hole No. 4

Collar Elevation

Coordinates

Bearing

Depth

Inclination 90°

Charleston

Cochise

County Arizona

Project

Page

By

Scale

Started

Completed

Core Recovery

Alteration

Chalcopyrite

Sphalerite

Galena

Ag

Pyrite

Rock Type

3300

++	Bericite
+	Kaolin
+	Silica
++	Chlorite

Alteration

++	Garnet
++	Serpentine
++	Biotite
++	K Feldspar

3293-3301 Bleached siltstone white to purple same as 2929-2958

3300

3301-3303 Brecciated and calcite filled arkosic qtz. Beginning of sulphide zone again 6" cpy at 3303

3350

3400

3450

3500



# GENERALIZED DESCRIPTIVE LOG

Charleston Lead Mine

Cochise County

James Stewart Construction Co.

## HORNE(STEWART)#5 DRILL HOLE

0-12	No core
12-369	Graywacke, gray, very fine-to coarse-grained, bedding 50°, locally very thin bedded, shaley, locally arkosic, volcanoclastic, and/or conglomeratic. Clasts up to 2" diam.
91-155	Conglomeratic 50% fragments of sediments and volcanics
166-173	Fracture zone; 166-167 red gouge remainder is broken core and gouge argillic, chloritic, Fe oxide
173-182	Conglomeratic, 70° fracture, argillic
191-203	Fracture zone, gouge and broken core, moderate Fe oxide, strong argillization
203-211	Calcite and clay stringers
211-213	Fracture zone
213-219	Weak Fe oxide
219-221	Fracture zone, gouge
239-259	Conglomeratic, clasts up to 2" diam., locally well broken
259-369	Massive, dark graywacke, high angle kaolin stringers
304-305	Pyritic, leached
328-329	Gouge zone, local calcite-quartz stringers
330-	15° fracture with drusy quartz
369-390	Andesite, dark green-gray, porphyritic-aphantic; feldspar phenocrysts up to 1 cm. Argillized, kaolinized, bottom on 50° fracture
390-537	Graywacke as above, kaolinized, fractured, Fe oxide in fractures
537-551	Breccia, maroon, arkosic, shaley, with clasts of graywacke up to 2". Clay along fractures, minor pyrite
551-837	Graywacke as above
551-566	Light gray pyritic rock, 1% pyrite, very fine-grained; calcite stringers, bleached, argillized
566-568	Fracture zone, finely broken, gouge
568-582	Dark gray graywacke conglomerate, clasts of shale, graywacke, volcanics drusy calcite on fractures, kaol. on slips
637-638	Fault zone 20°
651-677	Bleached, pyritic 0.5-1% pyrite, possible galena traces in fractures drusy calcite and broken core at 665
677-728	Arkosic graywacke conglomerate
728-730	Broken core
745-753	Bleached .5% pyrite on fractures
763-774	Bleached, pyrite



775-804	Irregular disseminated pyrite up to 3%, epidote	
821-837	Disseminated pyrite, argillic-intensity increasing toward bottom, abundant clots of epidote up to 1" diam.	
837-921	Alternating graywacke and light gray porphyritic andesite	
837-840	Andesite, phenocrystic plagioclase up to 2 mm, local clots of epidote and magnetite	
840-844	Graywacke	
844-846	Andesite	
846-850	graywacke	
850-853	Andesite	0.1-1% disseminated pyrite
853-862	Graywacke	
862-864	Andesite	
864-873	Graywacke	
873-875	Andesite	
875-902	Graywacke: baren	
902-903	Andesite	0.1-1% pyrite,
903-916	Graywacke, 909-912 gouge	trace chalcopryrite
916-921	Andesite	increasing with
921-936	Graywacke, galena stringer at 930	depth to 2% pyrite
936-947	Graywacke (?) thoroughly argillized, pyritized, pyrite 1-3%, galena stringers	
938-940	Gouge	
944	Bleb 5-8% pyrite, specks of sphalerite	
947-1398	Graywacke, dark gray, fine-grained, pyritic	
947-957	Calcite and pyrite stringers (2% pyrite), chloritized, bleached coarse euhedral pyrite	
957-975	1-3% disseminated pyrite	
975-985	Conglomeratic, tarnished pyrite decreasing to 1%, epidotization increasing with depth	
1007	1-2% irregular pyrite	
1017-1026	Intense alteration, pyrite 4-6%, blebs of sphalerite and galena stringers of galena-pyrite-epidote, trace chalcopryrite	
1026	Weakly chloritized, 1-2% pyrite	
1041	Fracture zone 20°, bleached 1' both sides, veins of quartz-calcite-epidote-galena-sphalerite	
	Below 1041 irregular steep quartz-calcite-pyrite-chalcopryrite-galena stringers. 1-3% disseminated pyrite	
1065-1067	Fracture zone; quartz-calcite-pyrite-chalcopryrite-sphalerite-galena strings. Galena weakening	
1080	All stringers weak. 3% pyrite decreasing with depth disappears at 1100	
1107	0.5% pyrite increasing with depth	
1115-1117	Fracture zone; broken core and gouge	

- 1117 Intense alteration or thermal metamorphism
- 1139 Pyrite decreasing with depth
- 1143 Chloritic hydrothermal alteration; trace galena
- 1147-1149 Fracture zone
- 1154 Fresh rock
- 1156 Thermal metamorphism, pyrite, epidote, recrystallization
- 1158 Chlorite-epidote-pyrite mineralization; trace galena, chalcoppyrite
- 1182 Galena-pyrite-chalcoppyrite stringers
- 1188-1191 Blebs of galena-chalcoppyrite-epidote-calcite up to 1" long. Disseminated galena-sphalerite.
- 1193 } Veins, up to 1.5", galena-pyrite-chalcoppyrite-sphalerite-
- 1195 } calcite, 15°. Disseminated galena-sphalerite
- 1197 }
- 1200 }
- 1201-1204 Broken core
- 1204 Chloritized graywacke; pyrite 1-2%
- 1212 8" quartz vein 60° 1% pyrite
- 1213 Graywacke, pyrite, stringers of galena
- 1220-1223 Quartz-pyrite vein 20°, minor galena and chalcoppyrite
- 1218-1222 5% pyrite, 0.1% Cu, 0.1% Pb
- 1230 Base metal zone
- 1230-1235 Graywacke conglomerate, clasts of sediments and volcanics up to 2" diam. 1% pyrite
- 1235-1246 Graywacke, 2% pyrite, minor epidote, pyrite decreases with depth
- 1258 2-3% pyrite, fine-grained chlorite-epidote alteration, trace galena
- 1270-1281 Conglomerate; thoroughly altered, galena-calcite-sphalerite stringers
- 1281 3" quartz-pyrite vein 50°
- 1300 Base metals zone. 0.5% pyrite
- 1308-1316 Fracture zone, no alteration, weak Fe oxides
- 1325 Chloritic, argillic alteration, 2% pyrite, rock fragments up to 8"
- 1342 Galena-epidote-calcite stringers; alteration becoming less pervasive, more irregular
- 1369 No alteration
- 1378 1/2" galena-pyrite-chalcoppyrite-sphalerite-calcite vein, 50° sulfide content increasing with depth
- 1398-1516 Gray arkosic sandstone conglomerate, clasts of sediments and volcanics. 0.5-1% disseminated pyrite, 1% galena and chalcoppyrite. Galena-chalcoppyrite-calcite stringers; chlorite-epidote, argillic alteration.

	1416	Stringers of sphalerite	] Frequency of clasts decreasing Pyrite 0.5% decreasing
	1428-1429	Quartz-calcite-pyrite vein	
	1430	Disseminated galena and chalcopryrite	
	1464	Sphalerite-epidote-quartz-chalcopryrite stringers	
	1496	Pyrite increasing to 1%	
	1502	1" sphalerite-pyrite-epidote-quartz vein, 25°	
	1510	1/4" vein same as above, 20°	
1516-1537		Gradational contact to massive light gray shale. Grades into dark very-thin-bedded shale then back to massive shale. Abundant calcite stringers. Pyrite 0.5-1%. Grades into limestone below.	
1537-1556		Light gray massive limestone, slightly recrystallized, 0.1-0.2% pyrite and few calcite stringers. Badly broken core near bottom.	
1556-1560		Light gray fine-grained quartzite, calcareous matrix 0.1% pyrite	
1560-1579		Argillaceous sandstone, with few clasts, partially epidotized, 0.5% pyrite argillic-chloritic alteration	
1579-1584		Coarse grained sandstone, no pyrite, argillic-chloritic-epidote alteration	
1584-1672		Fine-grained argillaceous sandstone 0.5% disseminated pyrite, light gray to white	
	1554-1674	Badly broken core. Local pebbles up to 1" diam. erratic pyrite distribution. Calcareous matrix below	
	1618		
	1638-1642	No core	
	1650	Silicified	
	1654-1658	Silicified sandstone or quartz vein, 10% pyrite with galena, chalcopryrite and sphalerite	
	1657-1663	Gouge, high pyrite	
	1658-1660	Lost core	
	1667-1672	Gouge	
1672-1700		Very fine-grained gray quartzite, very thinly bedded near top becoming more massive with depth, 40° on bedding, fine pyrite, 5-7% chalcopryrite minor galena.	
	1676-1700	Fine-grained, silicified, pyrite 0.5% locally, massive epidote nodules with pyrite and chalcopryrite	
1700-1704		Maroon, arkosic shale, trace pyrite, minor epidote	
1704-1795		Fine-grained argillaceous quartzite, light gray, 0.5% disseminated pyrite	
	1709	No pyrite	
	1714	Limestone inclusions	
	1718	0.5% pyrite	
	1729 and 1737	1/2" veins of quartz-sphalerite-chalcopryrite-galena with epidote rim	
	1772	Pyrite gone	
	1772-1782	Contact; 70°, with epidotic hornfelsic shale epidote-calcite nodules, trace pyrite	
	1795	End of drilling as of 24 September 1970	

GENERALIZED DESCRIPTIVE LOG (Cont.)

Charleston Lead Mine

Cochise County

James Stewart Construction Co.

HORNE (STEWART) # 5 DRILL HOLE

- |           |   |
|-----------|---|
| 1795-1805 | Quartzite, light gray, fine grained, trace of pyrite along fractures.<br>1798-1804 Fractured and bleached zone, calcite along fractures.                                  |
| 1805-1817 | Hornfelsic shale, dark gray, epidote nodules, pyrite and calcite in nodules and in stringers, 0.1-0.3% disseminated pyrite<br>1814-1817 Fracture zone, clay in stringers  |
| 1817-1824 | Quartzite, gray, calcite in stringers <0.1% pyrite  |
| 1824-1847 | Hornfelsic shale, epidote in nodules, <0.1% pyrite, dark gray with several maroon horizons; pyrite and chlorite on high-angle slips.                                      |
| 1847-1853 | Quartzite, light gray, fine-to-medium grained, 0.1% disseminated pyrite.  |
| 1853-1873 | Shale, maroon, epidote nodules, bleached with pyrite and epidote, calcite and clay on slips.  |
| 1873-1919 | Hornfelsic shales, gray, epidotized; epidote-calcite-chlorite nodules with pink matrix, <0.1% pyrite, last 20' is maroon and coarser grained.<br>1914-1917 Fracture zone. |
| 1919-1927 | Quartzite, light gray, very-fine-grained; some epidote on fractures.  |
| 1927-1947 | Hornfelsic shale, epidotized as above.  |
| 1947-1961 | Quartzite, fine grained as above.   |
| 1961-1978 | Hornfelsic shales, white to gray, epidote nodules, 0.1% disseminated pyrite.<br>1965-1966 Broken core, no pyrite below fracture.  |
| 1978-2014 | Quartzite, light gray, fine-to-medium grained. Calcite on slips, local thin beds of hornfelsic shale.   |
| 2014-2040 | Hornfelsic shale, epidote nodules with calcite, 0.1-0.2% disseminated pyrite irregularly distributed, trace of sphalerite in last 2'.                                     |
| 2040-2048 | Quartzite, light gray, locally epidotized, sphalerite in stringers and disseminated <0.1-0.2% pyrite, trace chalcopryrite, stringers of calcite.                          |



- 2048-2080 Hornfelsic shale, light to dark gray, epidote in stringers and nodules, 0.1-0.2% disseminated pyrite, trace chalcopyrite, trace galena and sphalerite in blebs and disseminated, sparse mineralization below 2064.  
2069-2074 chloritized, pyrite, sphalerite, chalcopyrite, galena disseminated in friable fractured rock.
- 2080-2083 Quartzite, chloritized, disseminated pyrite, chalcopyrite, sphalerite, galena.
- 2083-2105 Quartzite, trace of chlorite, trace disseminated pyrite, stringers of epidote-calcite-pyrite-chalcopyrite-sphalerite-galena.
- 2105-2118 Hornfelsic shale, epidotized, calcite-pyrite-epidote-sphalerite-chalcopyrite in stringers, local disseminated chalcopyrite, pyrite 0.5% decreasing with depth.
- 2118-2127 Quartzite, very fine-grained, gray, epidote-calcite stringers, < 0.1% pyrite.
- 2127-2147 Hornfelsic shale, as above.  
2130 3" long sphalerite-chalcopyrite bleb.
- 2147-2151 Quartzite as above.
- 2151-2213 Hornfelsic shale as above.  
2161 1' fracture zone  
2165 Pyrite stringers  
2169 Pyrite-epidote-calcite stringers, epidote nodules  
2191-2195 Fracture zone, finely broken, argillized, 0.5-0.1% pyrite disseminated and in veins.
- 2213-2231 Contact zone, abundant epidote-chlorite-calcite blebs and spots, 0.5-0.1% pyrite, dark gray quartzitic to volcanic rock, local phenocrysts of pink feldspar?, local intense brecciation
- 2231-2313 Dark to medium gray latite to andesite porphyry, phenocrysts are epidotized.  
1-3% disseminated pyrite  
2269-2275 Fracture zones with gouge
- 2313-2316 Contact zone, chloritized, bleached, broken rock fragments
- 2316-2318 Black, aphanitic rock with feldspar phenocrysts and epidote blebs.
- 2318-2322 Quartzite, gray, fine grained, relic bedding at 45°, interbedded with metashale at bottom, epidotized.
- 2322-2336 Hornfelsic shale as above.

2336-2374

Quartzite, light gray, fine-to-medium grained, local epidote stringers.

2352 2" dike andesite porphyry.

2369 6" of disseminated galena.

2374-2528

Alternating quartzite and hornfelsic shale, each 5 to 10' thick. Hornfelses are epidotized with minor local epidote nodules. 0.1% pyrite average distributed irregularly with no apparent control.

Broken core at 2497-2499, 2501-2507, 2514-2517

2528

End of hole.

JED:a

October 19, 1970



CHARLESTON MINE

Assay Summary

HOLE #1

<u>Depth</u>	<u>% Cu</u>	<u>oz/Ton Ag</u>	<u>oz/Ton Au</u>	<u>% Ni</u>	<u>% Pb</u>	<u>% Zn</u>
265	.09	0.4	--	--	.16	.44
280	.05	--	--	.03	--	--
315	1.0	--	--	--	--	--
360	.03	--	--	--	.09	.21
415	.10	--	--	--	.06	.10
510	.03	--	.03	--	.16	.21
525	.25	.7	.11	--	Tr	4.90
541	.01	--	--	--	.06	.12
642	.26	--	--	--	Tr	1.2
703 - 713	.08	--	--	.01	--	--
720	.08	--	--	--	--	11.40
810	.02	--	.02	--	--	--
860 - 887	--	--	--	.15	--	--
864	.055	.4	.02	--	.02	1.0
898	.04	0.7	.03	--	--	--
1102 - 1106	.485	0.7	Tr	--	--	--
1108	.095	.04	--	--	--	--
1106 - 1108	.10	3.0	Tr	--	0.6	--
1148	.035	.04	--	--	--	--
1300	.02	.02	--	--	--	--
1541	.07	.3	--	--	--	--
632 1632	.01	--	--	.03	--	--
636	.08	.5	--	.03	5.6	8.05





# CHARLESTON PROPERTY

## Assay Summary Drill Hole #2

Footage	% Cu	% Pb	% Zn	% MoS <sub>2</sub>	oz/ton	
					Au	Ag
580	.045					0.4
598	.03					0.3
620	.04					0.4
660	.035					0.3
750	.02	Tr				1.6✓
781	.03		0.9✓		.01	0.6✓
1005 - 1008	.43	4.88✓	9.2✓			
1028 - 1032	.07	.6	5.0	0.0021		
1028 - 1032	.084	.65✓	1.22✓		.003	.14
1028 - 1032	.049	.66✓	1.03✓			.11
1098 - 1107	.030	Tr	.08			
1107 - 1116.6	.041	Tr	.12			
1116.6 - 1128	.029	Tr	Tr			
1128 - 1138	.030	Tr	Tr			
1138 - 1148	.042	Tr	.05			
1148 - 1158	.021	Tr	Tr			
1158 - 1167	.068	Tr	.07			
1167 - 1179	.041	Tr	.05			
1175 - 1185	.16	.44	1.48✓	0.0028	.02	
1175 - 1185	.113	.05	1.35			.42
1175 - 1185				0.0028	.02	
1179 - 1188	.022	Tr	.06			
1188 - 1197	.051	Tr	.05			
1323 - 1331	.01	?	1.50✓	0.0021	.01	
1323 - 1331	.038	.40	.56✓			.11
1333.5 - 1337.5	.02	?	1.10✓	0.0023	.01	
1333.5 - 1337.5	.080	.05	.10✓			.04
1377 - 1382.5	.019	.12	.25			
1382.5 - 1387.5	.030	.07	.27			
1387.5 - 1391.75	.032	.07	.15			
1391.75 - 1396	.048	.24	.70✓			
1407 - 1411.5	.14	1.45✓	2.87✓			
1411.5 - 1416	.048	.10	Tr			
1416 - 1422.5	.029	.07	Tr			
1422.5 - 1429	.038	.10	.20			
1429 - 1434	.047	.12	.25			
1434 - 1439	.048	.02	.05			
1439 - 1444	.049	.30	.32			
1444 - 1448.5	.028	.25	.12			
1448.5 - 1453	.038	.13	.20			
1453 - 1457	.07	.66✓	1.40✓			
1457 - 1462	.16	.65✓	1.75✓			
1462 - 1467	.03	.05	.25			
1532 - 1534	.026	.21	.40			
1656.5 - 1661	.038	Tr	Tr			
1661 - 1665	.029	Tr	Tr			
1665 - 1670	.038	Tr	Tr			
1670 - 1675	.029	Tr	Tr			
1678 - 1680	.030	Tr	Tr			
1680 - 1685.5	.019	Tr	Tr			
1690.5 - 1694.5	.028	.05	.12			

Footcure	% Cu	% Pb	% Zn	% MoS <sub>2</sub>	oz/ton	
					Au	Ag
1694 - 1699	.028	.05	.10			
1699 - 1703	.029	.05	.12			
1703 - 1708	.027	.03	.12			
1708 - 1713	.049	.06	Tr			
1721.5 - 1726.5	.038	.36	.60 ✓			1.49 ✓
1726.5 - 1732	.101	.44	.64			1.49 ✓
1726.5 - 1732				0.0024	.02	
1726 - 1732	.10	.42	3.70 ✓	0.0024	.02	0.7
1732 - 1737	.047	.46	3.40 ✓			
1737 - 1741	.076	.03	.17			
1741 - 1745.5	.028	.12	.25			
1745.5 - 1750	.020	.07	.30			
1750.5 - 1755	.037	.07	.25			
1755 - 1759.5	.028	Tr	.05			
1759.5 - 1763.5	.047	Tr	.05			
1763.5 - 1767.5	.036	.05	.12			
1767.5 - 1772.5	.029	.03	.12			
1772.5 - 1776.5	.029	.03	Tr			
1776.5 - 1780	.037	.02	Tr			
1780.5 - 1785	.029	.03	Tr			
1785 - 1789.5	.048	.05	Tr			
1789.5 - 1793.5	.029	.02	Tr			
1793.5 - 1798.5	.048	.03	.05			
1798.5 - 1803	.037	.03	.07			
1803 - 1808	.029	.03	.07			
1808 - 1812	.037	.14	.50 ✓			
1812 - 1816	.076	.12	.40			
1816 - 1821.5	.048	Tr	Tr			
1820.5 -	1.9 ✓	.35	6.1 ✓		.02	
1821.5 - 1826.5	.029	Tr	Tr			
1826.5 - 1831	.029	Tr	Tr			
1831 - 1836	.037	Tr	Tr			
1836 - 1841	.029	Tr	Tr			
1841 - 1845	.037	Tr	Tr			
1845.5 - 1850.5	.029	.05	.02			
1850.5 - 1854.5	.21	.92 ✓	1.12 ✓	0.0025		
1850						
1850.5 - 1854	.239	.78	1.64		.01	0.2
1854.5 - 1858.5	.087	.10	.12			.27
1886 - 1889.5	.029	.02	Tr			
1893 - 1896.5	.057	Tr	Tr			
1896.5 - 1901	.029	Tr	Tr			
1901 - 1905	.037	.08	Tr			
1905 - 1910	.029	Tr	Tr			
1910 - 1915.5	.038	.02	Tr			
1915.5 - 1919	.019	Tr	Tr			
1923	.05		14.7 ✓			
1858.5 - 1862	.048	.34	.7 ✓			
1862 - 1867	.04	Tr	Tr			
1867.5 - 1872	.052	Tr	Tr			
1872 - 1876	.028	Tr	Tr			
1876.5 - 1881	.042	Tr	.05			
1881 - 1886	.028	.03	.03			
- 1923.5	.041	1.80 ✓	2.20			
1923.5 - 1928	.028	Tr	Tr			
1928 - 1931.5	.037	Tr	.07			

Footage	% Cu	% Pb	% Zn	% MoS <sub>2</sub>	oz/ton	
					Au	Ag
1931.5 - 1935	.039	Tr	.05			
1935 - 1937.5	.038	Tr	.06			
1937.5 - 1941	.030	Tr	.05			
1941 - 1946.5	.049	Tr	.03			
1946.5 - 1951	.032	Tr	Tr			
1951 - 1956	.049	Tr	Tr			
1956 - 1961	.031	Tr	Tr			
1961 - 1965.5	.042	Tr	.07			
1965.5 - 1969	.04	Tr	Tr			
1969 - 1974	.029	Tr	.05			
1974 - 1978	.041	Tr	Tr			
1978 - 1983.6	.03	Tr	.04			
1983.6 - 1988	.028	Tr	Tr			
1988 - 1993	.032	Tr	Tr			
1993 - 1998	.052	Tr	Tr			
1998 - 2002	.03	Tr	Tr			
2002 - 2007	.028	Tr	.02			
2007 - 2011	.032	Tr	.07			
2011 - 2015	.04	Tr	.04			
2015 - 2021	.042	Tr	.12			
2021 - 2024	.032	Tr	Tr			
2024 - 2027	.021	Tr	Tr			
2027 - 2031.5	.029	Tr	Tr			
2031.5 - 2036	.030	Tr	Tr			
2036 - 2040.5	.042	Tr	Tr			
2040 - 2045	.061	Tr	Tr			
2045 - 2050	.04	Tr	Tr			
2050 - 2054	.049	Tr	Tr			
2054 - 2058	.027	Tr	Tr			
2058 - 2063	.041	Tr	Tr			
2063 - 2068	.039	Tr				
2068 - 2073	.03	Tr				
2073 - 2078	.032	Tr				
2078 - 2082	.040	Tr	.05			
2082 - 2087	.059	Tr	.03			
2087 - 2092	.05	Tr	.05			
2093 - 2097	.042	Tr	.05			
2097 - 2103	.06	Tr	.045			
2103 - 2107	.072	Tr	Tr			
2107 - 2113	.039	Tr	Tr			
2113 - 2116	.04	Tr	Tr			
2116 - 2121	.062	Tr	Tr			
2121 - 2125	.03	Tr	Tr			
2125 - 2130	.042	Tr	.12			
2130 - 2135	.049	Tr	Tr			
2135 - 2139	.041	Tr	Tr			
2139 - 2144	.03	Tr	.07			
2144 - 2149	.039		.07			
2149 - 2154	.038		Tr			
2154 - 2157	.04		.05			
2157 - 2162	.031		.03			
2162 - 2167	.052		.05			
2167.5 - 2172	.03		.04			
2172 - 2176.5	.06	Tr	.07			
2176.5 - 2181	.06	Tr	.10			
2181.5 - 2185.7	.05	Tr	1.0			
2185.7 - 2189.7	.07	Tr	.9			
			.4			



Footage	% Cu	% Pb	% Zn	% MoS <sub>2</sub>	oz/ton	
					Au	Ag
2189.7 - 2195	.03	.15	.15			
2195 - 2200	.03	.12	.12			
2200 - 2205	.04	.05	.07			
2205 - 2209.5	.03	.12	.12			
2209.5 - 2214	.06	Tr	.25			
2214 - 2219	.07	Tr	.25			
2219 - 2223	.06	.14	.22			
2223 - 2229.5	.11	Tr	Tr			
2229.5 - 2236	.10	Tr	Tr			
2236 - 2241	.05	Tr	Tr			
2241 - 2245.5	.04	Tr	.05			
2246.5 - 2251.5	.05	Tr	.05			
2251.5 - 2256.5	.05	Tr	Tr			
2256.5 - 2261.5	.16	Tr	Tr			
2261.5 - 2266.5	3.40	Tr	.07			.86
2261 - 2266	3.36✓	.05	.10			.86✓
2266.5 - 2272	3.56	Tr	.05	0.0066	.02	.97
2266 - 2272	3.38	.05	.08		.002	.82
2266 - 2272	2.56	.05	.09			.97✓
2266.5 - 2272				0.0066	.02	.70
2272 - 2278	.28	Tr	Tr			
2278 - 2283	.05	Tr	Tr			
2283 - 2288	.05	Tr	1.25✓			
2288 - 2291.5	.037	Tr	.12			
2291.5 - 2293.7	.049	Tr	.05			
2293.7 - 2301	.041	Tr	Tr			
2306 - 2309	.021	Tr	.03			
2309.5 - 2314.5	.019	Tr	.05			
2314.5 - 2318.5	.020	Tr	Tr			
2318.5 - 2323.5	.022	Tr	Tr			
2323.5 - 2328	.039	Tr	.40			
2328 - 2332.5	.018	Tr	.07			
2332.5 - 2337	.04	Tr	Tr			
2337 - 2342	.06	Tr	.07			
2342 - 2347	.04	Tr	Tr			
2347 - 2351.5	.027	Tr	Tr			
2351 - 2356.5	.031	Tr	Tr			
2356.5 - 2361.5	.029	Tr	Tr			
2361.5 - 2366	.027	Tr	Tr			
2366 - 2371	.042	Tr	.03			
2371 - 2375	.031	Tr	.05			
2375 - 2380	.032	Tr	.07			
2380 - 2384	.029	Tr	Tr			
2384 - 2388	.030	Tr	Tr			
2388 - 2393	.042	Tr	Tr			
2393 - 2397.5	.029	Tr	Tr			
2397.5 - 2402	.07	Tr	Tr			
2402 - 2407	.07	Tr	.03			
2407 - 2412	.049	Tr	.02			
2412 - 2417	.03	Tr	.02			
2417 - 2421	.041	Tr	Tr			
2421 - 2426.5	.032	Tr	Tr			
2426.5 - 2430.5	.029	Tr	Tr			
2430.5 - 2435.7	.019	Tr	Tr			
2435.7 - 2440	.042	Tr	Tr			
2440 - 2445.9	.027	Tr	.07			
2445.9 - 2450	.038	Tr	.05			

<u>Footage</u>		<u>% Cu</u>	<u>% Pb</u>	<u>% Zn</u>	<u>% MoS<sub>2</sub></u>	<u>oz/ton</u>	
						<u>Au</u>	<u>Ag</u>
2450	- 2456	.04	Tr	.04			
2456	- 2461	.042	Tr	Tr			
2461	- 2464	.027	Tr	.06			
2464	- 2470	.019	Tr	Tr			
2470	- 2474	.0418	Tr	.05			
2474	- 2479	.02	Tr	Tr			
2479	- 2483	.032	Tr	Tr			
2483	- 2488	.029	Tr	.07			
2488	- 2492	.031	Tr	Tr			
2492	- 2497	.019	Tr	Tr			
2497	- 2502	.029	Tr	Tr			
2512	- 2515	.020	Tr	.03	0.0027		
2512	- 2516	.028					
2515	- 2526	.10	Tr	2.40			
2516	- 2520	.056			0.0029		
2516	- 2520	.053	.05	.05			.02
2578.25	- 2583	.09	Tr	.30			
2583	- 2588	.028	Tr	.07			
2588	- 2593	.042	Tr	1.20 ✓			
2593	- 2598	.031	Tr	.12			
2598	- 2603	.029	Tr	Tr			
2603	- 2607	.037	Tr	.07			
2607	- 2610	.04	Tr	.05			
2610	- 2615	.028	Tr	Tr			
2615	- 2620	.031	Tr	.08			
2620	- 2624	.088	Tr	.03			
2624	- 2628.5	.12	Tr	1.12 ✓			
2628.5	- 2633.5	.010					
2633.5	- 2639.5	.010					
2639.5	- 2644	.028			0.0021		
2644	- 2648.6	.048					
2648.6	- 2652	.010					
2652	- 2657.4	.026					
2657.4	- 2662	.036					
2662	- 2666.7	.026					
2666.7	- 2672	.018					
2672	- 2677	.018					
2677	- 2682	.027					
2682	- 2687	.018					
2687	- 2692	.016					
2692	- 2695.5	.016					
2695.5	- 2701	.010					
2701	- 2705	.028					
2705	- 2709	.016					
2709	- 2714	.010					
2714	- 2719	.028					
2719	- 2724.5	.010					
2724.5	- 2728	.029					
2728	- 2733	.016					
2733	- 2737.5	.018					
2845		.016					
2850		.027					
2854		.028					
2857	- 2862	.020					
2866	- 2871	.020					

Footage		% Cu	% Pb	% Zn	% MoS <sub>2</sub>	oz/ton	
						Au	Ag
2930	- 3935.5	.015					
2945	- 2947	.048					
2945	- 2947	.057					
2947	- 2949	1.03	.05	.05		.002	.15
2947	- 2949	1.11	.05	.05			.19
2947	- 2949	.83		.70	0.0027	.02	
2949	- 2951	.076			0.0022		
2951	- 2953	.67					
2953	- 2955	.36			0.0018		
2953	- 2955	3.40	.05	.22			.08
2955	- 2957	.048			0.0021		
2957	- 2959	5.52					
2959	- 2961	5.66				.002	1.09
2959	- 2961	4.57	.05	.05			1.09
2959	- 2961	6.76		.90	0.0020	.03	
2961	- 2963	.067					
2963	- 2964.5	.028					
2963	- 2964.5	.048	.05	.05			.46
2964.5	- 2966.5	.036					
2966.5	- 2968.5	.048					
2968.5	- 2969.5	.027					
2969.5	- 2971.5	.088					
2971.5	- 2973.5	.19					
2973.5	- 2975.5	.076					
2975.5	- 2977.5	.14					
2977.5	- 2979.5	.11					
3129.5	- 3134.5	.029					
3134	- 3138.5	.029					
3175	- 3178	.018					
3178	- 3181	.036					
3181	- 3183	.048					
3183	- 3185	.078					
3185	- 3187	.057					
3187	- 3189	.220					
3189	- 3190	.150					
3190	- 3195	.048					
3195	- 3199.5	.027					
1180	- 1184.5	.08	.73	2.03		.002	.30
1186	- 1191	.05	.50	.92		.003	.22
1197	- 1200	.05	1.15	1.85		.002	.40





CHARLESTON MINING PROPERTY  
Assay Summary  
Drill Hole #4

Footage	Percentage							oz/ton				ppm		
	Cu	Pb	Zn	Ni	Co	S	MoS <sub>2</sub>	Pd	Pt	Ag	Au	Mo	Co	Ni
1180	.005	.005	.010							.20	.001	4		
1478	.350	1.160	9.200							.90	.001	2		
1478	.410	1.05	8.90	.010	.006					.78				
1479.5-1481	.012	.1	.12	.012	.005					.04				
1479	.02	.71	1.48			2.62		.0013	.0014	.58	.0010	2		
1479.5-1481	.008	.022	.100							.15	.001			
1481	.069	.1	1.31	.009	.008					.08				
1481	.049	.031	1.600							.15	.001	25		
1485	.080	1.32	2.50	.008	.008					.13				
1486	.056	1.345	2.800							.30	.001	1		
1487	.009	.1	.39	.010	.008					.02				
1487	.006	.060	.310							.10	.001	3		
1494	.136	1.05	1.18	.012	.010					.27				
1494	.140	1.090	1.600							.15	.001	10		
1496	.024	.10	.10	.011	.033					.02				
1496	.015	.051	.086							.10	.001	5		
1498	.247	1.37	2.85	.011	.006					.38				
1498	.220	1.275	2.400							.40	.001	10		
1590	.029	.142	.440							.20	.001	6		
1611	.160	.222	.83							.20	.001	2		
1611	.14	.19	.83					.0014	.0016	.09	.001			
1729	.01	.10	.095			1.39		.0021	.0023	.09	.001			
1762	.290	.013	.074			1.19				.15	.001	3		
1762	1.53	.17	.13			2.26		.0025	.0026	1.46	.0038			
1791	7.70	.58	.81			8.88		.0018	.0018	5.84	.0018			
1791.5-1802	.029	.049	.073							.80	.001	45		
1791.5-1802	5.40	.24	.58	.010	.004					5.25	.002			
1791.5-1802	4.950	.234	.450							.50	.001	50		
1802	.048	.1	.05	.009	.002					.11				
1802	.052	.008	.028							.10	.001	20		
1810	1.59	.1	.10	.009	.005					.74				
1810	1.800	.029	.100							.75	.001	75		
1817.5-1822	1.400	.016	.048							.45	.001	30		
1817.5-1822	1.16	.1	.05	.011	.006					.27				
1852.5-1853.5	.020	.440	.480							.20	.001	5		
1890	.02	.32	1.93			1.22		.0018	.0018	.88	.001			
1895	.28	.25	5.3							1.3	.001	2		

Footage	Percentage							oz./ton				ppm		
	Cu	Pb	Zn	Ni	Co	S	MoS <sub>2</sub>	Pd	Pt	Ag	Au	Mo	Co	Ni
1895.5-1898.5	2.98✓	.26	6.40✓	.009	.010		.05			1.39✓	.001	2		
1898 -1902	.18	.48	2.7✓							1.5✓	.001			
1896 -1903	.53✓	.46	13.9✓	.009	.006	7.73		.0016	.0016	2.04✓				
1898.5-1902	.245✓	.37	2.00✓							1.26				
1902 -1903	.54✓	.40	10.0✓	.008	.011		.05			2.2✓	.001	1		
1902 -1903	.365	.37	10.00							2.16				
1902 -1903	.11	.005	.08							.1	.001	2		
2023 -2025	.78✓	.15	15.1✓							2.0✓	.003	1		
2097 -2099	1.15✓	.26	13.4✓					.0018	.0023	2.34✓	.0015			
2097 -2099	.690✓	.13	17.0✓	.009	.018	8.23				2.02✓				
2097.5-2099	.08	.02	2.9✓							.4	.002	1		
2099 -2101	.46✓	.03	4.0✓							.5	.002	1		
2101 -2104	.21	.04	1.41					.0021	.0030	.088	.001			
2099 -2104	.49✓	.06	12.0✓			.88		.0016	.0018	.58✓	.001			
2183 -2190	.67✓	.03	8.2✓			6.66				.8✓	.002	1		
2183.5-2190	.68✓	.03	2.4✓							.4	.001	3		
2230 -2232	.700✓	.02	1.90	.009	.005					.42✓	.001			
2230.5-2231.5	.44	.10	3.5✓							.8✓		3		
2231 -2236	.44	.10	2.80	.009	.005					.67✓				
2231.5-2236	1.30✓	.14	1.1✓							.7✓	.002	10		
2249 -2249.5	.004	.018	.02							.13	.002	4		
2276 -2278	.01	.03	.007					.0069	.0076	.09	.0016			
2424	.009	.035	17.00✓			3.15				.43	.002	2		
2438 -2439 10"	.365	.030	1.10✓							.65✓	.002	1		
2597 -2604	.080	.010	.03							.26	.002	13		
2699.5-2705.5	.05	.46	1.20							.21	.002			
1987 -1995														

#4



CARLOS ROCHIN  
MANAGER  
REGISTERED ASSAYER  
ARIZONA REG. 7126

ROCHIN ENGINEERING AND ASSAY OFFICE

P. O. BOX 218

PHONE (AC 602) 364-8092

DOUGLAS, ARIZONA - 85607

HECTOR A. ROCHIN, Jr.

MINING ENGINEER AND  
LAND SURVEYOR  
ARIZONA REG. No. 2473

ASSAYERS & METALLURGICAL CHEMISTS LOCATION:  
CERTIFICATE OF ASSAY CHARLESTON LEAD MINE  
TOMBSTONE QUAD., ARIZONA


Name Western Exploration, Drawer 1217, Douglas, Arizona D.D.H. STEWART NO.5

Attn: Mr. J. Forrester		GOLD OZS	SILVER OZS	COPPER %	Pb %	Zn %	INTERVALS	BOX NO.
30800	14462	Tr	Tr	0.058	0.25	0.79	1185 - 1189	129
30801	14463	Tr	Tr	0.058	0.31	0.96	1189 - 1191	"
30802	14464	Tr	Tr	0.068	0.32	0.78	1191 - 1193	"
30803	14465	0.08	0.78	0.116	0.34	1.68	1193 - 1195	"
30804	14466	Tr	0.18	0.280	2.88	4.27	1195 - 1197	"
30805	14467	Tr	0.08	0.165	0.64	2.29	1197 - 1198	"
30806	14468	Tr	0.02	0.145	0.22	1.69	1198 - 1200	130
30807	14469	Tr	Tr	0.129	0.27	1.29	1200 - 1202	"
30808	14470	Tr	Tr	0.068	0.37	1.28	1202 - 1204	"
30809	14471	Tr	Tr	0.087	0.25	1.09	1204 - 1206	"
30810	14472	Tr	Tr	0.097	0.25	1.00	1206 - 1208	"
30811	14473	Tr	Tr	0.107	0.32	1.08	1208 - 1210	131
30812	14474	Tr	Tr	0.078	Tr	1.18	1210 - 1212	"
30813	14475	Tr	Tr	0.078	Tr	0.98	1212 - 1220	132
30814	14476	Tr	Tr	0.089	Tr	1.28	1220 - 1222	"
30815	14477	Tr	0.02	0.097	Tr	1.86	1222 - 1224	"
30816	14478	Tr	0.02	0.078	Tr	1.97	1224 - 1226	"
30817	14479	Tr	0.18	0.107	Tr	1.19	1226 - 1228	"
30818	14480	Tr	Tr	0.087	Tr	1.27	1228 - 1233	"
30819	14481	Tr	Tr	0.068	Tr	Tr	1233 - 1237	"
30820	14482	0.02	12.32	0.087	Tr	Tr	1237 - 1242	"
30821	14483	Tr	Tr	0.079	Tr	Tr	1242 - 1248	"
30822	14484	Tr	Tr	0.068	Tr	Tr	1281 - 1282	138

REMARKS:

DATE:  
November 19, 1970

CHARGES:  
\$ 264.50





CARLOS ROCHIN  
MANAGER  
REGISTERED ASSAYER  
ARIZONA REG. 7126

ROCHIN ENGINEERING AND ASSAY OFFICE  
P. O. BOX 218 PHONE (AC 602) 364-8092  
DOUGLAS, ARIZONA - 85607

HECTOR A. ROCHIN, Jr.  
MINING ENGINEER AND  
LAND SURVEYOR  
ARIZONA REG. No. 2473

ASSAYERS & METALLURGICAL CHEMISTS  
CERTIFICATE OF ASSAY

LOCATION:  
CHARLESTON MINE  
TOMBSTONE QUAD., ARIZONA  
D.D.H. STEWART No. 5

Name Western Exploration, Drawer 1217, Douglas, Arizona

		GOLD OZS	SILVER OZS	COPPER %	Pb %	Zn %		INTERVALS	BOX No
30823	14485	Tr	Tr	0.068	tr	tr	CORE	1323 - 1325	143
30824	14486	Tr	Tr	0.058	0.10	tr		1325 - 1327	"
30825	14487	Tr	Tr	0.068	0.18	tr		1327 - 1329	"
30826	14488	0.01	1.93	0.058	0.21	0.80		1329 - 1331	"
30827	14489	Tr	0.04	0.068	0.15	tr		1331 - 1332	"
30828	14490	Tr	Tr	0.087	tr	0.50		1389 - 1394	150
30829	14491	Tr	0.08	0.079	tr	1.50		1394 - 1398	"
30830	14492	Tr	Tr	0.068	tr	tr		1398 - 1403	151
30831	14493	Tr	Tr	0.087	tr	tr		1403 - 1408	"
30832	14494	Tr	Tr	0.078	tr	tr		1408 - 1413	152
30833	14495	Tr	Tr	0.079	tr	tr		1413 - 1417	"
30834	14496	Tr	Tr	0.058	tr	tr		1417 - 1422	153
30835	14497	Tr	Tr	0.068	tr	tr		1422 - 1427	"
30836	14498	Tr	Tr	0.068	tr	tr		1427 - 1432	154
30837	14499	Tr	Tr	0.097	tr	tr		1432 - 1436	"
30838	14500	Tr	Tr	0.079	tr	tr		1436 - 1441	155
30839	14316	Tr	Tr	0.050	tr	tr		1441 - 1446	"
30840	14317	Tr	Tr	0.050	tr	tr		1512 - 1517	163
30841	14318	Tr	Tr	0.050	tr	tr		1517 - 1521	"
30842	14319	Tr	Tr	0.040	tr	tr		1605 - 1609	173
30843	14320	Tr	Tr	0.040	tr	tr		1609 - 1624	"
30844	14321	Tr	Tr	0.069	tr	tr		1624 - 1629	175
30845	14322	Tr	Tr	0.050	tr	tr			"


REMARKS:

DATE:

22 Nov 70

CHARGES:

\$ 284.50







# ASARCO GEOLOGIC LOG

Final depth 400  
Elevation  
Coordinates  
Inclination Vertical

HOLE NO. Chs-1  
Sheet No. 1  
Date Completed  
Logged by AR King

Project Charleston

From	To	Interval	Size	Spec	Recovery %	Total % Sulf.	Diss. / Fract.	Mineralization				Alteration					Rock	Remarks
								Ratio	Py	Cpy	Mo	Others	Phy	Arg	Pot	Mag		
22	22																	Blue Bit
22	181	159	NC		+85	6-8	3/1		+				✓	+				U.S. par oxidized to 150' alter is intense, breccia cavities occas. pres small fault 181-183 GRAB dike Heterolithic breccia with open cavities as above less open cavities small fault 236 & 284 good breccia w/ flu NATURE as w/ min. An per mik Gd par alter becoming more chl, mag as diss & uns. poss fault 470-490 beautiful heterolithic breccia as seen in outcrop breccia in part alter decreasing in CaCO <sub>3</sub> occurring along fract. less gneiss, lighter color, alter remains same intensity somewhat fluidize & brecciated, cpx both diss & fract. well mineral but alter decreasing silic in
181	228	47	NC		"	5-7	3/1		+				✓	+				An per
228	278	50	NC		"	4-3	3/1		+				✓	+				Δ (An per)
278	356	78	NC		"	7	3/1		+				+	✓				Δ
356	450	94	NC		"	6-8	3/1		+				+	✓				Δ
450	505	55	NE		"	3-5	4/1	100/1	+	tr			+			tr		An per
505	690	185	NC		"	5-7	3/1	100/1	+	tr			+					Δ
690	811	121	NC		"	4-6	2/1		+				+					An per
811	831	20	NC		"	6	4/1		+				+					Gd par
831	916	85	NC		"	4-5	2/1	20/1	+	tr			+					An per
916	950	34	NC		"	3-4	1/1	15/1	+	✓	?		+			tr		Gd par



## GEOLOGIC LOG

depth  
location  
ordinates  
termination

Logged by

12. King

[illegible]

HOLE NO. \_\_\_\_\_  
Sheet No. \_\_\_\_\_

Date Completed \_\_\_\_\_  
Logged by J. R.

[illegible]



From	To	Interval	Size	Spec	Recovery %	Total % Sulf.	Diss./Fract.	Mineralization				Alteration				Rock	Remarks
								Ratio	Py	Cpy	Mo	Others	Phy	Arg	Pot		
0	21		NC		+85	?	? 1/3								Lus por	Plus B.T.	
21	182															oxidized, with dikes of And por 80-100	
																132-159, alter is mod in Lus por, with in And por numerous	
																small faults 30, 80-85,	
																103, 132-133, CO <sub>2</sub> as above, alter	
182	619		NC		+85	1-3	20/1	+								Lus por "Uncle Sam" variable wk-mod, An por dikes 182-274-281, 479-463, pebble dikes frag. c. 550 w/ above faults 166 195-208, 219-221, 267-274, 289, 310, 376-403, 447, 460, 481	
619	1226		NC		+85	1-3	20/1	+								Kby Bronco volcanics contact approx, alter moderate min ser weaker An por 768-808 919-923, 942-1166 breccia 1189	
			↓													1226 - strong alter	
1226	1327		Nx		+90	1	20/1	+								An por dike - variable alt w/ some epidote	
1327	1355		Nx		+90	1-2	10/1	+								Bisbee sediments, silt-s-sed Bedding 10° alter weak to mod	
1355	1407		Nx		+75	1	20/1	+								An por as above, epidote common, mica weak	



# ASARCO GEOLOGIC LOG

HOLE NO.  
Sheet No.  
Date Comp  
Logged by

Chs-2

Project Charleston

Chs-2

Date Completed \_\_\_\_\_  
Logged by \_\_\_\_\_

2-1-SRB

[illegible]



# GEOLOGIC LOG

ASARCO  
LOGIC LOG  
Project Charleston

CHS-2W

HOLE NO.

Sheet No. 41

Date Completed

Logged by ALK

Chs-2

From	To	Interval	Size	Spec	Recovery %	Total % Sulf.	Diss./Fract.	Mineralization					Alteration				Rock	Remarks		
								Ratio	Py	Cpy	Mo	Others	Phy	Arg	Pot	Mag			Anhy	
Wedge			NX																	
2495	3415		3202 BX		90															as described on page three
			↓																	
3415	3895		BK		90	1-2	1/3	+	tr	GN	+	✓				Bisbee	siltst lime silt, sandst epidote garnet med to strong			
3895	4075		BK		70	1-2	1/2	+				tr				An por	Gd por silicification noted			
4075	4493		DX		+90	1	1/1	+	tr	GN	+	+	?			Bisbee	siltst alter strong silicification bedding 10°			
4493	4828		BK		+90	≥1	2/1	+	tr	GN	✓	✓				Bisbee	limest, congl alter weak to med silicif variable bedding 10°			
4828	4959		BK		+85	≥1	2/1	+	tr	GN						Paleozoic	marble alter 15 weak bedding 5°			
4959	4980		4985 AX		+90	2-4	3/1	+			+					An por	fine grained med alteration poor core recovery silicif noted			
			↓																	
4980	5028		AX		+80	5-2	3/1	+	tr	GN						Paleozoic	marble as before contact poor core recovery alteration wk, bedding 5° small fault 5027-28			





depth 3503  
ation  
dinates  
nation Vertical

ASARCO  
GEOLOGIC LOG

tr  
minor  
abundant  
+

HOLE NO. Chs-3  
Sheet No. 1  
Date Completed  
Logged by John R. [unclear]

Project Charleston

Chs-3

cm	To	Interval	Size	Spec	Recovery %	Total % Sulf.	Diss./Fract.	Mineralization					Alteration					Rock	Remarks
								Ratio	Py	Cpy	Mo	Others	Phy	Arg	Pot	Mag	Anhy		
0	23																		Plug B, F
23	115	92	NC		+80	7-14	-	-	+				+	+				Δ	Breccia w/ open cavity oxidation to ~ 150' pred per - 3 + US per dac + gd; phenos of plac, Hb, Qtz, Mca, Py alter bottom 10'
215	210	95	NC		+80	1-3	3/1		+					+				Dac per	breccia in part, py- filling some cavity alteration - strong faulting - 225, 255, 316 335, 355, 458, 470, 5 as before relation to breccia
560	610	50	NC 231		+85	3-6	4/1		+					+				Δ	heterolithic igneous breccia frag. alter - strong minor open cavity, Δ as above except no py phenos plag, hb, gtz heterolithic breccia above alter is decreasing
610	1070	460	NX		+85	2-5	3/1	100/1	+	tr		rub	+			tr	tr		Qtz, Mz, Plac with strong py dissem. plag at 1260 otherwise sulfide VAINING IS USUALLY NON-EXISTENT
1070	1093	23	NX		+85	2-3	5/1		+				+					Dac per	
1093	1104	11	NX		+85	2-3	2/1		+				+					Δ	
1104	1266	162	NX		+90	2-3	10/1		+			rub spall	+				✓		

# GEOLOGIC LOG

HOLE NO. Chs-3  
 Sheet No. 2  
 Date Completed  
 Logged by LRK

Chs-3

Project Charleston

From	To	Interval	Size	Spec	Recovery %	Total % Sulf.	Diss./Frac.	Mineralization					Alteration					Rock	Remarks
								Ratio	Py	Cpy	Mo	Others	Phy	Arg	Pot	Mag	Anhy		
1266	1484	218	NX		125	2	3/1	25/1	+	tr		+	tr	tr	tr	✓	Gd-por	with disseminated phenos, also plagioclase in matrix	
1484	1516	32	NX		90	2	3/1	20/1	+	✓	to 60	+	tr			✓	A	Heterolithic breccia with phenos, also plagioclase in matrix	
1516	1587	71	NX		115	1	4/1	20/1	+	✓		✓	tr			✓	Anpor	alter definitely decreasing	
1587	1930	343	NX		125	1-2	4/1	20/1	+	✓		✓	✓			✓	Gd-por	of An por of Chs-1 with K-spar phenos, alter wk to strong ser twinning	
1930	2103	173	NX		125	1	8/1	15/1	+	✓		✓	tr			✓	Gd-por	relatively unjointed K-phenos	
2103	2340	237	NX		125	1	4/1	10/1	+	✓		✓	✓			✓	Gdpor	mix and por quite possibly an intrusive breccia zone	
2340	2501	161	NX		125	1	3/1	15/1	+	✓		✓	✓			tr	Gd por-	mix and por both rocks with K-spar phenos, in part rock shows definite intrusive brecciation	
																		qtz veins & minerals prevalent	

## GEOLOGIC LOG

1 depth 3003

ation

ordinates

ation

Project

Chalcaton

Chs-3

HOLE NO.

Sheet No.

Date Completed

Logged by

JRK

From	To	Interval	Size	Spec	Recovery %	Total % Sulf.	Diss/ Fract	Mineralization					Alteration					Rock	Remarks
								Ratio	Py	Cpy	Mo	Others	Phy	Arg	Pot	Mag	Anhy		
2501	2910		NX		495	2	3/1	10/1	+	✓			+		✓	✓		HYALD	mod to strong, weak to weakly por in places not seen in Chs holes before breccia in places fault 3254 very fresh, with Kspar phenos after weak, i.e. chlorite.
2910	3003	73 TD	NX		495	≤ 1	2/1	15/1	+	✓			tr	tr	tr	tr		6d por	





Chs-1 - Table of Compos. Assays

0-1100	1100'	Approx.	.03% Cu or less			
1100-1650	550'	"	.09% Cu			
1650-2525	875'	"	.05% Cu or less			
2525-2665	140'		.15%	} 350'	.18%	} 455' .16%
2665-2875	210'		.195%			
2875-2980	105'		.12%			
2980-3180	200'		.05%			
3180-3365	185'		.135%	} 425'	.19%	
3365-3605	240'		.233%			
3605-3905	300'		.053%			
3905-4002	97'		.169%			
2525-4002	1477'		.133%			

CHARLESTON PROJECT  
Hole Chs-1

Depth	Cu	Mo	Pb	Zn
68-75	25	10	30	20
143-152	40	8	30	25
164-169	310	4	25	30
194-199	105	4	75	125
321-326	255	6	120	100
398-403	255	16	110	185
520-528	300	8	45	70
591-599	280	10	40	130
692-700	180	4	105	200
792-800	450	8	25	95
923-933	330	14	60	80
983-993	400	30	60	50
1087-1097	600	14	25	20
1257-1267	850	36	45	60
1347-1357	750	40	45	60
1442-1452	950	22	50	55
1552-1562	900	18	40	35
1632-1642	1350	14	35	20
1745-1754	20	22	30	5
1857-1867	235	2	15	10
1948-1958	610	6	35	40
1996-2006	475	4	20	5
2041-2051	135	30	20	5
2124-2134	1200	12	20	5
2207-2217	60	<2	10	5
2280-2290	630	2	10	10
2380-2390	620	10	10	5
2455-2465	1150	20	10	10
2525-2535	0.19%	12	1000	85
2612-2622	0.19%	18	20	20
2684-2694	0.19%	22	20	20
2787-2797	0.13%	16	15	15
2844-2854	0.41%	16	15	20
2919-2929	950	10	25	15
3011-3021	425	<2	15	15
3102-3112	495	2	10	15
3231-3241	1300	<2	10	30
3305-3315	0.20%	6	15	40
3401-3411	0.25%	10	15	15
3459-3469	0.21%	<2	10	35
3545-3554	0.23%	14	10	85
3626-3636	500	6	85	110
3710-3719	430	6	220	240
3849-3858	0.23%	18	15	35
3905-3914	0.26%	4	45	160
3979-3988	0.20	4	25	65
3992-4002	0.16	4	20	230

.18% - 474'

400'

.20 - 323'

325'

.21 15'


153'

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	As ppm			
1	Chs-1 68-75	<0.2	25	30	20	10				
2	143-152	<0.2	40	30	25	8				
3	164-169 <i>tr Cu?</i>	<0.2	310	25	30	4				
4	194-199		105	75	125	4				
5	321-326		255	120	100	6	5			
6	Chs-1 398-403	<0.2	255	110	185	16				

J. R. K.  
APR 20 1974

TO: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS: Trace analysis

CERTIFIED BY:



DATE REC'D: 4/20/74

DATE COMPL.: 4/24/74

JOB NUMBER: 740711


Attn.: Mr. J. R. King

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	CP-1 240-250		<0.2	15	50	185	2			
2	CP-1 330-350		0.2	15	65	180	2			
3	CP-1 370-395		<0.2	15	25	90	2			
4	Chs-2 4351-4356	<0.02	<0.2	10	45	40	8			
5	4470-4479	<0.02	<0.2	100	5	30	2			
6	4742-4747	<0.02	<0.2	15	65	70	2			
7	4971-4980	<0.02	<0.2	25	15	50	24			
8	Chs-2 5012-5021	<0.02	<0.2	35	50	320	2			

TO:

American Smelting & Refining Company

REMARKS:

Trace Analysis

CERTIFIED BY:





# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	CHS-1 520-528			300	45	70	8			
2	591-599			280	40	130	10			
3	692-700			180	105	200	4			
4	792-800			450	25	95	8			
5	CHS-1 923-933	<0.02	<0.2	330	60	80	14			

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

Trace analysis

CERTIFIED BY:



Attn.: Mr. J. R. King

DATE REC'D:


4/26/74

DATE COMPL.:

4/30/74

JOB NUMBER:


740759



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu ppm	Pb ppm	Zn ppm	Mo ppm					
1	CHS-1 983-993	400	60	50	30					
2	CHS-1 1087-1097	600	25	20	14					
3	CHS-1 1257-1267	850	45	60	36					
4	CHS-1 1347-1357	750	45	60	40					

TO:	American Smelting & Refining Company Southwestern Exploration Division P.O. Box 5747 Tucson, Arizona 85703  Attn.: Mr. J. R. King	REMARKS:	CERTIFIED BY:	
		Trace analysis		
		DATE REC'D:	DATE COMPL.:	JOB NUMBER:
		5/2/74	5/7/74	740816




# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION		Cu ppm	Pb ppm	Zn ppm	Mo ppm					
1	CHS-1	1442-1452	950	50	55	22					
2		1552-1562	900	40	35	18					
3		1632-1642	1350	35	20	14					
4	CHS-1	1745-1754	20	30	5	22					

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

Attn.: Mr. J. R. King

REMARKS:

Trace analysis

CERTIFIED BY:



DATE REC'D:


5/9/74

DATE COMPL.:

5/14/74

JOB NUMBER:

740857



# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	CHS-1 1857-1867			235	15	10	2			
2	1948-1958			610	35	40	6			
3	1996-2006			475	20	5	4			
4	2041-2051	<0.02	<0.2	135	20	5	30			
5	CHS-1 2124-2134			1200	20	5	12			

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

### REMARKS:

Trace analysis

### CERTIFIED BY:

*Charles E. Thompson*



### DATE REC'D:

5/17/74

### DATE COMPL:

5/22/74

### JOB NUMBER:

740923

Attn.: Mr. J. R. King

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	As ppm		
1	CHS-1 2207-2217			60	10	5	< 2			
2	2280-2290			630	10	10	2			
3	2380-2390	<0.02	<0.2	620	10	5	10	28		
4	CHS-1 2455-2465			1150	10	10	20			

to: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:  
Trace analysis

CERTIFIED BY:



DATE REC'D:

5/31/74

DATE COMPL.:


6/6/74

JOB NUMBER:

741018

Attn: Mr. John B. King





# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu %	Pb ppm	Zn ppm	Mo ppm					
1	CHS-1 2612-2622	0.19	20	20	18					
2	CHS-1 2525-2535	0.19	1000	85	12					

TO: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

### REMARKS:

Trace analysis  
Copper - single analysis

CERTIFIED BY



Attn.: Mr. John R. King

DATE REC'D:


6/7/74

DATE COMPL.:

6/13/74

JOB NUMBER:

741062



# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Ag ppm	Cu ppm	Cu %	Pb ppm	Zn ppm	Mo ppm	As ppm		
	<u>Series Chs-1:</u>									
1	2684-2694		>2000	0.19	20	20	22			
2	2787-2797		>2000	0.13	15	15	16			
3	2844-2854		>2000	0.41	15	20	16			
4	2919-2929	< 0.2	950		25	15	10			
5	2525-2535 (from 741062)	< 0.2						5		

American Smelting & Refining Co.  
Southwestern Exploration Division  
P. O. Box 5747  
Tucson, Arizona 85703

### REMARKS:

Trace analysis  
3 Copper single analysis

CERTIFIED BY: *[Signature]*



Attn: Mr. John R. King

DATE REC'D:


6/13/74

DATE COMPL.:

6/17/74

JOB NUMBER:

741098

**SKYLINE LABS, INC.**

Hawley & Hawley Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

**CERTIFICATE OF ANALYSIS**

ITEM NO.	SAMPLE IDENTIFICATION		Au ppm	Cu ppm	Cu %	Pb ppm	Zn ppm	Mo ppm			
1	Chs-1	3011-3021	<0.02	425		15	15	< 2			
2		3102-3112		495		10	15	2			
3		3231-3241		1300		10	30	< 2			
4		3305-3315		>2000	0.20	15	40	6			
5		3401-3411	<0.02	>2000	0.25	15	15	10			
6	Chs-1	3459-3469	<0.02	>2000	0.21	10	35	< 2			

0: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

**REMARKS:**

Trace analysis  
3 Copper - single analysis

**CERTIFIED BY:****DATE REC'D:**

6/28/74

**DATE COMPL.:**

6/29/74

**JOB NUMBER:**

741212

Attn: Mr. W. L. Kurtz

Attn.: Mr. Steven R. Davis

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu %	Pb ppm	Zn ppm	Mo ppm					
1	Chs-1 3849-3858	0.23	15	35	18					
2	Chs-1 3905-3914	0.26	45	160	4					

J. R. K.  
JUL 19 1974

To: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

CERTIFIED BY:



Attn.: Mr. S.R. Davis

DATE REC'D:

7/9/74

DATE COMPL.:

7/12/74

JOB NUMBER:

741282



# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu %	Pb ppm	Zn ppm	Mo ppm	Al	Mg	As		
1	Chs-1 3979-3988	0.20	25	65	4					
2	Chs-1 3992-4002	0.16	20	230	4					

*Reining Son  
Au Ag As* →

J. R. K.

JUL 19 1974

TO:

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

CERTIFIED BY



Attn.: Mr. S. R. Davis

DATE REC'D:


7/11/74

DATE COMPL:

7/16/74

JOB NUMBER:

741301



# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	As ppm						
1	Chs-1 3979-3988	<0.02	0.6	< 1						
2	Chs-1 3992-4002	<0.02	0.8	< 1						

Q: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

Trace analysis

CERTIFIED BY:



DATE REC'D:

DATE COMPL.:

JOB NUMBER:

7/29/74

741301-A


Attn.: Mr. S.R. Davis

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu %								
1	CHS - 1 2535-2545	0.08								
2	2545-2555	0.09								
3	2555-2565	0.20								
4	2565-2575	0.15								
5	2575-2585	0.13								
6	2585-2595	0.16								
7	2595-2605	0.08								
8	2605-2612	0.15								
9	2622-2632	0.14								
10	2632-2642	0.13								
11	2642-2652	0.21								
12	CHS - 1 2652-2662	0.17								

TO: American Smelting & Refining Co.  
Southwestern Exploration Division  
P. O. Box 5747  
Tucson, Arizona 85703  
  
Attn: Mr. W. L. Kurtz

REMARKS: Single determinations

CERTIFIED BY: *William L. Lehmbeck*

DATE REC'D: 8/5/74

DATE COMPL.: 8/13/74

JOB NUMBER: 741520

# CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu %							
	<u>Series CHS-1</u>							J. R. K.	
								AUG 20 1974	
1	2662-2672	0.11							
2	2672-2684	0.11							
3	2694-2705	0.30							
4	2705-2715	0.15							
5	2715-2725	0.16							
6	2725-2735	0.18							
7	2735-2745	0.21							
8	2745-2755	0.21							
9	2755-2765	0.17							
10	2765-2775	0.19							
11	2775-2787	0.25							
12	2797-2807	0.22							
13	2807-2817	0.20							
14	2817-2827	0.22							
15	2827-2837	0.18							
16	2837-2844	0.17							
<p>0060</p> <p>JKK</p>									
<p>TO: American Smelting &amp; Refining Co. Southwestern Exploration Division P.O. Box 5747 Tucson, Arizona 85703 Attention: Mr. John R. King</p>			<p>REMARKS: Single determination</p>		<p>CERTIFIED BY: <i>[Signature]</i></p>		<p>REGISTERED ASSAYER CERTIFICATE NO. 9413 WILLIAM J. LEINBERGER Tucson, Arizona 8/23/74</p>		
<p>DATE REC'D: 8/22/74</p>			<p>DATE COMPL.: 8/23/74</p>		<p>JOB NUMBER: 741656</p>				

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

J. F. K

## CERTIFICATE OF ANALYSIS

AUG 29 1974

ITEM NO.	SAMPLE IDENTIFICATION		Cu %							
1	CHS - 1	2854-2865	0.26							
2		2865-2875	0.24							
3		2875-2885	0.15							
4		2885-2895	0.18							
5		2895-2905	0.12							
6		2905-2915	0.10							
7		2915-2919	0.10							
8		2929-2940	0.14							
9		2940-2950	0.12							
10		2950-2960	0.12							
11		2960-2970	0.11							
12		2970-2980	0.09							
13		2980-2990	0.05							
14		2990-3000	0.05							
15		3000-3011	0.05							
16		3021-3030	0.03							
17		3030-3040	0.05							
18		3040-3050	0.04							
19		3050-3060	0.04							
20		3060-3070	0.04							
21		3070-3080	0.04							
22		3080-3090	0.10							
23		3090-3103	0.08							
24		3112-3120	0.06							
25		3120-3130	0.04							
26		3130-3140	0.09							
27		3140-3150	0.09							
28	CHS - 1	3150-3160	0.09							

TO: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

Single analysis

CERTIFIED BY:



DATE REC'D:

8/26/74

DATE COMPL.:

8/29/74

JOB NUMBER:

741694

Attn.: Mr. John King




# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION		Cu %							
1	CHS-1	3160-3170	0.05							
2		3170-3180	0.05							
3		3180-3190	0.13							
4		3190-3200	0.12							
5		3200-3210	0.10							
6		3210-3220	0.14							
7		3220-3232 *	0.11							
8		3242-3250 **	0.09							
9		3250-3260	0.16							
10		3260-3270	0.08							
11		3270-3280	0.10							
12		3280-3290	0.14							
13		3290-3305	0.20							
14		3315-3325	0.19							
15		3325-3335	0.20							
16		3335-3345	0.09							
17		3345-3355	0.06							
18		3355-3365	0.15							
19		3365-3375	0.20							
20		3375-3385	0.22							
21		3385-3401	0.25							
22		3411-3420	0.25							
23		3420-3430	0.20							
24		3430-3440	0.09							
25		3440-3450	0.16							
26		3450-3459	0.18							
27		3469-3480	0.26							
28		3480-3490	0.24							
29		3490-3500	0.28							
30		3500-3510	0.19							
31		3510-3520	0.29							
32		3520-3530	0.15							
33		3530-3545	0.33							
34		3554-3565	0.26							
35	CHS-1	3565-3575	0.16							

TO:  
American Smelting & Refining Company  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

CERTIFIED BY:

\* Sample marked 3220-3231  
\*\* Sample marked 3241-3250

Page 1 of 2

Attn.: Mr. S. R. Davis

DATE REC'D:

9/13/74

DATE COMPL.:

9/23/74

JOB NUMBER:


741873

## SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbek  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Cu %								
36	CHS-1	3575-3585	0.35							
37		3585-3595	0.32							
38		3595-3605	0.22							
39		3605-3615	0.07							
40		3615-3626	0.09							
41		3636-3645	0.05							
42		3645-3655	0.02							
43		3655-3665	0.04							
44		3665-3675	0.03							
45		3675-3685	0.01							
46		3685-3695	0.01							
47		3695-3710	0.03							
48		3719-3730	0.07							
49		3730-3740	0.01							
50		3740-3750	0.02							
51		3750-3760	0.03							
52		3760-3770	0.03							
53		3770-3780	0.02							
54		3780-3790	0.03							
55		3790-3800	0.04							
56		3800-3810	0.03							
57		3810-3820	0.04							
58		3820-3830	0.07							
59		3830-3840	0.06							
60		3840-3849	0.12							
61		3858-3870	0.07							
62		3870-3880	0.07							
63		3880-3890	0.06							
64		3890-3905	0.08							
65		3914-3925	0.21							
66		3925-3935	0.08							
67		3935-3945	0.17							
68		3945-3955	0.15							
69		3955-3965	0.09							
70		3965-3979	0.22							
71	CHS-1	3988-3992	0.09							

REMARKS: *fault*

CERTIFIED BY: *William L. Lehmbek*

TO: *cc. [unclear] + [unclear] (top-hat only) 3/12/75*

REGISTERED ASSAYER  
CERTIFICATE NO. 9425  
WILLIAM L. LEHMBECK  
DATE SIGNED 9/23/74  
ARIZONA U. S. A.

Page 2 of 2

DATE REC'D: 9/13/74

DATE COMPL.: 9/23/74

JOB NUMBER: 741873




# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS


ITEM NO.	SAMPLE IDENTIFICATION		Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm				
1	CHS-2	50-60	<0.2	5	10	65	< 2				
2		150-160	<0.2	35	15	95	< 2				
3		250-260	<0.2	10	15	60	< 2				
4		350-360	<0.2	5	10	75	< 2				
5		450-460	<0.2	45	35	120	< 2				
6		550-560	<0.2	10	50	65	< 2				
7		650-660	<0.2	5	20	65	< 2				
8		750-760	<0.2	5	20	65	< 2				
9		850-860	<0.2	15	30	65	< 2				
10	CHS-2	950-960	<0.2	5	35	35	< 2				

TO:	REMARKS:	CERTIFIED BY:
American Smelting & Refining Company P.O. Box 5747 Tucson, Arizona 85703		
Attn.: Mr. S. R. Davis	DATE REC'D: 9/27/74	DATE COMPL.: 10/2/74
		JOB NUMBER: 741959

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
P.O. Box 50106, 1700 W. Grant Rd., Tucson, Arizona 85703



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm				
1	CHS-2 1050-1060	<0.2	10	65	75	2				
2	1150-1160	<0.2	10	30	5	2				
3	1250-1260	<0.2	55	15	130	< 2				
4	1350-1360	<0.2	40	20	85	< 2				
5	1450-1460	<0.2	5	15	35	2				
6	1550-1560	<0.2	25	30	70	< 2				
7	1650-1660	<0.2	5	10	35	< 2				
8	1750-1760	<0.2	10	10	50	< 2				
9	1850-1860	<0.2	15	50	130	2				
10	1950-1960	<0.2	10	20	65	2				
11	2050-2060	<0.2	5	15	70	2				
12	2150-2160	<0.2	15	100	70	2				
13	2190-2200	<0.2	5	20	5	2				
14	2200-2210	<0.2	115	10	5	2				
15	2210-2220	<0.2	35	15	50	2				
16	CHS-2 2250-2260	<0.2	10	25	40	2				

TO: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

CERTIFIED BY:

DATE REC'D:

DATE COMPL:


Attn.: Mr. S. R. Davis

9/30/74

10/7/74

741973





# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9423

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm				
1	Chs-2 2911-2913	20.	485	5400	7600	< 2				

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

Trace analysis

CERTIFIED BY:

LEHMBECK

DATE REC'D:

DATE COMPL.:

JOB NUMBER:

12/20/74

12/20/74

712559

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	Chs-2 2988-2998	0.2	25	15	35	2			
2	Chs-2 3243-3253	0.6	210	1800	2100	2			

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

## CERTIFICATE OF ANALYSIS

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

SAMPLE IDENTIFICATION	GOLD ppm	SILVER	COPPER	LEAD	ZINC ppm	MO ppm			
Chs-2 3243-3253	<0.02								

TO: American Smelting & Refining Company  
P.O. Box 5747  
Tucson, Arizona 85703

### REMARKS:

2 Gold @ \$2.50  
1 Zinc - 1.25  
1 Molybdenum - \$1.50

CERTIFIED BY:

William L. Lehmbeck  
REGISTERED ASSAYER  
CERTIFICATE NO. 9425  
DATE SIGNED 11/11/74  
PREPARATION \$ 7.75  
ANALYSIS \$

Attn.: Mr. John R. King

DATE REC'D:

DATE COMPL:

JOB NUMBER:

11/11/74

742154-A

\$ 7.75

TO: American Smelting & Refining Company  
P.O. Box 5747  
Tucson, Arizona 85703

### REMARKS:

CERTIFIED BY:

William L. Lehmbeck  
REGISTERED ASSAYER  
CERTIFICATE NO. 9425  
DATE SIGNED 11/4/74  
PREPARATION \$ 7.75  
ANALYSIS \$

DATE REC'D:

DATE COMPL:

JOB NUMBER:

10/30/74

11/4/74

742154

Attn.: Mr. John King

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	Chs-2 3378-3388	<0.02	<0.2	55	55	250	< 2			

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

CERTIFIED BY:

*William L. Lehmbeck*  
11/14/74

DATE REC'D:

11/6/74


DATE COMPL.:

11/14/74

JOB NUMBER:

742199

Attn: Mr. John B. King



# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu %	Pb ppm	Zn ppm	Mo ppm			
	Chs-2 W 4205-4215	<0.02	27	1.04	295	220	< 2			

o: American Smelting & Refining Co.  
Southwestern Exploration Div.  
P. O. Box 5747  
Tucson, Arizona 85703

Attn: Mr. John King

REMARKS:

CERTIFIED BY:

DATE REC'D:

2/14/75

DATE COMPL:

2/26/75

JOB NUMBER:


750573

# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu %	Pb ppm	Zn ppm				
1	Chs 4195-4205	<0.02	6.6	0.53	210	530				

American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703

REMARKS:

CERTIFIED BY:



DATE REC'D:

DATE COMPL.:

JOB NUMBER:




# SKYLINE LABS, INC.

Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427

William L. Lehmbeck  
Arizona Registered Assayer No. 9425



## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	CP-1 240-250		<0.2	15	50	185	2			
2	CP-1 330-350		0.2	15	65	180	2			
3	CP-1 370-395		<0.2	15	25	90	2			
4	Cns-2 4351-4356	<0.02	<0.2	10	45	40	8			
5	4470-4479	<0.02	<0.2	100	5	30	2			
6	4742-4747	<0.02	<0.2	15	65	70	2			
7	4971-4980	<0.02	<0.2	25	15	50	24			
8	Cns-2 5012-5021	<0.02	<0.2	35	50	320	2			

TO:

American Smelting & Refining Company


REMARKS:

Trace Analysis

CERTIFIED BY:







Hawley & Hawley, Assayers and Chemists Division  
1700 W. Grant Rd., P.O. Box 50106, Tucson, Arizona 85703  
(602) 622-4836

Charles E. Thompson  
Arizona Registered Assayer No. 9427  
William L. Lehmbeck  
Arizona Registered Assayer No. 9425

## CERTIFICATE OF ANALYSIS

ITEM NO.	SAMPLE IDENTIFICATION	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm			
1	Chs-3 201-211	<0.02	<0.2	220	140	165	2			
2	602-610	<0.02	<0.2	110	65	65	8			
3	948-958	<0.02	<0.2	60	70	80	8			
4	1213-1223	<0.02	<0.2	50	30	45	2			
5	1486-1496	<0.02	3.2	870	820	1850	14			
6	1577-1587	<0.02	0.2	185	35	110	6			
7	2167-2176	<0.02	<0.2	295	40	50	16			
8	2789-2799	<0.02	<0.2	940	70	55	12			

TO: American Smelting & Refining Company  
Southwestern Exploration Division  
P.O. Box 5747  
Tucson, Arizona 85703  
Attn: Mr. John R. King

REMARKS:

Trace analysis

CERTIFIED BY



DATE REC'D:

8/13/75

DATE COMPL:

8/22/75

JOB NUMBER:

751769



R.21E.

R.22E.

24

19

26

20

21

27  
28  
29

20

21

19

14  
15  
16

18

4

T.20S.

25

30

17

29

28

5  
30  
6

7

3

22  
23  
9

24

10

11

12

13

Charleston Lead Mine

# SAMPLE SITES GEOCHEMICAL OVERLAY CHARLESTON MINING DISTRICT COCHISE CO., ARIZONA

scale 1:24,000

SEPT, 1973



ASSAYERS - CHEMISTS - METALLURGISTS

2 1973

SAMPLE SUBMITTED BY American Smelting & Refining Co.

DATE June 30, 1973

Invoice # 9411

80.00

ASSAYERS - CHEMISTS - METALLURGISTS

SAMPLE SUBMITTED BY American Smelting & Refining Company

DATE August 29, 1973

Invoice # 9716

**CHARGES \$**

75.00



THIN SECTION REPORT OF SPECIMENS

FROM CHARLESTON MINE

September 24, 1969

No. C-69-3977

Location: U.S.A.; Charleston Mine; Hole #4 @ 1,481'; H. L. Jones, Albuquerque, N. Mexico; Assay No. E-7853.

Classification: Highly altered rhyodacitic volcanic. Strongly carbonatized and saussuritized. Contains about 5% euhedral pyrite, minor v.f.g. disseminated sphalerite, and a trace of chalcopyrite. No molybdenite is present.

No. C-69-3978

Location: Ditto -3977; @ 1,500'; Assay No. E-7854.

Classification: Sample consists of small fragments up to 1/2" in size. Mineralogy as follows:

pale golden yellow sphalerite	60%
galena	10%
pyrite	5%
chalcopyrite	15%
gangue	10%

The sulphides are c.g. except for pyrite which is almost invariably surrounded and corroded by chalcopyrite. No molybdenite.

*P.S. enriched in sulphide relative to sample.*

No. C-69-3979

Location: Ditto -3977; @ 1,546'; Assay No. E-7855.

Classification: Porphyritic rhyodacite. Consists of rounded and corroded phenocrysts of quartz, phenocrysts of plagioclase and a rhyodacitic matrix. Sulphide mineralization is restricted to minor, f.g., disseminated pyrite.

EFP/lk

.....

THIN SECTION REPORT  
ON CHARLESTON PROPERTY

November 5, 1969

Preliminary thin section work was done on fifty-four diamond drill core specimens from borehole #4, Charleston Property. The specimen classification with brief explanatory notes is presented below:

<u>Sample</u>	<u>Footage</u>	<u>Classification</u>	<u>Remarks</u>
S69-920	1435'	Quartzite	Consists to over 90% of quartz grains with overgrowth in fg cementing quartz-chlorite matrix. Minor carbonate, feldspar. Well sorted.
S69-921	1460'	Quartzite	Ditto S69-920
S69-922	1477'	Quartzite	Ditto S69-920
S69-923	1488'	Quartzite	Ditto S69-920
S69-924	1506'	Quartz-andesite porphyry	Fg plagioclase-chlorite-(hornblende) matrix with phenocryst of quartz, partly saussuritized plagioclase and hornblende. Minor carbonate replacement. Green colour of phenocrysts in hand specimen is due to epidote replacing plagioclase.
S69-925	1520'	Quartz-andesite porphyry	Ditto S69-924
S69-926	1535'	Quartz-andesite porphyry	Ditto S69-924
S69-927	1570'	Quartz-andesite porphyry	Ditto S69-924



Sample	Footage	Classification	Remarks
S69-928	1604'	Lapilli tuff	Aphanitic quartz-chlorite rich matrix, holds strongly altered fragments of silicates, now largely consisting of epidote and carbonate. Some admixed clastic material.
S69-929	1630'	Tuffaceous sandstone, possibly brecciated	Very fragmental; partly a poorly sorted quartzite, but mostly a fg chlorite carbonate rock with particles of angular quartzite. Strong carbonate metasomatism.
S69-930	1640'	Tuffaceous sandstone to greywacke	A fg quartz-chlorite matrix holds abundant angular grains of quartz and some volcanic rock fragments.
S69-931	1650'	Quartzite, poorly sorted	Abundant angular quartz cemented by fg quartz matrix, partly replaced by carbonate with epidote. Some sericite.
S69-932	1670'	Arkosic quartzite	Poorly sorted, more plagioclase grains than in S69-931.
S69-933	1700'	Quartzite, poorly sorted	Mostly quartz cemented by quartz-sericite-chlorite. Some zeolites.
S69-934	1704'	Quartzite, poorly sorted	As S69-933
S69-935	1747'	Quartzite	As S69-920; quartz shows overgrowth.
S69-936	1768'	Quartz-andesite porphyry	Ditto S69-924
S69-937	1788'	Andesite porphyry	Ditto S69-924, no quartz phenocrysts
S69-938	1800'	Recrystallized greywacke?	Fragmental. A matrix of lathy quartz contains fragments of tuff, chloritic volcanics. Abundant disseminated pyrite cubes. True nature of this rock remains doubtful.

Sample	Footage	Classification	Remarks
S69-939	1812'	Arkosic quartzite	Ditto S69-932
S69-940	1817'	Recrystallized quartzite	Consists essentially of lathy quartz, some carbon metasomatism.
S69-941	1830'	Quartzite	Ditto S69-920
S69-942	1840'	Altered intermed. volcanic	Basically an altered andesite without phenocrysts
S69-943	1860'	Arkosic quartzite	Poorly sorted, as S69-932
S69-944	1880'	Arkosic quartzite	Poorly sorted.
S69-945	1890'	Quartzite	Ditto S69-920
S69-946	1898'	Quartzite	A somewhat pebbly appearance, otherwise as entry above.
S69-947	1900'	Quartzite	Ditto S69-920
S69-948	1902'	Tuffaceous sandstone?	Very fg matrix with clastic quartz grains, disseminated pyrite. Border case between a type of mudstone and tuffaceous sandstone.
S69-949	1930'	Quartzite	Ditto S69-920, but more interstitial fg matrix with much epidote and carbonate. Minor feldspar.
S69-950	1950'	Quartzite	Poorly sorted, ditto S69-931
S69-951	1975'	Quartzite	Poorly sorted, ditto S69-931
S69-952	1994'	Altered tuff	Much replacement by carbonate in coarse particles, and by epidote-amphibole in an interlocking intergrowth.
S69-953	2002'	Greywacke	Contains abundant clastic quartz and lithic fragments in a very fg interstitial quartz-chlorite-carbonate matrix.

Sample	Footage	Classification	Remarks
S69-954	2007'	Arkosic quartzite	Ditto S69-932, with abundant clastic feldspar.
S69-955	2045'	Dacite porphyry	Basically a quartz-feldspar porphyry, strong carbonate-epidote alteration. In general more sodic and silica rich than the quartz-andesite porphyries.
S69-956	2070'	Arkosic quartzite	Ditto S69-954
S69-957	2090'	Arkosic quartzite	Ditto S69-954, transitional to a greywacke.
S69-958	2115'	Tuffaceous sandstone	Mixture of clastic quartz and lithic fragments in very fg matrix; similar to S69-930.
S69-959	2125'	Tuffaceous sandstone	As above entry, less coarse particles, much matrix of ashy nature.
S69-960	2140'	Quartzite	Poorly sorted, ditto S69-931
S69-961	2150'	Quartzite	As above entry
S69-962	2180'	Quartzite	Ditto S69-920; well sorted with overgrowth of quartz.
S69-963	2210'	Greywacke	Similar to S69-953. Mixture of clastic particles in an interstitial fg quartz-chlorite-sericite-carbonate matrix.
S69-964	2240'	Arkosic quartzite	Transitional to a greywacke and a quartzite. Similar to S69-956
S69-965	2256'	Andesite porphyry	Ditto S69-937
S69-966	2276'	Andesite porphyry	Ditto S69-937
S69-967	2290'	Andesite porphyry	Ditto S69-937
S69-968	2300'	Quartzite	Poorly sorted, angular quartz, as S69-931



<u>Sample</u>	<u>Footage</u>	<u>Classification</u>	<u>Remarks</u>
S69-969	2330'	Tuff	A tuff with minor quartz sand; some lapilli; minor epidote.
S69-970	2340'	Tuffaceous sandstone	Mixture of quartz and lithic fragments in an ashy matrix; similar to S69-958
S69-971	2364'	Tuff to tuffaceous sandstone	Similar to above entry, finer grained.
S69-972	2374'	Tuff	Similar to S69-969
S69-973	2386'	Tuff	Similar to S69-969





## POLISHED SECTION REPORT

### ON CHARLESTON MINE

October 28, 1969

Three chips of diamond drill core from borehole #4, Charleston Property, Arizona, were received for polished section examination. The footages of the three specimens are given as: 1729' (S69-915); 1890' (S69-916) and 2424' (S69-917).

Specimen S69-915 @ 1729': A fine grained quartz-feldspar rich rock (latite?) carries about 5% disseminated sulfides. These are major pyrite, minor sphalerite, some galena and a very few specks of chalcopyrite. Pyrite occurs as euhedral cubes measuring up to 400 microns in diameter. Sphalerite forms very ragged, amoeba-like particles (figure 1) ranging in size up to one millimeter across. Smaller and more euhedral sphalerite grains are scattered throughout the rock matrix in minor amounts. Galena is present in trace amounts, usually in close association with sphalerite. Figure 1 shows a typical occurrence of galena as inclusions in sphalerite and as an intermittent rim around the sphalerite particle. In other places galena occurs as small isolated grains in the rock matrix. Small specks of chalcopyrite are found as inclusions in sphalerite.

Pyrite does not contain any visible inclusions of sphalerite, galena or chalcopyrite, but carries numerous inclusions of gangue constituents. A rough estimate of the relative sulfide proportion in the rock is about 85% pyrite, 10% sphalerite, <5% galena and <<1% chalcopyrite.

Specimen S69-916 @ 1890': A fine grained quartz rich rock with about 12 to 15% sulfides. Again the bulk of the sulfides is pyrite, here forming coarse grained lensoid to stringery aggregates. A small proportion of pyrite occurs as small disseminated euhedral grains in the rock matrix. Sphalerite and galena are present in minor amounts and form

angular disseminated grains, again showing a close affinity for each other (figure 2). Chalcopyrite occurs as small inclusions in sphalerite and also as minute grains disseminated throughout the matrix.

Sphalerite in this specimen lacks the ragged, amoeba shaped grain boundaries. It may contain inclusions of galena and chalcopyrite. Pyrite is full of inclusions of gangue constituents but free of other sulfide components. The relative sulfide proportions are estimated at 90% pyrite, 5% sphalerite and galena each and a trace of chalcopyrite. Silver minerals and lead sulfosalts were not observed.

Specimen S69-917 @ 2424': A fine grained volcanic (?) containing about 7% disseminated sulfides. These are mainly coarse grains of pyrite, small particles of sphalerite and a few specks of chalcopyrite. Galena was not observed.

Pyrite tends to form stringery aggregates measuring up to five millimeter in length. The individual euhedral pyrite grains measure up to half a millimeter across. Gangue inclusions in pyrite are less common than in the other two specimens, but a few minute specks of chalcopyrite were seen in some of the pyrites. Sphalerite is present as disseminated grains measuring up to 100 microns across. The relative sulfide proportions are roughly 95% pyrite, >3% sphalerite and <2% chalcopyrite.

The specimens were submitted for chemical analysis; the assay data will be reported when they become available.



