CONTACT INFORMATION
Mining Records Curator
Arizona Geological Survey
416 W. Congress St., Suite 100
Tucson, Arizona 85701
602-771-1601
http://www.azgs.az.gov
inquiries@azgs.az.gov

The following file is part of the JABA, Inc. Tombstone Mining Records

ACCESS STATEMENT

These digitized collections are accessible for purposes of education and research. We have indicated what we know about copyright and rights of privacy, publicity, or trademark. Due to the nature of archival collections, we are not always able to identify this information. We are eager to hear from any rights owners, so that we may obtain accurate information. Upon request, we will remove material from public view while we address a rights issue.

CONSTRAINTS STATEMENT

The Arizona Geological Survey does not claim to control all rights for all materials in its collection. These rights include, but are not limited to: copyright, privacy rights, and cultural protection rights. The User hereby assumes all responsibility for obtaining any rights to use the material in excess of "fair use."

The Survey makes no intellectual property claims to the products created by individual authors in the manuscript collections, except when the author deeded those rights to the Survey or when those authors were employed by the State of Arizona and created intellectual products as a function of their official duties. The Survey does maintain property rights to the physical and digital representations of the works.

QUALITY STATEMENT

The Arizona Geological Survey is not responsible for the accuracy of the records, information, or opinions that may be contained in the files. The Survey collects, catalogs, and archives data on mineral properties regardless of its views of the veracity or accuracy of those data.

VOLUME 5
BOOK 9

TOMBSTONE MINING DISTRICT
COCHISE CO., ARIZONA

TEI TRENCHING & DRILL ASSAY DATA

COPY #2
MVP/TOMBSTONE OFFICE

ELEV 4740

ASSAY REPORT

2-10-82

pg 1 of 2

	PL CN		Preg Au	Preg Ag	Effl Au	Effl Ag	Spc Ag	B Ag		Spray CN	Spray pH
1	2-10-2	0900	.031	1.26	.035	1.36	.19	.09			
2		1000		1.35				.14			
3		1100	.035	1.27	.031	1.26	.11	.10			
4		1200		1.28				.10			
5		1300	.036	1.27	.032	1.17	.11	.04		1.2	8.5
6		1400	.037	1.40				.01			
7		1500									
8		1600									
9		1700	.027	1.30		.91	.32	.05			
10		1800		1.23				.06			
11		1900	.029	1.20		.87	.28	.06			
12		2000		1.18				.07			
13		2100	.027	1.15		.75	.24	.07			
14		2200		1.19				.08			
15		2300	.027	1.19		.70	.26	.05			
16		2400									
17	2-11-2	0100	.024	1.14		.73	.30	.07			
18		0200		1.09				.03			
19		0300	.024	1.07		.68	.31	.03			
20		0400		1.07				.03			
21		0500	.023	1.04		.60	.34	.04			
22		0600		1.04				.04			
23		0700	.022	1.04		.62	.36	.02			
24		0700 Pond C	.022	.98							
25											
26	Fire Assays										
27											
28		ORC		Ag		Au					
29											
30	2-4-2	4740 10525N 0-8		13.20		.046					
31		32-37		10.35		.042					
32		37-39		13.57		.048					
33		39-44		.85		.008					
34	2-3-2	4740 10225N 0-10		.31							
35		4740 10250N 10-19		.35							
36	-6-2	4740 10475N 52-65		.26							
37		65-73		.17							
38		73-77		.05							
39		77-84		Tr							
40		84-90		.04							
		90-96		.06							

ASSAY REPORT

2-10-82

pg 18 2

	PL CN		Preg Au	Preg Ag	Eff Au	Eff Ag	Sec Ag	B Ag		Spray CN	Spray pH
1	2-10-2	0900	.031	1.26	.035	1.36	.19	.09			
2		1000		1.35				.14			
3		1100	.035	1.27	.031	1.26	.11	.10			
4		1200		1.28				.10			
5		1300	.036	1.27	.032	1.17	.11	.04		1.2	8.5
6		1400	.037	1.40				.01			
7		1500									
8		1600									
9		1700	.027	1.30		.91	.32	.05			
10		1800		1.23				.06			
11		1900	.029	1.20		.87	.28	.06			
12		2000		1.18				.07			
13		2100	.027	1.15		.75	.24	.07			
14		2200		1.19				.08			
15		2300	.027	1.19		.70	.26	.05			
16		2400									
17	-11-2	0100	.024	1.14		.73	.30	.07			
18		0200		1.09				.03			
19		0300	.024	1.07		.68	.31	.03			
20		0400		1.07				.03			
21		0500	.023	1.04		.60	.34	.04			
22		0600		1.04				.04			
23		0700	.022	1.04		.62	.36	.02			
24		0700 Pond C	.022	.95							
25											
26	Fire Assays										
27											
28		ORC		Ag		Au					
29											
30	2-4-2	4740 10525N 0-8		13.20		.046					
31		32-37		10.35		.042					
32		37-39		13.57		.048					
33		39-44		.85		.008					
34	2-3-2	4740 10225N 0-10		.31							
35		4740 10250N 10-19		.35							
36	-6-2	4740 10475N 52-65		.26							
37		65-73		.17							
38		73-77		.05							
39		77-84		Tr							
40		84-90		.04							
		90-96		.06							

(weekend)

Assay Report

2-5-82 to 2-7-82

pg 5 of 8

	A.A.			
	ORC			Ag
1	2-2-2	4740 1055ON	0-3	.18
2			3-9	.12
3			9-15	.24
4			15-21	.10
5			21-27	.12
6			27-32	.24
7			32-37	.18
8			37-42	.08
9			4248	.30
10				
11				
12				
13		Fire Assay		Ag
14				
15	2-3-2	4740 1027SN		
16			0-9	.55
17			9-18	.52
18			18-28	.50
19			28-33	.57
20		4740 10300N	0-10	.60
21			10-18	.40
22			18-27	.42
23			27-32	.47
24		4740 10350N	0-5	Tr
25			5-12	.23
26			12-19	.18
27			19-29	.64
28			29-38	.15
29			38-44	.12
30			44-49	.64
31		4740 10400N	0-5	.02
32			5-10	.01
33			10-20	.19
34			20-27	.23
35			27-38	.32
36			38-47	.22
37			47-53	.73
38			53-63	.71
39				
40				

(Weekend)

2-5-82 to 2-7-82

pg 5 of 8

Assay Report

	A.A.		ORC	Ag
1	2-2-2	4740 10550N	0-3	.18
2			3-9	.12
3			9-15	.24
4			15-21	.10
5			21-27	.12
6			27-32	.24
7			32-37	.18
8			37-42	.08
9			42-48	.30
10				
11				
12				
13		Fire Assay		Ag
14				
15	2-3-2	4740 10275N		
16			0-9	.55
17			9-18	.52
18			18-28	.50
19			28-33	.57
20		4740 10300N	0-10	.60
21			10-18	.40
22			18-27	.42
23			27-32	.47
24		4740 10350N	0-5	Tr
25			5-12	.23
26			12-19	.18
27			19-29	.64
28			29-38	.15
29			38-44	.12
30			44-49	.64
31		4740 10400N	0-5	.02
32			5-10	.01
33			10-20	.19
34			20-27	.23
35			27-38	.32
36			38-47	.22
37			47-53	.73
38			53-63	.71
39				
40				

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
P7608

Fire Assay

	ORC			Ag.
1	2-2-2	4740 10700N	0-7	2.46
2			7-14	.08
3			14-21	.04
4			21-25	.10
5			25-30	.03
6			36-42	.03
7			42-49	.08
8			49-56	.07
9	2-3-2	4740 10325N	0-5	.61
10			5-11	1.45
11			11-17	.78
12			17-23	.04
13			23-30	1.12
14			30-36	.44
15		4740 10400N		
16			MINUS 10	.20
17		4740 10375N		
18			MINUS 6-0	.08
19	2-2-2	4740 10550N	0-3	.09
20				
21				
22	2-4-2	PO	0700	.54
23			0800	.72
24			0900	1.19
25			1000	.92
26			1100	.65
27			1230	.42
28			1330	.48
29			1530	.05
30			1630	1.05
31			1730	.55
32			1830	1.10
33			1930	.74
34				
35	2-1-2	Pad #2		
36			H-3	.38
37			4	.51
38			5	.69
39			6	.86
40			7	.56

Assay Report

(Weekend)
2-5-82 to 2-7-82
pg 5 of 8

	A.A.			
	ORC		Ag	
1	2-2-2	4740 1055ON 0-3	.18	
2		3-9	.12	
3		9-15	.24	
4		15-21	.10	
5		21-27	.12	
6		27-32	.24	
7		32-37	.18	
8		37-42	.08	
9		42-48	.30	
10				
11				
12				
13		Fire Assay	Ag	
14				
15	2-3-2	4740 1027SN		
16		0-9	.55	
17		9-18	.52	
18		18-28	.50	
19		28-33	.57	
20		4740 10300N 0-10	.60	
21		10-18	.40	
22		18-27	.42	
23		27-32	.47	
24		4740 10350N 0-5	Tr	
25		5-12	.23	
26		12-19	.18	
27		19-29	.64	
28		29-38	.15	
29		38-44	.12	
30		44-49	.64	
31		4740 10400N 0-5	.02	
32		5-10	.01	
33		10-20	.19	
34		20-27	.23	
35		27-38	.32	
36		38-47	.22	
37		47-53	.73	
38		53-63	.71	
39				
40				

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
P9678

Fire Assay
ORE

			Au.
2-2-2	4740 10700N	0-7	2.46
		7-14	.08
		14-21	.04
		21-25	.10
		25-30	.03
		36-42	.03
		42-49	.08
		49-56	.07
2-3-2	4740 10325N	0-5	.61
		5-11	1.45
		11-17	.78
		17-23	.04
		23-30	1.12
		30-36	.44
	4740 10400N		
		MINUS 1-0	.20
	4740 10375N		
		MINUS 6-0	.08
2-2-2	4740 10550N	0-3	.09
2-4-2	PO	0700	.54
		0800	.72
		0900	1.19
		1000	.92
		1100	.65
		1230	.42
		1330	.48
		1530	.05
		1630	1.05
		1730	.55
		1830	1.10
		1930	.74
2-1-2	Pad #2		
		H-3	.38
		4	.51
		5	.69
		6	.85
		7	.56

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
PS4578

Acid Digestion - A.A.
ORE

			Ag
2-3-2	Pad #3	14	.90
		15	1.10
		16	.65
		17	.80
		18	.55
2-8-82	4740 10600N		
		0-5	.06
		5-8	.04
		8-14	.08
		14-17	.10
		17-23	.06
		23-30	.10
		30-35	.16
		35-42	.14
		42-45	.10
2-3-2	4740 10375N	0-8	.20
		8-12	.16
		12-20	.30
		20-30	.22
		30-40	.24
2-3-2	4740 10375N	Minus	
		14-6	.22
		23-14	.20
2-3-2	4740 10425N	0-7	.38
		7-15	.28
		15-20	.36
		20-26	.34
		26-33	.32
		33-42	.36
		42-48	.48
		48-52	.54
		52-58	.50

Assay Report

| | | |

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
P7678

Fire Assay

	ORC		Au.
1	2-2-2	4740 10700N 0-7	2.46
2		7-14	.08
3		14-21	.04
4		21-25	.10
5		25-30	.03
6		36-42	.03
7		42-49	.08
8		49-56	.07
9	2-3-2	4740 10325N 0-5	.61
10		5-11	1.45
11		11-17	.78
12		17-23	.04
13		23-30	1.12
14		30-36	.44
15		4740 10400N	
16		MINUS 1-0	.20
17		4740 10375N	
18		MINUS 6-0	.08
19	2-2-2	4740 10550N 0-3	.09
20			
21			
22	2-4-2	PO 0700	.54
23		0800	.72
24		0900	1.19
25		1000	.92
26		1100	.65
27		1230	.42
28		1330	.48
29		1530	.05
30		1630	1.05
31		1730	.55
32		1830	1.10
33		1930	.74
34			
35	2-1-2	Pad #2	
36		H-3	.38
37		4	.51
38		5	.69
39		6	.86
40		7	.56

(Weekend)

2-5-82 to 2-7-82

pg 5 of 8

Assay Report

	A.A.	ORC		Ag
1	2-2-2	4740 10550N	0-3	.18
2			3-9	.12
3			9-15	.24
4			15-21	.10
5			21-27	.12
6			27-32	.24
7			32-37	.18
8			37-42	.08
9			42-48	.30
10				
11				
12				
13		Fire Assay		Ag
14				
15	2-3-2	4740 10275N		
16			0-9	.55
17			9-18	.52
18			18-28	.50
19			28-33	.57
20		4740 10300N	0-10	.60
21			10-18	.40
22			18-27	.42
23			27-32	.47
24		4740 10350N	0-5	Tr
25			5-12	.23
26			12-19	.18
27			19-29	.64
28			29-38	.15
29			38-44	.12
30			44-49	.64
31		4740 10400N	0-5	.02
32			5-10	.01
33			10-20	.19
34			20-27	.23
35			27-38	.32
36			38-47	.22
37			47-53	.73
38			53-63	.71
39				
40				

2-11-2

Assay Report

pg 3 of 3

Fire Assays
ORC

			Au
2-8-2	4740 10425N	160-162	.14
		162-167	.53
		167-170	.75
2-9-2	4740 10400N	114-119	1.26
		119-124	.35
		124-128	.37
		128-129	.22
		129-137	.01
		140-143	Tr
		143-148	.44
		148-151	.13
		151-157	.20
		157-161	.22
		161-165	.35
		165-171	.29
		171-177	.28
2-2-2	4740 10650N	0-8	.18
		8-15	Tr
		15-19	.16
		19-25	.01
		25-31	.24
		31-35	Tr
		35-38	.01
		38-42	.05
		42-49	.22

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
PS4578

Acid Digestion - A.A.
ORE

			Ag
2-3-2	Pad #314		.90
		15	1.10
		16	.65
		17	.80
		18	.55
2-82	4740 10600N		
		0-5	.06
		5-8	.04
		8-14	.08
		14-17	.10
		17-23	.06
		23-30	.10
		30-35	.16
		35-42	.14
		42-45	.10
2-3-2	4740 10375N	0-8	.20
		8-12	.16
		12-20	.30
		20-30	.22
		30-40	.24
2-3-2	4740 10375N	Minus	
		14-6	.22
		23-14	.20
3-2	4740 10425N	0-7	.38
		7-15	.28
		15-20	.36
		20-26	.34
		26-33	.32
		33-42	.36
		42-48	.48
		48-52	.54
		52-58	.50

Assay Report

Fire Assays
ORC

2-11-2
pg 2 of 3

			Ag
2-4-2	4740 10525N	8-13	.75
		13-20	.70
		20-26	.95
		26-32	8.70
		44-49	19.49
2-8-2	4740 10600N	122-126	.19
		126-131	.14
		131-136	.71
		164-170	1.65
		170-174	1.06
		174-179	.11
		179-184	.11
		184-186	.11
		186-190	Tr
2-9-2	4740 10375N	100-106	.10
		106-110	Tr
		110-112	.11
		112-116	.09
		116-120	1.59
		120-123	.66
		123-130	1.40
		130-134	.46
		162-167	.65
		167-172	.71
		172-178	1.08
		178-185	.77
-2	4740 10425N	133-138	.18
		138-139	.55
		139-145	.46
		145-149	.45
		149-153	Tr
		153-160	Tr

2-11-2

Assay Report

pg 3 of 3

Fire Assays
ORC

			Au
2-8-2	4740 10425N	160-162	.14
		162-167	.53
		167-170	.75
2-9-2	4740 10400N	114-119	1.26
		119-124	.35
		124-128	.37
		128-129	.22
		129-137	.01
		140-143	Tr
		143-148	.44
		148-151	.13
		151-157	.20
		157-161	.22
		161-165	.35
		165-171	.29
		171-177	.28
2-2-2	4740 10650N	0-8	.18
		8-15	Tr
		15-19	.16
		19-25	.01
		25-31	.24
		31-35	Tr
		35-38	.01
		38-42	.05
		42-49	.22

2-8-82

Assay Reports

pg 2 of 3

			1	2	3	4	5	6
	Fire Assay		Au					
2-1-2	Pad #2	H 8	1.02					
2-3-2	Pad #3	2 H	.85					
		3 H	.97					
		4 HS	.82					
		5 HS	.50					
		6 HS	.54					
		7 HS	1.11					
		8 HS	.67					
		9 H	.71					
		10 H	.62					
		11 H	1.63					
		12 H	1.09					
1-28-2	Pad #2	H 9	1.30					
		H 10	1.11					
		H 11	.97					
1-28-2	Pad #4	TL 6	.04					
		TL 7	.18					
4-2	4740 10475N	0-4	.08					
		4-8	.10					
		8-10	.26					
		10-14	.21					
		14-18	.09					
		18-21	.04					
		21-27	Tr					
		27-30	Tr					
		30-33	.05					
		33-38	.06					
		38-42	.33					
		42-46	.22					
		46-52	.10					
24-2	4740 10525N	49-56	.06					
		56-61	.06					
		61-67	.20					
		67-74	.16					
		74-78	.12					
		78-85	.10					
		85-91	.08					
		91-96	.06					
		96-100	.10					
		100-106	.12					
		106-110	.08					

ASSAY REPORT

2-10-82

pg 1 of 2

			Preg		Effl		Spc	B		Spray	
	PL	CN	Av	Ag	Av	Ag	Ag	Ag		CN	pH
2-10-2		0900	.031	1.26	.035	1.36	.19	.09			
		1000		1.35				.14			
		1100	.035	1.27	.031	1.26	.11	.10			
		1200		1.28				.10			
		1300	.036	1.27	.032	1.17	.11	.04		1.2	8.5
		1400	.037	1.40				.01			
		1500									
		1600									
		1700	.027	1.30		.91	.32	.05			
		1800		1.23				.06			
		1900	.029	1.20		.87	.28	.06			
		2000		1.18				.07			
		2100	.027	1.15		.75	.24	.07			
		2200		1.19				.08			
		2300	.027	1.19		.70	.26	.05			
		2400									
-11-2		0100	.024	1.14		.73	.30	.07			
		0200		1.09				.03			
		0300	.024	1.07		.68	.31	.03			
		0400		1.07				.03			
		0500	.023	1.04		.60	.34	.04			
		0600		1.04				.04			
		0700	.022	1.04		.62	.36	.02			
		0700 Pond C	.022	.95							
	Fire Assays										
	ORC			Ag		Au					
2-4-2	4740 10525N	0-8		13.20		.046					
		32-37		10.35		.042					
		37-39		13.57		.048					
		39-44		.85		.008					
2-3-2	4740 10225N	0-10		.31							
	4740 10250N	10-19		.35							
-2	4740 10475N	52-65		.26							
		65-73		.17							
		73-77		.05							
		77-84		Tr							
		84-90		.04							
		90-96		.06							

ASSAY REPORT

2-10-82

pg 2 of 2

			Ag
	Assays ORC		
2-6-2	4740 10475N	96-104	.04
		104-110	Tr
2-2	4740 10725N	0-8	.02
		8-12	.03
		12-18	.02
		18-24	Tr
		24-31	Tr
		31-41	.04
		41-45	.04
		45-52	.04
		52-55	.08
		55-60	.06
2-6-2	4740 10500N	54-60	.07
		60-66	Tr
		66-71	Tr
		71-76	Tr
		76-83	Tr
		83-90	Tr
		90-97	.80
		97-105	.38
		105-111	.62
		111-119	.34
2-4-2	Pad #4 T	11	.42
		12	.31
		13	.40
		14	.65
		15	.70
		16	.89
2-3-2	Pad #3 HS	16	.85
		17	.80
		18	.77
2-6-2	PO	1030	.84
		1130	.89
2-4-2	Pad #4 HS	1	.46
		2	.50
		3	.59
		4	.99
		5	.30
		6	.21
		7	.18
2-4-2	Pad #4 HS	8	.12
		9	.72
		10	.50
		11	.22

ASSAY REPORT

2-10-82

pg 28 2

	ie Assays ORC			1 Ag	2	3	4		5		6
1	2-6-2	4740 10475N	96-104	.04							
2			104-110	Tr							
3	2-2	4740 10725N	0-8	.02							
4			8-12	.03							
5			12-18	.02							
6			18-24	Tr							
7			24-31	Tr							
8			31-41	.04							
9			41-45	.04							
10			45-52	.04							
11			52-55	.08							
12			55-60	.06							
13	2-6-2	4740 10500N	54-60	.07							
14			60-66	Tr							
15			66-71	Tr							
16			71-76	Tr							
17			76-83	Tr							
18			83-90	Tr							
19			90-97	.80							
20			97-105	.38							
21			105-111	.62							
22			111-119	.34							
23											
24	2-4-2	Pad #4 T 11		.42							
25			12	.31							
26			13	.40							
27			14	.65							
28			15	.70							
29			16	.89							
30	2-3-2	Pad #3 HS 16		.85							
31			17	.80							
32			18	.77							
33	2-6-2	PO 1030		.84							
34		1130		.89							
35	2-4-2	Pad #4 HS 1		.46		2-4-2 Pad #4 HS	8		.12		
36			2	.50			9		.72		
37			3	.59			10		.50		
38			4	.99			11		.22		
39			5	.30							
40			6	.21							
			7	.18							

ASSAY REPORT

2-10-82

pg 1 of 2

	PL CN	Preg Au	Preg Ag	Effl Au	Effl Ag	Spc Ag	B Ag		Spray CN	Spray pH
2-10-2	0900	.031	1.26	.035	1.36	.19	.09			
	1000		1.35				.14			
	1100	.035	1.27	.031	1.26	.11	.10			
	1200		1.28				.10			
	1300	.036	1.27	.032	1.17	.11	.04		1.2	8.5
	1400	.037	1.40				.01			
	1500									
	1600									
	1700	.027	1.30		.91	.32	.05			
	1800		1.23				.06			
	1900	.029	1.20		.87	.28	.06			
	2000		1.18				.07			
	2100	.027	1.15		.75	.24	.07			
	2200		1.19				.08			
	2300	.027	1.19		.70	.26	.05			
	2400									
-11-2	0100	.024	1.14		.73	.30	.07			
	0200		1.09				.03			
	0300	.024	1.07		.68	.31	.03			
	0400		1.07				.03			
	0500	.023	1.04		.60	.34	.04			
	0600		1.04				.04			
	0700	.022	1.04		.62	.36	.02			
	0700 Pond C	.022	.95							

Fire Assays

		ORC Ag	ORC Au
2-4-2	4740 10525N 0-8	13.20	.046
	32-37	10.35	.042
	37-39	13.57	.048
	39-44	.85	.008
2-3-2	4740 10225N 0-10	.31	
	4740 10250N 10-19	.35	
-6-2	4740 10475N 52-65	.26	
	65-73	.17	
	73-77	.05	
	77-84	Tr	
	84-90	.04	
	90-94	.06	

Assay Report

Fire Assays
ORC

2-11-2
pg 2 of 3

			AG
2-4-2	4740 10525N	8-13	.75
		13-20	.70
		20-26	.95
		26-32	8.70
		44-49	19.49
2-8-2	4740 10600N	122-126	.19
		126-131	.14
		131-136	.71
		164-170	1.65
		170-174	1.06
		174-179	.11
		179-184	.11
		184-186	.11
		186-190	Tr
2-9-2	4740 10375N	100-106	.10
		106-110	Tr
		110-112	.11
		112-116	.09
		116-120	1.59
		120-123	.66
		123-130	1.40
		130-134	.46
		162-167	.65
		167-172	.71
		172-178	1.08
		178-185	.77
-2	4740 10425N	133-138	.18
		138-139	.55
		139-145	.46
		145-149	.45
		149-153	Tr
		153-160	Tr

2-8-82

Assay Report

pg 2 of 3

		Fire Assay	Au
2-1-2	Pad #2	H 8	1.02
2-3-2	Pad #3	2 H	.85
		3 H	.97
		4 HS	.82
		5 HS	.50
		6 HS	.54
		7 HS	1.11
		8 HS	.67
		9 H	.71
		10 H	.62
		11 H	1.63
		12 H	1.09
1-28-2	Pad #2	H 9	1.30
		H 10	1.11
		H 11	.97
1-28-2	Pad #4	TL 6	.04
		TL 7	.18
4-2	4740 10475N	0-4	.08
		4-8	.10
		8-10	.26
		10-14	.21
		14-18	.09
		18-21	.04
		21-27	Tr
		27-30	Tr
		30-33	.05
		33-38	.06
		38-42	.33
		42-46	.22
		46-52	.10
24-2	4740 10525N	49-56	.06
		56-61	.06
		61-67	.20
		67-74	.16
		74-78	.12
		78-85	.10
		85-91	.08
		91-96	.06
		96-100	.10
		100-106	.12
		106-110	.08

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
P7678

Fire Assay

ORC			Ag.
2-2-2	4740 10700N	0-7	2.46
		7-14	.08
		14-21	.04
		21-25	.10
		25-30	.03
		36-42	.03
		42-49	.08
		49-56	.07
2-3-2	4740 10325N	0-5	.61
		5-11	1.45
		11-17	.78
		17-23	.04
		23-30	1.12
		30-36	.44
	4740 10400N		
		MINUS -10	.20
	4740 10375N		
		MINUS 6-0	.08
2-2-2	4740 10550N	0-3	.09
2-4-2	PO	0700	.54
		0800	.72
		0900	1.19
		1000	.92
		1100	.65
		1230	.42
		1330	.48
		1530	.05
		1630	1.05
		1730	.55
		1830	1.10
		1930	.74
2-1-2	Pad #2		
		H-3	.38
		4	.51
		5	.69
		6	.86
		7	.56

(Weekend)

2-5-82 to 2-7-82

pg 5 of 8

Assay Report

			A.A. Au
			ORC
2-2-2	4740 10550N	0-3	.18
		3-9	.12
		9-15	.24
		15-21	.10
		21-27	.12
		27-32	.24
		32-37	.18
		37-42	.08
		42-48	.30
			Fire Assay Au
2-3-2	4740 10275N		
		0-9	.55
		9-18	.52
		18-28	.50
		28-33	.57
	4740 10300N	0-10	.60
		10-18	.40
		18-27	.42
		27-32	.47
	4740 10350N	0-5	Tr
		5-12	.23
		12-19	.18
		19-29	.64
		29-38	.15
		38-44	.12
		44-49	.64
	4740 10400N	0-5	.02
		5-10	.01
		10-20	.19
		20-27	.23
		27-38	.32
		38-47	.22
		47-53	.73
		53-63	.71

Assay Report

2-8-82

Pg 3 of 3

		Fire Assay	Au
1	2-2-2	4740 10675N	
2		0-9	1.53
3		9-16	1.68
4		16-22	2.42
5		22-28	.47
6		28-35	.04
7		35-43	.16
8		43-49	.31
9		49-51	.38
10		51-60	.53
11	2-5-2	4740 10550N 48-54	
12		54-57	
13		57-62	
14		62-68	
15		68-74	
16		74-79	.01
17		79-86	
18		86-91	
19		91-96	
20		96-100	

Assay Report

2-4-82

pg 2 of 3

AA

ORC

				Au
2-2-2	CO	0700		1.25
		0800		1.40
		0900		1.30
		1000		1.55
		1100		1.60
		1200		1.15
		1300		.70
		1600		.60
		1700		1.00
		1800		.75
		1900		.80
		2000		1.50
		2100		1.25
		2200		1.10
		2300		1.45
2-3-2	CO	0630		1.30
		0730		1.40
		0830		1.60
2-2-2	PO	0700		.90
		0800		.70
		0900		.80
		1000		1.05
		1100		1.40
		1200		2.90
		1300		.65
-2	4740 10625N	0-8		.08
		8-13		.08
		13-20		.18
		20-29		.08
		29-35		.06
		35-39		.06
		39-44		.08
		44-50		.06
2-2	4740 10575N	0-6		.06
		6-7		.04
		7-10		.04
		10-16		.04
		16-22		.04
			4740 10575N	22-27 .04
				27-33 .06
				33-39 .06
				39-47 .10

(Weekend)

2-5-82 to 2-7-82

PS4578

ASSAY REPORT

Acid Digestion - A.A.

ORC

			Au
2-3-2	Pad #314		.90
		15	1.10
		16	.65
		17	.80
		18	.55
2-82	4740 10600N		
		0-5	.06
		5-8	.04
		8-14	.08
		14-17	.10
		17-23	.06
		23-30	.10
		30-35	.16
		35-42	.14
		42-45	.10
2-3-2	4740 10375N	0-8	.20
		8-12	.16
		12-20	.30
		20-30	.22
		30-40	.24
2-3-2	4740 10375N	Minus	
		14-6	.22
		23-14	.20
2-3-2	4740 10425N	0-7	.38
		7-15	.28
		15-20	.36
		20-26	.34
		26-33	.32
		33-42	.36
		42-48	.48
		48-52	.54
		52-58	.50

Assay Report

Fire Assays
ORC

2-11-2
pg 2 of 3

			AG	
2-4-2	4740 10525N	8-13	.75	
		13-20	.70	
		20-26	.95	
		26-32	8.70	
		44-49	19.49	
2-8-2	4740 10600N	122-126	.19	
		126-131	.14	
		131-136	.71	
		164-170	1.65	
		170-174	1.06	
		174-179	.11	
		179-184	.11	
		184-186	.11	
		186-190	Tr	
2-9-2	4740 10375N	100-106	.10	
		106-110	Tr	
		110-112	.11	
		112-116	.09	
		116-120	1.59	
		120-123	.66	
		123-130	1.40	
		130-134	.46	
		162-167	.65	
		167-172	.71	
		172-178	1.08	
		178-185	.77	
-2	4740 10425N	133-138	.18	
		138-139	.55	
		139-145	.46	
		145-149	.45	
		149-153	Tr	
		153-160	Tr	

Assay Report

2-4-82

pg 2 of 3

AA

ORC

				Au
1	2-2-2	CO	0700	1.25
2			0800	1.40
3			0900	1.30
4			1000	1.55
5			1100	1.60
6			1200	1.15
7			1300	.70
8			1600	.60
9			1700	1.00
10			1800	.75
11			1900	.80
12			2000	1.50
13			2100	1.25
14			2200	1.10
15			2300	1.45
16	2-3-2	CO	0630	1.30
17			0730	1.40
18			0830	1.60
19				
20	2-2-2	PO	0700	.90
21			0800	.70
22			0900	.80
23			1000	1.05
24			1100	1.40
25			1200	2.90
26			1300	.65
27				
28	-2	4740 10625N	0-8	.08
29			8-13	.08
30			13-20	.18
31			20-29	.08
32			29-35	.06
33			35-39	.06
34			39-44	.08
35			44-50	.06
36				
37	-2-2	4740 10575N	0-6	.06
38			6-7	.04
39			7-10	.04
40			10-16	.04
			16-22	.04

			Au
4740 10575N	22-27		.04
	27-33		.06
	33-39		.06
	39-47		.10

2-11-2

Assay Report

Fire Assays
ORC

			Au
2-8-2	4740 10425N	160-162	.14
		162-167	.53
		167-170	.75
2-9-2	4740 10400N	114-119	1.26
		119-124	.35
		124-128	.37
		128-129	.22
		129-137	.01
		140-143	Tr
		143-148	.44
		148-151	.13
		151-157	.20
		157-161	.22
		161-165	.35
		165-171	.29
		171-177	.28
2-2-2	4740 10650N	0-8	.18
		8-15	Tr
		15-19	.16
		19-25	.01
		25-31	.24
		31-35	Tr
		35-38	.01
		38-42	.05
		42-49	.22

Assay Report

2-8-82

pg 3 of 3

		Fire Assay	Au
1	2-2-2	4740 10675N	
2		0-9	1.53
3		9-16	1.68
4		16-22	2.42
5		22-28	.47
6		28-35	.04
7		35-43	.16
8		43-49	.31
9		49-51	.38
10		51-60	.53
11	2-5-2	4740 10550N 48-54	Tr
12		54-57	Tr
13		57-62	Tr
14		62-68	Tr
15		68-74	Tr
16		74-79	.01
17		79-86	Tr
18		86-91	Tr
19		91-96	Tr
20		96-100	Tr

ASSAY REPORT

(Weekend)
2-5-82 to 2-7-82
P7678

Fire Assay

			Ag.
ORC			
2-2-2	4740 10700N	0-7	2.46
		7-14	.08
		14-21	.04
		21-25	.10
		25-30	.03
		36-42	.03
		42-49	.08
		49-56	.07
2-3-2	4740 10325N	0-5	.61
		5-11	1.45
		11-17	.78
		17-23	.04
		23-30	1.12
		30-36	.44
	4740 10400N		
		MINUS 10	.20
	4740 10375N		
		MINUS 6-0	.08
2-2-2	4740 10550N	0-3	.09
2-4-2	PO	0700	.54
		0800	.72
		0900	1.19
		1000	.92
		1100	.65
		1230	.42
		1330	.48
		1530	.05
		1630	1.05
		1730	.55
		1830	1.10
		1930	.74
2-1-2	Pad #2		
		H-3	.38
		4	.51
		5	.69
		6	.86
		7	.56

ASSAY REPORT

2-10-82

pg 2 of 2

Fire Assays
ORC

				Ag
2-6-2	4740 10475N	96-104		.04
		104-110		Tr
2-6-2	4740 10725N	0-8		.02
		8-12		.03
		12-18		.02
		18-24		Tr
		24-31		Tr
		31-41		.04
		41-45		.04
		45-52		.04
		52-55		.08
		55-60		.06
2-6-2	4740 10500N	54-60		.07
		60-66		Tr
		66-71		Tr
		71-76		Tr
		76-83		Tr
		83-90		Tr
		90-97		.80
		97-105		.38
		105-111		.62
		111-119		.34
2-4-2	Pad #4 T	11		.42
		12		.31
		13		.40
		14		.65
		15		.70
		16		.89
2-3-2	Pad #3 HS	16		.85
		17		.80
		18		.77
2-6-2	PO	1030		.84
		1130		.89
2-4-2	Pad #4 HS	1		.46
		2		.50
		3		.59
		4		.99
		5		.30
		6		.21
		7		.18
2-4-2	Pad #4 HS	8		.12
		9		.72
		10		.50
		11		.22

ELEV. 4730

Assay Report

2-2-82

pg 3 of 3

	ORC		AGOT
1-27-2	4730W 10925N	0-5	.10
		5-12	.12
		12-17	.08
		17-23	.10
		23-29	.08
		29-36	.06
		36-43	.06
		43-51	.12
		51-59	.10
1-27-2	4680W 11300N	0-10	.20
		10-15	.12
		15-19	.48

Assay Report

2-182

pg 474

		ORC		AGOT							
1	1-27-2	4730W 10950N	0-9	.04							
2			9-17	.08							
3			17-24	.04							
4			24-31	.04							
5			31-38	.06							
6			38-44	.04							
7			44-51	.04							
8			51-57	.04							
9											
10		4730W 10975N	0-8	.06							
11			8-14	.06							
12			14-23	.04							
13			23-30	.06							
14			30-37	.04							
15			37-44	.04							
16			44-51	.06							
17			51-58	.06							
18			58-65	.06							
19			65-72	.04							
20											
21		4730W 11000N	0-8	.12							
22			8-16	.08							
23			16-23	.08							
24			23-30	.06							
25			30-39	.08							
26			39-45	.06							
27			45-48	.06							
28			48-55	.08							
29			55-62	.10							
30			62-69	.08							
31			69-76	.06							
32			76-81	.08							
33										AGOT	
34	1-26-2	4730W 11050N	0-7	.04	1-26-2	4730W 11050N	51-56	.04			
35			7-14	.04			56-63	.06			
36			14-19	.04			63-69	.04			
37			19-26	.04			69-74	.04			
38			26-36	.04							
39			36-42	.04							
40			42-47	.04							
			47-51	.04							

Assay Report

2-182

pg. 474

			ORC AG-OT									
1-27-2	4730W 10950N	0-9	.04									
		9-17	.08									
		17-24	.04									
		24-31	.04									
		31-38	.06									
		38-44	.04									
		44-51	.04									
		51-57	.04									
	4730W 10975N	0-8	.06									
		8-14	.06									
		14-23	.04									
		23-30	.06									
		30-37	.04									
		37-44	.04									
		44-51	.06									
		51-58	.06									
		58-65	.06									
		65-72	.04									
	4730W 11000N	0-8	.12									
		8-16	.08									
		16-23	.08									
		23-30	.06									
		30-39	.08									
		39-45	.06									
		45-48	.06									
		48-55	.08									
		55-62	.10									
		62-69	.08									
		69-76	.06									
		76-81	.08									
1-26-2	4730W 11050N	0-7	.04	1-26-2	4730W 11050N	51-56	.04	AG-OT				
		7-14	.04			56-63	.06					
		14-19	.04			63-69	.04					
		19-26	.04			69-74	.04					
		26-36	.04									
		36-42	.04									
		42-47	.04									
		47-51	.04									

Assay Report

2-182

pg 474

	ORC		AGOT				AGOT
1-27-2	4730W 10950N	0-9	.04				
		9-17	.08				
		17-24	.04				
		24-31	.04				
		31-38	.06				
		38-44	.04				
		44-51	.04				
		51-57	.04				
	4730W 10975N	0-8	.06				
		8-14	.06				
		14-23	.04				
		23-30	.06				
		30-37	.04				
		37-44	.04				
		44-51	.06				
		51-58	.06				
		58-65	.06				
		65-72	.04				
	4730W 11000N	0-8	.12				
		8-16	.08				
		16-23	.08				
		23-30	.06				
		30-39	.08				
		39-45	.06				
		45-48	.06				
		48-55	.08				
		55-62	.10				
		62-69	.08				
		69-76	.06				
		76-81	.08				
1-26-2	4730W 11050N	0-7	.04	1-26-2	4730W 11050N	51-56	.04
		7-14	.04			56-63	.06
		14-19	.04			63-69	.04
		19-26	.04			69-74	.04
		26-36	.04				
		36-42	.04				
		42-47	.04				
		47-51	.04				

Assay Report

2-2-82
pg 2 of 3

				Au oz/T
	ORC			
1-30-2	CO	1000		.55
		1100		.60
		1200		1.10
		1300		1.05
		1400		.40
		1500		.40
		1600		.40
		1700		.35
		1800		.40
		1900		.40
		2030		.35
		2130		.45
1-30-2	PO	1000		.60
		1100		.60
		1200		.55
		1300		.65
		1400		.50
		1500		.45
		1600		.45
		1700		.40
		1800		.55
		1900		.45
		2000		.40
		2100		.45
1-27-2	4730W 11025N	0-8		.04
		8-16		.06
		16-21		.06
		21-29		.04
		29-37		.04
		37-44		.06
		44-46		.04
		46-53		.12
		53-59		.10
		59-66		.10
		66-74		.10
		74-81		.08

Assay Report

2-182

pg. 474

	ORC		AGOT				AGOT
1-27-2	4730W 10950N	0-9	.04				
		9-17	.08				
		17-24	.04				
		24-31	.04				
		31-38	.06				
		38-44	.04				
		44-51	.04				
		51-57	.04				
	4730W 10975N	0-8	.06				
		8-14	.06				
		14-23	.04				
		23-30	.06				
		30-37	.04				
		37-44	.04				
		44-51	.06				
		51-58	.06				
		58-65	.06				
		65-72	.04				
	4730W 11000N	0-8	.12				
		8-16	.08				
		16-23	.08				
		23-30	.06				
		30-39	.08				
		39-45	.06				
		45-48	.06				
		48-55	.08				
		55-62	.10				
		62-69	.08				
		69-76	.06				
		76-81	.08				
1-26-2	4730W 11050N	0-7	.04	1-26-2	4730W 11050N	51-56	.04
		7-14	.04			56-63	.06
		14-19	.04			63-69	.04
		19-26	.04			69-74	.04
		26-36	.04				
		36-42	.04				
		42-47	.04				
		47-51	.04				

Assay Report (Weekend) 1-29-2 to 1-31-2

Pg 5 of 5

	ORC		AuOT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46	.04	
		134-140	.64			46-52	.04	
		140-146	.04			71-77	.04	
		146-151	.04					
1-7-2	4680 CC17	154-168	.06	1-26-2	4730W 11220N	49-55	.08	
	4680 CC17N	107-115	.04			55-61	.06	
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42	.04	
		124-129	.04			42-49	.04	
1-8-2	4680 CC17S	0-10	1.08			49-56	.06	
		10-20	.56			56-62	.04	
1-41-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

Assay Report

(weekend)
1-29-2 to 1-31-2
pg 5 of 5

	ORC		AuOT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46		.04
		134-140	.64			46-52		.04
		140-146	.04			71-77		.04
		146-151	.04					
1-7-2	4680 CC17	154-165	.06	1-26-2	4730W 11220N	49-55		.08
	4680 CC17N	107-115	.04			55-61		.06
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42		.04
		124-129	.04			42-49		.04
						49-56		.06
1-8-2	4680 CC17S	0-10	1.08					
		10-20	.56			56-62		.04
1-11-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

Assay Report

1-28-2
pg 1 of 3

	ORC		AGOT			AGOT
1-7-2	4680 CC165	0-9	.08	1-7-2	4680 CC17	
		9-16	.62		0-10	.56
		16-21	.28		10-15	.32
		21-25	1.12		15-22	.16
		25-28	.26		22-26	.44
		28-35	.50		26-33	.16
		35-42	.22		33-41	.14
		42-47	.28		41-44	1.64
		47-53	.20		44-52	1.90
		53-61	.28		52-56	3.26
		61-64	.26		56-58	1.18
		64-68	.48		58-64	1.44
		68-72	.28		64-70	.62
		72-75	.24		70-75	.10
		75-81	2.28		75-82	.08
		81-82	2.14		82-86	.06
		82-88	.44		86-92	.14
		88-90	.12		92-97	.08
		90-97	.18		97-106	.06
		97-105	.10		106-114	.06
		105-113	.06		114-120	.06
		113-118	.04		120-127	.10
		118-124	.08		127-134	.06
		124-130	.10		141-149	.06
		130-132	.10		149-154	.06
		132-134	.02			
1-26-2	4730W 11125N	0-7	.04			
		7-11	.04			
		11-17	.02			
		17-23	.02			
		23-28	.04			
		28-34	.04			
		34-40	.04			
		40-43	.12			
		43-51	.20			
		51-58	.18			
		58-65	.08			
		65-71	.10			

Assay Report

	ORC		AuOT					AuOT	
1-19-2	42N	166-173	.12		1-20-2	4-730W 11150N	8-14	.06	1
		173-178	.14				14-21	.04	2
		178-183	.14				21-28	.06	3
		183-189	.06				28-34	.10	4
		189-195	.10				34-41	.14	5
		195-200	.04				41-47	.14	6
		200-208	.06				47-53	.06	7
		208-213	.10				53-58	.08	8
		213-220	.06				58-65	.04	9
		220-227	.14				65-71	.06	10
		227-232	.06				71-76	.10	11
		232-240	.08		1-20-2	42	0-9	.10	12
		240-247	.08				9-13	.06	13
		247-252	.06				13-21	.06	14
		252-258	.06				21-27	.04	15
		258-265	.04				27-33	.08	16
		265-270	.06				33-40	.06	17
		270-275	.04				40-47	.08	18
		275-281	.08				47-55	.06	19
		281-288	.08				55-61	.10	20
		288-297	.06				61-66	.08	21
		297-308	.10				66-70	.08	22
		308-320	.08				70-78	.20	23
1-18-2	41S	0-8	.10				78-85	.44	24
		162-170	.14				85-89	.22	25
		176-181	.16				89-95	.14	26
		189-199	.14				95-100	.12	27
		199-208	.10				100-109	.06	28
		208-213	.10				109-113	.08	29
		213-219	.12				113-121	.04	30
		219-226	.08				121-126	.08	31
		226-232	.12						32
		232-237	.08						33
		237-243	.08						34
		243-249	.06						35
		249-252	.10						36
		252-259	.12						37
		259-269	.14						38
1-21-2	Jim Special		.10						39
									40

Assay Report

1-22-2 to 1-24-2

PS 4074

	ORC		AGOT					AGOT
1-20-2	42	288-294	.06		1-12-2	4730W 11175	0-7	.04
		294-299	.04				7-14	.06
		299-305	.04				14-19	.04
	425	0-10	.06				19-25	.04
		10-15	.04				25-29	.04
		15-20	.08				29-32	.06
		20-26	.08				32-36	.04
		26-32	.20				36-39	.04
		32-37	.60				39-44	.04
		37-43	5.92				44-49	.06
		43-49	.54				62-66	.06
		49-53	.18				66-71	.08
		53-60	.16		1-21-2	4730W 11200	0-7	.02
		60-66	.06				7-10	.02
		66-74	.06				10-16	.02
		74-84	.06		1-22-2	#1 Special Quartz		.04
		84-93	.04					
		93-100	.04					
		100-107	.04					
		107-113	.02					
		113-120	.02					
		120-128	.08					
		128-138	.04					
		138-146	.04					
		146-154	.06					
		154-163	.04					
		163-170	.06					
		170-179	.04					
		179-186	.04					
		186-194	.02					
		194-200	.06					
		200-208	.02					
		208-215	.02					
		215-224	.02					
		224-234	.04					
		234-241	.02					
		241-248	.04					
		248-255	.04					
		255-260	.04					
		264-268	.02					
		264-274	.06					
		274-280	.02					

Assay Report

1-22-2 to 1-24-2

PS 4 of 4

	ORC		AGOT					AGOT
1-20-2	42	288-294	.06		1-12-2	4730W 11175	0-7	.04
		294-299	.04				7-14	.06
		299-305	.04				14-19	.04
	42S	0-10	.06				19-25	.04
		10-15	.04				25-29	.04
		15-20	.08				29-32	.06
		20-26	.08				32-36	.04
		26-32	.20				36-39	.04
		32-37	.60				39-44	.04
		37-43	5.92				44-49	.06
		43-49	.54				62-66	.06
		49-53	.18				66-71	.08
		53-60	.16		1-21-2	4730W 11200	0-7	.02
		60-66	.06				7-10	.02
		66-74	.06				10-16	.02
		74-84	.06		1-22-2	#1 Special Quartz		.04
		84-93	.04					
		93-100	.04					
		100-107	.04					
		107-113	.02					
		113-120	.02					
		120-128	.08					
		128-138	.04					
		138-146	.04					
		146-154	.06					
		154-163	.04					
		163-170	.06					
		170-179	.04					
		179-186	.04					
		186-194	.02					
		194-200	.06					
		200-208	.02					
		208-215	.02					
		215-224	.02					
		224-234	.04					
		234-241	.02					
		241-248	.04					
		248-255	.04					
		255-260	.04					
		264-268	.02					
		264-274	.06					
		274-280	.02					

Assay Report

1-26-2
pg. 173

	ORC		AGOT				
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06
		0930	.95			15-22	.04
		1030	.60			22-30	.06
		1130	.55			30-39	.04
		1230	.50			39-45	.04
		1330	1.35			45-51	.02
		1330	4.70			51-53	.02
		1430	1.40			53-62	.02
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04
		0800	.80			7-13	.02
		0900	.55			13-19	.06
		1000	.65			19-25	.04
		1100	.60			25-32	.04
		1200	.55			32-39	.02
		1300	.50			52-56	.18
						56-62	.24
1-23-2	Tails Pad #1		.70				
				1-21-2	4730W 11250N	0-9	.12
12-28-1	DH 5B	0-20	.08			9-13	.12
12-29-1	6SB	0-20	.08			13-19	.14
12-30-1	11SB	0-20	.10			19-25	.14
12-31-1	11GB	0-20	.14			25-29	.12
12-30-1	12GB	0-20	.12			29-36	.14
12-31-1	14GB	0-20	.18			49-55	.12
	C13	0-20	.12			55-64	.18
	C13	0-20	.10			64-68	.20
1-11-2	4480 CC19S	4-7	.10				
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN pH 8.5			
		20-25	.08				
		25-30	.02				
		30-36	.04				
		36-43	.02				
		43-49	.02				
		61-67	.04				
		67-69	.08				
		69-74	.02				
1-21-2	4730W 11275N	0-3	.02				
		3-9	.04				

Assay Report (Weekend)

1-29-2 to 1-31-2

Pg 5 of 5

	ORC		Au oT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46	.04	
		134-140	.64			46-52	.04	
		140-146	.04			71-77	.04	
		146-151	.04					
1-7-2	4680 CC17	154-160	.06	1-26-2	4730W 11220N	49-55	.08	
	4680 CC17N	107-115	.04			55-61	.06	
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42	.04	
		124-129	.04			42-49	.04	
1-8-2	4680 CC17S	0-10	1.08			49-56	.06	
		10-20	.56			56-62	.04	
1-11-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

Assay Report

1-26-2
pg. 173

	ORC		AGOT				
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06
		0930	.95			15-22	.04
		1030	.60			22-30	.06
		1130	.55			30-39	.04
		1230	.50			39-45	.04
		1330	1.35			45-51	.02
		1330	4.70			51-53	.02
		1430	1.40			53-62	.02
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04
		0800	.80			7-13	.02
		0900	.55			13-19	.06
		1000	.65			19-25	.04
		1100	.60			25-32	.04
		1200	.55			32-39	.02
		1300	.50			52-56	.18
						56-62	.24
1-23-2	Tails Pad #1		.70				
				1-21-2	4730W 11250N	0-9	.12
12-28-1	DH	5B 0-20	.08			9-13	.12
12-29-1		6SB 0-20	.08			13-19	.14
12-30-1		11SB 0-20	.10			19-25	.14
12-31-1		11 6B 0-20	.14			25-29	.12
12-30-1		124B 0-20	.12			29-36	.14
12-31-1		149B 0-20	.18			49-55	.12
		C13 0-20	.12			55-64	.18
		C13 0-20	.10			64-68	.20
1-11-2	4480 CC19S	4-7	.10				
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN pH 8.5			
		20-25	.08				
		25-30	.02				
		30-36	.04				
		36-43	.02				
		43-49	.02				
		61-67	.04				
		67-69	.08				
		69-74	.02				
1-21-2	4730W 11275N	0-3	.02				
		3-9	.04				

Assay Report (Weekend)

1-29-2 to 1-31-2

Pg 5 of 5

	ORC		Au oz/T					
1-7-2	4680 CC16S			1-22-2	4730W 11225N	39-42	.04	
		134-140	.64			46-52	.04	
		140-146	.04			71-77	.04	
		146-151	.04					
1-7-2	4680 CC17	154-168	.06	1-26-2	4730W 11220N	49-55	.08	
	4680 CC17N	107-115	.04			55-61	.06	
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42	.04	
		124-129	.04			42-49	.04	
1-8-2	4680 CC17S	0-10	1.08			49-56	.06	
		10-20	.56			56-62	.04	
1-41-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

Assay Report

1-26-2
pg. 173

	ORC		AGOT				
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06
		0930	.95			15-22	.04
		1030	.60			22-30	.06
		1130	.55			30-39	.04
		1230	.50			39-45	.04
		1330	1.35			45-51	.02
		1330	4.70			51-53	.02
		1430	1.40			53-62	.02
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04
		0800	.80			7-13	.02
		0900	.55			13-19	.06
		1000	.65			19-25	.04
		1100	.60			25-32	.04
		1200	.55			32-39	.02
		1300	.50			52-56	.18
						56-62	.24
1-23-2	Tails Pad #1		.70				
				1-21-2	4730W 11250N	0-9	.12
12-28-1	DH 5B	0-20	.08			9-13	.12
12-29-1	65B	0-20	.08			13-19	.14
12-30-1	115B	0-20	.10			19-25	.14
12-31-1	116B	0-20	.14			25-29	.12
12-30-1	124B	0-20	.12			29-36	.14
12-31-1	149B	0-20	.18			49-55	.12
	C13	0-20	.12			55-64	.18
	C13	0-20	.10			64-68	.20
1-11-2	4480 CC19S	4-7	.10				
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN PH 8.5			
		20-25	.08				
		25-30	.02				
		30-36	.04				
		36-43	.02				
		43-49	.02				
		61-67	.04				
		67-69	.08				
		69-74	.02				
1-21-2	4730W 11275N	0-3	.02				
		3-9	.04				

Assay Report (weekend)

1-29-2 to 1-31-2

Pg 5 of 5

	ORC		AuOT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-42	.04	
		134-140	.64			46-52	.04	
		140-146	.04			71-77	.04	
		146-151	.04					
1-7-2	4680 CC17	154-168	.06	1-26-2	4730W 11220N	49-55	.08	
	4680 CC17N	107-115	.04			55-61	.06	
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42	.04	
		124-129	.04			42-49	.04	
1-8-2	4680 CC17S	0-10	1.08			49-56	.06	
		10-20	.56			56-62	.04	
1-41-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

Assay Report

1-26-2
pg. 173

	ORC		AGOT				
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06
		0930	.95			15-22	.04
		1030	.60			22-30	.06
		1130	.55			30-39	.04
		1230	.50			39-45	.04
		1330	1.35			45-51	.02
		1330	4.70			51-53	.02
		1430	1.40			53-62	.02
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04
		0800	.80			7-13	.02
		0900	.55			13-19	.06
		1000	.65			19-25	.04
		1100	.60			25-32	.04
		1200	.55			32-39	.02
		1300	.50			52-56	.18
						56-62	.24
1-23-2	Tails Pad #1		.70				
				1-21-2	4730W 11250N	0-9	.12
12-28-1	DH 5B	0-20	.08			9-13	.12
12-29-1	6SB	0-20	.08			13-19	.14
12-30-1	11SB	0-20	.10			19-25	.14
12-31-1	11GB	0-20	.14			25-29	.12
12-30-1	12GB	0-20	.12			29-36	.14
12-31-1	14GB	0-20	.18			49-55	.12
	C13	0-20	.12			55-64	.18
	C13	0-20	.10			64-68	.20
1-11-2	4480 CC19S	4-7	.10				
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN PH 8.5			
		20-25	.08				
		25-30	.02				
		30-36	.04				
		36-43	.02				
		43-49	.02				
		61-67	.04				
		67-69	.08				
		69-74	.02				
1-21-2	4730W 11275N	0-3	.02				
		3-9	.04				

Assay Report

1-27-2
pg. 3 of 3

	ORC		Au oz/T
1-21-2	4730W 11300N	0-8	.12
		8-11	.10
		11-18	.08
		18-22	.06
		22-26	.08
		26-33	.06
		33-39	.08
		39-45	.06
		45-53	.08
		53-59	.12
		59-64	.10
1-21-2	4730W 11325N	0-10	.08
		10-19	.10
		19-24	.10
		24-33	.10
		33-41	.08
		41-48	.10
1-7-2	4680 CC17N	0-4	.58
		4-8	.56
		8-10	.98
		10-13	2.08
		13-19	13.04
		19-24	4.48
		24-30	1.08
		30-33	1.06
		33-36	3.10
		36-42	.50
		42-46	.32
		46-50	.42
		50-54	.50
		54-58	.48
		58-63	.24
		63-70	.12
		70-74	1.02
		74-79	.01
		79-86	.06
		86-89	.08

1-27-2
pg. 3 of 3

Assay Report

	ORC		AuOT
1-21-2	4730W 11300N	0-8	.12
		8-11	.10
		11-18	.08
		18-22	.06
		22-26	.08
		26-33	.06
		33-39	.08
		39-45	.06
		45-53	.08
		53-59	.12
		59-64	.10
1-21-2	4730W 11325 N	0-10	.08
		10-19	.10
		19-24	.10
		24-33	.10
		33-41	.08
		41-48	.10
1-7-2	4680 CC17 N	0-4	.58
		4-8	.56
		8-10	.98
		10-13	2.08
		13-19	13.04
		19-24	4.48
		24-30	1.08
		30-33	1.06
		33-36	3.10
		36-42	.50
		42-46	.32
		46-50	.42
		50-54	.50
		54-58	.48
		58-63	.24
		63-70	.12
		70-74	1.02
		74-79	.01
		79-84	.06
		86-89	.08

ELEV. 4680

Assay Report

2-2-82

pg 3 of 3

	ORC		AGOT
1-27-2	4730W 10925N	0-5	.10
		5-12	.12
		12-17	.08
		17-23	.10
		23-29	.08
		29-36	.06
		36-43	.06
		43-51	.12
		51-59	.10
1-27-2	4680W 11300N	0-10	.20
		10-15	.12
		15-19	.48

Assay Report

2-3-82
Page 2 of 4

	1			2	3	4	5	6	
	ORC			AGOT				AGOT	
1	2-1-82	CO 2	0300	2.00	1-28-82	11325N 4680	40-42	3.36	1
2		3	0900	.90			42-50	2.72	2
3		4	1130	1.45			50-55	.56	3
4		5	1230	.95			55-60	4.30	4
5		6	1530	1.65			60-67	.52	5
6		7	1630	2.10	1-28-82	11350N 4680	0-5	.22	6
7		8	1730	1.80			5-11	.14	7
8		9	1830	1.50			11-17	.14	8
9		10	1930	1.60			17-23	.14	9
10		11	2030	1.55			23-28	.08	10
11		12	2130	1.80			28-30	.08	11
12		PO 1	0700	.45			30-33	.06	12
13		2	0800	.40			33-38	.16	13
14		3	0900	.35			38-45	.06	14
15		4	1000	.95			45-53	.12	15
16		5	1130	1.35			53-59	.12	16
17		6	1230	1.05			59-63	.08	17
18		7	1330	.85			63-67	.06	18
19		8	1530	2.40			67-73	.08	19
20		9	1630	1.30			73-79	.06	20
21		10	1730	1.80					21
22		11	1830	10.65					22
23		12	1930	1.10					23
24		13	2030	1.30					24
25		14	2130	1.55					25
26		15	2230	.65	2-1-82	Pad 3	T-1	.90	26
27					1-28-82		T-2	.60	27
28					2-1-82		T-3	.45	28
29					2-1-82		T-4	.80	29
30	1-27-82	4680 11300N	19-24	.38	2-1-82		H-1	.60	30
31			24-33	.20	2-1-82		H-2	.55	31
32			33-40	5.80					32
33			40-48	4.68					33
34			48-53	4.40					34
35		Fines	10-15	4.16					35
36	1-27-82	4680 11325N	0-9	.50					36
37			9-13	.32					37
38			13-18	.24					38
39			18-25	.74					39
40			25-32	1.04					40
			32-40	.58					

Assay Report

2-3-82
Page 2 of 4

	1			2		3		4		5		6	
	ORC			AGOT								AGOT	
1	2-1-82	CO	2	0800	2.00			1-28-82	11325N	40-42		3.36	1
2			3	0900	.90					42-50		2.72	2
3			4	1130	1.45					50-55		.56	3
4			5	1230	.95					55-60		4.30	4
5			6	1530	1.65					60-67		.52	5
6			7	1630	2.10			1-28-82	4680 11350N	0-5		.22	6
7			8	1730	1.80					5-11		.14	7
8			9	1830	1.50					11-17		.14	8
9			10	1930	1.60					17-23		.14	9
10			11	2030	1.55					23-28		.08	10
11			12	2130	1.80					28-30		.08	11
12		PO	1	0700	.45					30-33		.06	12
13			2	0800	.40					33-38		.16	13
14			3	0900	.35					38-45		.06	14
15			4	1000	.95					45-53		.12	15
16			5	1130	1.35					53-59		.12	16
17			6	1230	1.05					59-63		.08	17
18			7	1330	.85					63-67		.06	18
19			8	1530	2.40					67-73		.08	19
20			9	1630	1.30					73-79		.06	20
21			10	1730	1.80								21
22			11	1830	10.65								22
23			12	1930	1.10								23
24			13	2030	1.30								24
25			14	2130	1.55								25
26			15	2230	.65			2-1-82	Prod 3	T-1		.90	26
27								1-28-82		T-2		.60	27
28								2-1-82		T-3		.45	28
29								2-1-82		T-4		.80	29
30	1-27-82	4680 11300N		15-24	.38			2-1-82		H-1		.60	30
31				24-33	.20			2-1-82		H-2		.55	31
32				33-40	5.80								32
33				40-48	4.68								33
34				48-53	4.40								34
35		Fines		10-15	4.16								35
36	1-27-82	4680 11325N		0-9	.50								36
37				9-13	.32								37
38				13-18	.24								38
39				18-25	.74								39
40				25-32	1.04								40
				32-40	.58								

Assay Report

2-3-82

					AGOT						AGOT	
		ORC										
1	2-1-82	CO	2	0800	2.00			1-28-82	11325N	40-42	3.36	1
2			3	0900	.90					42-50	2.72	2
3			4	1130	1.45					50-55	.56	3
4			5	1230	.95					55-60	4.30	4
5			6	1530	1.65					60-67	.52	5
6			7	1630	2.10			1-28-82	4680 11350N	0-5	.22	6
7			8	1730	1.80					5-11	.14	7
8			9	1830	1.50					11-17	.14	8
9			10	1930	1.60					17-23	.14	9
10			11	2030	1.55					23-28	.08	10
11			12	2130	1.80					28-30	.08	11
12		PO	1	0700	.45					30-33	.06	12
13			2	0800	.40					33-38	.16	13
14			3	0900	.35					38-45	.06	14
15			4	1000	.95					45-53	.12	15
16			5	1130	1.35					53-59	.12	16
17			6	1230	1.05					59-63	.08	17
18			7	1330	.85					63-67	.06	18
19			8	1530	2.40					67-73	.08	19
20			9	1630	1.30					73-79	.06	20
21			10	1730	1.80							21
22			11	1830	10.65							22
23			12	1930	1.10							23
24			13	2030	1.30							24
25			14	2130	1.55							25
26			15	2230	.65			2-1-82	Prod 3	T-1	.90	26
27								1-28-82		T-2	.60	27
28								2-1-82		T-3	.45	28
29								2-1-82		T-4	.80	29
30	1-27-82	4680 11300N		19-24	.38			2-1-82		H-1	.60	30
31				24-33	.20			2-1-82		H-2	.55	31
32				33-40	5.80							32
33				40-48	4.68							33
34				48-53	4.40							34
35		Fines		10-15	4.16							35
36	1-27-82	4680 11325N		0-9	.50							36
37				9-13	.32							37
38				13-18	.24							38
39				18-25	.74							39
40				25-32	1.04							40
				32-40	.58							

CC TRENCHES
ELEV. 4680

Assay Report

1-28-2
Pg 1 of 3

	ORC		AgOT				AgOT
1-7-2	4680 CC165	0-9	.08	1-7-2	4680 CC17		
		9-16	.62			0-10	.56
		16-21	.28			10-15	.32
		21-25	1.12			15-22	.16
		25-28	.26			22-26	.44
		28-35	.50			26-33	.16
		35-42	.22			33-41	.14
		42-47	.28			41-44	1.64
		47-53	.20			44-52	1.90
		53-61	.28			52-56	3.26
		61-64	.26			56-58	1.18
		64-68	.48			58-64	1.44
		68-72	.28			64-70	.62
		72-75	.24			70-75	.10
		75-81	2.28			75-82	.08
		81-82	2.14			82-86	.06
		82-88	.44			86-92	.14
		88-90	.12			92-97	.08
		90-97	.18			97-106	.06
		97-105	.10			106-114	.06
		105-113	.06			114-120	.06
		113-118	.04			120-127	.10
		118-124	.08			127-134	.06
		124-130	.10			141-149	.06
		130-132	.10			149-154	.06
		132-134	.02				
-26-2	4730W 11125N	0-7	.04				
		7-11	.04				
		11-17	.02				
		17-23	.02				
		23-28	.04				
		28-34	.04				
		34-40	.04				
		40-43	.12				
		43-51	.20				
		51-58	.18				
		58-65	.08				
		65-71	.10				

Assay Report

1-19-2

			AGOT			AGOT
1-18-2	CO	0830	2.75	1-18-2 PO	# 1	2.90
		0900			# 2	2.90
		1000			# 3	1.80
		1100			# 4	3.00
		1200	.75		# 5	.75
		1300			# 6	.90
		1400			# 7	1.60
		1500	1.28		# 8	1.55
		1600	4.90		# 9	1.80
		1700	2.50		# 10	1.85
		1800	2.10		# 11	.90
		1900	3.50		# 12	2.35
		2000	3.05		# 13	.75
		2100	4.25		# 14	.85
		2200	1.90		# 15	2.60
		2300				
		2400				

	ORC		AGOT			AGOT
1-7-2	CC17 4680	134-141	.24	1-11-2	CC19S 4680	31-40 .52
1-8-2	CC18 4680	20-29	.38			47-57 .28
		29-35	.56			82-88 .16
		35-40	.26	1-12-2	CC20S 4680	11-13 .16
		40-47	.38	1-11-2	CC20 4680	32-37 .18
		47-50	.34			37-43 .20
		50-58	.40			53-56 .18
		58-65	.32	1-18-2	GC41	55-63 .16
		69-74	.28			63-70 1.00
		80-90	.34			70-74 .32
		95-104	.52			74-80 .44
		65-69	.28			80-87 .24
		74-80	.08			87-92 .26
		90-95	.20			92-96 .16
		104-110	.16			96-100 .12
		110-120	.10			100-106 .10
		120-127	.28			106-113 .16
		127-131	.20			113-116 .20
1-11-2	CC19S 4680	11-13	.36			116-124 .22
		13-18	.30			124-129 .30

Assay Report

Weekly

1-29-2 to 1-31-2

Pg 5 of 5

ORC		AuoT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46	.04
	134-140	.64				46-52	.04
	140-146	.04				71-77	.04
	146-151	.04					
1-7-2	4680 CC17 154-168	.06		1-26-2	4730W 11220N	49-55	.03
	4680 CC17N 107-115	.04				55-61	.06
	115-119	.04					
	119-124	.04		1-26-2	4730W 11250N	36-42	.04
	124-129	.04				42-49	.04
1-8-2	4680 CC17S 0-10	1.08				49-56	.06
	10-20	.56				56-62	.04
1-11-2	4680 CC19N 50-54	.08					
1-26-2	4730W 11100N 0-9	.04					
	9-15	.34					
	15-22	.12					
	22-29	.04					
	29-37	.06					
	37-45	.04					
	45-52	.10					
	52-60	.10					
	60-67	.04					
	67-73	.04					
1-26-2	4730W 11075N 0-7	.04					
	7-11	.04					
	11-14	.04					
	14-21	.06					
	21-23	.04					
	23-30	.04					
	30-37	.04					
	37-44	.04					
	44-50	.06					
	50-52	.04					
	52-58	.16					
	58-61	.08					
	61-68	.04					

Assay Report

1-19-2

pg 2 of 3

			AGOT			AGOT
1-18-2	CO	0830	2.75	1-18-2 PO	# 1	2.90
		0900			# 2	2.90
		1000			# 3	1.80
		1100			# 4	3.00
		1200	.75		# 5	.75
		1300			# 6	.90
		1400			# 7	1.60
		1500	1.28		# 8	1.55
		1600	4.90		# 9	1.80
		1700	2.50		# 10	1.85
		1800	2.10		# 11	.90
		1900	3.50		# 12	2.35
		2000	3.05		# 13	.75
		2100	4.25		# 14	.85
		2200	1.90		# 15	2.60
		2300				
		2400				
	ORC		AGOT			AGOT
1-7-2	CC17 4680	134-141	.24	1-11-2 CC19S 4680	31-40	.52
1-8-2	CC18 4680	20-29	.38		47-57	.28
		29-35	.56		82-88	.16
		35-40	.26	1-12-2 CC20S 4680	11-13	.16
		40-47	.38	1-11-2 CC20 4680	32-37	.18
		47-50	.34		37-43	.20
		50-58	.40		53-56	.18
		58-65	.32	1-18-2 GC41	55-63	.16
		69-74	.28		63-70	1.00
		80-90	.34		70-74	.32
		95-104	.52		74-80	.44
		65-69	.28		80-87	.24
		74-80	.08		87-92	.26
		90-95	.20		92-96	.16
		104-110	.16		96-100	.12
		110-120	.10		100-106	.10
		120-127	.28		106-113	.16
		127-131	.20		113-116	.20
1-11-2	CC19S 4680	11-13	.36		116-124	.22
		13-18	.30		124-129	.30

Assay Report

1-19-2
pg 2 of 3

			AGOT			AGOT
1-18-2	CO	0830	2.75	1-18-2 PO	# 1	2.90
		0900			# 2	2.90
		1000			# 3	1.80
		1100			# 4	3.00
		1200	.75		# 5	.75
		1300			# 6	.90
		1400			# 7	1.60
		1500	1.28		# 8	1.55
		1600	4.90		# 9	1.80
		1700	2.50		# 10	1.85
		1800	2.10		# 11	.90
		1900	3.50		# 12	2.35
		2000	3.05		# 13	.75
		2100	4.25		# 14	.85
		2200	1.90		# 15	2.60
		2300				
		2400				

			AGOT			AGOT
	ORC					
1-7-2	CC17 4680	134-141	.24	1-11-2 CC19S 4680	31-40	.52
1-8-2	CC18 4680	20-29	.38		47-57	.28
		29-35	.56		82-88	.16
		35-40	.26	1-12-2 CC20S 4680	11-13	.16
		40-47	.38	1-11-2 CC20 4680	32-37	.18
		47-50	.34		37-43	.20
		50-58	.40		53-56	.18
		58-65	.32	1-18-2 GC 41	55-63	.16
		69-74	.28		63-70	1.00
		80-90	.34		70-74	.32
		95-104	.52		74-80	.44
		65-69	.28		80-87	.24
		74-80	.08		87-92	.26
		90-95	.20		92-96	.16
		104-110	.16		96-100	.12
		110-120	.10		100-106	.10
		120-127	.28		106-113	.16
		127-131	.20		113-116	.20
1-11-2	CC19S 4680	11-13	.36		116-124	.22
		13-18	.30		124-129	.30

1-20-82

Assay Report

pg. 3 of 3

		ORC 4680		
1	1-11-2	CC 195	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		4680 CC 20	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		4680 CC 20N	50-55	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	4680 CC 205	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH 4B	0-20	.26
23		25B	0-20	.08
24		33B	0-20	.10
25	12-15-1	62B	0-5	.12
26	12-30-1	95B	0-20	.06
27		111B	0-20	.04
28		114B	0-20	.10
29	12-20-1	142B	0-20	.22
30		231B	0-10	.06
31	12-21-1	255B	0-10	.10
	12-20-1	269B	0-20	.28
33	12-30-1	253B	10-20	.12
34	12-10-1	307B	0-10	.06
35	12-20-1	5C	0-20	.18
		6C	0-20	.10
37	12-28-1	3C	0-20	.10
38		9C	0-20	.20
39				
40				

CC TRENCHES NORTH
ELEV. 4680'

2-3-82

Pg 3 of 4

Assay Report

	Fire Assays	AGOT	AUOT
1-28-82	Pad 2 H-5	1.22	.018
	H-6	.84	.006
1-27-82	Pad 3 T-4	.30	Nil
1-28-82	Pad 4 TL-4	.49	Nil
1-27-82	Pad 3 T-6	.97	.002
	T-8	1.28	.005
	T-9	.95	.002
	T-10	.52	Tr
	4680		
1-7-82	CC(TI) #1 0-4	1.02	.008
	#2 4-8	1.11	.024
	#3 8-10	1.68	.044
	#4 10-13	3.12	.032
	#5 13-19		
	#6 19-24	5.37	.030
	#7 24-30	1.39	.009
	#8 30-33	1.24	.010
	#9 33-38	3.48	.022
	#10 38-42	.70	.008
	#11 42-46	.46	.006
	#12 46-50	.58	.010
	#13 50-54	.68	.010
	#14	.73	.008
	#15	.32	.002
	#16	.14	Tr
	#17	.25	Tr
1-28-82	Pad 3 T-13	.68	.004
	T-9	.51	Tr
	T-8	.68	.002
1-28-82	Pad 2 H-4	.54	.006
	Pad 4 TL 5	.46	.006
	Pad 3 T-6	.53	.006
	Pad 3 H-7	.58	.006
1-27-82	Pad 3 T-10	.60	Tr
1-28-82	Pad 4 TL-3	.34	Tr

1-27-2
Pg. 3 of 3

Assay Report

	ORC			Ag oz/T
1	1-21-2	4730W 11300N	0-8	.12
2			8-11	.10
3			11-18	.08
4			18-22	.06
5			22-26	.08
6			26-33	.06
7			33-39	.08
8			39-45	.06
9			45-53	.08
10			53-59	.12
11			59-64	.10
12				
13	1-21-2	4730W 11325N	0-10	.08
14			10-19	.10
15			19-24	.10
16			24-33	.10
17			33-41	.08
18			41-48	.10
19				
20	1-7-2	4680 CC17N	0-4	.58
21			4-8	.56
22			8-10	.98
23			10-13	2.08
24			13-19	13.04
25			19-24	4.48
26			24-30	1.08
27			30-33	1.06
28			33-36	3.10
29			36-42	.50
30			42-46	.32
31			46-50	.42
32			50-54	.50
33			54-58	.48
34			58-63	.24
35			63-70	.12
36			70-74	1.02
37			74-79	.01
38			79-86	.06
39			86-89	.08
40				

Assay Report

(Weekend)
1-29-2 to 1-31-2
Pg 505

	ORC		AuOT				
1-7-2	4680 CC16S			1-2C-2	4730W 11225N	39-46	.04
		134-140	.64			46-52	.04
		140-146	.04			71-77	.04
		146-151	.04				
1-7-2	4680 CC17	134-168	.06	1-26-2	4730W 11220N	49-55	.08
	4680 CC17N	107-115	.04			55-61	.06
		115-119	.04				
		119-124	.04	1-26-2	4730W 11250N	36-42	.04
		124-129	.04			42-49	.04
1-8-2	4680 CC17S	0-10	1.08			49-56	.06
		10-20	.56			56-62	.04
1-41-2	4680 CC19N	50-54	.08				
1-26-2	4730W 11100N	0-9	.04				
		9-15	.34				
		15-22	.12				
		22-29	.04				
		29-37	.06				
		37-45	.04				
		45-52	.10				
		52-60	.10				
		60-67	.04				
		67-73	.04				
1-26-2	4730W 11075N	0-7	.04				
		7-11	.04				
		11-14	.04				
		14-21	.06				
		21-23	.04				
		23-30	.04				
		30-37	.04				
		37-44	.04				
		44-50	.06				
		50-52	.04				
		52-58	.16				
		58-61	.08				
		61-68	.04				

Assay Report (Weekend)

1-29-2 to 1-31-2

Pg 5 of 5

		ORC		Au oT					
1	1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46	.04	1
2			134-140	.64			46-52	.04	2
3			140-146	.04			71-77	.04	3
4			146-151	.04					4
5	1-7-2	4680 CC17	154-168	.06	1-26-2	4730W 11220N	49-55	.08	5
6		4680 CC17N	107-115	.04			55-61	.06	6
7			115-119	.04					7
8			119-124	.04	1-26-2	4730W 11250N	36-42	.04	8
9			124-129	.04			42-49	.04	9
10	1-8-2	4680 CC17S	0-10	1.08			49-56	.06	10
11			10-20	.56			56-62	.04	11
12	1-41-2	4680 CC19N	50-54	.08					12
13									13
14									14
15	1-26-2	4730W 11100N	0-9	.04					15
16			9-15	.34					16
17			15-22	.12					17
18			22-29	.04					18
19			29-37	.06					19
20			37-45	.04					20
21			45-52	.10					21
22			52-60	.10					22
23			60-67	.04					23
24			67-73	.04					24
25									25
26	1-26-2	4730W 11075N	0-7	.04					26
27			7-11	.04					27
28			11-14	.04					28
29			14-21	.06					29
30			21-23	.04					30
31			23-30	.04					31
32			30-37	.04					32
33			37-44	.04					33
34			44-50	.06					34
35			50-52	.04					35
36			52-58	.16					36
37			58-61	.08					37
38			61-68	.04					38
39									39
40									40

1-20-82

Assay Report

pg. 3 of 3

| | | |

CC TRENCHES SOUTH
ELEV 4480'

Assay Report (Weekend) 1-29-2 to 1-31-2

Pg 5 of 5

	ORC		Au oT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46	.04	
		134-140	.64			46-52	.04	
		140-146	.04			71-77	.04	
		146-151	.04					
1-7-2	4680 CC17	154-165	.06	1-26-2	4730W 11220N	49-55	.08	
	4680 CC17N	107-115	.04			55-61	.06	
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42	.04	
		124-129	.04			42-49	.04	
1-8-2	4680 CC17S	0-10	1.08			49-56	.06	
		10-20	.56			56-62	.04	
1-11-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

Assay Report

1-28-2
Pg 1 of 3

	ORC		AgOT				AgOT
1-7-2	4680 CC165	0-9	.08	1-7-2	4680 CC17		
		9-16	.62			0-10	.56
		16-21	.28			10-15	.32
		21-25	1.12			15-22	.16
		25-28	.26			22-26	.44
		28-35	.50			26-33	.16
		35-42	.22			33-41	.14
		42-47	.28			41-44	1.64
		47-53	.20			44-52	1.90
		53-61	.28			52-56	3.26
		61-64	.26			56-58	1.18
		64-68	.48			58-64	1.44
		68-72	.28			64-70	.62
		72-75	.24			70-75	.10
		75-81	2.28			75-82	.08
		81-82	2.14			82-86	.06
		82-88	.44			86-92	.14
		88-90	.12			92-97	.08
		90-97	.18			97-106	.06
		97-105	.10			106-114	.06
		105-113	.06			114-120	.06
		113-118	.04			120-127	.10
		118-124	.08			127-134	.06
		124-130	.10			141-149	.06
		130-132	.10			149-154	.06
		132-134	.02				
	4730W						
-26-2	11125N	0-7	.04				
		7-11	.04				
		11-17	.02				
		17-23	.02				
		23-28	.04				
		28-34	.04				
		34-40	.04				
		40-43	.12				
		43-51	.20				
		51-58	.18				
		58-65	.08				
		65-71	.10				

Assay Report (Weekend) 1-29-2 to 1-31-2

Pg 5 of 5

	ORC		Au oT					
1-7-2	4680 CC16S			1-26-2	4730W 11225N	39-46	.04	
		134-140	.64			46-52	.04	
		140-146	.04			71-77	.04	
		146-151	.04					
1-7-2	4680 CC17	154-165	.06	1-26-2	4730W 11220N	49-55	.08	
	4680 CC17N	107-115	.04			55-61	.06	
		115-119	.04					
		119-124	.04	1-26-2	4730W 11250N	36-42	.04	
		124-129	.04			42-49	.04	
1-8-2	4680 CC17S	0-10	1.08			49-56	.06	
		10-20	.56			56-62	.04	
1-41-2	4680 CC19N	50-54	.08					
1-26-2	4730W 11100N	0-9	.04					
		9-15	.34					
		15-22	.12					
		22-29	.04					
		29-37	.06					
		37-45	.04					
		45-52	.10					
		52-60	.10					
		60-67	.04					
		67-73	.04					
1-26-2	4730W 11075N	0-7	.04					
		7-11	.04					
		11-14	.04					
		14-21	.06					
		21-23	.04					
		23-30	.04					
		30-37	.04					
		37-44	.04					
		44-50	.06					
		50-52	.04					
		52-58	.16					
		58-61	.08					
		61-68	.04					

1-20-82

Assay Report

| | | |

Assay Report

1-26-2
pg. 1 of 3

	ORC		AGOT					
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06	
		0930	.95			15-22	.04	
		1030	.60			22-30	.06	
		1130	.55			30-39	.04	
		1230	.50			39-45	.04	
		1330	1.35			45-51	.02	
		1330	4.70			51-53	.02	
		1430	1.40			53-62	.02	
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04	
		0800	.80			7-13	.02	
		0900	.55			13-19	.06	
		1000	.65			19-25	.04	
		1100	.60			25-32	.04	
		1200	.55			32-39	.02	
		1300	.50			52-56	.18	
						56-62	.24	
1-23-2	Tails Pad #1		.70					
				1-21-2	4730W 11250N	0-9	.12	
12-28-1	DH	5B 0-20	.08			9-13	.12	
12-29-1		6SB 0-20	.08			13-19	.14	
12-30-1		11SB 0-20	.10			19-25	.14	
12-31-1		11 6B 0-20	.14			25-29	.12	
12-30-1		12 4B 0-20	.12			29-36	.14	
12-31-1		14 9B 0-20	.18			49-55	.12	
		C13 0-20	.12			55-64	.18	
		C13 0-20	.10			64-68	.20	
1-11-2	4480 CC19S	4-7	.10					
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN pH 8.5				
		20-25	.08					
		25-30	.02					
		30-36	.04					
		36-43	.02					
		43-49	.02					
		61-67	.04					
		67-69	.08					
		69-74	.02					
1-21-2	4730W 11275N	0-3	.02					
		3-9	.04					

Assay Report

1-19-2

pg 2 of 3

			AGOT			AGOT
1-18-2	CO	0830	2.75	1-18-2 PO	#1	2.90
		0900			#2	2.90
		1000			#3	1.80
		1100			#4	3.00
		1200	.75		#5	.75
		1300			#6	.90
		1400			#7	1.60
		1500	1.28		#8	1.55
		1600	4.90		#9	1.80
		1700	2.50		#10	1.85
		1800	2.10		#11	.90
		1900	3.50		#12	2.35
		2000	3.05		#13	.75
		2100	4.25		#14	.85
		2200	1.90		#15	2.60
		2300				
		2400				
	ORC		AGOT			AGOT
1-7-2	CC17 4680	134-141	.24	1-11-2 CC19S 4680	31-40	.52
1-8-2	CC18 4680	20-29	.38		47-57	.28
		29-35	.56		82-88	.16
		35-40	.26	1-12-2 CC20S 4680	11-13	.16
		40-47	.38	1-11-2 CC20 4680	32-37	.18
		47-50	.34		37-43	.20
		50-58	.40		53-56	.18
		58-65	.32	1-18-2 GC41	55-63	.16
		69-74	.28		63-70	1.00
		80-90	.34		70-74	.32
		95-104	.52		74-80	.44
		65-69	.28		80-87	.24
		74-80	.08		87-92	.26
		90-95	.20		92-96	.16
		104-110	.16		96-100	.12
		110-120	.10		100-106	.10
		120-127	.28		106-113	.16
		127-131	.20		113-116	.20
1-11-2	CC19S 4680	11-13	.36		116-124	.22
		13-18	.30		124-129	.30

Assay Report

1-19-2

pg 2 of 3

			AGOT
1-18-2	CO	0830	2.75
		0900	
		1000	
		1100	
		1200	.75
		1300	
		1400	
		1500	1.28
		1600	4.90
		1700	2.50
		1800	2.10
		1900	3.50
		2000	3.05
		2100	4.25
		2200	1.90
		2300	
		2400	

1-18-2 PO

	AGOT
# 1	2.90
# 2	2.90
# 3	1.80
# 4	3.00
# 5	.75
# 6	.90
# 7	1.60
# 8	1.55
# 9	1.80
# 10	1.85
# 11	.90
# 12	2.35
# 13	.75
# 14	.85
# 15	2.60

	ORC		AGOT
1-7-2	CC17 4680	134-141	.24
1-8-2	CC18 4680	20-29	.38
		29-35	.56
		35-40	.26
		40-47	.38
		47-50	.34
		50-58	.40
		58-65	.32
		69-74	.28
		80-90	.34
		95-104	.52
		65-69	.28
		74-80	.08
		90-95	.20
		104-110	.16
		110-120	.10
		120-127	.28
		127-131	.20
1-11-2	CC19S 4680	11-13	.36
		13-18	.30

	AGOT
1-11-2 CC19S 4680	31-40 .52
	47-57 .28
	82-88 .16
1-12-2 CC20S 4680	11-13 .16
1-11-2 CC20 4680	32-37 .18
	37-43 .20
	53-56 .18
1-18-2 GC41	55-63 .16
	63-70 1.00
	70-74 .32
	74-80 .44
	80-87 .24
	87-92 .26
	92-96 .16
	96-100 .12
	100-106 .10
	106-113 .16
	113-116 .20
	116-124 .22
	124-129 .30

1-20-82

pg. 303

Assay Report

		ORC		
1-11-2	CC 195 (4680)	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 (4680)	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N (4680)	50-55	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 (4680)	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH	4B 0-20	.26	
		25B 0-20	.08	
		33B 0-20	.10	
12-15-1		62B 0-5	.12	
12-30-1		95B 0-20	.06	
		111B 0-20	.04	
		114B 0-20	.10	
12-20-1		142B 0-20	.22	
		231B 0-10	.06	
12-21-1		255B 0-10	.10	
12-20-1		269B 0-20	.28	
12-30-1		253B 10-20	.12	
12-10-1		307B 0-10	.06	
12-20-1		5C 0-20	.18	
		6C 0-20	.10	
12-28-1		3C 0-20	.10	
		9C 0-20	.20	

TRENCH 42

Assay Report

1-21-2
pg. 2 of 3

	ORC		AGOT					AGOT	
1-19-2	42N	166-173	.12		1-20-2	4730W 1150N	8-14	.06	1
		173-178	.14				14-21	.04	2
		178-183	.14				21-28	.06	3
		183-189	.06				28-34	.10	4
		189-195	.10				34-41	.14	5
		195-200	.04				41-47	.14	6
		200-208	.06				47-53	.06	7
		208-213	.10				53-58	.08	8
		213-220	.06				58-65	.04	9
		220-227	.14				65-71	.06	10
		227-232	.06				71-76	.10	11
		232-240	.08		1-20-2	42	0-9	.10	12
		240-247	.08				9-13	.06	13
		247-252	.06				13-21	.06	14
		252-258	.06				21-27	.04	15
		258-265	.04				27-33	.08	16
		265-270	.06				33-40	.06	17
		270-275	.04				40-47	.08	18
		275-281	.08				47-55	.06	19
		281-288	.08				55-61	.10	20
		288-297	.06				61-66	.08	21
		297-308	.10				66-70	.08	22
		308-320	.08				70-78	.20	23
1-18-2	41S	0-8	.10				78-85	.44	24
		162-170	.14				85-89	.22	25
		176-181	.16				89-95	.14	26
		189-199	.14				95-100	.12	27
		199-208	.10				100-109	.06	28
		208-213	.10				109-113	.08	29
		213-219	.12				113-121	.04	30
		219-226	.08				121-126	.08	31
		226-232	.12						32
		232-237	.08						33
		237-243	.08						34
		243-249	.06						35
		249-252	.10						36
		252-259	.12						37
		259-269	.14						38
1-21-2	Jim Special		.10						39
									40

(Weekend)
1-22-2 to 1-24-2

Assay Report

P 3 7 4

		90M	AGOL	AUOL			
PL PPT							
Lot. 1-19-2 #1		36.8	681.80	9.468			
#2		38.6	876.12	12.369			
SMT		TEBP	TEAG	TEAU			PREG
Lot# 1-13-2		99.10	97.69	1.412			
RM		98.43	97.02	1.411			
1-14-2		98.49	97.09	1.408			
RM		98.30	96.88	1.417			
1-15-2		95.80	94.54	1.264			
RM		97.89	96.55	1.337			
1-16-2		98.24	97.09	1.145			
RM		99.76	98.56	1.204			
1-17-2		94.72	93.41	1.314			
RM		99.18	97.71	1.467			
1-18-2		97.87	96.47	1.399			
RM		98.14	98.14	1.444			
1-19-2		97.11	95.79	1.318			1.10
RM		99.04	97.67	1.374			
ORC			AGOT				
1-20-2	42	126-135		.04			
		135-141		.06			
		141-150		.06			
		150-157		.08			
		157-165		.06			
		165-173		.08			
		173-182		.08			
		182-190		.04			
		190-200		.04			
		200-210		.08			
		210-217		.06			
		217-223		.14			
		223-233		.16			
		233-243		.12			
		243-251		.26			
		251-258		.08			
		258-265		.06			
		265-272		.06			
		272-288		.04			

Assay Report

1-22-2 to 1-24-2
RS 4 of 4

	ORC		AGOT					AGOT
1-20-2	42	288-294	.06			4730W	0-7	.04
		294-299	.04	1-12-2	11175		7-14	.06
		299-305	.04				14-19	.04
	425	0-10	.06				19-25	.04
		10-15	.04				25-29	.04
		15-20	.08				29-32	.06
		20-26	.08				32-36	.04
		26-32	.20				36-39	.04
		32-37	.60				39-44	.04
		37-43	5.92				44-49	.06
		43-49	.54				62-66	.06
		49-53	.18				66-71	.08
		53-60	.16	1-21-2	11200	4730W	0-7	.02
		60-66	.06				7-10	.02
		66-74	.06				10-16	.02
		74-84	.06	1-22-2	#1	Special	Quartz	.04
		84-93	.04					
		93-100	.04					
		100-107	.04					
		107-113	.02					
		113-120	.02					
		120-128	.08					
		128-138	.04					
		138-146	.04					
		146-154	.06					
		154-163	.04					
		163-170	.06					
		170-179	.04					
		179-186	.04					
		186-194	.02					
		194-200	.06					
		200-208	.02					
		208-215	.02					
		215-224	.02					
		224-234	.04					
		234-241	.02					
		241-248	.04					
		248-255	.04					
		255-260	.04					
		264-268	.02					
		264-274	.06					
		274-280	.02					

TRENCH 42N

Assay Report

1-21-82

pg 1 of 3

			PG		EF	SPR	B		
			Au	Ag	Ag	Au	Ag		
1-21-2	PL CN	0700							
		0800							
		0900		.72	.40	.07	.01		
		1000		.70			Tr		
		1100		.80	.40	.06	Tr		
		1200		.83			.01		
		1300		.81	.94	.12	.01		
		1400		.80			.02		
		1500		.80		.14	.01		
		1600							
		1700	.013	1.03	1.54	.07	Tr		
		1800		1.17			Tr		
		1900		1.19	1.50	.06	Tr		
		2000	.036	1.00			.01		
		2100		.94	1.29	.03	Tr		
		2200		.97			Tr		
		2300		1.04	1.14	.02	Tr		
		2400							
		0100	.029	1.06	.96	.04	Tr		
		0200		1.07			Tr		
		0300	.028	1.06	.89	.06	Tr		
		0400		1.06			.01		
		0500		1.03	.76	.04	Tr		
		0600		1.00			Tr		
1-22-2		0700	.027	.98	.70	.05	Tr		
	Pond C	1400		.80					
	Pond C	0700		.74					
	Auto Sampler	Shift A					.06		
	ORC			AgOT					AgOT
1-19-2	42N	8-16		.12		42N	79-85		.14
		16-22		.10			85-92		.10
		22-30		.14			92-100		.10
		30-36		.14			100-113		.10
		36-42		.12			113-124		.12
		42-50		.08			124-131		.14
		50-57		6.02			131-139		.08
		57-61		.64			139-146		.18
		61-68		.30			146-154		.18
		68-73		.26			154-160		.18
		73-79		.14			160-166		.20

Assay Report

1-21-2
pg. 2 of 3

	ORC		AuOT					AuOT	
1-19-2	42N	166-173	.12		1-20-2	4730W 1150N	8-14	.06	1
		173-178	.14				14-21	.04	2
		178-183	.14				21-28	.06	3
		183-189	.06				28-34	.10	4
		189-195	.10				34-41	.14	5
		195-200	.04				41-47	.14	6
		200-208	.06				47-53	.06	7
		208-213	.10				53-58	.08	8
		213-220	.06				58-65	.04	9
		220-227	.14				65-71	.06	10
		227-232	.06				71-76	.10	11
		232-240	.08		1-20-2	42	0-9	.10	12
		240-247	.08				9-13	.06	13
		247-252	.06				13-21	.06	14
		252-258	.06				21-27	.04	15
		258-265	.04				27-33	.08	16
		265-270	.06				33-40	.06	17
		270-275	.04				40-47	.08	18
		275-281	.08				47-55	.06	19
		281-288	.08				55-61	.10	20
		288-297	.06				61-66	.08	21
		297-308	.10				66-70	.08	22
		308-320	.08				70-78	.20	23
1-18-2	41S	0-8	.10				78-85	.44	24
		162-170	.14				85-89	.22	25
		176-181	.16				89-95	.14	26
		189-199	.14				95-100	.12	27
		199-208	.10				100-109	.06	28
		208-213	.10				109-113	.08	29
		213-219	.12				113-121	.04	30
		219-226	.08				121-126	.08	31
		226-232	.12						32
		232-237	.08						33
		237-243	.08						34
		243-249	.06						35
		249-252	.10						36
		252-259	.12						37
		259-269	.14						38
1-21-2	Jim Special		.10						39
									40

TRENCHES 41 042 S 24H 1/4

Assay Report

1-21-2
pg. 2 of 3

	ORC		AgOT						AgOT
1-19-2	42N	166-173	.12		1-20-2	47 30 W 1150N	8-14		.06
		173-178	.14				14-21		.04
		178-183	.14				21-28		.06
		183-189	.06				28-34		.10
		189-195	.10				34-41		.14
		195-200	.04				41-47		.14
		200-208	.06				47-53		.06
		208-213	.10				53-58		.08
		213-220	.06				58-65		.04
		220-227	.14				65-71		.06
		227-232	.06				71-76		.10
		232-240	.08		1-20-2	42	0-9		.10
		240-247	.08				9-13		.06
		247-252	.06				13-21		.06
		252-258	.06				21-27		.04
		258-265	.04				27-33		.08
		265-270	.06				33-40		.06
		270-275	.04				40-47		.08
		275-281	.08				47-55		.06
		281-288	.08				55-61		.10
		288-297	.06				61-66		.08
		297-308	.10				66-70		.08
		308-320	.08				70-78		.20
1-18-2	41S	0-8	.10				78-85		.44
		162-170	.14				85-89		.22
		176-181	.16				89-95		.14
		189-199	.14				95-100		.12
		199-208	.10				100-109		.06
		208-213	.10				109-113		.08
		213-219	.12				113-121		.04
		219-226	.08				121-126		.08
		226-232	.12						
		232-237	.08						
		237-243	.08						
		243-249	.06						
		249-252	.10						
		252-259	.12						
		259-269	.14						
1-21-2	Jim Special		.10						

Assay Report

1-22-2 to 1-24-2
pg 4 of 4

	ORC		AGOT				AGOT
1-20-2	42	288-294	.06	1-12-2	4730W 11175	0-7	.04
		294-299	.04			7-14	.06
		299-305	.04			14-19	.04
	42S	0-10	.06			19-25	.04
		10-15	.04			25-29	.04
		15-20	.08			29-32	.06
		20-26	.08			32-36	.04
		26-32	.20			36-39	.04
		32-37	.60			39-44	.04
		37-43	5.92			44-49	.06
		43-49	.54			62-66	.06
		49-53	.18			66-71	.08
		53-60	.16	1-21-2	4730W 11200	0-7	.02
		60-66	.06			7-10	.02
		66-74	.06			10-16	.02
		74-84	.06	1-22-2	#1 Special Quartz		.04
		84-93	.04				
		93-100	.04				
		100-107	.04				
		107-113	.02				
		113-120	.02				
		120-128	.08				
		128-138	.04				
		138-146	.04				
		146-154	.06				
		154-163	.04				
		163-170	.06				
		170-179	.04				
		179-186	.04				
		186-194	.02				
		194-200	.06				
		200-208	.02				
		208-215	.02				
		215-224	.02				
		224-234	.04				
		234-241	.02				
		241-248	.04				
		248-255	.04				
		255-260	.04				
		264-268	.02				
		264-274	.06				
		274-280	.02				

G.C. TRENCHES
41

Assay Report

1-19-2
pg 2 of 3

			AGOT			AGOT
1-18-2	CO	0830	2.75	1-18-2 PO	# 1	2.90
		0900			# 2	2.90
		1000			# 3	1.80
		1100			# 4	3.00
		1200	.75		# 5	.75
		1300			# 6	.90
		1400			# 7	1.60
		1500	1.28		# 8	1.55
		1600	4.90		# 9	1.80
		1700	2.50		# 10	1.85
		1800	2.10		# 11	.90
		1900	3.50		# 12	2.35
		2000	3.05		# 13	.75
		2100	4.25		# 14	.85
		2200	1.90		# 15	2.60
		2300				
		2400				

			AGOT			AGOT
	ORC					
1-7-2	CC17 4680	134-141	.24	1-11-2 CC19S 4680	31-40	.52
1-8-2	CC18 4680	20-29	.38		47-57	.28
		29-35	.56		82-88	.16
		35-40	.26	1-12-2 CC20S 4680	11-13	.16
		40-47	.38	1-11-2 CC20 4680	32-37	.18
		47-50	.34		37-43	.20
		50-58	.40		53-56	.18
		58-65	.32	1-18-2 GC41	55-63	.16
		69-74	.28		63-70	1.00
		80-90	.34		70-74	.32
		95-104	.52		74-80	.44
		65-69	.28		80-87	.24
		74-80	.08		87-92	.26
		90-95	.20		92-96	.16
		104-110	.16		96-100	.12
		110-120	.10		100-106	.10
		120-127	.28		106-113	.16
		127-131	.20		113-116	.20
1-11-2	CC19S 4680	11-13	.36		116-124	.22
		13-18	.30		124-129	.30

Assay Report

	ORC	AGOT
1-18-2 GC41	129-137	.32
	137-146	.54
	146-152	.26
	152-157	.12
	157-161	.16
	161-170	.12
	170-178	.14
	150-156	.36
	178-185	.38
	185-192	.22
	192-200	.34
	200-208	.30
	208-213	.28
	213-221	.32
	221-228	.20
	228-232	.28
	232-235	.30
	235-243	.36
	243-250	.54
	265-271	.60
	271-280	.64
	280-289	.36
	289-298	.44
	298-305	.42
	305-313	.42
	313-320	.36
	320-328	.34
	328-336	.30
	336-342	.12
	342-347	.78
	347-355	.30
	355-362	.38
	362-369	.32
	369-377	.28
	377-382	.24
	382-391	.20
	391-400	.28
	400-406	.28
	406-416	.12
	416-424	.20
	424-430	.18

		AGOT
1-18-2 GC41	256-265	.16
1-18-2 GC41S	23-29	.76
	29-36	.16
	36-43	.10
	43-47	.12
	47-55	.14
	55-65	6.68
	65-72	.10
	72-77	.12
	85-94	.12
	94-100	.10
	100-108	.74
	108-114	.12
	114-119	.08
	119-126	.12
	126-133	.16
	133-139	.08
	139-147	.10
	154-162	.06
	181-189	.08

G.C. TRENCH
4-S.

1-19-2

Assay Report

		ORC	AGOT			AGOT
1	1-18-2	GC41 129-137	.32	1-18-2 GC41	256-265	.16
2		137-146	.54	1-18-2 GC41S	23-29	.76
3		146-152	.26		29-36	.16
4		152-157	.12		36-43	.10
5		157-161	.16		43-47	.12
6		161-170	.12		47-55	.14
7		170-178	.14		55-65	6.68
8		150-156	.36		65-72	.10
9		178-185	.38		72-77	.12
10		185-192	.22		85-94	.12
11		192-200	.34		94-100	.10
12		200-208	.30		100-108	.74
13		208-213	.28		108-114	.12
14		213-221	.32		114-119	.08
15		221-228	.20		119-126	.12
16		228-232	.28		126-133	.16
17		232-235	.30		133-139	.08
18		235-243	.36		139-147	.10
19		243-250	.54		154-162	.06
20		265-271	.60		181-189	.08
21		271-280	.64			
22		280-289	.36			
23		289-298	.44			
24		298-305	.42			
25		305-313	.42			
26		313-320	.36			
27		320-328	.34			
28		328-336	.30			
29		336-342	.12			
30		342-347	.78			
31		347-355	.30			
32		355-362	.38			
33		362-369	.32			
34		369-377	.28			
35		377-382	.24			
36		382-391	.20			
37		391-400	.28			
38		400-406	.28			
39		406-416	.12			
40		416-424	.20			
		424-430	.18			

1-20-82

Assay Report

pg. 3 of 3

		ORC 4680		
1	1-11-2	CC 195	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		4680 CC 20	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		4680 CC 20N	50-55	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	4680 CC 205	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH 4B	0-20	.26
23		25B	0-20	.08
24		33B	0-20	.10
25	12-15-1	62B	0-5	.12
26	12-30-1	95B	0-20	.06
27		111B	0-20	.04
28		114B	0-20	.10
29	12-20-1	142B	0-20	.22
30		231B	0-10	.06
31	12-21-1	255B	0-10	.10
32	12-20-1	269B	0-20	.28
33	12-30-1	253B	10-20	.12
34	12-10-1	307B	0-10	.06
35	12-20-1	5C	0-20	.18
36		6C	0-20	.10
37	12-28-1	3C	0-20	.10
38		9C	0-20	.20
39				
40				

B- SERIES OF DRILL HOLES

1-20-82

Assay Report

| | | |

Assay Report

1-26-2
pg. 173

	ORC		AGOT					
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06	
		0930	.95			15-22	.04	
		1030	.60			22-30	.06	
		1130	.55			30-39	.04	
		1230	.50			39-45	.04	
		1330	1.35			45-51	.02	
		1330	4.70			51-53	.02	
		1430	1.40			53-62	.02	
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04	
		0800	.80			7-13	.02	
		0900	.55			13-19	.06	
		1000	.65			19-25	.04	
		1100	.60			25-32	.04	
		1200	.55			32-39	.02	
		1300	.50			52-56	.18	
						56-62	.24	
1-23-2	Tails Pad #1		.70					
				1-21-2	4730W 11250N	0-9	.12	
12-28-1	DH	5B 0-20	.08			9-13	.12	
12-29-1		6SB 0-20	.08			13-19	.14	
12-30-1		11SB 0-20	.10			19-25	.14	
12-31-1		11 6B 0-20	.14			25-29	.12	
12-30-1		12 4B 0-20	.12			29-36	.14	
12-31-1		14 9B 0-20	.18			49-55	.12	
		C13 0-20	.12			55-64	.18	
		C13 0-20	.10			64-68	.20	
1-11-2	4480 CC19S	4-7	.10					
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN pH 8.5				
		20-25	.08					
		25-30	.02					
		30-36	.04					
		36-43	.02					
		43-49	.02					
		61-67	.04					
		67-69	.08					
		69-74	.02					
1-21-2	4730W 11275N	0-3	.02					
		3-9	.04					

ASSAY REPORT

1-25-2
Pg 1 of 2

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

ASSAY REPORT

		Acid Digestion			AGOT	
1	1-20-2	Rerun Tails Pad #4			1.52	
2		Rerun 42S 37-43			6.40	
3						
4						
5		Fire Assay		Dore	Ag	Au
6	1-20-2	Tails Pad #4		1.50	1.50	Tr
7	1-22-2	Special Quartz #1		0.04	0.04	Nil
8	1-20-2	42S 37-43		6.41	6.39	-0.19
9						
10		ORC				
11		DH	C-1	0-20	.14	
12			C-8	0-20	.12	
13	12-28-1		B-10	0-20	.10	
14			C-10	0-20	.10	
15			B-16	0-20	.16	
16			B-23	0-20	.10	
17	12-29-1		B-50	0-20	.12	
18	12-27-1		B-78	0-20	.10	
19	12-30-1		B-87	0-20	.08	
20			B-91	0-20	.14	
21			B-136	0-20	.14	
22	12-31-1		B-133	0-20	.10	
23			B-111		.16	
24			B-161		.20	
25			B-162		.22	
26	1-10-2		B-166		.16	
27	1-6-2		B-198	0-20	.22	
28	12-21-1		B-242	7-15	.16	
29			B-254	0-10	.20	
30	1-11-2		B-263	0-20	.40	
31			B-265	0-20	.24	
32			B-275	0-20	.20	
33			B-279	10-20	.28	
34	12-22-1		B-300		.16	
35						
36						
37						
38						
39						
40						

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

1-20-82

Assay Report

pg. 3 of 3

		ORC		
1	1-11-2	CC 195 4680	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		CC 20 4680	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		CC 20N 4680	50-55	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	CC 205 4680	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH 4B	0-20	.26
23		25B	0-20	.08
24		33B	0-20	.10
25	12-15-1	62B	0-5	.12
26	12-30-1	95B	0-20	.06
27		111B	0-20	.04
28		114B	0-20	.10
29	12-20-1	142B	0-20	.22
30		231B	0-10	.06
31	12-21-1	255B	0-10	.10
32	12-20-1	269B	0-20	.28
33	12-30-1	253B	10-20	.12
34	12-10-1	307B	0-10	.06
35	12-20-1	5C	0-20	.18
36		6C	0-20	.10
37	12-28-1	3C	0-20	.10
38		9C	0-20	.20
39				
40				

1-20-82

pg. 3 of 3

Assay Report

1	1-11-2	CC 195 4680 ORC	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		CC 20 4680	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		CC 20N 4680	50-55	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	CC 205 4680	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH 4B	0-20	.26
23		25B	0-20	.08
24		33B	0-20	.10
25	12-15-1	42B	0-5	.12
26	12-30-1	95B	0-20	.06
27		111B	0-20	.04
28		114B	0-20	.10
29	12-20-1	142B	0-20	.22
30		231B	0-10	.06
31	12-21-1	255B	0-10	.10
32	12-20-1	269B	0-20	.28
33	12-30-1	253B	10-20	.12
34	12-10-1	307B	0-10	.06
35	12-20-1	5C	0-20	.18
36		6C	0-20	.10
37	12-28-1	3C	0-20	.10
38		9C	0-20	.20
39				
40				

ASSAY REPORT

		Acid Digestion			AGOT	
1	1-20-2	Rerun Tails Pad #4			1.52	
2		Rerun 425 37-43			6.40	
5		Fire Assay		Dore	Ag	Au
6	1-20-2	Tails Pad #4		1.50	1.50	Tr
7	1-22-2	Special Quartz #1		0.04	0.04	Nil
8	1-20-2	42 S 37-43		6.41	6.39	-0.19
10		ORC				
11		DH	C-1	0-20	.14	
12			C-8	0-20	.12	
13	12-28-1		B-10	0-20	.10	
14			C-10	0-20	.10	
15			B-16	0-20	.16	
16			B-23	0-20	.10	
17	12-29-1		B-50	0-20	.12	
18	12-27-1		B-78	0-20	.10	
19	12-30-1		B-87	0-20	.08	
20			B-91	0-20	.14	
21			B-136	0-20	.14	
22	12-31-1		B-133	0-20	.10	
23			B-111		.16	
24			B-161		.20	
25			B-162		.22	
26	1-10-2		B-166		.16	
27	1-6-2		B-198	0-20	.22	
28	12-21-1		B-242	7-15	.16	
29			B-254	0-10	.20	
30	1-11-2		B-263	0-20	.40	
31			B-265	0-20	.24	
32			B-275	0-20	.20	
33			B-279	10-20	.28	
34	12-22-1		B-300		.16	

1-20-82

Assay Report

		ORC							
1	1-11-2	CC 195 (4680)	0-4	.18					
2			7-11	.12					
3			18-20	.10					
4			24-31	.18					
5			63-66	.10					
6			75-79	.08					
7			88-97	.08					
8		CC 20 (4680)	43-45	.08					
9			45-50	.10					
10			56-63	.14					
11			63-67	.12					
12			67-73	.08					
13			73-80	.08					
14		CC 20N (4680)	50-55	.06					
15			66-72	.06					
16			85-93	.12					
17	1-12-2	CC 205 (4680)	46-49	.08					
18	1-18-2	GC 415	147-154	.10					
19			170-176	.06					
20									
21									
22	12-28-1	DH	4B 0-20	.26					
23			25B 0-20	.08					
24			33B 0-20	.10					
25	12-15-1		62B 0-5	.12					
26	12-30-1		95B 0-20	.06					
27			111B 0-20	.04					
28			114B 0-20	.10					
29	12-20-1		142B 0-20	.22					
30			231B 0-10	.06					
31	12-21-1		255B 0-10	.10					
32	12-20-1		269B 0-20	.28					
33	12-30-1		253B 10-20	.12					
34	12-10-1		307B 0-10	.06					
35	12-20-1		5C 0-20	.18					
36			6C 0-20	.10					
37	12-28-1		3C 0-20	.10					
38			9C 0-20	.20					
39									
40									

Assay Report

1-26-2
pg. 173

	ORC		AGOT					
1-25-2	CO	0830	.70		1-21-2	4730W 11275N	9-15	.06
		0930	.95				15-22	.04
		1030	.60				22-30	.06
		1130	.55				30-39	.04
		1230	.50				39-45	.04
		1330	1.35				45-51	.02
		1330	4.70				51-53	.02
		1430	1.40				53-62	.02
1-25-2	PO	0700	1.60		1-21-2	4730W 11225N	0-7	.04
		0800	.80				7-13	.02
		0900	.55				13-19	.06
		1000	.65				19-25	.04
		1100	.60				25-32	.04
		1200	.55				32-39	.02
		1300	.50				52-56	.18
							56-62	.24
1-23-2	Tails Pad #1		.70					
					1-21-2	4730W 11250N	0-9	.12
12-28-1	DH 5B	0-20	.08				9-13	.12
12-29-1	6SB	0-20	.08				13-19	.14
12-30-1	11SB	0-20	.10				19-25	.14
12-31-1	11 6B	0-20	.14				25-29	.12
12-30-1	12 4B	0-20	.12				29-36	.14
12-31-1	14 9B	0-20	.18				49-55	.12
	C13	0-20	.12				55-64	.18
	C13	0-20	.10				64-68	.20
1-11-2	4480 CC19S	4-7	.10					
1-21-2	4730W 11200N	16-20	.08		Titration plant spray 1400 hrs. 0.8 CN pH 8.5			
		20-25	.08					
		25-30	.02					
		30-36	.04					
		36-43	.02					
		43-49	.02					
		61-67	.04					
		67-69	.08					
		69-74	.02					
1-21-2	4730W 11275N	0-3	.02					
		3-9	.04					

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

ASSAY REPORT

	Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4			1.52	
	Rerun 42S 37-43			6.40	
	Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4		1.50	1.50	Tr
1-22-2	Special Quartz #1		0.04	0.04	Nil
1-20-2	42S 37-43		6.41	6.39	-0.19
	ORC				
	DH	C-1	0-20	.14	
		C-8	0-20	.12	
12-28-1		B-10	0-20	.10	
		C-10	0-20	.10	
		B-16	0-20	.16	
		B-23	0-20	.10	
12-29-1		B-50	0-20	.12	
12-27-1		B-78	0-20	.10	
12-30-1		B-87	0-20	.08	
		B-91	0-20	.14	
		B-136	0-20	.14	
12-31-1		B-133	0-20	.10	
		B-111		.16	
		B-161		.20	
		B-162		.22	
1-10-2		B-166		.16	
1-6-2		B-198	0-20	.22	
12-21-1		B-242	7-15	.16	
		B-254	0-10	.20	
1-11-2		B-263	0-20	.40	
		B-265	0-20	.24	
		B-275	0-20	.20	
		B-279	10-20	.28	
12-22-1		B-300		.16	

ASSAY REPORT

1-25-2
Pg 1 of 2

	Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4			1.52	
	Rerun 42S 37-43			6.40	
	Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4		1.50	1.50	Tr
1-22-2	Special Quartz #1		0.04	0.04	Nil
1-20-2	42S 37-43		6.41	6.39	-0.19
	ORC				
	DH	C-1	0-20	.14	
		C-8	0-20	.12	
12-28-1		B-10	0-20	.10	
		C-10	0-20	.10	
		B-16	0-20	.16	
		B-23	0-20	.10	
12-29-1		B-50	0-20	.12	
12-27-1		B-78	0-20	.10	
12-30-1		B-87	0-20	.08	
		B-91	0-20	.14	
		B-136	0-20	.14	
12-31-1		B-133	0-20	.10	
		B-111		.16	
		B-161		.20	
		B-162		.22	
1-10-2		B-166		.16	
1-6-2		B-198	0-20	.22	
12-21-1		B-242	7-15	.16	
		B-254	0-10	.20	
1-11-2		B-263	0-20	.40	
		B-265	0-20	.24	
		B-275	0-20	.20	
		B-279	10-20	.28	
12-22-1		B-300		.16	

1-20-82

Assay Report

	ORC			
1-11-2	CC 195 4680	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 4680	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N 4680	50-65	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 4680	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH 4B	0-20	.26	
	1 25B	0-20	.08	
	33B	0-20	.10	
12-15-1	42B	0-5	.12	
12-30-1	95B	0-20	.06	
	111B	0-20	.04	
	114B	0-20	.10	
12-20-1	142B	0-20	.22	
	231B	0-10	.06	
12-21-1	255B	0-10	.10	
12-20-1	269B	0-20	.28	
12-30-1	253B	10-20	.12	
12-10-1	307B	0-10	.06	
12-20-1	5C	0-20	.18	
	6C	0-20	.10	
12-28-1	3C	0-20	.10	
	9C	0-20	.20	

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

1-20-82

pg. 3 of 3

Assay Report

		ORC			
1	1-11-2	CC 195 4680	0-4	.18	
2			7-11	.12	
3			18-20	.10	
4			24-31	.18	
5			63-66	.10	
6			75-79	.08	
7			88-97	.08	
8		CC 20 4680	43-45	.08	
9			45-50	.10	
10			56-63	.14	
11			63-67	.12	
12			67-73	.08	
13			73-80	.08	
14		CC 20N 4680	50-65	.06	
15			66-72	.06	
16			85-93	.12	
17	1-12-2	CC 205 4680	46-49	.08	
18	1-18-2	GC 415	147-154	.10	
19			170-176	.06	
20					
21					
22	12-28-1	DH	4B 0-20	.26	
23			25B 0-20	.08	
24			33B 0-20	.10	
25	12-15-1		62B 0-5	.12	
26	12-30-1		95B 0-20	.06	
27			111B 0-20	.04	
28			114B 0-20	.10	
29	12-20-1		142B 0-20	.22	
30			231B 0-10	.06	
31	12-21-1		255B 0-10	.10	
32	12-20-1		269B 0-20	.28	
33	12-30-1		253B 10-20	.12	
34	12-10-1		307B 0-10	.06	
35	12-20-1		5C 0-20	.18	
36			6C 0-20	.10	
37	12-28-1		3C 0-20	.10	
38			9C 0-20	.20	
39					
40					

1-20-82

Assay Report

		ORC		
1	1-11-2	CC 195 4680	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		CC 20 4680	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		CC 20N 4680	50-65	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	CC 205 4680	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH	4B 0-20	.26
23			25B 0-20	.08
24			33B 0-20	.10
25	12-15-1		42B 0-5	.12
26	12-30-1		95B 0-20	.06
27			111B 0-20	.04
28			114B 0-20	.10
29	12-20-1		142B 0-20	.22
30			231B 0-10	.06
31	12-21-1		255B 0-10	.10
32	12-20-1		269B 0-20	.28
33	12-30-1		253B 10-20	.12
34	12-10-1		307B 0-10	.06
35	12-20-1		5C 0-20	.18
36			6C 0-20	.10
37	12-28-1		3C 0-20	.10
38			9C 0-20	.20
39				
40				

Assay Report

1-26-2
pg. 173

	ORC		AGOT					
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06	
		0930	.95			15-22	.04	
		1030	.60			22-30	.06	
		1130	.55			30-39	.04	
		1230	.50			39-45	.04	
		1330	1.35			45-51	.02	
		1330	4.70			51-53	.02	
		1430	1.40			53-62	.02	
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04	
		0800	.80			7-13	.02	
		0900	.55			13-19	.06	
		1000	.65			19-25	.04	
		1100	.60			25-32	.04	
		1200	.55			32-39	.02	
		1300	.50			52-56	.18	
						56-62	.24	
1-23-2	Tails Pad #1		.70					
				1-21-2	4730W 11250N	0-9	.12	
12-28-1	DH	5B 0-20	.08			9-13	.12	
12-29-1		6SB 0-20	.08			13-19	.14	
12-30-1		11SB 0-20	.10			19-25	.14	
12-31-1		11 6B 0-20	.14			25-29	.12	
12-30-1		12 4B 0-20	.12			29-36	.14	
12-31-1		14 9B 0-20	.18			49-55	.12	
		C13 0-20	.12			55-64	.18	
		C13 0-20	.10			64-68	.20	
1-11-2	4480 CC19S	4-7	.10					
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN pH 8.5				
		20-25	.08					
		25-30	.02					
		30-36	.04					
		36-43	.02					
		43-49	.02					
		61-67	.04					
		67-69	.08					
		69-74	.02					
1-21-2	4730W 11275N	0-3	.02					
		3-9	.04					

Assay Report

1-26-2
Pg. 173

	ORC		AGOT					
1-25-2	CO	0830	.70		1-21-2	4730W 11275N	9-15	.06
		0930	.95				15-22	.04
		1030	.60				22-30	.06
		1130	.55				30-39	.04
		1230	.50				39-45	.04
		1330	1.35				45-51	.02
		1330	4.70				51-53	.02
		1430	1.40				53-62	.02
1-25-2	PO	0700	1.60		1-21-2	4730W 11225N	0-7	.04
		0800	.80				7-13	.02
		0900	.55				13-19	.06
		1000	.65				19-25	.04
		1100	.60				25-32	.04
		1200	.55				32-39	.02
		1300	.50				52-56	.18
							56-62	.24
1-23-2	Tails Pad #1		.70					
					1-21-2	4730W 11250N	0-9	.12
12-28-1	DH	5B 0-20	.08				9-13	.12
12-29-1		6SB 0-20	.08				13-19	.14
12-30-1		11SB 0-20	.10				19-25	.14
12-31-1		11 6B 0-20	.14				25-29	.12
12-30-1		12 4B 0-20	.12				29-36	.14
12-31-1		14 9B 0-20	.18				49-55	.12
		C13 0-20	.12				55-64	.18
		C13 0-20	.10				64-68	.20
1-11-2	4480 CC19S	4-7	.10					
1-21-2	4730W 11200N	16-20	.08		Titration plant spray 1400 hrs. 0.8 CN pH 8.5			
		20-25	.08					
		25-30	.02					
		30-36	.04					
		36-43	.02					
		43-49	.02					
		61-67	.04					
		67-69	.08					
		69-74	.02					
1-21-2	4730W 11275N	0-3	.02					
		3-9	.04					

Assay Report

1-26-2
pg. 173

	ORC		AGOT					
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06
		0930	.95			15-22	.04
		1030	.60			22-30	.06
		1130	.55			30-39	.04
		1230	.50			39-45	.04
		1330	1.35			45-51	.02
		1330	4.70			51-53	.02
		1430	1.40			53-62	.02
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04
		0800	.80			7-13	.02
		0900	.55			13-19	.06
		1000	.65			19-25	.04
		1100	.60			25-32	.04
		1200	.55			32-39	.02
		1300	.50			52-56	.18
						56-62	.24
1-23-2	Tails Pad #1		.70				
				1-21-2	4730W 11250N	0-9	.12
12-28-1	DH SB	0-20	.08			9-13	.12
12-29-1	65B	0-20	.08			13-19	.14
12-30-1	115B	0-20	.10			19-25	.14
12-31-1	116B	0-20	.14			25-29	.12
12-30-1	124B	0-20	.12			29-36	.14
12-31-1	149B	0-20	.18			49-55	.12
	C13	0-20	.12			55-64	.18
	C13	0-20	.10			64-68	.20
1-11-2	4480 CC19S	4-7	.10				
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN PH 8.5			
		20-25	.08				
		25-30	.02				
		30-36	.04				
		36-43	.02				
		43-49	.02				
		61-67	.04				
		67-69	.08				
		69-74	.02				
1-21-2	4730W 11275N	0-3	.02				
		3-9	.04				

ASSAY REPORT

1-25-2
Pg 1 of 2

	Acid Digestion			Ag Gpt		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 42S 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 42S 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

1-20-82

Assay Report

		ORC		
1	1-11-2	CC 195 (4680)	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		CC 20 (4680)	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		CC 20N (4680)	50-65	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	CC 205 (4680)	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH	4B 0-20	.26
23			25B 0-20	.08
24			33B 0-20	.10
25	12-15-1		62B 0-5	.12
26	12-30-1		95B 0-20	.06
27			111B 0-20	.04
28			114B 0-20	.10
29	12-20-1		142B 0-20	.22
30			231B 0-10	.06
31	12-21-1		255B 0-10	.10
32	12-20-1		269B 0-20	.28
33	12-30-1		253B 10-20	.12
34	12-10-1		307B 0-10	.06
35	12-20-1		5C 0-20	.18
36			6C 0-20	.10
37	12-28-1		3C 0-20	.10
38			9C 0-20	.20
39				
40				

Assay Report

1-26-2
pg. 173

		ORC		AGOT					
1	1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06	1
2			0930	.95			15-22	.04	2
3			1030	.60			22-30	.06	3
4			1130	.55			30-39	.04	4
5			1230	.50			39-45	.04	5
6			1330	1.35			45-51	.02	6
7			1330	4.70			51-53	.02	7
8			1430	1.40			53-62	.02	8
9									9
10	1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04	10
11			0800	.80			7-13	.02	11
12			0900	.55			13-19	.06	12
13			1000	.65			19-25	.04	13
14			1100	.60			25-32	.04	14
15			1200	.55			32-39	.02	15
16			1300	.50			52-56	.18	16
17							56-62	.24	17
18									18
19	1-23-2	Tails Pad #1		.70	1-21-2	4730W 11250N	0-9	.12	19
20	12-28-1	DH 5B	0-20	.08			9-13	.12	20
21	12-29-1	65B	0-20	.08			13-19	.14	21
22	12-30-1	115B	0-20	.10			19-25	.14	22
23	12-31-1	116B	0-20	.14			25-29	.12	23
24	12-30-1	124B	0-20	.12			29-36	.14	24
25	12-31-1	149B	0-20	.18			49-55	.12	25
26		C13	0-20	.12			55-64	.18	26
27		C13	0-20	.10			64-68	.20	27
28									28
29	1-11-2	4480 CC19S	4-7	.10					29
30									30
31	1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN PH 8.5				31
32			20-25	.08					32
33			25-30	.02					33
34			30-36	.04					34
35			36-43	.02					35
36			43-49	.02					36
37			61-67	.04					37
38			67-69	.08					38
39			69-74	.02					39
40	1-21-2	4730W 11275N	0-3	.02					40
			3-9	.04					

ASSAY REPORT

	Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4			1.52	
	Rerun 425 37-43			6.40	
	Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4		1.50	1.50	Tr
1-22-2	Special Quartz #1		0.04	0.04	Nil
1-20-2	425 37-43		6.41	6.39	-0.19
	ORC				
	DH	C-1	0-20	.14	
		C-8	0-20	.12	
12-28-1		B-10	0-20	.10	
		C-10	0-20	.10	
		B-16	0-20	.16	
		B-23	0-20	.10	
12-29-1		B-50	0-20	.12	
12-27-1		B-78	0-20	.10	
12-30-1		B-87	0-20	.08	
		B-91	0-20	.14	
		B-136	0-20	.14	
12-31-1		B-133	0-20	.10	
		B-111		.16	
		B-161		.20	
		B-162		.22	
1-10-2		B-166		.16	
1-6-2		B-198	0-20	.22	
12-21-1		B-242	7-15	.16	
		B-254	0-10	.20	
1-11-2		B-263	0-20	.40	
		B-265	0-20	.24	
		B-275	0-20	.20	
		B-279	10-20	.28	
12-22-1		B-300		.16	

ASSAY REPORT

	Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4			1.52	
	Rerun 425 37-43			6.40	
	Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4		1.50	1.50	Tr
1-22-2	Special Quartz #1		0.04	0.04	Nil
1-20-2	42 S	37-43	6.41	6.39	-0.19
	ORC				
	DH	C-1	0-20	.14	
		C-8	0-20	.12	
12-28-1		B-10	0-20	.10	
		C-10	0-20	.10	
		B-16	0-20	.16	
		B-23	0-20	.10	
12-29-1		B-50	0-20	.12	
12-27-1		B-78	0-20	.10	
12-30-1		B-87	0-20	.08	
		B-91	0-20	.14	
		B-136	0-20	.14	
12-31-1		B-133	0-20	.10	
		B-111		.16	
		B-161		.20	
		B-162		.22	
1-10-2		B-166		.16	
1-6-2		B-198	0-20	.22	
12-21-1		B-242	7-15	.16	
		B-254	0-10	.20	
1-11-2		B-263	0-20	.40	
		B-265	0-20	.24	
		B-275	0-20	.20	
		B-279	10-20	.28	
12-22-1		B-300		.16	

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

ASSAY REPORT

	Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4			1.52	
	Rerun 42S 37-43			6.40	
	Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4		1.50	1.50	Tr
1-22-2	Special Quartz #1		0.04	0.04	Nil
1-20-2	42 S 37-43		6.41	6.39	-0.19
	ORC				
	DH	C-1	0-20	.14	
		C-8	0-20	.12	
12-28-1		B-10	0-20	.10	
		C-10	0-20	.10	
		B-16	0-20	.16	
		B-23	0-20	.10	
12-29-1		B-50	0-20	.12	
12-27-1		B-78	0-20	.10	
12-30-1		B-87	0-20	.08	
		B-91	0-20	.14	
		B-136	0-20	.14	
12-31-1		B-133	0-20	.10	
		B-111		.16	
		B-161		.20	
		B-162		.22	
1-10-2		B-166		.16	
1-6-2		B-198	0-20	.22	
12-21-1		B-242	7-15	.16	
		B-254	0-10	.20	
1-11-2		B-263	0-20	.40	
		B-265	0-20	.24	
		B-275	0-20	.20	
		B-279	10-20	.28	
12-22-1		B-300		.16	

1-20-82

Assay Report

		ORC							
1	1-11-2	CC 195 (4680)	0-4	.18					
2			7-11	.12					
3			18-20	.10					
4			24-31	.18					
5			63-66	.10					
6			75-79	.08					
7			88-97	.08					
8		CC 20 (4680)	43-45	.08					
9			45-50	.10					
10			56-63	.14					
11			63-67	.12					
12			67-73	.08					
13			73-80	.08					
14		CC 20N (4680)	50-65	.06					
15			66-72	.06					
16			85-93	.12					
17	1-12-2	CC 205 (4680)	46-49	.08					
18	1-18-2	GC 415	147-154	.10					
19			170-176	.06					
20									
21									
22	12-28-1	DH 4B	0-20	.26					
23		25B	0-20	.08					
24		33B	0-20	.10					
25	12-15-1	62B	0-5	.12					
26	12-30-1	95B	0-20	.06					
27		111B	0-20	.04					
28		114B	0-20	.10					
29	12-20-1	142B	0-20	.22					
30		231B	0-10	.06					
31	12-21-1	255B	0-10	.10					
32	12-20-1	269B	0-20	.28					
33	12-30-1	253B	10-20	.12					
34	12-10-1	307B	0-10	.06					
35	12-20-1	5C	0-20	.18					
36		6C	0-20	.10					
37	12-28-1	3C	0-20	.10					
38		9C	0-20	.20					
39									
40									

ASSAY REPORT

		Acid Digestion			AGOT	
1	1-20-2	Rerun Tails Pad #4			1.52	
2		Rerun 425 37-43			6.40	
5		Fire Assay		Dore	Ag	Au
6	1-20-2	Tails Pad #4		1.50	1.50	Tr
7	1-22-2	Special Quartz #1		0.04	0.04	Nil
8	1-20-2	425	37-43	6.41	6.39	-0.19
10		ORC				
11		DH	C-1	0-20	.14	
12			C-8	0-20	.12	
13	12-28-1		B-10	0-20	.10	
14			C-10	0-20	.10	
15			B-16	0-20	.16	
16			B-23	0-20	.10	
17	12-29-1		B-50	0-20	.12	
18	12-27-1		B-78	0-20	.10	
19	12-30-1		B-87	0-20	.08	
20			B-91	0-20	.14	
21			B-136	0-20	.14	
22	12-31-1		B-133	0-20	.10	
23			B-111		.16	
24			B-161		.20	
25			B-162		.22	
26	1-10-2		B-166		.16	
27	1-6-2		B-198	0-20	.22	
28	12-21-1		B-242	7-15	.16	
29			B-254	0-10	.20	
30	1-11-2		B-263	0-20	.40	
31			B-265	0-20	.24	
32			B-275	0-20	.20	
33			B-279	10-20	.28	
34	12-22-1		B-300		.16	

1-20-82

Assay Report

	ORC			
1-11-2	CC 195 4680	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 4680	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N 4680	50-65	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 4680	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH 4B	0-20	.26	
	1 25B	0-20	.08	
	33B	0-20	.10	
12-15-1	62B	0-5	.12	
12-30-1	95B	0-20	.06	
	111B	0-20	.04	
	114B	0-20	.10	
12-20-1	142B	0-20	.22	
	231B	0-10	.06	
12-21-1	255B	0-10	.10	
12-20-1	269B	0-20	.28	
12-30-1	253B	10-20	.12	
12-10-1	307B	0-10	.06	
12-20-1	5C	0-20	.18	
	6C	0-20	.10	
12-28-1	3C	0-20	.10	
	9C	0-20	.20	

ASSAY REPORT

	Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4			1.52	
	Rerun 42S 37-43			6.40	
	Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4		1.50	1.50	Tr
1-22-2	Special Quartz #1		0.04	0.04	Nil
1-20-2	42S 37-43		6.41	6.39	-0.19
	ORC				
	DH	C-1	0-20	.14	
		C-8	0-20	.12	
12-28-1		B-10	0-20	.10	
		C-10	0-20	.10	
		B-16	0-20	.16	
		B-23	0-20	.10	
12-29-1		B-50	0-20	.12	
12-27-1		B-78	0-20	.10	
12-30-1		B-87	0-20	.08	
		B-91	0-20	.14	
		B-136	0-20	.14	
12-31-1		B-133	0-20	.10	
		B-111		.16	
		B-161		.20	
		B-162		.22	
1-10-2		B-166		.16	
1-6-2		B-198	0-20	.22	
12-21-1		B-242	7-15	.16	
		B-254	0-10	.20	
1-11-2		B-263	0-20	.40	
		B-265	0-20	.24	
		B-275	0-20	.20	
		B-279	10-20	.28	
12-22-1		B-300		.16	

1-20-82

pg. 3 of 3

Assay Report

		ORC		
1-11-2	CC 195 4680	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 4680	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N 4680	50-65	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 4680	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH 4B	0-20	.26	
	125B	0-20	.08	
	33B	0-20	.10	
12-15-1	62B	0-5	.12	
12-30-1	95B	0-20	.06	
	111B	0-20	.04	
	114B	0-20	.10	
12-20-1	142B	0-20	.22	
	231B	0-10	.06	
12-21-1	255B	0-10	.10	
12-20-1	269B	0-20	.28	
12-30-1	253B	10-20	.12	
12-10-1	307B	0-10	.06	
12-20-1	5C	0-20	.18	
	6C	0-20	.10	
12-28-1	3C	0-20	.10	
	9C	0-20	.20	

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 42S 37-43			6.40		
	Fire Assay	Dore		Ag	Au	
1-20-2	Tails Pad #4	1.50		1.50	Tr	
1-22-2	Special Quartz #1	0.04		0.04	Nil	
1-20-2	42S 37-43	6.41		6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

1-20-82

Assay Report

	ORC			
1	1-11-2	CC 4680 195	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		CC 4680 20	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		CC 4680 20N	50-55	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	CC 4680 205	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH 4B	0-20	.26
23		25B	0-20	.08
24		33B	0-20	.10
25	12-15-1	62B	0-5	.12
26	12-30-1	95B	0-20	.06
27		111B	0-20	.04
28		114B	0-20	.10
29	12-20-1	142B	0-20	.22
30		231B	0-10	.06
31	12-21-1	255B	0-10	.10
32	12-20-1	269B	0-20	.28
33	12-30-1	253B	10-20	.12
34	12-10-1	307B	0-10	.06
35	12-20-1	5C	0-20	.18
36		6C	0-20	.10
37	12-28-1	3C	0-20	.10
38		9C	0-20	.20
39				
40				

ASSAY REPORT

	Acid Digestion			AgOT			
1-20-2	Rerun Tails Pad #4			1.52			
	Rerun 425 37-43			6.40			
	Fire Assay		Dore	Ag	Au		
1-20-2	Tails Pad #4		1.50	1.50	Tr		
1-22-2	Special Quartz #1		0.04	0.04	Nil		
1-20-2	42 S 37-43		6.41	6.39	-0.19		
	ORC						
	DH	C-1	0-20	.14			
		C-8	0-20	.12			
12-28-1		B-10	0-20	.10			
		C-10	0-20	.10			
		B-16	0-20	.16			
		B-23	0-20	.10			
12-29-1		B-50	0-20	.12			
12-27-1		B-78	0-20	.10			
12-30-1		B-87	0-20	.08			
		B-91	0-20	.14			
		B-136	0-20	.14			
12-31-1		B-133	0-20	.10			
		B-111		.16			
		B-161		.20			
		B-162		.22			
1-10-2		B-166		.16			
1-6-2		B-198	0-20	.22			
12-21-1		B-242	7-15	.16			
		B-254	0-10	.20			
1-11-2		B-263	0-20	.40			
		B-265	0-20	.24			
		B-275	0-20	.20			
		B-279	10-20	.28			
12-22-1		B-300		.16			

ASSAY REPORT

		Acid Digestion			AGOT	
1	1-20-2	Rerun Tails Pad #4			1.52	
2		Rerun 425 37-43			6.40	
5		Fire Assay		Dore	Ag	Au
6	1-20-2	Tails Pad #4		1.50	1.50	Tr
7	1-22-2	Special Quartz #1		0.04	0.04	Nil
8	1-20-2	42 S 37-43		6.41	6.39	-0.19
10		ORC				
11		DH	C-1	0-20	.14	
12			C-8	0-20	.12	
13	12-28-1		B-10	0-20	.10	
14			C-10	0-20	.10	
15			B-16	0-20	.16	
16			B-23	0-20	.10	
17	12-29-1		B-50	0-20	.12	
18	12-27-1		B-78	0-20	.10	
19	12-30-1		B-87	0-20	.08	
20			B-91	0-20	.14	
21			B-136	0-20	.14	
22	12-31-1		B-133	0-20	.10	
23			B-111		.16	
24			B-161		.20	
25			B-162		.22	
26	1-10-2		B-166		.16	
27	1-6-2		B-198	0-20	.22	
28	12-21-1		B-242	7-15	.16	
29			B-254	0-10	.20	
30	1-11-2		B-263	0-20	.40	
31			B-265	0-20	.24	
32			B-275	0-20	.20	
33			B-279	10-20	.28	
34	12-22-1		B-300		.16	

ASSAY REPORT

		Acid Digestion			AgOT				
1	1-20-2	Rerun Tails Pad #4			1.52				
2		Rerun 42S 37-43			6.40				
3									
4									
5		Fire Assay		Dore	Ag	Au			
6	1-20-2	Tails Pad #4		1.50	1.50	Tr			
7	1-22-2	Special Quartz #1		0.04	0.04	Nil			
8	1-20-2	42S 37-43		6.41	6.39	-0.19			
9									
10		ORC							
11		DH	C-1	0-20	.14				
12			C-8	0-20	.12				
13	12-28-1		B-10	0-20	.10				
14			C-10	0-20	.10				
15			B-16	0-20	.16				
16			B-23	0-20	.10				
17	12-29-1		B-50	0-20	.12				
18	12-27-1		B-78	0-20	.10				
19	12-30-1		B-87	0-20	.08				
20			B-91	0-20	.14				
21			B-136	0-20	.14				
22	12-31-1		B-133	0-20	.10				
23			B-111		.16				
24			B-161		.20				
25			B-162		.22				
26	1-10-2		B-166		.16				
27	1-6-2		B-198	0-20	.22				
28	12-21-1		B-242	7-15	.16				
29			B-254	0-10	.20				
30	1-11-2		B-263	0-20	.40				
31			B-265	0-20	.24				
32			B-275	0-20	.20				
33			B-279	10-20	.28				
34	12-22-1		B-300		.16				
35									
36									
37									
38									
39									
40									

1-20-82

pg. 3 of 3

Assay Report

	ORC			
1-11-2	CC 195 4680	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 4680	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N 4680	50-55	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 4680	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH 4B	0-20	.26	
	25B	0-20	.08	
	33B	0-20	.10	
12-45-1	62B	0-5	.12	
12-30-1	95B	0-20	.06	
	111B	0-20	.04	
	114B	0-20	.10	
12-20-1	142B	0-20	.22	
	231B	0-10	.06	
12-21-1	255B	0-10	.10	
12-20-1	269B	0-20	.28	
12-30-1	253B	10-20	.12	
12-10-1	307B	0-10	.06	
12-20-1	5C	0-20	.18	
	6C	0-20	.10	
12-28-1	3C	0-20	.10	
	9C	0-20	.20	

C - SERIES OF DRILL HOLES

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 425 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42 S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.12		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

1-20-82

Assay Report

		ORC			
1	1-11-2	CC 195 4680	0-4	.18	
2			7-11	.12	
3			18-20	.10	
4			24-31	.18	
5			63-66	.10	
6			75-79	.08	
7			88-97	.08	
8		CC 20 4680	43-45	.08	
9			45-50	.10	
10			56-63	.14	
11			63-67	.12	
12			67-73	.08	
13			73-80	.08	
14		CC 20N 4680	50-55	.06	
15			66-72	.06	
16			85-93	.12	
17	1-12-2	CC 20S 4680	46-49	.08	
18	1-18-2	GC 415	147-154	.10	
19			170-176	.06	
20					
21					
22	12-28-1	DH	4B 0-20	.26	
23			25B 0-20	.08	
24			33B 0-20	.10	
25	12-15-1		62B 0-5	.12	
26	12-30-1		95B 0-20	.06	
27			111B 0-20	.04	
28			114B 0-20	.10	
29	12-20-1		142B 0-20	.22	
30			231B 0-10	.06	
31	12-21-1		255B 0-10	.10	
32	12-20-1		269B 0-20	.28	
33	12-30-1		253B 10-20	.12	
34	12-10-1		307B 0-10	.06	
35	12-20-1		5C 0-20	.18	
36			6C 0-20	.10	
37	12-28-1		3C 0-20	.10	
38			9C 0-20	.20	
39					
40					

1-20-82

pg. 3 of 3

Assay Report

		ORC		
1	1-11-2	CC 195 (4680)	0-4	.18
2			7-11	.12
3			18-20	.10
4			24-31	.18
5			63-66	.10
6			75-79	.08
7			88-97	.08
8		CC 20 (4680)	43-45	.08
9			45-50	.10
10			56-63	.14
11			63-67	.12
12			67-73	.08
13			73-80	.08
14		CC 20N (4680)	50-55	.06
15			66-72	.06
16			85-93	.12
17	1-12-2	CC 205 (4680)	46-49	.08
18	1-18-2	GC 415	147-154	.10
19			170-176	.06
20				
21				
22	12-28-1	DH 4B	0-20	.26
23		25B	0-20	.08
24		33B	0-20	.10
25	12-15-1	62B	0-5	.12
26	12-30-1	95B	0-20	.06
27		111B	0-20	.04
28		114B	0-20	.10
29	12-20-1	142B	0-20	.22
30		231B	0-10	.06
31	12-21-1	255B	0-10	.10
32	12-20-1	269B	0-20	.28
33	12-30-1	253B	10-20	.12
34	12-10-1	307B	0-10	.06
35	12-20-1	5C	0-20	.18
36		6C	0-20	.10
37	12-28-1	3C	0-20	.10
38		9C	0-20	.20
39				
40				

1-20-82

Assay Report

	ORC			
1-11-2	CC 195 4680	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 4680	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N 4680	50-55	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 4680	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH 4B	0-20	.26	
	25B	0-20	.08	
	33B	0-20	.10	
12-15-1	62B	0-5	.12	
12-30-1	95B	0-20	.06	
	111B	0-20	.04	
	114B	0-20	.10	
12-20-1	142B	0-20	.22	
	231B	0-10	.06	
12-21-1	255B	0-10	.10	
12-20-1	269B	0-20	.28	
12-30-1	253B	10-20	.12	
12-10-1	307B	0-10	.06	
12-20-1	5C	0-20	.18	
	6C	0-20	.10	
12-28-1	3C	0-20	.10	
	9C	0-20	.20	

ASSAY REPORT

		Acid Digestion			AGOT	
1-20-2	Rerun Tails Pad #4				1.52	
	Rerun 425 37-43				6.40	
		Fire Assay		Dore	Ag	Au
1-20-2	Tails Pad #4			1.50	1.50	Tr
1-22-2	Special Quartz #1			0.04	0.04	Nil
1-20-2	425 37-43			6.41	6.39	-0.19
	ORC					
	DH	C-1	0-20		.14	
		C-8	0-20		.12	
12-28-1		B-10	0-20		.10	
		C-10	0-20		.10	
		B-16	0-20		.16	
		B-23	0-20		.10	
12-29-1		B-50	0-20		.12	
12-27-1		B-78	0-20		.10	
12-30-1		B-87	0-20		.08	
		B-91	0-20		.14	
		B-136	0-20		.14	
12-31-1		B-133	0-20		.10	
		B-111			.16	
		B-161			.20	
		B-162			.22	
1-10-2		B-166			.16	
1-6-2		B-198	0-20		.22	
12-21-1		B-242	7-15		.16	
		B-254	0-10		.20	
1-11-2		B-263	0-20		.40	
		B-265	0-20		.24	
		B-275	0-20		.20	
		B-279	10-20		.28	
12-22-1		B-300			.16	

1-20-82

Assay Report

	ORC			
1-11-2	CC 195 4680	0-4	.18	
		7-11	.12	
		18-20	.10	
		24-31	.18	
		63-66	.10	
		75-79	.08	
		88-97	.08	
	CC 20 4680	43-45	.08	
		45-50	.10	
		56-63	.14	
		63-67	.12	
		67-73	.08	
		73-80	.08	
	CC 20N 4680	50-55	.06	
		66-72	.06	
		85-93	.12	
1-12-2	CC 205 4680	46-49	.08	
1-18-2	GC 415	147-154	.10	
		170-176	.06	
12-28-1	DH 4B	0-20	.26	
	1 25B	0-20	.08	
	33B	0-20	.10	
12-15-1	62B	0-5	.12	
12-30-1	95B	0-20	.06	
	111B	0-20	.04	
	114B	0-20	.10	
12-20-1	142B	0-20	.22	
	231B	0-10	.06	
12-21-1	255B	0-10	.10	
12-20-1	269B	0-20	.28	
12-30-1	253B	10-20	.12	
12-10-1	307B	0-10	.06	
12-20-1	5C	0-20	.18	
	6C	0-20	.10	
12-28-1	3C	0-20	.10	
	9C	0-20	.20	

ASSAY REPORT

	Acid Digestion			AGOT		
1-20-2	Rerun Tails Pad #4			1.52		
	Rerun 42S 37-43			6.40		
	Fire Assay		Dore	Ag	Au	
1-20-2	Tails Pad #4		1.50	1.50	Tr	
1-22-2	Special Quartz #1		0.04	0.04	Nil	
1-20-2	42S 37-43		6.41	6.39	-0.19	
	ORC					
	DH	C-1	0-20	.14		
		C-8	0-20	.12		
12-28-1		B-10	0-20	.10		
		C-10	0-20	.10		
		B-16	0-20	.16		
		B-23	0-20	.10		
12-29-1		B-50	0-20	.12		
12-27-1		B-78	0-20	.10		
12-30-1		B-87	0-20	.08		
		B-91	0-20	.14		
		B-136	0-20	.14		
12-31-1		B-133	0-20	.10		
		B-111		.16		
		B-161		.20		
		B-162		.22		
1-10-2		B-166		.16		
1-6-2		B-198	0-20	.22		
12-21-1		B-242	7-15	.16		
		B-254	0-10	.20		
1-11-2		B-263	0-20	.40		
		B-265	0-20	.24		
		B-275	0-20	.20		
		B-279	10-20	.28		
12-22-1		B-300		.16		

Assay Report

1-26-2
pg. 173

	ORC		AGOT					
1-25-2	CO	0830	.70	1-21-2	4730W 11275N	9-15	.06	
		0930	.95			15-22	.04	
		1030	.60			22-30	.06	
		1130	.55			30-39	.04	
		1230	.50			39-45	.04	
		1330	1.35			45-51	.02	
		1330	4.70			51-53	.02	
		1430	1.40			53-62	.02	
1-25-2	PO	0700	1.60	1-21-2	4730W 11225N	0-7	.04	
		0800	.80			7-13	.02	
		0900	.55			13-19	.06	
		1000	.65			19-25	.04	
		1100	.60			25-32	.04	
		1200	.55			32-39	.02	
		1300	.50			52-56	.18	
						56-62	.24	
1-23-2	Tails Pad #1		.70					
				1-21-2	4730W 11250N	0-9	.12	
12-28-1	DH 5B	0-20	.08			9-13	.12	
12-29-1	6SB	0-20	.08			13-19	.14	
12-30-1	11SB	0-20	.10			19-25	.14	
12-31-1	11GB	0-20	.14			25-29	.12	
12-30-1	12GB	0-20	.12			29-36	.14	
12-31-1	14GB	0-20	.18			49-55	.12	
	C13	0-20	.12			55-64	.18	
	C13	0-20	.10			64-68	.20	
1-11-2	4480 CC19S	4-7	.10					
1-21-2	4730W 11200N	16-20	.08	Titration plant spray 1400 hrs. 0.8 CN PH 8.5				
		20-25	.08					
		25-30	.02					
		30-36	.04					
		36-43	.02					
		43-49	.02					
		61-67	.04					
		67-69	.08					
		69-74	.02					
1-21-2	4730W 11275N	0-3	.02					
		3-9	.04					